

INTERNATIONAL STANDARD



Optical fibre cables –
Part 1-1: Generic specification – General

iTeh Standards
(<https://standards.itih.ai>)
Document Preview

IEC 60794-1-1:2015

<https://standards.itih.ai/standards/iec/60794-1-1:2015>

Withhold





THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2015 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing more than 30 000 terms and definitions in English and French, with equivalent terms in 15 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

More than 60 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

IEC 60794-1-1:2015

<https://standards.iteh.ai/standards/iec/60794-1-1-2015>

INTERNATIONAL STANDARD



**Optical fibre cables –
Part 1-1: Generic specification – General**

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60794-1-1:2015

<https://standards.iteh.ai/standards/iec/ess313d8-2f7c-42b5-833a-27c7258785a4/iec-60794-1-1-2015>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.180.10

ISBN 978-2-8322-3018-3

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	6
3 Terms and definitions	7
4 Graphical symbols and abbreviations.....	12
5 Optical fibre cables.....	13
6 Materials	13
6.1 Optical fibre	13
6.1.1 General	13
6.1.2 Attenuation coefficient	13
6.1.3 Attenuation uniformity – Attenuation discontinuities	14
6.1.4 Cable cut-off wavelength	14
6.1.5 Fibre colouring.....	14
6.1.6 Polarization mode dispersion (PMD).....	14
6.2 Electrical conductors.....	14
6.3 Other materials	14
6.4 Environmental requirements	14
7 Cable construction.....	15
7.1 General.....	15
7.2 Colour coding	15
7.2.1 Overview	15
7.2.2 Unit colour coding.....	15
7.2.3 Sheath colour coding.....	15
8 Measuring methods.....	15
8.1 General.....	15
8.2 Measuring methods for dimensions	16
8.3 Measuring methods for mechanical characteristics	16
8.4 Measuring methods for electrical characteristics	16
8.5 Measuring methods for transmission and optical characteristics.....	17
8.6 Measuring methods for environmental characteristics	17
8.7 Measuring methods for cable element characterisation	17
9 Related Technical Reports.....	17
Annex A (informative) Guide to Guidelines for specific defined applications and cabled fibre performance	19
A.1 General.....	19
A.2 Cabled fibre attenuation requirements.....	19
A.3 Cabled fibre bandwidth requirements	20
A.4 Type testing at 1 625 nm.....	21
Annex B (informative) Guide to Guidelines for qualification sampling	22
B.1 Introduction General	22
B.2 Fibre selection for cable testing	22
B.3 Pass/fail criteria	23
Bibliography.....	24
Table 1 – Measuring methods for dimensions	16

Table 2 – Measuring methods for electrical characteristics	16
Table 3 – Measuring methods for transmission and optical characteristics of cabled optical fibres	17
Table A.1 – Maximum cabled fibre attenuation coefficient (dB/km), as given by ITU-T	19
Table A.2 – Category A1 multimode fibre maximum cable attenuation coefficient (dB/km).....	20
Table A.3 – Single-mode maximum cable attenuation coefficient (dB/km)	20
Table A.4 – Category A1 multimode cabled fibre bandwidth (MHz·km).....	21
Table A.5 – Guidance values for 1 625 nm type test acceptance criteria	21

Withheld

iTech Standards
(<https://standards.iteh.ai>)
Document Preview

IEC 60794-1-1:2015
<https://standards.iteh.ai/catalog/standards/iec/ess313d8-2f7c-42b5-833a-27c7258785a4/iec-60794-1-1-2015>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRE CABLES –

Part 1-1: Generic specification – General

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 60794-1-1 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This fourth edition cancels and replaces the third edition, published in 2011. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the expansion of the definitions, graphical symbols, terminology and abbreviations content, with the aim of making this standard the default and reference for all others in the IEC 60794-x series;
- b) the inclusion of updated and expanded optical fibre, attenuation and bandwidth sections, with the aim of making this standard the default and reference for all others in the IEC 60794-x series.

The text of this standard is based on the following documents:

CDV	Report on voting
86A/1651/CDV	86A/1667/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

A list of all parts in the IEC 60794 series, published under the general title *Optical fibre cables*, can be found on the IEC website.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

OPTICAL FIBRE CABLES –

Part 1-1: Generic specification – General

1 Scope

This part of IEC 60794 applies to optical fibre cables for use with communication equipment and devices employing similar techniques and to cables having a combination of both optical fibres and electrical conductors.

The object of this standard is to establish uniform generic requirements for the geometrical, transmission, material, mechanical, ageing (environmental exposure), climatic and electrical properties of optical fibre cables and cable elements, where appropriate.

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60189-1, *Low-frequency cables and wires with PVC insulation and PVC sheath – Part 1: General test and measuring methods*

~~IEC 60793-1-1, *Optical fibres – Part 1-1: Measurement methods and test procedures – General and guidance*~~

IEC 60304, *Standard colours for insulation for low-frequency cables and wires*

IEC 60793-1-21, *Optical Fibres – Part 1-21: Measurement methods and test procedures – Coating geometry*

~~IEC 60793-1-22, *Optical fibres – Part 1-22: Measurement methods and test procedures – Length measurement*~~
~~IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*~~

IEC 60793-1-40, *Optical fibres – Part 1-40: Measurement methods and test procedures – Attenuation*

IEC 60793-1-44, *Optical fibres – Part 1-44: Measurement methods and test procedures – Cut-off wavelength*

IEC 60793-1-46, *Optical fibres – Part 1-46: Measurement methods and test procedures – Monitoring of changes in optical transmittance*

IEC 60793-1-48, *Optical fibres – Part 1-48: Measurement methods and test procedures – Polarization mode dispersion*

IEC 60793-2, *Optical fibres – Part 2: Product specifications – General*

IEC 60793-2-50, *Optical fibres – Part 2-50: Product specifications – Sectional specification for class B single-mode fibres*

~~IEC 60794-1-2, Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures~~

~~IEC 60794-1-2:2003, Optical fibre cables – Part 1-2: Generic specification – Basic optical cable test procedures¹~~

IEC 60794-1-21, Optical fibre cables – Part 1-21: Generic specification – Basic optical cable test procedures – Mechanical tests methods

IEC 60794-1-22, Optical fibre cables – Part 1-22: Generic specification – Basic optical cable test procedures – Environmental tests methods

~~IEC 60794-4-20², Optical fibre cables – Part 4-20: Aerial optical cables along electrical power lines – Family specification for ADSS (All Dielectric Self Supported) Optical cables~~

IEC 60811-201, Electric and optical fibre cables – Test methods for non-metallic materials – Part 201: General tests – Measurement of insulation thickness³

IEC 60811-202, Electric and optical fibre cables – Test methods for non-metallic materials – Part 202: General tests – Measurement of thickness of non-metallic sheath⁴

IEC 60811-203, Electric and optical fibre cables – Test methods for non-metallic materials – Part 203: General tests – Measurement of overall dimensions⁵

IEC TR 61931, Fibre optic – Terminology

ISO 14001, Environmental management systems – Requirements with guidance for use

ISO 14064-1, Greenhouse gases – Part 1: Specification with guidance at the organization level for quantification and reporting of greenhouse gas emissions and removals

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

no change in attenuation

acceptance criterion for attenuation measurement that includes an allowance for measurement uncertainty arising from measurement errors or calibration errors due to a lack of suitable reference standards

Note 1 to entry: For a practical interpretation, ~~see IEC 60794-1-20~~ the following values shall be used:

a) no change in attenuation, single-mode (Class B): the total uncertainty of measurement shall be $\leq \pm 0,05$ dB for attenuation or $\leq \pm 0,05$ dB/km for attenuation coefficient. Any measured value within this range shall be considered as “no change in attenuation”

The requirement for these parameters is indicated as “No change ($\leq \pm 0,05$ dB or $\leq \pm 0,05$ dB/km)”.

¹ ~~To be replaced by future IEC 60794-1-22.~~

² ~~To be published.~~

³ ~~To be published.~~

⁴ ~~To be published.~~

⁵ ~~To be published.~~

By agreement between customer and supplier, minor deviation from this limit may be accepted at some low frequency, e.g. less than 10%. However for mechanical tests no deviation in excess of 0,15 dB shall be accepted. For environmental tests no deviation in excess of 0,10 dB/km shall be accepted.

b) no change in attenuation, multimode (Category A1): the total uncertainty of measurement shall be $\leq \pm 0,2$ dB for attenuation or $\leq \pm 0,2$ dB/km for attenuation coefficient

Any measured value within this range shall be considered as “no change in attenuation”.

The requirement for these parameters is indicated as “No change ($\leq \pm 0,2$ dB or $\leq \pm 0,2$ dB/km)”.

By agreement between customer and supplier, minor deviation from this limit may be accepted at some low frequency, e.g. less than 10%. However for mechanical tests no deviation in excess of 0,5 dB shall be accepted. For environmental tests no deviation in excess of 0,5 dB/km shall be accepted.

c) no change in attenuation, plastic optical fibre (Category A4): the total uncertainty of measurement for this standard shall be ≤ 2 % of maximum specified attenuation in IEC 60793-2-40 Annex A to G.

Any measured value within this range shall be considered as “no change in attenuation”.

3.2 allowable change in attenuation

<during mechanical and environmental tests> change in attenuation that may be a value larger than the no change limits, depending on fibre category, single-mode or multimode, cable design and application

3.3 link design attenuation LDA

statistical average attenuation value for a link of concatenated cables

3.4 no change in fibre strain

acceptance criterion for fibre strain measurement that includes an allowance for measurement uncertainty arising from measurement errors or calibration errors due to a lack of suitable reference standards

Note 1 to entry: For a practical interpretation, see IEC 60794-1-20 the total uncertainty of measurement shall be $\pm 0,05$ % strain. Any measured value within this range shall be considered as “no change in strain”.

3.5 allowable change in fibre strain

<during mechanical and environmental tests> level of strain that will not compromise fibre mechanical reliability for some of the parameters specified

Note 1 to entry: For 1 % proof-tested fibres, the fibre strain under long term tensile load (T_L) shall not exceed 20 % of this fibre proof strain (equal to absolute 0,2 % strain) and there shall be no change in attenuation during the test

Under short term tensile load (T_S) the fibre strain shall not exceed 60 % of the fibre proof strain and the attenuation change during test shall be measured and recorded.

Other criteria may be agreed between the customer and the supplier.

For fibres proof tested at higher levels the safe long-term load will not scale linearly with proof strain, so a lower percentage of the proof strain is applicable. For greater than 1 % up to 2 % proof-tested fibres, the strain at T_L shall be limited to 17 % of the proof-test strain (equal to absolute 0,34 % strain for 2 % proof tested fibres).

3.6 cable load definitions (non-aerial applications)

3.6.1 long term load

T_L
acceptable amount of long term load which the cable may experience during operation (i.e. after installation is completed)

Note 1 to entry: Long term load may be due to residual loading from the installation process and/or environmental effect. This is the rated maximum load for which a cable is subject to in long term tests.

3.6.2

short term load

T_s
 T_M

acceptable amount of short-term load that can be applied to a cable without permanent degradation of the characteristics of the fibres, cable elements or sheath

Note 1 to entry: Short term load is often called rated installation load.

3.7

cable load definitions and tensile testing terminology (self-supporting aerial applications)

3.7.1

maximum allowable tension

MAT

maximum tensile load that may be applied to the cable without detriment to the performance requirements (e.g. attenuation, fibre reliability) due to fibre strain

Note 1 to entry: Due to installation codes the MAT value is sometimes restricted to be less than 60 % of the breaking tension of the cable.

3.7.2

strain margin

value of cable elongation at the onset of fibre strain

Note 1 to entry: Strain margin may also be expressed as cable load (N) at the onset of fibre strain.

3.7.3

breaking tension

tensile load that will produce physical rupture of the cable

Note 1 to entry: The breaking tension may be calculated, provided that the design model has been validated.

3.7.4

maximum installation tension

MIT

maximum recommended stringing tension during installation

3.7.5

rated tensile strength

RTS

summation of the product of nominal cross-sectional area, nominal tensile strength and stranding factor for each load bearing material in the cable construction

Note 1 to entry: See IEC 60794-4:2003, Annex A for details of the recommended method to calculate breaking tension of OPGW.

3.7.6

creep

tendency of a solid material to slowly move or deform permanently under the influence of stress

Note 1 to entry: The information derived from creep testing may be used in the sag-tension calculations during the design layout of aerial optical cables used along electrical power lines.

3.8

cable section

individual reel of cable, as produced

3.9 fittings

hardware used for stringing and clipping of aerial cables to the structures (e.g. towers, poles) at the end of the installation procedure

Note 1 to entry: Suspension, dead end, vibration damper and bonding clamps hardware are designed for a specific size and/or type of aerial cable.

3.10 cable element

component of a cable designed to house and protect the optical fibres

Note 1 to entry: Changed from "fibre optic unit" in IEC 60794-4-10 to "cable element" to be consistent with IEC 60794-1-23 and also to avoid confusion with IEC 60794-5-20.

3.11 polarization mode dispersion (PMD) terms

3.11.1 differential group delay DGD

relative time delay between the two fundamental polarization modes (principal states of polarization) at the end of an optical fibre cable, at a particular time and wavelength

Note 1 to entry: Differential group delay is expressed in ps.

3.11.2 polarization mode dispersion (PMD) value average of DGD values across wavelengths

Note 1 to entry: The polarization mode dispersion value is expressed in ps.

3.11.3 polarization mode dispersion (PMD) coefficient PMD value of an optical fibre cable divided by the square root sum of its length (km)

Note 1 to entry: The polarization mode dispersion coefficient is expressed in ps/√km.

3.11.4 link length of cable composed of a number of individual cable sections

Note 1 to entry: Link PMD values are generally calculated according to the formulae given in IEC TR 61282-3:2006 but may be measured.

3.12 recovery time time allowed for any of the tests before performing the after test measurement

Note 1 to entry: For a practical interpretation, this is typically 5 minutes minimum.

3.13 Ruggedized cable cable having enhanced mechanical performances

3.14 terminated cable assembly length of cable provisioned with a connector at each end

Note 1 to entry: The following synonyms are used in ISO/IEC 11801: patch cords, work area cords and equipment cords.

3.15 aerial cable types

3.15.1 all dielectric self-supporting ADSS

cable that is capable to endure aerial installation and provide long term service, without any external tensile support

3.15.2 optical attached cable OPAC

dielectric cable that is not self-supported, but attached to an electrical earth wire or phase conductor, using one of the following attachment methods: wrapped, lashed or preform attached

3.15.3 wrapped

lightweight flexible non-metallic ("wrap") cable that can be wrapped helically around either the earth wire or the phase conductor using special machinery

3.15.4 lashed

non-metallic cables that are installed longitudinally alongside the earth wire, the phase conductor or on a separate support cable (on a pole route) and are held in position with a binder or adhesive cord

3.15.5 preform/spiral attached

cable similar to the lashed cables but attached with the use of special preformed spiral attachment clips

3.15.6 optical ground wire OPGW

metallic optical cable that has the dual performance functions of a conventional ground wire with telecommunication capabilities

3.16 composite cable

optical fibre cable containing more than one fibre category

3.17 hybrid cable

cable that contains more than one media type, including but not limited to optical fibres and/or twisted pair/quad cables and/or coaxial cables

3.18 rounding error

rule of "rounding half away from zero" when the results recorded display more than the significant number of digits required in the acceptance criteria

EXAMPLE 1: Against a requirement of 0,22 dB/km maximum attenuation, values up to 0,224 dB/km conform, whilst values of 0,225 dB/km and above are failures.

EXAMPLE 2: Against a requirement of $\pm 0,05$ dB, values between -0,054 and +0,054 are deemed acceptable.

3.19**maximum allowable ovality**

largest permissible ovality of the optical unit or its component calculated as: $(d1 - d2) / (d1 + d2)$ in % where:

$d1$ is the maximum measured diameter of the cable or the component;

$d2$ is the minimum diameter of the cable or the component at the same cross-section as $d1$.

3.20**breakout cable**

cable consisting of subunits which may be separate fibre optical cables surrounded by a sheath of suitable material

Note 1 to entry: In the application this outer sheath of the breakout cable can be removed over a certain length and the subunits can be used as separate fibre optic cables.

4 Graphical symbols and abbreviations

For the purposes of this document, the abbreviations given in IEC TR 61931 as well as the following apply

ADSS	all dielectric self-supporting
APL	aluminium/polyethylene laminate
ΔD	minimum wall thickness of a microduct
$\Delta D'$	minimum thickness of the outer sheath of a protected microduct
D	nominal outer diameter of a microduct cable
d	nominal outer diameter of a cable (including microduct fibre units)
d_c	nominal outer diameter of a conduit or subduct
DS	detail specification
ID	nominal inner diameter of a microduct
I/O-port	input/output port for launching OF cables into and out of a pipe
λ_{CC}	cable cut-off wavelength
$\lambda_{operational}$	operational wavelength
LDA	link design attenuation (tbd)
m	mass of 1 km of cable (in the context of tensile testing)
MAOC	maximum allowable ovality of cable
MAT	maximum allowable tension
MIT	maximum installation tension
$n \times d$	The product of a variable and the cable outer diameter used for determining appropriate sizes for bends, mandrels, etc.
$n \times OD$	The product of a variable and the outer diameter of a microduct used for determining appropriate sizes for bends, mandrels, etc.
$n \times OD'$	The product of a variable and the outer diameter of a protected microduct used for determining appropriate sizes for bends, mandrels, etc.
OD	nominal outer diameter of a microduct
OD'	nominal outer diameter of a protected microduct
OPAC	optical attached cable (or optical power attached cable)
OPGW	optical ground wire
PE	polyethylene