



**SLOVENSKI STANDARD**  
**SIST EN 4058:2002**

**01-januar-2002**

---

**Aerospace series - Filler rods and filler wires for welding in titanium and titanium alloys - Diameter 0,5 mm  $\leq$  D  $\leq$  5,0 mm - Dimensions**

Aerospace series - Filler rods and filler wires for welding in titanium and titanium alloys - Diameter 0,5 mm  $\leq$  D  $\leq$  5,0 mm - Dimensions

Luft- und Raumfahrt - Schweißzusatzstäbe und -drähte aus Titan und Titanlegierungen - Durchmesser 0,5 mm  $\leq$  D  $\leq$  5,0 mm - Maße

Série aérospatiale - Baguettes et fils d'apport de soudage en titane et alliages de titane - Diamètres 0,5 mm  $\leq$  D  $\leq$  5,0 mm - Dimensions

<https://standards.iteh.ai/catalog/standards/sist/6d0cb3e1-5369-4bde-80f5-74a25927f297/sist-en-4058-2002>

**Ta slovenski standard je istoveten z: EN 4058:2001**

---

**ICS:**

49.025.30 Titan Titanium

**SIST EN 4058:2002 en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 4058:2002

<https://standards.iteh.ai/catalog/standards/sist/6d0cb3e1-5369-4bde-80f5-74a25927f297/sist-en-4058-2002>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 4058**

September 2001

ICS 49.025.30

English version

**Aerospace series - Filler rods and filler wires for welding in  
titanium and titanium alloys - Diameter  $0,5 \text{ mm} \leq D \leq 5,0 \text{ mm}$  -  
Dimensions**

Série aérospatiale - Baguettes et fils d'apport de soudage  
en titane et alliages de titane - Diamètres  $0,5 \text{ mm} \leq D \leq 5,0$   
mm - Dimensions

Luft- und Raumfahrt - Schweißzusatzstäbe und -drähte aus  
Titan und Titanlegierungen - Durchmesser  $0,5 \text{ mm} \leq D \leq$   
5,0 mm - Maße

This European Standard was approved by CEN on 2 May 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/6d0cb3e1-5369-4bde-80f5-74a25927f297/sist-en-4058-2002>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2002, and conflicting national standards shall be withdrawn at the latest by March 2002.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

## 0 Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

## 1 Scope

This standard specifies the dimensions and tolerances of:

Filler rods and filler wires for welding  
in titanium and titanium alloys  
Diameter  $0,5 \text{ mm} \leq D \leq 5,0 \text{ mm}$

for aerospace applications.

## 2 Normatives references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 4258 Aerospace series – Metallic materials – General organization of standardization – Links between types of EN standards and their use

<https://standards.iteh.ai/catalog/standards/sist/6d0cb3e1-5369-4bde-80f5-74a25927f297/sist-en-4058-2002>

## 3 Form

See figure 1.




Figure 1

## 4 Recommended dimensions and mass

### 4.1 Diameter and mass

See table 1.

Table 1

Rod	Nominal <i>D</i> mm		Section mm <sup>2</sup>	Linear mass <sup>a</sup> g/m
		Wire		
–		0,5	0,20	9
–		0,6	0,28	13
0,8		0,8	0,50	23
–		0,9	0,64	29
1,0		1,0	0,79	36
1,2		1,2	1,13	51
1,6		1,6	2,01	91
2,0		2,0	3,14	141
2,4		–	4,52	203
3,0		3,0	7,07	318
3,2		3,2	8,04	362
4,0		–	12,57	566
5,0		–	19,63	883

<sup>a</sup> For information, calculated with a density of 4,5 kg/dm<sup>3</sup>

### 4.2 Length

The order shall specify if bars are to be supplied in fixed or in random lengths. In the event of a supply of random lengths the minimum and maximum values for the lengths shall be specified on the order.

Length of rods  $\leq 1\ 000$  mm.

Length of wires: to be specified on the order.

## 5 Tolerances

### 5.1 Dimensional tolerances

#### 5.1.1 Diameter

##### 5.1.1.1 Rods

See table 2.

Table 2

Dimensions in millimetres

Diameter	Tolerance
$0,8 \leq D \leq 5,0$	$\pm 0,1$

**5.1.1.2 Wires**

See table 3.

**Table 3**

Dimensions in millimetres

Diameter	Tolerances
$0,5 \leq D < 0,8$	+ 0,01 - 0,03
$0,8 \leq D < 2,8$	+ 0,01 - 0,04
$2,8 \leq D \leq 3,2$	+ 0,01 - 0,07

**5.1.2 Length**

Tolerances on length of rods:  $\pm 5$  mm.

**5.2 Geometric tolerances – Roundness**

Roundness shall be contained within the diameter tolerances.

ITeH STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN 4058:2002

<https://standards.iteh.ai/catalog/standards/sist/6d0cb3e1-5369-4bde-80f5-74a25927f297/sist-en-4058-2002>