



SLOVENSKI STANDARD
SIST EN 4059:2002

01-januar-2002

Aerospace series - Filler rods and filler wires for welding in steel - Diameter 0,5 mm < D < 5,0 mm - Dimensions

Aerospace series - Filler rods and filler wires for welding in steel - Diameter 0,5 mm < D < 5,0 mm - Dimensions

Luft- und Raumfahrt - Schweißzusatzstäbe und -drähte aus Stahl - Durchmesser 0,5 mm < D < 5,0 mm - Maße

Série aérospatiale - Baguettes et fils d'apport de soudage en acier - Diamètres 0,5 mm < D < 5,0 mm - Dimensions

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/12c1bce1-58dc-4dc9-a0a6-395382102096/sist-en-4059-2002>

Ta slovenski standard je istoveten z: EN 4059:2001

ICS:

49.025.10 Jekla Steels

SIST EN 4059:2002 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4059:2002

<https://standards.iteh.ai/catalog/standards/sist/12c1bce1-58dc-4dc9-a0a6-395382102096/sist-en-4059-2002>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 4059

June 2001

ICS 49.025.10

English version

**Aerospace series - Filler rods and filler wires for welding in steel
- Diameter $0,5 \text{ mm} \leq D \leq 5,0 \text{ mm}$ - Dimensions**

Série aérospatiale - Baguettes et fils d'apport de soudage
en acier - Diamètres $0,5 \text{ mm} \leq D \leq 5,0 \text{ mm}$ - Dimensions

Luft- und Raumfahrt - Schweißzusatzstäbe und -drähte aus
Stahl - Durchmesser $0,5 \text{ mm} \leq D \leq 5,0 \text{ mm}$ - Maße

This European Standard was approved by CEN on 2 May 2001.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 4059:2002](https://standards.iteh.ai/catalog/standards/sist/12c1bce1-58dc-4dc9-a0a6-395382102096/sist-en-4059-2002)

<https://standards.iteh.ai/catalog/standards/sist/12c1bce1-58dc-4dc9-a0a6-395382102096/sist-en-4059-2002>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This European Standard has been prepared by the European Association of Aerospace Manufacturers (AECMA).

After inquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2001, and conflicting national standards shall be withdrawn at the latest by December 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

0 Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

1 Scope

This standard specifies the dimensions and tolerances of:

Filler rods and filler wires for welding
in steel
Diameter $0,5 \text{ mm} \leq D \leq 5,0 \text{ mm}$

for aerospace applications.

2 Normative references

This European Standard incorporates by dated or undated reference provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

EN 4258 Aerospace series – Metallic materials – General organization of standardization – Links between types of EN standards and their use

<https://standards.iteh.ai/catalog/standards/sist/12c1bce1-58dc-4dc9-a0a6-395382102096/sist-en-4059-2002>

3 Form

See figure 1.




Figure 1

4 Recommended dimensions and mass

4.1 Diameter and mass

See table 1.

Table 1

Rod	Nominal D mm		Section mm ²	Linear mass ^a g/m
		Wire		
–		0,5	0,20	16
–		0,6	0,28	22
0,8		0,8	0,50	39
–		0,9	0,64	50
1,0		1,0	0,79	62
1,2		1,2	1,13	89
1,6		1,6	2,01	158
2,0		2,0	3,14	247
2,4		–	4,52	355
3,0		3,0	7,07	555
3,2		3,2	8,04	631
4,0		4,0	12,57	987
5,0		5,0	19,63	1 541

^a For information, calculated with a density of 7,85 kg/dm³

4.2 Length

The order shall specify if bars are to be supplied in fixed or in random lengths. In the event of a supply of random lengths the minimum and maximum values for the lengths shall be specified on the order.

Length of rods $\leq 1\ 000$ mm.

Length of wires: to be specified on the order.

5 Tolerances

5.1 Dimensional tolerances

5.1.1 Diameter

5.1.1.1 Rods

See table 2.

Table 2

Dimensions in millimetres

Diameter	Tolerance
$0,8 \leq D \leq 5,0$	$\pm 0,1$

5.1.1.2 Wires

See table 3.

Table 3

Dimensions in millimetres

Diameter	Tolerances
$0,5 \leq D < 0,8$	+ 0,01 - 0,03
$0,8 \leq D < 2,8$	+ 0,01 - 0,04
$2,8 \leq D \leq 5,0$	+ 0,01 - 0,07

5.1.2 Length

Tolerances on length of rods: ± 5 mm.

5.2 Geometric tolerances – Roundness

Roundness shall be contained within the diameter tolerances.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4059:2002

<https://standards.iteh.ai/catalog/standards/sist/12c1bce1-58dc-4dc9-a0a6-395382102096/sist-en-4059-2002>