

INTERNATIONAL STANDARD



Secondary cells and batteries containing alkaline or other non-acid electrolytes – ~~Portable sealed rechargeable single cells~~ Secondary sealed cells and batteries for portable applications –
Part 2: Nickel-metal hydride

IEC 61951-2:2017

<https://standards.iteh.ai/catalog/standards/iec/2ba2c0d1-1a5a-49bf-b5b1-593589ba1d53/iec-61951-2-2017>



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2017 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
Fax: +41 22 919 03 00
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: csc@iec.ch.

[IEC 61951-2:2017](https://standards.iteh.ai/catalog/standards/iec/2ba2c0d1-1a5a-49bf-b5b1-593589ba1d53/iec-61951-2-2017)

<https://standards.iteh.ai/catalog/standards/iec/2ba2c0d1-1a5a-49bf-b5b1-593589ba1d53/iec-61951-2-2017>



IEC 61951-2

Edition 4.0 2017-03
REDLINE VERSION

INTERNATIONAL STANDARD



Secondary cells and batteries containing alkaline or other non-acid electrolytes – ~~Portable sealed rechargeable single cells~~ Secondary sealed cells and batteries for portable applications –
Part 2: Nickel-metal hydride

[IEC 61951-2:2017](https://standards.iteh.ai/catalog/standards/iec/2ba2c0d1-1a5a-49bf-b5b1-593589ba1d53/iec-61951-2-2017)

<https://standards.iteh.ai/catalog/standards/iec/2ba2c0d1-1a5a-49bf-b5b1-593589ba1d53/iec-61951-2-2017>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 29.220.30

ISBN 978-2-8322-4140-0

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	5
1 Scope.....	7
2 Normative references	7
3 Terms and definitions	7
4 Parameter measurement tolerances	9
5 Cell and battery designation and marking	10
5.1 Cell and battery designation.....	10
5.1.1 Small prismatic cells and cylindrical cells.....	10
5.1.2 Button cells.....	11
5.1.3 Batteries.....	12
5.2 Cell or battery termination.....	12
5.3 Marking.....	12
5.3.1 Small prismatic cells and cylindrical cells.....	12
5.3.2 Button cells.....	13
5.3.3 Batteries.....	13
5.4 Exemption of wording.....	13
6 Dimensions.....	13
6.1 Small prismatic cells and cylindrical cells.....	13
6.1.1 General.....	13
6.1.2 Small prismatic cells.....	14
6.1.3 Cylindrical cells.....	14
6.2 Button cells.....	16
6.3 9 V type nickel-metal hydride batteries.....	17
7 Electrical tests.....	18
7.1 General.....	18
7.2 Charging procedure for test purposes	18
7.2.1 Charging procedure for cell.....	18
7.2.2 Charging procedure for battery	18
7.3 Discharge performance	18
7.3.1 General	18
7.3.2 Discharge performance at 20 °C	19
7.3.3 Discharge performance at 0 °C.....	20
7.3.4 Discharge performance for rapid charge cells (R cells)	21
7.4 Charge (capacity) retention.....	21
7.5 Endurance	22
7.5.1 Endurance in cycles.....	22
7.5.2 Permanent charge endurance.....	25
7.6 Charge acceptance at constant voltage.....	29
7.7 Overcharge.....	29
7.7.1 Small prismatic, L, M, H, X, LS or MS cylindrical, and button cells.....	29
7.7.2 LT/LU, MT/MU or HT/HU cylindrical cells.....	30
7.7.3 J cylindrical cells	30
7.7.4 JT cylindrical cells	30
7.7.5 R cylindrical cells.....	31
7.8 Safety device operation	31
7.9 Surface temperature limitation device operation (for S cell only)	31

7.10	Storage	32
7.10.1	Button cells or batteries, small prismatic cells or batteries, cylindrical cells or batteries	32
7.10.2	Button cells or batteries, small prismatic cells or batteries, cylindrical cells or batteries (high recovery type)	33
7.11	Charge acceptance at +55 °C for LT, MT or HT cylindrical cells	34
7.12	Trickle charge acceptance for JT cylindrical cells	35
7.13	Internal resistance	35
7.13.1	General	35
7.13.2	Measurement of the internal AC resistance	36
7.13.3	Measurement of the internal DC resistance	36
8	Mechanical tests	37
9	Safety requirements	37
10	Type approval and batch acceptance	37
10.1	General	37
10.2	Type approval	37
10.2.1	Type approval for small prismatic cells and button cells	37
10.2.2	Type approval for cylindrical cells	41
10.2.3	Type approval for batteries	43
10.3	Batch acceptance	44
	Bibliography	46
	Figure 1 – Jacketed cylindrical cells	14
	Figure 2 – Jacketed small prismatic cells	14
	Figure 3 – Jacketed cells dimensionally interchangeable with primary cells	15
	Figure 4 – Button cells	17
	Figure 5 – 9 V type nickel-metal hydride batteries	17
	Table 1 – Dimensions of jacketed small prismatic cells	14
	Table 2 – Dimensions of jacketed cylindrical cells dimensionally interchangeable with primary cells	15
	Table 3 – Dimensions of jacketed cylindrical cells not dimensionally interchangeable with primary cells	16
	Table 4 – Dimensions of button cells	17
	Table 5 – Dimensions of 9 V type nickel-metal hydride batteries	18
	Table 6 – Discharge performance at 20 °C for small prismatic cells and cylindrical cells	19
	Table 7 – Discharge performance at 20 °C for button cells	19
	Table 8 – Discharge performance at 20 °C for batteries	20
	Table 9 – Rated capacity (mAh) compliance test (example)	20
	Table 10 – Discharge performance at 0 °C for small prismatic cells and cylindrical cells	21
	Table 11 – Discharge performance at 0 °C for button cells	21
	Table 12 – Endurance in cycles for small prismatic, button and cylindrical cells not dimensionally interchangeable with primary cells	22
	Table 13 – Endurance in cycles for H or X cells	23
	Table 14 – Endurance in cycles for X cells	23
	Table 15 – Endurance in cycles for HR or XR cells	24

Table 16 – Endurance in cycles for cylindrical cells dimensionally interchangeable with primary cells	24
Table 17 – Permanent charge endurance for L, M, H or X cells	25
Table 18 – Permanent charge endurance for LT, MT or HT cells	27
Table 19 – Permanent charge endurance for LU, MU or HU cells	29
Table 20 – Overcharge at 0 °C	30
Table 21 – Capacity deterioration due to storage period for cells or batteries	33
Table 22 – Capacity deterioration due to storage period for cells or batteries (high recovery type)	34
Table 23 – Charge and discharge at +55 °C	35
Table 24 – Trickle charge acceptance for JT cylindrical cells	35
Table 25 – Constant discharge currents used for measurement of DC resistance	37
Table 26 – Sequence of tests for type approval for small prismatic and for button cells	38
Table 27 – Sequence of tests for type approval for small prismatic cells (high recovery type)	39
Table 28 – Sequence of tests for type approval for button cells	40
Table 29 – Sequence of tests for type approval for button cells (high recovery type)	41
Table 30 – Sequence of tests for type approval for cylindrical cells	42
Table 31 – Sequence of tests for type approval for cylindrical cells (high recovery type)	43
Table 32 – Sequence of tests for type approval for batteries	44
Table 33 – Sequence of tests for type approval for batteries (high recovery type)	44
Table 34 – Recommended test sequence for batch acceptance	45

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SECONDARY CELLS AND BATTERIES CONTAINING
ALKALINE OR OTHER NON-ACID ELECTROLYTES –
~~PORTABLE SEALED RECHARGEABLE SINGLE CELLS~~ SECONDARY
SEALED CELLS AND BATTERIES FOR PORTABLE APPLICATIONS –

Part 2: Nickel-metal hydride

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.

International Standard IEC 61951-2 has been prepared by subcommittee 21A: Secondary cells and batteries containing alkaline or other non-acid electrolytes, of IEC technical committee 21: Secondary cells and batteries.

This fourth edition cancels and replaces the third edition published in 2011 of which it constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- addition of battery type;
- addition of 'F' (high recovery type) designation for cells and batteries;
- addition of 'I' (low self-discharge type) designation for cells;
- revision of Figure 3 (6.1.3.1);
- addition of "optional pip" note to positive contact;
- changed leader line position from pip to flats of positive contact (B and G).

The text of this standard is based on the following documents:

FDIS	Report on voting
21A/623/FDIS	21A/629/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61951 series can be found, under the general title *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Secondary sealed cells and batteries for portable applications*, on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.

**SECONDARY CELLS AND BATTERIES CONTAINING
ALKALINE OR OTHER NON-ACID ELECTROLYTES –
~~PORTABLE SEALED RECHARGEABLE SINGLE CELLS~~ **SECONDARY
SEALED CELLS AND BATTERIES FOR PORTABLE APPLICATIONS –****

Part 2: Nickel-metal hydride

1 Scope

This part of IEC 61951 specifies marking, designation, dimensions, tests and requirements for ~~portable secondary~~ sealed nickel-metal hydride small prismatic, cylindrical and button ~~rechargeable single~~ cells and batteries, suitable for use in any orientation, for portable applications.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-482:2004, *International Electrotechnical Vocabulary (IEV) – Part 482: Primary and secondary cells and batteries*

~~IEC 60086 (all parts), Primary batteries~~

IEC 60086-1 ~~(2006)~~, *Primary batteries – Part 1: General*

IEC 60086-2 ~~(2006)~~, *Primary batteries – Part 2: Physical and electrical specifications*

~~IEC 60410, Sampling plans and procedures for inspection by attributes~~

IEC 61959, *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Mechanical tests for sealed portable secondary cells and batteries*

IEC 62133-1, *Secondary cells and batteries containing alkaline or other non-acid electrolytes – Safety requirements for portable sealed secondary cells and for batteries made from them, for use in portable applications – Part 1: Nickel systems*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-482 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1 nominal voltage

suitable approximate value of the voltage used to designate or identify ~~the voltage of~~ a cell or a battery

Note 1 to entry: The nominal voltage of a sealed nickel-metal hydride rechargeable single cell is 1,2 V.

Note 2 to entry: The nominal voltage of a battery of n series connected cells is equal to n times the nominal voltage of a single cell.

[SOURCE: IEC 60050-482:2004, 482-03-31, modified – Addition of Notes 1 and 2 to entry.]

3.2 rated capacity

capacity value of a cell or battery determined under specified conditions and declared by the manufacturer

Note 1 to entry: The rated capacity is the quantity of electricity C_5 Ah (ampere-hours) declared by the manufacturer which a single cell can deliver during a 5 h period when charging, storing and discharging under the conditions specified in 7.3.2.

Note 2 to entry: The capacity of a battery is the quantity of electricity C_5 Ah (ampere-hours) declared by the manufacturer which a battery can deliver during a 5 h period, when charged, stored and discharged under the procedure described in 7.3.2.

[SOURCE: IEC 60050-482:2004, 482-03-15, modified – Addition of Notes 1 and 2 to entry.]

3.3 small prismatic cell

cell in the form of a rectangular parallelepiped whose width and thickness dimensions are not more than 25 mm

3.4 cylindrical cell

cell of circular cross-section in which the overall height is equal to, or greater than the overall diameter

3.5 button cell

cell of circular cross-section in which the overall height is less than the overall diameter

3.6 nickel-metal hydride cell

cell containing a nickel hydroxide compound for the positive electrode, a hydrogen absorbing alloy for the negative electrode, and potassium hydroxide or other alkaline solution as electrolyte

Note 1 to entry: Positive electrodes are isolated from negative electrodes by a separator

3.7 nickel-metal hydride battery

assembly of secondary cell(s) as a source of electrical energy characterized by its voltage, size, terminal arrangement, capacity and rate capability

3.8 sealed cell

cell which remains closed and does not release either gas or liquid when operated within the limits of charge and temperature specified by the manufacturer

Note 1 to entry: The cell is equipped with a safety device to prevent dangerously high internal pressure.

Note 2 to entry: The cell does not require addition to the electrolyte and is designed to operate during its life in its original sealed state.

Note 3 to entry: The nickel-metal hydride cell, however, may release gas towards the end of its life due to the accumulation of hydrogen in the cell.

[SOURCE: IEC 60050-482:2004, 482-05-17, modified – The existing note has been developed into Notes 1, 2 and 3 to entry.]

3.9

portable cell

cell designed mainly for use in an easily hand-carried battery

3.10

battery for portable applications

battery for use in device or appliance which is conveniently hand-carried

3.11

surface temperature limited cell

cell which performs a function that prevents the temperature increase from a certain standard point even at the moment of ~~anomaly~~ an abnormal occurrence such as short circuit of cell

3.12

high recovery type cell or battery

cell or battery which has lower “permanent capacity loss” than normal type after storage

Note 1 to entry: It is defined as “high recovery type” in 7.10.2, Table 22.

3.13

low self-discharge type cell

cell which is able to retain higher charge capacity than normal type after storage by reducing self-discharge

Note 1 to entry: It is defined as “low self-discharge type” in 7.4.

3.14

9 V type nickel-metal hydride battery

nickel-metal hydride battery which is interchangeable with 9 V primary batteries and is composed of cylindrical cells, small prismatic cells or button cells

4 Parameter measurement tolerances

The overall accuracy of controlled or measured values, relative to the specified or actual values, shall be within the following tolerances:

- a) ± 1 % for voltage;
- b) ± 1 % for current;
- c) ± 1 % for capacity;
- d) ± 2 °C for temperature;
- e) $\pm 0,1$ % for time;
- f) $\pm 0,1$ mm for dimensions;
- g) $\pm 2,5$ % for humidity.

These tolerances comprise the combined accuracy of the measuring instruments, the measurement techniques used and all other sources of error in the test procedure.

The details of the instrumentation used shall be provided in each report of results.

5 Cell and battery designation and marking

5.1 Cell and battery designation

5.1.1 Small prismatic cells and cylindrical cells

5.1.1.1 General

Sealed nickel-metal hydride small prismatic rechargeable single cells and cylindrical rechargeable single cells shall be designated by a letter L, M, J, H or X which signifies:

- low rate of discharge (L);
- medium rate of discharge (M);
- medium high rate of discharge (J);
- high rate of discharge (H);
- very high rate of discharge (X).

NOTE 1 These cells are typically but not exclusively used for the following discharge rates:

- L up to $0,5 I_t$ A;
- M up to $3,5 I_t$ A;
- J up to $5,0 I_t$ A;
- H up to $7,0 I_t$ A;
- X up to and above $7,0 I_t$ A.

NOTE 2 These currents are expressed as multiples of I_t A, where I_t A = C_5 Ah/1 h (see IEC 61434).

When a cell is intended for permanent charge at elevated temperatures, typically higher than $40\text{ }^\circ\text{C}$, a letter "T" is placed after the letter L, M, J, H or X.

When a cell is intended for permanent charge at elevated temperatures, typically higher than $50\text{ }^\circ\text{C}$, a letter "U" is placed after the letter L, M, J, H or X.

When a cell is intended for surface temperature limitation, a letter "S" is placed after the letter L or M.

When a cell is intended for rapid charge, typically at $1,0 I_t$ A, a letter "R" is placed after the letter L, M, J, H or X.

When a cell or battery is intended as a high recovery type, a letter "F" is placed after the letter L, M, J, H or X.

When a cell is intended as a low self-discharge cell, a letter "I" is placed after the letter L, M, J, H or X.

5.1.1.2 Small prismatic cells

Sealed nickel-metal hydride small prismatic rechargeable single cells shall be designated by the letters "HF" followed by a letter L, M, J, H or X followed by letter F, followed by, if designated, letter I, followed by three groups of figures, each group being separated by a solidus, as follows:

- a) The two figures to the left of the first solidus shall indicate the maximum width specified for the cell, expressed in millimetres, rounded up to the next whole number.
- b) The two figures in the middle shall indicate the maximum thickness specified for the cell, expressed in millimetres, rounded up to the next whole number.

- c) The two figures to the right of the second solidus shall indicate the maximum height specified for the cell, expressed in millimetres, rounded up to the next whole number.

EXAMPLE HFLF 18/07/49 designation identifies a small prismatic cell of low discharge rate capability, **high recovery type** with a maximum width of 18 mm, a maximum thickness of 7 mm and a maximum height of 49 mm.

5.1.1.3 Cylindrical cells

Sealed nickel-metal hydride cylindrical rechargeable single cells shall be designated by the letters "HR" followed by a letter L, M, J, H or X **followed by letter F, followed by, if designated, letter I**, followed by two groups of figures, each group being separated by a solidus, as follows:

- a) The two figures to the left of the solidus shall indicate the maximum diameter specified for the cell, expressed in millimetres, rounded up to the next whole number.
- b) The two figures to the right of the solidus shall indicate the maximum height specified for the cell, expressed in millimetres, rounded up to the next whole number.

When a manufacturer designs a cell with dimensions and tolerances which make it interchangeable with a primary cell, the designation of Table 2 shall also be marked on the cell.

EXAMPLE 1 HRLF 33/62 designation identifies a cylindrical cell of low discharge rate capability, **high recovery type** with a maximum diameter of 33 mm and a maximum height of 61,5 mm.

EXAMPLE 2 HRLTF 33/62 designation identifies a cylindrical cell of low discharge rate capability, intended for permanent charge at elevated temperatures, **high recovery type**, with a maximum diameter of 33 mm and a maximum height of 61,5 mm.

EXAMPLE 3 HRXRFI 23/43 designation identifies a cylindrical cell of very high discharge rate capability, intended for rapid charge, **high recovery type, low self-discharge type** with a maximum diameter of 23 mm and a maximum height of 43 mm.

For cells dimensionally interchangeable with primary cells, the following single or double figures following the letter ~~L, M, R or S~~ **F or I** may indicate:

- 20- Size D;
- 14- Size C;
- 6- Size AA;
- 03- Size AAA.

NOTE Cells dimensionally interchangeable with primary cells correspond to M type unless otherwise specified

For the purpose of this explanation, an example is given below.

EXAMPLE 4 HRMRFI03 designation identifies a sealed nickel-metal hydride cylindrical rechargeable single cell, of medium discharge rate capability, also intended for rapid charge, **high recovery type and low self-discharge type**, dimensionally interchangeable with primary cell and whose type designation is AAA.

5.1.2 Button cells

Sealed nickel-metal hydride button rechargeable single cells shall be designated by the letters "HB" **followed by letter F, followed by, if designated, letter I**, followed by two groups of figures, **each group being** separated by a solidus, as follows:

- a) The three figures to the left of the solidus shall indicate the maximum diameter specified for the cell, expressed in tenths of millimetres, rounded up to the next whole number.
- b) The three figures to the right of the solidus shall indicate the maximum height specified for the cell, expressed in tenths of millimetres, rounded up to the next whole number.

EXAMPLE HBFI 116/054 designation identifies a button cell, **intended as a high recovery type, low self-discharge type**, with a maximum diameter of 11,6 mm and a maximum height of 5,4 mm.

5.1.3 Batteries

Sealed nickel-metal hydride rechargeable batteries shall be designated with the following form:

N1 single cell designation – N2

where

N1 is the number of series connected cells in the battery;

N2 is the number of parallel connected cells if 2 or greater (not shown if value is 1).

Sealed nickel-metal hydride battery designation will be identified based on single cells within the series and not the battery as a whole.

- **Small prismatic cells in battery**

EXAMPLE 1 2HFLF 18/07/49 designation identifies a small prismatic cell of low discharge rate capability, high recovery type with a maximum width of 18 mm, a maximum thickness of 7 mm and a maximum height of 49 mm with two series connected cells.

- **Cylindrical cells in battery**

EXAMPLE 2 3HRLF 33/62 designation identifies a cylindrical cell of low discharge rate capability, high recovery type with a maximum diameter of 33 mm and a maximum height of 61,5 mm with three series connected cells.

EXAMPLE 3 4HRLTF 33/62 designation identifies a cylindrical cell of low discharge rate capability, intended for permanent charge at elevated temperatures, high recovery type, with a maximum diameter of 33 mm and a maximum height of 61,5 mm with four series connected cells.

EXAMPLE 4 HRXRFI 23/43 -2 designation identifies a cylindrical cell of very high discharge rate capability, intended for rapid charge, high recovery type, low self-discharge type with a maximum diameter of 23 mm and a maximum height of 43 mm with two parallel connected cells.

- **Cells interchangeable with primary cells in batteries**

EXAMPLE 5 HRMRFI03-3 designation identifies a sealed nickel-metal hydride cylindrical rechargeable single cell, of medium discharge rate capability, also intended for rapid charge, high recovery type and low self-discharge type, dimensionally interchangeable with primary cell whose type designation is AAA with three parallel connected cells.

- **Button cells in battery**

EXAMPLE 6 HB 116/054-3 designation identifies a button cell, with a maximum diameter of 11,6 mm and a maximum height of 5,4 mm with three parallel connected cells.

5.2 Cell or battery termination

This standard does not specify cell or battery termination.

5.3 Marking

5.3.1 Small prismatic cells and cylindrical cells

Each jacketed cell supplied without connections shall carry durable markings giving the following minimum information:

- sealed rechargeable nickel-metal hydride or Ni-MH;
- ~~designation as specified in 5.1 (in addition, it is permissible for a manufacturer to use his own type designation);~~
- rated capacity;
- nominal voltage;
- ~~recommended charge rate and time or permanent charge current for "T" cells;~~
- polarity (+ and –);
- date of manufacture (which may be in code);
- name or identification of manufacturer or supplier;
- mark for promoting useful use of cell resources.