



Designation: D 5817 – 03

Standard Practice for Carbon Black, Pelleted—Reduction, Blending, and Drying of Gross Samples for Testing¹

This standard is issued under the fixed designation D 5817; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice describes the procedure for blending of pelleted carbon black, the procedure for the reduction of gross samples of pelleted carbon black to the appropriate size for testing and the preparation of the sample for testing. These techniques are intended to minimize variations in measured characteristics between test samples. Standard terminology relating to carbon black samples is found in Terminology D 3053.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 412 Test Methods for Vulcanized Rubber and Thermoplastic Elastomers—Tension²
- D 1506 Test Methods for Carbon Black—Ash Content²
- D 1508 Test Method for Carbon Black, Pelleted Fines and Attrition²
- D 1509 Test Methods for Carbon Black—Heating Loss²
- D 1510 Test Method for Carbon Black—Iodine Adsorption Number²
- D 1511 Test Method for Carbon Black—Pellet Size Distribution²
- D 1512 Test Methods for Carbon Black—pH Value²
- D 1513 Test Method for Carbon Black, Pelleted—Pour Density²
- D 1514 Test Method for Carbon Black—Sieve Residue²

- D 1618 Test Method for Carbon Black Extractables—Transmittance of Toluene Extract²
- D 1619 Test Methods for Carbon Black—Sulfur Content²
- D 1765 Classification System for Carbon Blacks Used in Rubber Products²
- D 1799 Practice for Carbon Black—Sampling Packaged Shipments²
- D 1900 Practice for Carbon Black—Sampling Bulk Shipments²
- D 2414 Test Method for Carbon Black—Oil Absorption Number²
- D 3053 Terminology Relating to Carbon Black²
- D 3191 Test Methods for Carbon Black in SBR (Styrene-Butadiene Rubber)—Recipe and Evaluation Procedures²
- D 3192 Test Methods for Carbon Black Evaluation in NR (Natural Rubber)²
- D 3265 Test Method for Carbon Black—Tint Strength²
- D 3493 Test Method for Carbon Black—Oil Absorption Number of Compressed Sample²
- D 5230 Test Method for Carbon Black—Automated Individual Pellet Hardness²
- D 6556 Test Method for Carbon Black—Total and External Surface Area by Nitrogen Adsorption²

3. Summary of Test Methods

3.1 Test Method A—Reduction of Sample Size:

3.1.1 The gross bulk sample is poured through the riffle sample splitter. A portion of the sample is reintroduced into the splitter as many times as necessary to reduce the gross sample to the size desired for the intended test portion. The test portion may not be homogeneous.

3.2 Test Method B—Blending of Carbon Black:

3.2.1 The gross sample is poured through the riffle sample splitter a minimum of four times in a specific sequence to prepare a homogeneous test portion. The black must be cross-blended to accomplish a homogeneous portion for testing.

3.3 Test Method C—Drying of Carbon Black:

3.3.1 For all test methods listed in Section 2 except: the Fines and Attrition (Test Method D 1508), Heating Loss (Test Methods D 1509), Pellet Size Distribution (Test Method

¹ This practice is under the jurisdiction of ASTM Committee D24 on Carbon Black and is the direct responsibility of Subcommittee D24.61 on Carbon Black Sampling and Statistical Analysis.

Current edition approved Jan. 10, 2003. Published February 2003. Originally approved in 1995. Last previous edition approved in 1996 as D 5817 – 96.

² *Annual Book of ASTM Standards*, Vol 09.01.