



**SLOVENSKI STANDARD**  
**SIST EN ISO 10308:2006**

**01-marec-2006**

**BUXca Yý U**

**SIST EN ISO 10308:1999**

---

**Kovinske prevleke – Pregled preskusov za ugotavljanje poroznosti (ISO 10308:2006)**

Metallic coatings - Review of porosity tests (ISO 10308:2006)

Metallische Überzüge - Übersicht der Porenprüfverfahren (ISO 10308:2006)

Revetements métalliques - Passage en revue des essais de porosité (ISO 10308:2006)

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-fébb5440bda4/sist-en-iso-10308-2006>

**Ta slovenski standard je istoveten z: EN ISO 10308:2006**

---

**ICS:**

25.220.40

Kovinske prevleke

Metallic coatings

**SIST EN ISO 10308:2006**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 10308:2006](#)

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-febb5440bda4/sist-en-iso-10308-2006>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN ISO 10308**

January 2006

ICS 25.220.40

Supersedes EN ISO 10308:1997

English Version

**Metallic coatings - Review of porosity tests (ISO 10308:2006)**

Revêtements métalliques - Passage en revue des essais  
de porosité (ISO 10308:2006)

Metallische Überzüge - Übersicht der Porenprüfverfahren  
(ISO 10308:2006)

This European Standard was approved by CEN on 28 December 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

**ITih STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-fébb5440bda4/sist-en-iso-10308-2006>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**EN ISO 10308:2006 (E)****Foreword**

This document (EN ISO 10308:2006) has been prepared by Technical Committee ISO/TC 107 "Metallic and other inorganic coatings" in collaboration with Technical Committee CEN/TC 262 "Metallic and other inorganic coatings", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2006, and conflicting national standards shall be withdrawn at the latest by July 2006.

This document supersedes EN ISO 10308:1997.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

**Endorsement notice**

The text of ISO 10308:2006 has been approved by CEN as EN ISO 10308:2006 without any modifications.

**(standards.iteh.ai)**

[SIST EN ISO 10308:2006](https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006)

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006>

INTERNATIONAL  
STANDARD

ISO  
10308

Second edition  
2006-01-15

---

---

**Metallic coatings — Review of porosity tests**

*Revêtements métalliques — Passage en revue des essais de porosité*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 10308:2006](https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-fèbb5440bda4/sist-en-iso-10308-2006)

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-fèbb5440bda4/sist-en-iso-10308-2006>



Reference number  
ISO 10308:2006(E)

© ISO 2006

**ISO 10308:2006(E)****PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 10308:2006](https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006)

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006>

© ISO 2006

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Contents

Page

Foreword.....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Normative references .....</b>	<b>1</b>
<b>3 Terms and definitions.....</b>	<b>1</b>
<b>4 Principle.....</b>	<b>2</b>
<b>5 Common features of porosity tests .....</b>	<b>2</b>
<b>6 Test specimens .....</b>	<b>2</b>
<b>7 Specific porosity tests.....</b>	<b>2</b>
7.1 Alizarin test.....	2
7.2 Anthraquinone test.....	3
7.3 Cadmium sulfide test.....	3
7.4 Copper sulfate (Preece) test .....	3
7.5 Copper sulfate (Dupernell) test .....	3
7.6 Corrodkote test (CORR) .....	4
7.7 Electrographic tests .....	4
7.8 Ferrocyanide test .....	5
7.9 Ferron test .....	5
7.10 Ferroxyl test .....	6
7.11 Flowers-of-sulfur porosity test.....	6
7.12 Hot-water test .....	6
7.13 Hydrogen sulfide or sulfur dioxide/hydrogen sulfide test.....	6
7.14 Haematoxylin test .....	7
7.15 Magneson test.....	7
7.16 Nitric acid vapour test .....	7
7.17 Oxine test.....	8
7.18 Permanganate test.....	8
7.19 Polysulfide test .....	8
7.20 Porotest test .....	8
7.21 Salt spray tests [neutral (NSS), acetic (AASS) and cuproacetic (CASS)] .....	9
7.22 Sulfur dioxide test.....	9
7.23 Sulfurous acid/sulfur dioxide vapour test.....	9
7.24 Thiocyanate test.....	9
7.25 Thioacetamide test (TAA) .....	10
7.26 Watch-case acetic acid test.....	10
7.27 Watch-case sodium bisulfite test.....	10
<b>Annex A (normative) Tables of porosity tests.....</b>	<b>11</b>
<b>Annex B (informative) Typical report and evaluation of porosity tests .....</b>	<b>14</b>
<b>Annex C (informative) Schematic representation of types of pore .....</b>	<b>16</b>
<b>Annex D (informative) Classification of discontinuities in metallic and other inorganic coatings .....</b>	<b>17</b>
<b>Annex E (informative) Classification of methods of testing coating porosity .....</b>	<b>18</b>
<b>Annex F (informative) Alphabetical list of tests by substrate and coating .....</b>	<b>19</b>
<b>Bibliography .....</b>	<b>30</b>

**ISO 10308:2006(E)****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10308 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 7, *Corrosion tests*.

This second edition cancels and replaces the first edition (ISO 10308:1995), which has been technically revised.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 10308:2006  
<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006>



# Metallic coatings — Review of porosity tests

**WARNING —** This international Standard calls for the use of substances and/or procedures that can be injurious to health if adequate precautions are not taken. It refers only to technical suitability and in no way absolves either the designer, the producer, the supplier or the user from statutory and all other legal obligations relating to health and safety at any stage of manufacture or use.

## 1 Scope

This International Standard reviews published methods for revealing pores (see ISO 2080) and discontinuities in coatings of aluminium, anodized aluminium, brass, cadmium, chromium, cobalt, copper, gold, indium, lead, nickel, nickel-boron, nickel-cobalt, nickel-iron, nickel-phosphorus, palladium, platinum, vitreous or porcelain enamel, rhodium, silver, tin, tin-lead, tin-nickel, tin-zinc, zinc and chromate or phosphate conversion coatings (including associated organic films) on aluminium, beryllium-copper, brass, copper, iron, NiFeCo alloys, magnesium, nickel, nickel-boron, nickel-phosphorus, phosphor-bronze, silver, steel, tin-nickel and zinc alloy basis metal.

The tests summarized in this International Standard are designed to react with the substrate when exposed, by a discontinuity, in such a way as to form an observable reaction product.

NOTE 1 Pores are usually perpendicular to the coating surface but may be inclined to the coating surface. They are frequently cylindrical in shape but may also assume a twisted shape (see Annex C).

NOTE 2 Porosity may vary in size from the submicroscopic, invisible using a light microscope, to the microscopic, visible from  $\times 10$  to  $\times 1\,000$ , to the macroscopic, visible to the naked eye.

NOTE 3 Porosity may be visibly indicated by discolouration of the coated surface.

NOTE 4 Porosity in a coating is not always detrimental. In microdiscontinuous chromium, for example, porosity or microcracking is beneficial and tests are conducted to indicate the pores.

NOTE 5 Results obtained from porosity tests, expressed in terms such as pores per square centimeter, are relative values associated with the specific test method used and the magnification used during examination. Annex B gives typical report criteria.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2080:1981, *Electroplating and related processes — Vocabulary*

ISO 10289:1999, *Methods for corrosion testing of metallic and other inorganic coatings on metallic substrates — Rating of test specimens and manufactured articles subjected to corrosion tests*

## 3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 2080 and the following apply.

**ISO 10308:2006(E)**

**3.1 discontinuities**  
 cracks, micro-holes, pits, scratches or any other opening in the coating surface that exposes a different underlying metal

NOTE For further information on discontinuities, see Annex D and reference [1] in the Bibliography.

**4 Principle**

The results of porosity tests are the end products of a chemical reaction with a metallic substrate. Some occur *in situ*, others on paper or in a gel coating. Observations are made that are consistent with the test method and the items being tested, as specified by the purchaser. These may be visual inspections (naked eye) or at  $\times 10$  magnification (microscope). Other methods may involve enlarged photographs or photo-micrographs. See references [1,2, 3, 5 and 6] in the Bibliography (see also Annex A for a tabular summary of the porosity tests and Annex D for a classification of discontinuities).

**5 Common features of porosity tests**

Porosity tests differ from corrosion tests and, particularly, ageing tests regarding test duration. Porosity tests are primarily short-time tests. A good porosity test process shall clean, depolarize and activate the substrate metal exposed by the pore and attack it to such a degree as to cause the reaction product to fill the pore to the surface of the coating. The corrosive shall not react with the coating. It is essential that the time of reaction be limited, particularly with thin coatings, since the corrosive will attack the substrate in all directions and, in so doing, will undermine the coatings resulting in misleading observations. When the corrosion product is soluble in the reagent, the precipitating indicator is used to form the reaction product. (See Annex E for a classification of methods of porosity testing).

SIST EN ISO 10308:2006

**6 Test specimens**

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006>

Porosity tests are generally destructive in nature and are designed to assess the quality of the coating process of the substrate. Therefore, as a rule, separate test specimens are not used.

**7 Specific porosity tests****7.1 Alizarin test****7.1.1 Scope**

For coatings of chromium (including Cr/Ni/Cu and Cr/Ni/Ni), cobalt, copper, nickel, nickel-boron, nickel-cobalt, nickel-iron and nickel-phosphorus on aluminium substrate.

**7.1.2 Summary of method**

The test specimens are treated with sodium hydroxide, sodium alizarin sulfonate and glacial acetic acid under defined conditions. Formation of red markings or spots indicates porosity. Details of the test procedure can be found in references [9, 21 and 25] in the Bibliography.

## 7.2 Anthraquinone test

### 7.2.1 Scope

For coatings of chromium (including Cr/Ni/Ni), cobalt, nickel, nickel-boron, nickel-cobalt, nickel-iron and nickel-phosphorus on aluminium, magnesium or zinc alloy substrates.

### 7.2.2 Summary of method

The test specimens are treated with sodium hydroxide and potassium 1-aminoanthraquinone-2-carboxylic acid under defined conditions. The formation of red markings or spots indicates porosity. Details of the test procedure can be found in reference [13] in the Bibliography.

## 7.3 Cadmium sulfide test

### 7.3.1 Scope

For metallic coatings of chromium (including Cr/Ni/Ni), gold, palladium, platinum and rhodium on beryllium-copper, brass, copper, phosphor-bronze and silver substrates.

### 7.3.2 Summary of method

Filter paper is soaked in cadmium chloride and then treated with sodium sulfide to precipitate cadmium sulfide. The sample is sandwiched between the cadmium sulfide paper (which acts as the anode) and the moistened blotting paper fastened to a high-purity clean aluminium or stainless steel platen (which acts as the cathode). D.C. current is applied for a specific time. Brown stains on the paper indicate pores. Details of the test procedure can be found in ISO 4524-3.

## 7.4 Copper sulfate (Preece) test SIST EN ISO 10308:2006

<https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006>

### 7.4.1 Scope

**Variation A.** For coatings of cadmium and zinc on iron, steel or iron-based alloy substrates.

**Variation B.** For thin (< 5 µm) anodic oxide coatings on aluminium and aluminium alloy substrates.

### 7.4.2 Summary of method

The test specimen is immersed in a solution of copper sulfate; different solution compositions are used for aluminium alloy and iron alloy substrates. Reddish markings or spots, of copper, indicate pores on ferrous substrates; black markings or spots indicate pores on aluminium alloy substrates. Details of the test procedures can be found in ISO 2085. See also reference [26] in the Bibliography.

## 7.5 Copper sulfate (Dupernell) test

### 7.5.1 Scope

For coatings of chromium and micro-cracked or microporous chromium on nickel/copper or nickel/nickel on iron, steel, zinc alloys, copper and copper alloys, aluminium and aluminium alloy, plastic substrates.

### 7.5.2 Summary of method

The test specimen is used as the cathode in an acid copper plating bath. Copper is deposited only where the basis metal or the substrate is exposed, the chromium remaining passive. After the test, examine the surface for cracks using an optical microscope. Details of the test procedure can be found in ISO 1456, ISO 4525 and ISO 6158. See also references [27 and 28] in the Bibliography.

**ISO 10308:2006(E)****7.6 Corrodkote test (CORR)****7.6.1 Scope**

For coatings of chromium and micro-cracked or microporous chromium on nickel/copper or nickel/nickel on aluminium alloy, plastic, steel and iron alloy or zinc alloy substrates.

**7.6.2 Summary of method**

The test specimen is coated with a slurry of corrosive salts and dried. The coated specimens are exposed to high relative humidity for a specified period of time, then cleaned and treated for redeveloping the points of failure, e.g. in a salt spray cabinet. Porosity is indicated by black markings or red rust on the iron-based substrates or by white markings on the aluminium and zinc substrates (see ISO 10289). Details of the test procedure can be found in ISO 4541. See also reference [ 38] in the Bibliography.

**7.7 Electrographic tests****7.7.1 Scope**

**Variation A.** Acrylamide electrography (See warning in 7.7.2.)

For gold coatings on nickel and silver, or nickel coatings on copper substrates.

**Variation B.** Gel bulk electrography.

For gold, cobalt, nickel and palladium coatings on copper; gold, copper, cobalt and palladium coatings on nickel; gold on silver substrates.

**Variation C.** Paper electrography.

For the following combinations of indicator-coatings/substrate that have flat or nearly flat surfaces.

<b>Indicator</b>	<b>Coating/substrate</b>
1. Cadmium sulfide	Chromium, gold, palladium, platinum and rhodium on beryllium-copper, brass, copper, phosphor-bronze and silver substrates
2. Dimethylglyoxime	Gold, palladium, platinum, rhodium and silver on brass, beryllium-copper, copper, phosphor-bronze, nickel, nickel-boron and nickel-phosphorus substrates
3. Dithioamide	Chromium, gold, palladium, platinum and rhodium on beryllium-copper, brass, copper and phosphor-bronze substrates
4. Nioxime	Gold, palladium, platinum and rhodium on nickel, nickel-boron, nickel-iron, nickel-phosphorus and tin-nickel substrates
5. Potassium ferrocyanide	Chromium, gold, palladium platinum and rhodium on brass, beryllium-copper, copper and phosphor-bronze substrates
6. Potassium ferricyanide	Cadmium, nickel, tin and zinc on brass, silver and steel substrates
7. Magneson	Chromium, cobalt, copper, nickel, nickel-boron, nickel-cobalt, nickel-iron and nickel-phosphorus on magnesium substrates

### 7.7.2 Summary of methods

#### Variation A. Acrylamide electrography.

Acrylamide solution containing a hardener and an indicator is poured onto the sample shortly before gelatinizing. The sample is made the anode in a cell with a chloride solution and electrolyzed. Pores are revealed as coloured marks or spots. Details of the test procedure can be found in reference [7] in the Bibliography.

**WARNING — Acrylamide has been identified as a neurotoxin and carcinogen; use with extreme caution.**

#### Variation B. Gel bulk electrography.

A mixture of clear gelatin, conducting salts and an indicator are poured into an electrolytic cell with a gold or platinum cathode and with the specimen as the anode. The composite gel solution is allowed to solidify, following which the cell is electrolyzed. Pores are revealed as coloured spots or blooms. Details of the test procedure can be found in ISO 15720. See also reference [39] in the Bibliography.

#### Variation C. Paper electrography.

Test specimens are sandwiched as an anode between electrolyte-soaked paper and indicator paper and clamped with two cathode covers (of non-reactive materials such as gold or stainless steel). A specified current (usually 0,15 mA/cm<sup>2</sup> to 1,55 mA/cm<sup>2</sup>) for a specified time (usually 10 s to 30 s) is applied. After exposure, the test paper is wetted with indicator and allowed to dry. Pores are revealed as coloured spots.

A variety of commercially prepared test papers is available. Details of the test procedures can be found in ISO 4524-3. See also references [15, 18, 24 and 29] in the Bibliography.

## 7.8 Ferrocyanide test

SIST EN ISO 10308:2006

[https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-](https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006)

[f6bb5440bda4/sist-en-iso-10308-2006](https://standards.iteh.ai/catalog/standards/sist/5beae478-2071-4bec-9317-f6bb5440bda4/sist-en-iso-10308-2006)

### 7.8.1 Scope

For coatings of chromium, cobalt, gold, nickel, nickel-boron, nickel-iron, nickel-phosphorus, palladium, platinum and rhodium on copper substrate.

### 7.8.2 Summary of method

The test specimens are treated with glacial acetic acid and potassium ferrocyanide under defined conditions. Formation of brown markings or spots indicates porosity. Details of the test procedure can be found in references [12 and 37] in the Bibliography.

## 7.9 Ferron test

### 7.9.1 Scope

For coatings of aluminium, brass, cadmium, chromium, cobalt, indium, lead, nickel, nickel-boron, nickel-phosphorus, organic films, silver, tin, tin-lead, tin-nickel, tin-zinc and zinc, on iron and steel substrates.

### 7.9.2 Summary of method

The test specimens are treated with acid and a 0,1 % solution of ferron (8-hydroxyquinoline 7-iodo-5-sulfonic acid), under defined conditions. Formation of red markings or spots indicates porosity. Details of the test procedure can be found in reference [4] in the Bibliography.