

SLOVENSKI STANDARD SIST EN 62420:2009

01-januar-2009

D`YhYb]'_cbWYblf] bc `YÿY]'bUXnYa b]'Y'Y_lf] b]'j cX]'n'Ybc 'U]'j Y 'fYÿUa]'fl97 * &(&\$.&\$\$, Ł

Concentric lay stranded overhead electrical conductors containing one or more gap(s)

Leiter für Freileitungen aus konzentrisch verseilten runden Drähten mit einem oder mehreren Zwischenraum/räumen

iTeh STANDARD PREVIEW

Conducteurs pour lignes électriques aériennes câblés en couches concentriques comprenant un ou plusieurs intervalle(s)

SIST EN 62420:2009

Ta slovenski standard je istoveten za dag/ski-ch 13c7-454

ICS:

29.240.20 Daljnovodi Power transmission and

distribution lines

SIST EN 62420:2009 en,de

SIST EN 62420:2009

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62420:2009

EUROPEAN STANDARD

EN 62420

NORME EUROPÉENNE EUROPÄISCHE NORM

August 2008

ICS 29.240.20; 29.060.10

English version

Concentric lay stranded overhead electrical conductors containing one or more gap(s)

(IEC 62420:2008)

Conducteurs pour lignes électriques aériennes câblés en couches concentriques comprenant un ou plusieurs intervalle(s) (CEI 62420:2008)

Leiter für Freileitungen aus konzentrisch verseilten runden Drähten mit einem oder mehreren Zwischenraum/räumen (IEC 62420:2008)

iTeh STANDARD PREVIEW

This European Standard was approved by CENELEC on 2008-06-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member 9-13c7-4540-92c9-e467eb6a2daa/sist-en-62420-2009

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

Central Secretariat: rue de Stassart 35, B - 1050 Brussels

- 2 -

Foreword

The text of document 7/587/FDIS, future edition 1 of IEC 62420, prepared by IEC TC 7, Overhead electrical conductors, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 62420 on 2008-06-01.

The following dates were fixed:

 latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement

(dop) 2009-03-01

 latest date by which the national standards conflicting with the EN have to be withdrawn

(dow) 2011-06-01

Annex ZA has been added by CENELEC.

Endorsement notice

The text of the International Standard IEC 62420:2008 was approved by CENELEC as a European Standard without any modification.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62420:2009

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	EN/HD	<u>Year</u>
IEC 60104	1987	Aluminium-magnesium-silicon alloy wire for overhead line conductors	-	-
IEC 60888	1987	Zinc-coated steel wires for stranded conductors	-	-
IEC 60889	1987	Hard-drawn aluminium wire for overhead line conductors	EN 60889	1997
IEC 61232 (mod)	1993	Aluminium-clad steel wires for electrical purposes	EN 61232 + corr. February + A11	1995 1996 2000
IEC 61395	1998	Overhead electrical conductors - Creep test procedures for stranded conductors	EN 61395	1998
IEC 62004	2007	Thermal resistant aluminium alloy wire for overhead line conductor	_	_

SIST EN 62420:2009

SIST EN 62420:2009

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62420:2009



IEC 62420

Edition 1.0 2008-04

INTERNATIONAL STANDARD

Concentric lay stranded overhead electrical conductors containing one or more gap(s) (standards.iteh.ai)

SIST EN 62420:2009

https://standards.iteh.ai/catalog/standards/sist/6012f0e6-13c7-4540-92c9-e467eb6a2daa/sist-en-62420-2009

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRICE CODE



CONTENTS

FO	REW	ORD		4		
1	Scor	ne		6		
2			eferences			
3		Terms and definitions				
4						
		esignation system				
5	-		its for stranded conductors			
	5.1	Material				
	5.2		uctor sizes			
	5.3		Ce			
	5.4	5.4.1	dingGeneral			
		5.4.1	Lay ratio for core wires			
		5.4.2	Lay ratio for aluminium layer(s)			
		5.4.4	Joints			
		5.4.5	Linear mass			
		5.4.6	Conductor strength			
6	Test		iTeh STANDARD PREVIEW	10		
Ū	6.1					
	6.2	Type	fication of tests (standards.iteh.ai) Tests	10		
	0.2	6.2.1	Length of sample required	10		
		6.2.2	Joints/star aluminium wires standards/sist/6012/0e6-13c7-4540-92c9	10		
		6.2.3	Annular gap(s).e467eb6a2daa/sist-en-62420-2009			
		6.2.4	Stress-strain curves			
		6.2.5	Breaking strength of conductor			
		6.2.6	Creep curves			
	6.3	Samp	le tests	11		
		6.3.1	Cross-sectional area	12		
		6.3.2	Overall diameter	12		
		6.3.3	Linear mass	12		
		6.3.4	Surface condition	12		
		6.3.5	Lay ratio and direction of lay	12		
		6.3.6	Breaking strength of wires after stranding (if requested)	13		
		6.3.7	Wire canting on the outside layer (if requested)	13		
7	Insp	ection		13		
	7.1	Test lo	ocation	13		
	7.2	Accep	tance or rejection	13		
8	Pack	kaging a	and marking	14		
	8.1	Packa	ging	14		
	8.2	Markir	ng and tare	14		
	8.3 Random lengths			14		
Anı	nex A	(norma	tive) Information to be supplied by purchaser	18		
Anı	nex B	(norma	tive) Stress-strain test method	19		
Anı	nex C	(norma	tive) Nominal mass of grease for stranded conductors	22		

Annex D (informative) Alternate method of measuring the gap(s) within the conductor	25
Annex E (informative) Recommended conductor sizes and tables of conductor properties	26
Figure 1 – Examples of conductors containing one or more gaps	16
Figure 2 – Method of measuring wire canting	17
Figure C.1 – Illustration for calculation of mass of grease in round wire layer (s)	22
Figure C.2 – Illustration of calculation of mass of grease for core layer(s)	23
Figure C.3 – Illustration of calculation of grease for annular gap(s)	24
Table 1 – Metal combinations permitted	15
Table 2 – Number of joints permitted in aluminium wires	16
Table 3 – Standard increments ^a due to stranding	16
Table E.1 – Properties of some A1G/S1A conductors with gaps	27

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62420:2009

INTERNATIONAL ELECTROTECHNICAL COMMISSION

CONCENTRIC LAY STRANDED OVERHEAD ELECTRICAL CONDUCTORS CONTAINING ONE OR MORE GAP(S)

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC/National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication!
- 6) All users should ensure that they have the latest edition of this publication 7-4540-92c9-
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 62420 has been prepared by IEC technical committee 7: Overhead electrical conductors.

The text of this standard is based on the following documents:

FDIS	Report on voting	
7/587/FDIS	7/588/RVD	

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

62420 © IEC:2008(E)

- 5 -

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- · reconfirmed,
- withdrawn,
- · replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 62420:2009

CONCENTRIC LAY STRANDED OVERHEAD ELECTRICAL CONDUCTORS CONTAINING ONE OR MORE GAP(S)

1 Scope

This International Standard specifies the electrical and mechanical characteristics of concentric lay stranded overhead electrical conductors, containing one or more self-supporting aluminium or aluminium alloy layer(s) as depicted in Figure 1, made of combinations of any of the following metal wires:

- a) hard-drawn aluminium as per IEC 60889, designated A1;
- b) aluminium alloy type A or B as per IEC 60104, designated A2 or A3;
- c) thermal resistant aluminium alloy type as per IEC 62004, designated AT1, AT2, AT3 or AT4;
- d) regular strength steel as per IEC 60888, designated S1A or S1B;
- e) high strength steel as per IEC 60888, designated S2A or S2B;
- f) extra-high strength steel as per IEC 60888, designated S3A;
- g) aluminium-clad steel as per IEC 61232, designated 20SA, 27SA, 30SA or 40SA.

NOTE This standard covers the construction of self-damping conductors, as well as gap-type conductors. Although both types of conductors share a common design feature and the presence of one or more gaps between layers, they are intended for different purposes. Self-damping conductors (SDC) may have more than one gap to provide increased self-damping, whereas gap-type conductors are so designed as to allow the aluminium layers to slide freely over the core during installation, and therefore usually do not require more than one gap.

The various metal combinations permitted by this standard shall be in accordance with Table 1.

https://standards.iteh.ai/catalog/standards/sist/6012f0e6-13c7-4540-92c9-

2 Normative references

e467eb6a2daa/sist-en-62420-2009

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60104:1987, Aluminium-magnesium-silicon alloy wire for overhead line conductors

IEC 60888:1987, Zinc-coated steel wires for stranded conductors

IEC 60889:1987, Hard-drawn aluminium wire for overhead line conductors

IEC 61232:1993, Aluminium-clad steel wires for electrical purposes

IEC 61395:1998, Creep test procedures for stranded conductors

IEC 62004:2007, Thermal resistant aluminium alloy wire for overhead line conductors

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

aluminium

all types of aluminium and aluminium alloys listed in Clause 1

3.2

annular gap

constant space, void of any material except for air or grease, between two layers of a conductor