



SLOVENSKI STANDARD

SIST EN 13877-3:2005

01-junij-2005

Betonska vozišča – 3. del: Specifikacije za moznike (spojne elemente), ki se uporabljajo pri betonskih voziščih

Concrete pavements - Part 3: Specifications for dowels to be used in concrete pavements

Fahrbahnbefestigungen aus Beton - Teil 3: Anforderungen an Dübel für Fahrbahnbefestigungen aus Beton

Chaussées en béton - Partie 3: Spécifications relatives aux goujons à utiliser dans les chaussées en béton

[SIST EN 13877-3:2005](https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005)

<https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005>

Ta slovenski standard je istoveten z: EN 13877-3:2004

ICS:

91.100.30	Beton in betonski izdelki	Concrete and concrete products
93.080.20	Materiali za gradnjo cest	Road construction materials

SIST EN 13877-3:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 13877-3:2005

<https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13877-3

December 2004

ICS 93.080.20

English version

Concrete pavements - Part 3: Specifications for dowels to be used in concrete pavements

Chaussées en béton - Partie 3: Spécifications relatives aux goujons à utiliser dans les chaussées en béton

Fahrbahnbefestigungen aus Beton - Teil 3: Anforderungen an Dübel für Fahrbahnbefestigungen aus Beton

This European Standard was approved by CEN on 20 October 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 13877-3:2005](https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005)

<https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	Page
Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Requirements	4
5 Durability	4
6 Evaluation of Conformity	4
6.1 General.....	4
6.2 Type Testing.....	5
6.2.1 Initial Type Testing	5
6.2.2 Further Type Testing	5
6.3 Factory Production Control (FPC)	5
6.3.1 General.....	5
6.3.2 Frequency of testing	5
6.3.3 Equipment	5
6.3.4 Raw materials and components	5
6.3.5 Product testing and evaluation	6
Annex ZA (informative) Clauses of this European standard addressing the provisions of the EU Construction Products Directive.....	7
ZA.1 Scope and relevant characteristics	7
ZA.2 Procedure(s) for attestation of conformity of dowels.....	8
ZA.2.1 System(s) of attestation of conformity.....	8
ZA.2.2 Certificate and Declaration of conformity	8
ZA.3 CE Marking	9

Foreword

This document (EN 13877-3:2004) has been prepared by Technical Committee CEN/TC 227 “Road materials”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2005, and conflicting national standards shall be withdrawn at the latest by June 2005.

The European Standard is one of a series of standards as follows:

EN 13877-1, *Concrete pavements — Part 1: Materials.*

EN 13877-2, *Concrete pavements — Part 2: Functional requirements for concrete pavements.*

EN 13877-3, *Concrete pavements — Part 3: Specifications for dowels to be used in concrete pavements.*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

SIST EN 13877-3:2005

<https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005>

EN 13877-3:2004 (E)**1 Scope**

This document specifies the requirements for dowels to be used in cast “in situ” concrete pavements for roads, airfields and other trafficked areas.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10060, *Hot rolled round steel bars for general purposes. Dimensions and tolerances on shape and dimensions.*

EN 13877-1:2004, *Concrete pavements — Part 1: Materials.*

EN ISO 9001, *Quality management systems — Requirements (ISO 9001:2000).*

EN ISO 15630-1, *Steel for the reinforcement and prestressing of concrete. Test methods — Part 1: Reinforcing bars, wire rod and wire (ISO 15630-1:2002).*

3 Terms and definitions**ITeh STANDARD PREVIEW****(standards.iteh.ai)**

For the purposes of this document, the terms and definitions given in EN 13877-1:2004 apply.

4 Requirements

[SIST EN 13877-3:2005
https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005](https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005)

Dowels shall have at least a tensile strength of 250 MPa when tested in accordance with EN ISO 15630-1.

Diameter and tolerances on diameters of dowels shall be in accordance with EN 10060. The minimum diameter shall be 16 mm. The tolerances in length shall be ± 10 mm.

Dowels shall be straight, free of burrs and other irregularities and the sliding ends sawn with no protrusions outside the normal diameter of the bar.

NOTE 1 The length of dowels should conform to national application provisions in the place of use.

NOTE 2 Before the use, half of their length at least, should be covered with a thin bituminous coating or a thin plastic sheet to prevent them from adhering to the concrete. The average thickness should be not greater than 1,25 mm.

5 Durability

The durability shall be ensured either by a protective coating factory made, or by on site treatments as a national application provision.

NOTE Protective measures against corrosion have to conform to national standards or provisions in the place of use.

6 Evaluation of Conformity**6.1 General**

The compliance of the product with the requirements of this document shall be demonstrated by:

- Initial Type Testing;
- Factory Production Control by the manufacturer, including product assessment.

When tested by an external body, the characteristics indicated in Clause 5 shall be determined within 3 months to the date of delivery from the manufacturer.

6.2 Type Testing

6.2.1 Initial Type Testing

Initial Type Testing shall be performed to show conformity with this document. Tests previously performed in accordance with the provisions of this document (same product, same characteristic(s), test method, sampling procedure, system of attestation of conformity, etc.) may be taken into account. In addition, Initial Type Testing shall be performed at the beginning of the production of a new product type or at the beginning of a new method of production (where this may affect the stated properties).

All characteristics in the relevant clauses shall be subject to Initial Type Testing, where relevant.

6.2.2 Further Type Testing

Whenever a change occurs in the product design, the raw material or supplier of the components, or the production process, which would change significantly one or more of the characteristics, the type tests shall be repeated for the appropriate characteristic(s).

6.3 Factory Production Control (FPC)

6.3.1 General

The manufacturer shall establish, document and maintain an FPC system to ensure that the products placed on the market conform with the stated performance characteristics. The FPC system shall consist of procedures, regular inspections and tests and/or assessments and the use of the results to control raw and other incoming materials or components, equipment, the production process and the product.

A FPC system conforming with the requirements of EN ISO 9001, and made product specific to the requirements of this document, is considered to satisfy the above requirements.

The results of inspections, tests or assessments requiring action shall be recorded and retained during the period specified by the producer, as shall any action taken. The actions to be taken when control values or criteria are not met shall be recorded.

6.3.2 Frequency of testing

Minimum frequencies of testing for Factory Production Quality control are shown in Table 1.

6.3.3 Equipment

All weighing, measuring and testing equipment shall be calibrated and regularly inspected according to documents procedure, frequencies and criteria.

6.3.4 Raw materials and components

The specifications of all incoming raw materials and components shall be documented, as shall the inspection scheme for ensuring their conformity.

EN 13877-3:2004 (E)**6.3.5 Product testing and evaluation**

The manufacturer shall establish procedures to ensure that the stated values of all of the characteristics are maintained.

Table 1 — Initial Type Testing and frequencies of testing for Factory Production Control

Product characteristic	Clause	Initial Type Testing	Factory Production Control
			Minimum frequencies of testing
Tensile strength	4	X	One per 2 500 dowels

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13877-3:2005](https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005)

<https://standards.iteh.ai/catalog/standards/sist/9ab12af9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005>

Annex ZA (informative)

Clauses of this European standard addressing the provisions of the EU Construction Products Directive

ZA.1 Scope and relevant characteristics

This European Standard has been prepared under Mandate M/124 "Road construction products" given to CEN by the European Commission and the European Free Trade Association.

The clauses of this European Standard shown in this annex meet the requirements of the Mandate given under the EU Construction Products Directive (89/106/EEC). Compliance with these clauses confers a presumption of fitness of the construction products covered by this annex for their intended uses indicated herein; reference shall be made to the information accompanying the CE marking.

WARNING — Other requirements and other EU Directives, not affecting the fitness for intended use, may be applicable to the construction products falling within the scope of this standard.

NOTE 1 In addition to any specific clauses relating to dangerous substances contained in this Standard, there may be other requirements applicable to the products falling within its scope (e.g. transposed European legislation and national laws, regulations and administrative provisions). In order to meet the provisions of the EU Construction Products Directive, these requirements need also to be complied with, when and where they apply.

NOTE 2 An informative database of European and national provisions on dangerous substances is available at the Construction web site on EUROPA (accessed through <http://europa.eu.int>).

<https://standards.iteh.ai/catalog/standards/sist/9ab12a9-fa02-4533-8c65-f8737d667352/sist-en-13877-3-2005>

This annex has the same scope as Clause 1 of this standard with regard to the products covered. It establishes the conditions for the CE marking of road construction products and shows the relevant clauses applicable (see Table ZA.1).

Construction Product: **dowels for concrete pavements**

Intended uses: **concrete pavements for roads, airfields and other trafficked areas.**

Table ZA.1 — Dowels for concrete pavements

Product: Dowels for concrete pavements			
Intended use: Concrete pavements for roads, airfields and other trafficked areas			
Requirement/Characteristics from the mandate (1)	Requirement clauses in this and other European Standard(s)	Mandated levels and/or classes)	Notes
Tensile strength	4		Threshold
Durability	5		Pass/fail
Release of dangerous substances ^a	See clause	No	Less than ppm
^a In particular, those dangerous substances defined in Council Directive 76/769/EEC, as amended			

The requirement on a certain characteristic is not applicable in those Member States where there are no regulatory requirements on that characteristic for the intended end use of the product. In this case,