
**Textile conveyor belts — Adhesive strength
between constitutive elements —**

**Part 1:
Methods of test**

*Courroies transporteuses à carcasse textile — Adhérence entre éléments
constitutifs —*

Partie 1: Méthodes d'essai

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 252-1:1999

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-7210609ebc65/iso-252-1-1999>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 252-1:1999

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-7210609ebc65/iso-252-1-1999>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to member bodies for voting. Publication as an International Standard requires approval by at least 75 % of member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 252 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 252-1 was prepared by the European Committee for Standardization (CEN) in collaboration with ISO Technical Committee TC 41, *Pulleys and belts (including veebelts)*, Subcommittee SC 3, *Conveyor belts*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Throughout the text of this standard, read "...this European Standard..." to mean "...this International Standard...".

This first edition of ISO 252-1 partially cancels and replaces ISO 252:1988, in particular the methods of test. The performances will be the subject of ISO 252-2, which will definitively cancel and replace ISO 252:1988.

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-410e300a1127>

ISO 252 consists of the following parts, under the general title *Textile conveyor belts — Adhesive strength between constitutive elements*:

- *Part 1: Methods of test*
- *Part 2: Performance values*

Contents

	Page
Foreword	v
1 Scope	1
2 Normative references	1
3 Principle	1
4 Apparatus	1
5 Test pieces	2
6 Conditioning	2
7 Procedure	3
8 Expression of results	4
9 Test report	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-7210609ebc65/iso-252-1-1999>

Foreword

The text of EN ISO 252-1:1999 has been prepared by Technical Committee CEN/TC 188 "Conveyor belts", the secretariat of which is held by BSI, in collaboration with Technical Committee ISO/TC 41 "Pulleys and belts(including veebelts)".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2000, and conflicting national standards shall be withdrawn at the latest by January 2000.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 252-1:1999](https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-7210609ebc65/iso-252-1-1999)

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-7210609ebc65/iso-252-1-1999>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 252-1:1999

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-7210609ebc65/iso-252-1-1999>

1 Scope

This Standard specifies two test methods , A and B, for determining the adhesion strength between plies, and between covers and carcass, of conveyor belts. Basic test conditions are in conformity with ISO 36.

It applies to all types of construction of conveyor belting with the exception of belts containing steel cord reinforcement, and textile-reinforced belts with a tensile strength less than 160 N/mm. It is not suitable or valid for light conveyor belts described in EN 873.

Note 1. Method A and Method B are alternative options but the mean adhesion force values calculated for Method A and Method B may be different. Also as both methods may not be equally suitable for all belt constructions , it is advisable that the advice of the belt manufacturer should be sought.

2 Normative references

This European Standard incorporates by dated and undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

(standards.iteh.ai)

- | | |
|----------|---|
| ISO 36 | Rubber, vulcanized or thermoplastic - Determination of adhesion to textile fabric |
| ISO 6133 | Rubber and plastics - Analysis of multi-peak traces obtained in determinations of tear strength and adhesion strength |

3 Principle

The mean force required to strip the covers from the carcass, and also each ply from the next, is determined using a constant rate of traverse machine.

4 Apparatus

Suitable power-driven tensile testing machine, complying with the requirements of ISO 36.

5 Test pieces

5.1 Time between manufacture and test

The test pieces shall be cut at least 24h after the belt is manufactured.

5.2 Shape and dimensions

Each test piece shall consist of a strip of belting of rectangular cross-section with clean-cut edges, $(25 \pm 0,5)$ mm wide, and 200 mm minimum length so as to permit a length of at least 100 mm to be stripped. If necessary and possible, the thickness shall be reduced to a suitable value which will ensure that during the test the line of separation remains as near as possible to the plane through the axes of the components of the test piece held between the grips (see figure 1).

The minimum thickness shall be such that the weakest component can transmit the necessary force for separation without breaking.

5.3 Number

For both methods A and B two test pieces in the longitudinal direction are required.

Note 2. The test can also be conducted with two transverse test pieces.

5.4 Selection of test pieces from the sample

The test pieces shall be taken not less than 100 mm from the edges of the available belt sample and from places as widely spaced as possible.

6 Conditioning

The tests shall start not less than 24h after manufacturing. This time includes 8h for conditioning at one of the temperature specified below.

$(23 \pm 2)^{\circ}\text{C}$ or $(20 \pm 2)^{\circ}\text{C}$ for temperate temperature control only, or

$(27 \pm 2)^{\circ}\text{C}$ for tropical temperature control only

The tests shall be conducted at the same temperature as used for conditioning. A certain humidity for conditioning and testing is not required.

The temperature at which the test pieces were conditioned and tested shall be reported in the test report.

7 Procedure

7.1 Method A (see figure 2)

At one end of the longitudinal test piece, separate the face cover from the first ply for a suitable distance appropriate to the test grips to be used. Fix the separated ends in the grips of the tensile testing machine and make an autographic record of the force required to strip a further 100 mm with a rate of traverse of the driven jaw of (100 ± 10) mm/min. The test piece shall be unsupported.

Repeat this procedure using the same test piece for each consecutive ply up to the middle of the test piece.

Carry out a similar series of tests on a second longitudinal test piece but commencing with the back cover.

If the test is to be made on transverse test pieces the test is conducted in the same manner.

7.2 Method B (see figure 3)

At one end of the longitudinal test piece, separate the face cover from the first ply for a suitable distance appropriate to the test grips to be used. Fix the separated ends in the grips of the tensile testing machine and make an autographic record of the force required to strip a further 100 mm with a rate of traverse of the driven jaw of (100 ± 10) mm/min. The test piece shall be unsupported.

Repeat this procedure using the same test piece, stripping consecutively two unseparated plies from the remainder of the test piece.

ISO 252-1:1999

<https://standards.iteh.ai/catalog/standards/sist/85981d73-9d7b-4ceb-bbde-721009c6c6/iso-252-1-1999>

Carry out a similar series of tests on a second longitudinal test piece but commencing by separating the unseparated face cover and first ply, from the second ply.

If the test is to be made on transverse test pieces the test is conducted in the same manner.

NOTE 3 - Any separation occurring outside the plane of contact between the two components, for example inside one of the components (such as a cover) subjected to the test, is considered as a rupture of the material which constitutes the component. Such a separation should be noted but should not be considered as representative of the adhesion strength.