

# INTERNATIONAL STANDARD

**Magnetic materials – Part 8-7: Specifications for individual materials – Cold-rolled grain-oriented electrical steel strip and sheet delivered in the fully-processed state**

**STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/14e79be2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017>



**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2017 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
Fax: +41 22 919 03 00  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

**About the IEC**

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

**About IEC publications**

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

**IEC Catalogue - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)**

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

**Electropedia - [www.electropedia.org](http://www.electropedia.org)**

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

**IEC publications search - [www.iec.ch/searchpub](http://www.iec.ch/searchpub)**

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

**IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)**

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

**IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)**

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

**IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)**

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [csc@iec.ch](mailto:csc@iec.ch).

IEC STANDARD PREVIEW  
(standards.iec.ch)  
IEC 60048-8:2017  
<https://standards.iec.ch/catalog/standards/60048-8-2017>  
70e1a7Bea35/iec-60048-8-2017

# INTERNATIONAL STANDARD

---

**Magnetic materials – Part 8-7: Specifications for individual materials – Cold-rolled grain-oriented electrical steel strip and sheet delivered in the fully-processed state**

[IEC 60404-8-7:2017](https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017)

<https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017>

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

---

ICS 29.030

ISBN 978-2-8322-4804-1

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD .....	4
1 Scope .....	6
2 Normative references .....	6
3 Terms and definitions .....	7
4 Classification .....	7
5 Designation .....	7
6 General requirements .....	8
6.1 Production process .....	8
6.2 Form of supply .....	8
6.3 Delivery condition .....	9
6.4 Surface condition .....	9
6.5 Suitability for cutting .....	9
7 Technical requirements .....	9
7.1 Magnetic properties .....	9
7.1.1 General .....	9
7.1.2 Magnetic polarization .....	9
7.1.3 Specific total loss .....	9
7.2 Geometric characteristics and tolerances .....	11
7.2.1 Thickness .....	11
7.2.2 Width .....	12
7.2.3 Length .....	12
7.2.4 Edge camber .....	12
7.2.5 Edge wave (wave factor) .....	13
7.2.6 Residual curvature .....	13
7.2.7 Burr height .....	13
7.3 Technological characteristics .....	13
7.3.1 Density .....	13
7.3.2 Stacking factor .....	13
7.3.3 Number of bends .....	13
7.3.4 Internal stresses .....	13
7.3.5 Insulation coating resistance .....	13
8 Inspection and testing .....	14
8.1 General .....	14
8.2 Selection of samples .....	14
8.3 Preparation of test specimens .....	14
8.3.1 Magnetic properties .....	14
8.3.2 Geometrical characteristics and tolerances .....	15
8.3.3 Technological characteristics .....	15
8.4 Test methods .....	16
8.4.1 General .....	16
8.4.2 Magnetic properties .....	16
8.4.3 Geometrical characteristics and tolerances .....	16
8.4.4 Technological characteristics .....	16
8.5 Retests .....	17
9 Marking, labelling and packaging .....	17

10 Complaints ..... 17

11 Information to be supplied by the purchaser ..... 17

Bibliography..... 19

  

Table 1 – Technological and magnetic properties of the conventional grades of grain-oriented electrical steel strip and sheet ..... 10

Table 2 – Technological and magnetic properties of the high permeability grades of grain-oriented electrical steel strip and sheet ..... 11

Table 3 – Tolerances on nominal width ..... 12

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60404-8-7:2017](https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017)  
<https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

---

**MAGNETIC MATERIALS –****Part 8-7: Specifications for individual materials –  
Cold-rolled grain-oriented electrical steel strip  
and sheet delivered in the fully-processed state**

## FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-8-7 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

This fourth edition cancels and replaces the third edition published in 2008. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- extension of the range of electrical steels to include the improved grades.

The text of this International Standard is based on the following documents:

CDV	Report on voting
68/545/CDV	68/561/RVC

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60404 series, published under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

**ITEH STANDARD PREVIEW**  
**(standards.iteh.ai)**

[IEC 60404-8-7:2017](https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017)

<https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017>

## MAGNETIC MATERIALS –

### Part 8-7: Specifications for individual materials – Cold-rolled grain-oriented electrical steel strip and sheet delivered in the fully-processed state

#### 1 Scope

This part of IEC 60404 defines the grades of cold-rolled grain-oriented electrical steel strip and sheet in nominal thicknesses of 0,23 mm, 0,27 mm, 0,30 mm and 0,35 mm. In particular, it gives general requirements, magnetic properties, geometric characteristics, tolerances and technological characteristics, as well as inspection procedures.

This document applies to Goss textured grain-oriented electrical steel strip and sheet supplied in the final annealed condition in coils or sheets, and intended for the construction of magnetic circuits.

The grades are grouped into two classes:

- conventional grades;
- high permeability grades, including grades which may be delivered in the domain refined condition.

They correspond to Class C22 of IEC 60404-1.

[IEC 60404-8-7:2017](#)

<https://standards.iteh.ai/catalog/standards/sist/14e79be2-64fd-4fb5-a2a8-70e1a7Bea35/iec-60404-8-7-2017>

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050-121, *International Electrotechnical Vocabulary – Part 121: Electromagnetism* (available at <http://www.electropedia.org/>)

IEC 60050-221, *International Electrotechnical Vocabulary – Chapter 221: Magnetic materials and components* (available at <http://www.electropedia.org/>)

IEC 60404-1, *Magnetic materials – Part 1: Classification*

IEC 60404-2, *Magnetic materials – Part 2: Methods of measurement of the magnetic properties of electrical steel sheet and strip by means of an Epstein frame*

IEC 60404-3:1992, *Magnetic materials – Part 3: Methods of measurement of the magnetic properties of magnetic sheet and strip by means of a single sheet tester*  
IEC 60404-3:1992/AMD1:2002

IEC 60404-9, *Magnetic materials – Part 9: Methods of determination of the geometrical characteristics of magnetic steel sheet and strip*

IEC 60404-13, *Magnetic materials – Part 13: Methods of measurement of density, resistivity and stacking factor of electrical steel sheet and strip*



ISO 404, *Steel and steel products – General technical delivery requirements*

ISO 7799, *Metallic materials – Sheet and strip 3 mm thick or less – Reverse bend test*

ISO 10474, *Steel and steel products – Inspection documents*

### 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-121 and IEC 60050-221 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1

##### **edge camber**

greatest distance between a longitudinal edge of a length of strip or a sheet and the line joining the two extremities of the measured length of this edge

Note 1 to entry: See IEC 60404-9.

#### 3.2

##### **edge wave**

##### **wave factor**

variations of flatness of a length of strip or a sheet taking a form of waves at the slit edge of the product

<https://standards.iteh.ai/catalog/standards/sist/14e79bc2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017>

Note 1 to entry: The edge wave is characterized by the wave factor which is the relation of the height of the wave to its length, expressed as a percentage.

#### 3.3

##### **number of bends**

number of alternate bends possible before the appearance of the first crack in the base metal visible to the naked eye

Note 1 to entry: The number of bends constitutes an indication of the ductility of the product.

#### 3.4

##### **internal stresses**

stresses which are characterized by a deviation in relation to the line of cutting

### 4 Classification

The grades covered by this document are classified according to the value of maximum specific total loss in watts per kilogram and according to the nominal thickness of the product<sup>1</sup> (0,23 mm, 0,27 mm, 0,30 mm and 0,35 mm).

### 5 Designation

The steel name comprises the following in the order given:

---

<sup>1</sup> In the rest of the document, the word "product" is used to mean "strip and sheet".

- 1) the letter M for electrical steel;
- 2) one hundred times the specified value of maximum specific total loss at 1,7 T and 50 Hz, in watts per kilogram;
- 3) one hundred times the nominal thickness of the product, in millimetres;
- 4) the characteristic letter
  - S for conventional grades;
  - P for high permeability grades;
- 5) one tenth of the frequency 50 Hz, i.e. 5.

EXAMPLE M140-30S5 for cold-rolled grain-oriented electrical steel strip or sheet of conventional grade with a maximum specific total loss of 1,40 W/kg at 1,7 T and 50 Hz, and a nominal thickness of 0,30 mm, supplied in the fully-processed state.

## 6 General requirements

### 6.1 Production process

The production process of the steel and its chemical composition are left to the discretion of the manufacturer.

### 6.2 Form of supply

The product is supplied in coils in the case of strip and in bundles in the case of sheets.

The mass of the coils or bundles (sheets) shall be agreed between the manufacturer and purchaser at the time of enquiry and order.

The recommended value for the internal diameter of coils is approximately 508 mm.

Strip shall be of constant width and wound in such a manner that the edges are superimposed in a regular manner and the side faces of the coil are substantially flat.

Coils shall be sufficiently tightly wound in order that they do not collapse under their own weight.

Strip may exhibit welds or interleaves resulting from the removal of defective zones if agreed between the manufacturer and purchaser at the time of enquiry and order. If necessary, the marking of welds or interleaves may be agreed between the manufacturer and purchaser at the time of enquiry and order.

For coils containing repair welds or interleaves, each part of the strip shall be of the same grade.

The edges of parts welded together shall not be so much out of alignment as to affect the further processing of the product.

Sheets which make up each bundle shall be stacked so that the side faces are substantially flat and approximately perpendicular to the top face.

### 6.3 Delivery condition

Cold-rolled grain-oriented electrical steel products are usually supplied with an insulating coating on both sides. This coating generally consists of an EC-5-G coating on an EC-2 coating in accordance with IEC 60404-1-12.

### 6.4 Surface condition

The surfaces shall be smooth and clean, free from grease and rust<sup>3</sup>. Dispersed defects such as scratches, blisters, cracks, etc. are permitted if they are within the limits of the tolerances on thickness and if they are not detrimental to the correct use of the supplied product.

The insulation coating present on the surface of the product shall be sufficiently adherent so that it does not become detached during cutting operations or heat treatment under conditions specified by the supplier.

If the product is to be immersed in a fluid, an agreement between the manufacturer and purchaser, initiated by the purchaser, should be reached to ensure compatibility between the fluid and the coating.

### 6.5 Suitability for cutting

The product shall be suitable for cutting accurately into the usual shapes at any point when appropriate cutting tools are used.

iTeh STANDARD PREVIEW

## 7 Technical requirements (standards.iteh.ai)

### 7.1 Magnetic properties

[IEC 60404-8-7:2017](#)

#### 7.1.1 General <https://standards.iteh.ai/catalog/standards/sist/14e79be2-64fd-4fb5-a2a8-70e1a73ea35/iec-60404-8-7-2017>

The properties defined in 7.1.2 and 7.1.3 shall apply to products in the delivery condition defined in 6.3 and to the aged condition defined in 8.3.1.

The Epstein strips shall receive a stress relief heat treatment after cutting under conditions specified by the manufacturer.

The single sheet test specimens shall not be heat treated.

#### 7.1.2 Magnetic polarization

The specified minimum values of peak magnetic polarization at the peak magnetic field strength of 800 A/m at 50 Hz or 60 Hz shall be as given in Table 1 and Table 2.

#### 7.1.3 Specific total loss

The specified values of maximum specific total loss at 50 Hz or 60 Hz shall be as given in Table 1 and Table 2.

---

<sup>2</sup> Other types of coating exist which are used only when particularly specified.

<sup>3</sup> Not to be confused with some coloration of the insulating coating inherent to the manufacturing process.