



Edition 2.0 2017-09

# INTERNATIONAL STANDARD

Magnetic materials Feh STANDARD PREVIEW Part 8-8: Specifications for individual materials – Thin electrical steel strip and sheet for use at medium frequencies

> <u>IEC 60404-8-8:2017</u> https://standards.iteh.ai/catalog/standards/sist/194afa35-8ae6-49b7-9eb5af79cefdb042/iec-60404-8-8-2017





# THIS PUBLICATION IS COPYRIGHT PROTECTED Copyright © 2017 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

| IEC Central Office | Tel.: +41 22 919 02 11 |
|--------------------|------------------------|
| 3, rue de Varembé  | Fax: +41 22 919 03 00  |
| CH-1211 Geneva 20  | info@iec.ch            |
| Switzerland        | www.iec.ch             |

#### About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

#### About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

#### IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

#### IEC publications search - www.iec.ch/searchpub

The advanced search enables to find IEC publications by a variety of criteria (reference number text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

#### IEC Just Published - webstore.iec.ch/justpublished Stay up to date on all new IEC publications. Just Published

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 20 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

#### IEC Glossary - std.iec.ch/glossary

65 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

#### IEC Customer Service Centre - webstore.iec.ch/csc

details all new publications released. Available online and 4- If you wish to give us your feedback on this publication or also once a month by emailtips://standards.itch.ai/catalog/standardsedtfutther.assistance; please bontact the Customer Service af79cefdb042/iec-66entre; csc@iec.ch.





Edition 2.0 2017-09

# INTERNATIONAL STANDARD

Magnetic material **STANDARD PREVIEW** 

Part 8-8: Specifications for individual materials – Thin electrical steel strip and sheet for use at medium frequencies

IEC 60404-8-8:2017 https://standards.iteh.ai/catalog/standards/sist/194afa35-8ae6-49b7-9eb5af79cefdb042/iec-60404-8-8-2017

INTERNATIONAL ELECTROTECHNICAL COMMISSION

ICS 29.030

ISBN 978-2-8322-4805-8

Warning! Make sure that you obtained this publication from an authorized distributor.

# CONTENTS

| FC | DREWO  | RD   | 4    |  |
|----|--|--|------|--|
| 1  | Scop   | e  | 6    |  |
| 2  | Norm   | ative references   | 6    |  |
| 3  | 3 Terms and definitions7                                 |  |      |  |
| 4  | Class  | sification   | 7    |  |
| 5  | Desig  | nation   | 7    |  |
| 6  | General requirements                                     |  |      |  |
| -  | 6 1  | Production process   | 7    |  |
|    | 6.2  | Form of supply   | 7    |  |
|    | 6.3  | Delivery condition   | 8    |  |
|    | 6.4  | Surface condition  | 8    |  |
|    | 6.5  | Suitability for cutting  | 8    |  |
| 7  | Tech   | nical requirements   | 9    |  |
|    | 7.1  | Magnetic properties  | 9    |  |
|    | 7.1.1  | Magnetic polarization  | 9    |  |
|    | 7.1.2  | Specific total loss  | .10  |  |
|    | 7.2  | Geometric characteristics and tolerances                               | . 10 |  |
|    | 7.2.1  | Thickness and Str.A.N.D.A.R.D.D.R.T.V.T.T.V.                           | . 10 |  |
|    | 7.2.2  | Width  | .12  |  |
|    | 7.2.3  | Edge camber (Stanuar us.nen.ar)  | .12  |  |
|    | 7.2.4  | Residual curvature   | .12  |  |
|    | 7.2.5  | Burr height  | . 13 |  |
|    | 7.3  | lechnological characteristics  | .13  |  |
|    | 7.3.1  | Density  | 13   |  |
|    | 732  | Stacking factor  | 12   |  |
|    | 7.3.3  | Insulation coating resistance  | 13   |  |
| 8  | Inspe  | ection and testing   | 13   |  |
| U  | Q 1  | General  | 12   |  |
|    | 0.1<br>8.2   | Selection of samples   | 1/   |  |
|    | 8.3  | Preparation of test specimens  | 14   |  |
|    | 831  | Magnetic properties  | 14   |  |
|    | 8.3.2  | Geometrical characteristics and tolerances                             | . 15 |  |
|    | 8.3.3  | Technological characteristics  | . 15 |  |
|    | 8.4  | Test methods   | . 15 |  |
|    | 8.4.1  | General  | . 15 |  |
|    | 8.4.2  | Magnetic properties  | . 15 |  |
|    | 8.4.3  | Geometrical characteristics and tolerances                             | . 16 |  |
|    | 8.4.4  | Technological characteristics  | . 16 |  |
|    | 8.5  | Retests  | . 17 |  |
| 9  | Mark   | ing, labelling and packaging   | . 17 |  |
| 10 | Com  | plaints  | . 17 |  |
| 11 | 11 Information to be supplied by the purchaser17         |  |      |  |
| Ar | inex A (   | informative) Optional stacking factor for non-oriented coated products | . 18 |  |
| Ar | Annex B (informative) Optional magnetic specifications19 |  |      |  |

IEC 60404-8-8:2017 © IEC 2017 - 3 -

| Annex C (informative) | Calculation of density values | 20 |
|-----------------------|-------------------------------|----|
| Bibliography          |                               | 21 |

| Table 1 – Magnetic and technological characteristics of non-oriented electrical steel   strip and sheet   | 9  |
|---|----|
| Table 2 – Magnetic and technological characteristics of grain-oriented electrical steel   strip and sheet | 10 |
| Table 3 – Thickness tolerances  | 11 |
| Table 4 – Width tolerance of non-oriented strip and sheet   | 12 |
| Table 5 – Width tolerance of grain oriented electrical steel products                                     | 12 |
| Table A.1 – Optional stacking factor for non-oriented coated products                                     | 18 |
| Table B.1 – Optional magnetic specifications for non-oriented electrical steel strip and sheet            | 19 |

# iTeh STANDARD PREVIEW (standards.iteh.ai)

IEC 60404-8-8:2017 https://standards.iteh.ai/catalog/standards/sist/194afa35-8ae6-49b7-9eb5af79cefdb042/iec-60404-8-8-2017 – 4 –

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

# **MAGNETIC MATERIALS –**

# Part 8-8: Specifications for individual materials – Thin electrical steel strip and sheet for use at medium frequencies

### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible <u>6in</u> (their <u>inational</u> and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter. af79cefdb042/iec-60404-8-8-2017
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60404-8-8 has been prepared by IEC technical committee 68: Magnetic alloys and steels.

This second edition cancels and replaces the first edition published in 1991.

This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- extension of the range of electrical steels to include the improved grades.

The text of this International Standard is based on the following documents:

| CDV        | Report on voting |  |  |
|------------|------------------|--|--|
| 68/546/CDV | 68/562/RVC       |  |  |

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60404 series, under the general title *Magnetic materials*, can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date. (standards.iteh.ai)

IEC 60404-8-8:2017 https://standards.iteh.ai/catalog/standards/sist/194afa35-8ae6-49b7-9eb5af79cefdb042/iec-60404-8-8-2017

# MAGNETIC MATERIALS –

# Part 8-8: Specifications for individual materials – Thin electrical steel strip and sheet for use at medium frequencies

#### 1 Scope

This part of IEC 60404 defines the grades of thin non-oriented electrical steel strip and sheet in nominal thicknesses of 0,05 mm, 0,10 mm, 0,15 mm, 0,20 mm, 0,25 mm, 0,30 mm and 0,35 mm and of thin grain-oriented electrical steel strip and sheet in nominal thicknesses of 0,05 mm, 0,10 mm, 0,15 mm and 0,18 mm. In particular, it gives general requirements, magnetic properties, geometric characteristics and tolerances, technological characteristics, as well as inspection procedures.

NOTE For thin non-oriented electrical steel strip and sheet, other nominal thicknesses (i.e. 0,12 mm, 0,18 mm, 0,23 mm and 0,27 mm) can be agreed between the manufacturer and the purchaser.

This document applies to electrical steel strip and sheet supplied in the finally annealed condition in coils or sheets and intended for the construction of magnetic circuits predominantly used at frequencies in the range from 100 Hz to 10 kHz.

# iTeh STANDARD PREVIEW (standards.iteh.ai)

# 2 Normative references (sta

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this documentolF or dated references, only the edition cited applies. For undated references athe/latest edition/of the referenced document (including any amendments) applies. af79cefdb042/iec-60404-8-8-2017

IEC 60050-121, International Electrotechnical Vocabulary – Part 121: Electromagnetism (available at http://www.electropedia.org/)

IEC 60050-221, International Electrotechnical Vocabulary – Chapter 221: Magnetic materials and components (available at http://www.electropedia.org/)

IEC 60404-2, Magnetic materials – Part 2: Methods of measurement of the magnetic properties of electrical steel sheet and strip by means of an Epstein frame

IEC 60404-9, Magnetic materials – Part 9: Methods of determination of the geometrical characteristics of magnetic steel sheet and strip

IEC 60404-10, Magnetic materials – Part 10: Methods of measurement of magnetic properties of magnetic steel sheet and strip at medium frequencies

IEC 60404-13, Magnetic materials – Part 13: Methods of measurement of resistivity, density and stacking factor of electrical steel strip and sheet

ISO 404, Steel and steel products – General technical delivery requirements

ISO 7799, Metallic materials – Sheet and strip 3 mm thick or less – Reverse bend test

ISO 10474, Steel and steel products – Inspection documents

# 3 Terms and definitions

For the purposes of this document, the terms and definitions given in IEC 60050-121 and IEC 60050-221 and the following apply.

#### 3.1

#### number of bends

number of alternate bends possible before the appearance of the first crack in the base metal visible to the naked eye

Note 1 to entry The number of bends constitutes an indication of the ductility of the product.

#### 3.2

#### edge camber

greatest distance between a longitudinal edge of a length of strip or a sheet and the line joining the two extremities of the measured length of this edge

Note 1 to entry: See IEC 60404-9.

## 4 Classification

The grades covered by this document are classified according to the maximum value of the specific total loss in watts per kilogram and according to the nominal thickness of the product<sup>1</sup> (0,05 mm, 0,10 mm, 0,15 mm, 0,20 mm, 0,25 mm, 0,30 mm and 0,35 mm for non-oriented electrical steel; 0,05 mm, 0,10 mm, 0,15 mm and 0,18 mm for grain-oriented electrical steel).

## 5 Designation

# (standards.iteh.ai)

#### IEC 60404-8-8:2017

The steel name comprises the following lin/the lorder given 35-8ae6-49b7-9eb5-

af79cefdb042/iec-60404-8-8-2017

a) the characteristic letters:

- NO for non-oriented electrical steel;
- GO for grain-oriented electrical steel;
- b) one hundred times the nominal thickness of the product, in millimetres;
- c) the specified value of the maximum specific total loss at 1,0 T and the given frequency for non-oriented electrical steel grades.

EXAMPLE: NO 20-13: non-oriented strip or sheet in nominal thickness of 0,20 mm with a maximum specific total loss of 13 W/kg at 1,0 T and 400 Hz.

### 6 General requirements

#### 6.1 **Production process**

The production process of the steel and its chemical composition are left to the discretion of the manufacturer.

### 6.2 Form of supply

The product is supplied in coils in the case of strip and in bundles in the case of sheets.

The mass of the coils or the bundles of sheets shall be agreed between the manufacturer and the purchaser at the time of enquiry and order.

<sup>1</sup> In the rest of the document, the word "product" is used to mean "strip and sheet".

The recommended value for the internal diameter of coils is 508 mm; however, another value (e.g. 400 mm) may be agreed for the internal diameter of coils between the manufacturer and the purchaser.

The strip shall be of constant width and wound in such a manner that the edges are superimposed in a regular manner and that the side faces of the coil are substantially flat.

The coils shall be sufficiently tightly wound in order that they do not collapse under their own weight.

The strip may exhibit welds or interleaves resulting from the removal of defective zones, subject to prior agreement between the manufacturer and the purchaser at the time of enquiry and order. The value of the additional thickness due to the weld shall be the subject of an agreement. If necessary, the marking of welds or interleaves may form the subject of a special agreement.

For coils containing repair welds or interleaves, each part of the strip shall be of the same grade.

The edges of parts welded together shall not be so much out of alignment as to affect the further processing of the product.

Sheets which make up each bundle shall be stacked so that the side faces are substantially flat and approximately perpendicular to the top face. **PREVIEW** 

# 6.3 Delivery condition (standards.iteh.ai)

Products according to this document are delivered without coating or with a coating on one or both sides. Different types of coating can be provided (see IEC 60404-1-1).

s://standards.iteh.ai/catalog/standards/sist/194afa35-8ae6-49b7-9 af79cefdb042/jec-60404-8-8-2017

#### 6.4 Surface condition

The surfaces shall be smooth and clean, free from grease and rust<sup>2</sup>. Dispersed defects such as scratches, blisters, cracks, etc. are permitted if they are within the limits of the tolerances on thickness and if they are not detrimental to the correct use of the supplied products.

The insulation coating present on the surface of the product shall be sufficiently adherent so that it does not become detached during cutting operations or heat treatment under conditions specified by the supplier.

If the product is to be immersed in a fluid, an agreement between the manufacturer and the purchaser, initiated by the purchaser, should be reached to ensure compatibility between the fluid and the coating.

### 6.5 Suitability for cutting

The product shall be suitable for cutting accurately into the usual shapes at any point when appropriate cutting tools are used.

<sup>&</sup>lt;sup>2</sup> Not to be confused with some coloration of the insulating coating inherent to the manufacturing process.

## 7 Technical requirements

#### 7.1 Magnetic properties

#### 7.1.1 Magnetic polarization

The specified minimum values of magnetic polarization for a magnetic field strength of 5 000 A/m (peak value) and at 50 Hz for non-oriented electrical steel shall be as given in Table 1.

-9-

| Steel name | Nominal<br>thickness | al<br>ss Waximum specific<br>total loss at 1,0 T<br>and <sup>b,c</sup><br>W/kg |                 | Minimum<br>magnetic<br>polarization<br>at 50 Hz<br>for 5 000 A/m <sup>d</sup> | Minimum<br>stacking<br>factor <sup>a</sup> | Minimum<br>number of<br>bends | Conventional<br>density <sup>e</sup><br>kɑ/dm <sup>3</sup> |
|------------|----------------------|--|-----------------|---|--|-------------------------------|--|
|            |                      | at 400 Hz  | at 1 000 Hz     | т   |  |                               |  |
| NO 5-45    | 0,05                 | Ι  | 45              | 1,50  | 0,88                                       | C                             | 7 60   |
| NO 10-13   | 0,10                 | 13   | -               | 1,55  | 0,91                                       | 2                             | 7,60   |
| NO 15-11   | 0.45                 | 11   | -               | 1,55  | 0.02                                       | 0                             | 7.00   |
| NO 15-14   | 0,15                 | 14   | -               | 1,55  | 0,92                                       | 2                             | 7,60   |
| NO 20-13   | 0,20                 | 1 <sup>3</sup> e   | h STA           | ND 1/58RD   | PREVI                                      | EW,                           | 7.60   |
| NO 20-15   |                      | 15   | Tata            | 1,59  |  | 2                             | 7,00   |
| NO 25-14   | 0.25                 | 14   | (sta            | 1,59  |  | 0                             | 7 60   |
| NO 25-17   | - 0,25               | 17   | -               | 1,60<br>IFC 60404-8-8:20  | 0,94                                       | 2                             | 7,00   |
| NO 30-16   | 0,30                 | https1,6stand  | lards.iteh.ai/c | atalog/stahaards/sist/1   | 94afa35-8ae6-4                             | 9b7-9eb5-                     | 7.60   |
| NO 30-19   |                      | 19   | _af79c          | efdb042/iç6060404-8   | -8-2017                                    | 2                             | 7,00   |
| NO 35-19   | 0,35                 | 19   | -               | 1,60  | 0.05                                       | 2                             | 7,60   |
| NO 35-22   |                      | 22   | _               | 1,60  | 0,95                                       | 2                             | 7,65   |

Table 1 – Magnetic and technological characteristics of non-oriented electrical steel strip and sheet

<sup>a</sup> Values determined on test specimens without coating. For coated products, the values given in Annex A, Table A.1 apply.

<sup>b</sup> For some steel grades in nominal thicknesses of 0,20 mm; 0,30 mm and 0,35 mm values for the optional maximum specific total loss at 1,0 T and 700 Hz are given in Annex B and may be agreed between the manufacturer and the purchaser at the time of enquiry and order.

<sup>c</sup> For some steel grades in nominal thicknesses of 0,25 mm and 0,30 mm, values for the optional maximum specific total loss at 1,0 T and 1 000 Hz are given in Annex B and may be agreed between the manufacturer and the purchaser at the time of enquiry and order.

<sup>d</sup> The values of minimum magnetic polarization at 50 Hz for 2 500 A/m and 10 000 A/m may be agreed between the manufacturer and the purchaser at the time of enquiry and order (see Annex B).

<sup>e</sup> Other values may be agreed between the manufacturer and the purchaser, see Annex C.

The specified minimum values of magnetic polarization for a magnetic field strength of 800 A/m (peak value) and at 50 Hz for grain-oriented electrical steel shall be as given in Table 2.