



SLOVENSKI STANDARD
SIST ISO 13545:2001
01-junij-2001

98 H5`dc`fUh`cdi`j`_[g]b]`
?cbWbhfUh]gj]b Yj Y[Ugi`Z[XU!`8c`c Yj Ub`Y`gj]bWU!`H]f]a Yff]`g_Ua YfcXU`n

Lead sulfide concentrates -- Determination of lead content -- EDTA titration method after acid digestion

iTeh STANDARD PREVIEW

Concentrés sulfurés de plomb -- Dosage du plomb -- Méthode par titrage à l'EDTA après digestion acide

[SIST ISO 13545:2001](https://standards.iteh.ai/catalog/standards/sist/bec98d44-4aa6-45e5-9f05-cc5d5c768bc9/sist-iso-13545-2001)

Ta slovenski standard je istoveten z: **ISO 13545:2000**

ICS:

73.060.99 Druge rude

Other metalliferous minerals

SIST ISO 13545:2001

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13545:2001](#)

<https://standards.iteh.ai/catalog/standards/sist/bec98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001>

INTERNATIONAL STANDARD

ISO
13545

First edition
2000-03-01

Lead sulfide concentrates — Determination of lead content — EDTA titration method after acid digestion

*Concentrés sulfurés de plomb — Dosage du plomb — Méthode par titrage
à l'EDTA après digestion acide*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13545:2001](https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001)

[https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-
cc5d3c768bc9/sist-iso-13545-2001](https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001)



Reference number
ISO 13545:2000(E)

© ISO 2000

ISO 13545:2000(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 13545:2001](https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001)

<https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
Foreword.....	iv
1 Scope	1
2 Normative references	1
3 Principle.....	1
4 Reagents.....	2
5 Apparatus	4
6 Sampling.....	4
7 Procedure	5
8 Expression of results	7
9 Accuracy.....	8
10 Test report	10
Annex A (normative) Procedure for the preparation and determination of the mass of a predried test portion.....	11
Annex B (normative) Flowchart of the procedure for the acceptance of analytical values for test samples.....	13
Annex C (informative) Derivation of precision equations.....	14

<https://standards.iteh.ai/catalog/standards/sist/bec98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001>

ISO 13545:2000(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 13545 was prepared by Technical Committee ISO/TC 183, *Copper, lead and zinc ores and concentrates*.

Annexes A and B form a normative part of this International Standard. Annex C is for information only.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 13545:2001

<https://standards.iteh.ai/catalog/standards/sist/bec98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001>

Lead sulfide concentrates — Determination of lead content — EDTA titration method after acid digestion

WARNING — This International Standard may involve hazardous materials, operations and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies a lead sulfate precipitation EDTA titrimetric method after acid decomposition for determination of the lead content of lead sulfide concentrates.

The method is applicable to lead sulfide concentrates having lead content in the range 50 % (*m/m*) to 80 % (*m/m*). The method is not applicable to lead concentrates containing more than 1 % (*m/m*) of barium.

2 Normative references

The following normative documents contain certain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements*.

ISO 648:1977, *Laboratory glassware — One-mark pipettes*.

ISO 1042:1998, *Laboratory glassware — One-mark volumetric flasks*.

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods*.

ISO 4787:1984, *Laboratory glassware — Volumetric glassware — Methods for use and testing of capacity*.

ISO 9599:1991, *Copper, lead and zinc sulfide concentrates — Determination of hygroscopic moisture in the analysis sample — Gravimetric method*.

ISO Guide 35:1989, *Certification of reference materials — General and statistical principles*.

3 Principle

Decomposition of the test portion in nitric and sulfuric acids and bromine, and removal of arsenic, antimony and tin by hydrobromic acid treatment. Separation of lead from interfering elements by precipitation of lead sulfate. Dissolution of the precipitate in an ammonium acetate solution. Titration of the solution with EDTA using xylenol orange as the indicator.

ISO 13545:2000(E)**4 Reagents**

During the analysis, use only reagents of recognized analytical grade and water that complies with grade 2 of ISO 3696.

4.1 Dilute hydrochloric acid (1+1)

To 500 ml of water slowly add 500 ml of hydrochloric acid (ρ_{20} 1,16 g/ml to 1,19 g/ml).

4.2 Nitric acid, ρ_{20} 1,42 g/ml**4.3 Dilute nitric acid, (1+3)**

To 300 ml of water slowly add 100 ml of nitric acid (4.2).

4.4 Dilute nitric acid, (1+9)

To 450 ml of water slowly add 50 ml of nitric acid (4.2).

4.5 Perchloric acid, ρ_{20} 1,70 g/ml**4.6 Hydrofluoric acid, ρ_{20} 1,14 g/ml****4.7 Hydrobromic acid, ρ_{20} 1,50 g/ml****4.8 Dilute sulfuric acid, (1+1)**

To 500 ml of water slowly add, with stirring and cooling, 500 ml of sulfuric acid (ρ_{20} 1,84 g/ml).

4.9 Dilute sulfuric acid, (1+99)

To 490 ml of water slowly add 10 ml of dilute sulfuric acid (4.8).

4.10 Dilute sulfuric acid washing solution

To 500 ml of sulfuric acid (4.9) add 50 ml of ethanol or methanol (4.21) and cool.

4.11 Nitration mixture

To 250 ml of nitric acid (4.2) slowly add, with stirring and cooling, 250 ml of sulfuric acid (ρ_{20} 1,84 g/ml).

4.12 Dilute ammonium hydroxide, (1+1)

To 500 ml of water slowly add 500 ml of ammonium hydroxide (ρ_{20} 0,90 g/ml).

4.13 Lead metal, minimum 99,99 % purity

The surface of the metal shall be free from oxide prior to use and may be cleaned by immersing the metal in nitric acid (4.4) for 1 min, washing well with water followed by acetone and drying in an oven at 50 °C.

4.14 Bromine**4.15 Sodium chloride****4.16 Potassium chloride****4.17 Sodium peroxide**

4.18 Fusion mixture, one part sodium carbonate mixed with one part potassium carbonate.

4.19 Ammonium acetate solution

Dissolve 250 g of ammonium acetate in water and dilute to 1 000 ml. Add 25 ml of acetic acid to the solution and mix.

4.20 Ammonium acetate washing solution

To 950 ml of water, add 50 ml of ammonium acetate solution (4.19).

4.21 Ethanol [99,5 % (V/V)] or **methanol** [99,5 % (V/V)].

4.22 L (+) - ascorbic acid

4.23 Iron(III) solution, (10 mg Fe/ml)

Dissolve 1 g of iron in 30 ml of dilute hydrochloric acid (4.1) by heating. Add 5 ml of nitric acid (4.2) to oxidize to iron(III) ion, cool and dilute to 100 ml with water. This solution shall be used for matrix matching.

4.24 Zinc solution, (10 mg Zn/ml)

Dissolve 1 g of zinc [minimum purity 99,9 % and maximum lead content 0,001 % (m/m)] in 20 ml of dilute hydrochloric acid (4.1) by heating, cool and dilute to 100 ml with water. This solution shall be used for matrix matching.

4.25 Lead standard solution, (0,1 mg Pb/ml)

Weigh 0,1 g of clean lead metal (4.13), accurately to the nearest 0,1 mg, transfer it to a 200 ml beaker and decompose with 20 ml of dilute nitric acid (4.3). Heat to remove nitrogen oxides, cool to room temperature and add about 50 ml of water. Transfer to a 1 000 ml volumetric flask and dilute to the mark with water.

4.26 Disodium ethylenediaminetetraacetic acid solution, (0,01 mol/l EDTA solution)

Dissolve 0,38 g of disodium ethylenediaminetetraacetate (dihydrate) in 100 ml of water. This solution is used for titration of bismuth in the alternative titration described in 7.6.

4.27 Disodium ethylenediaminetetraacetic acid volumetric standard solution, (0,025 mol/l EDTA standard solution).

4.27.1 Preparation

Dissolve 9,4 g of disodium ethylenediaminetetraacetate (dihydrate) in 1 000 ml of water; 1 ml of this solution corresponds to about 5,2 mg of lead. Standardize by the procedure specified in 4.27.2.

4.27.2 Standardization

Accurately weigh three samples of clean lead metal (4.13), each of 200 mg, to the nearest 0,1 mg, and transfer them to three 400 ml conical beakers. Record these masses as m_1 , m_2 and m_3 .

NOTE The mass of lead metal should match the estimated mass of lead in the test portion.

Add 20 ml of dilute nitric acid (4.3), cover with a watch glass and heat to complete dissolution. After rinsing the underside of the watch glass and inside of the conical beakers with water, boil gently to expel nitrogen oxides and cool. Add 30 ml of ammonium acetate solution (4.19) and dilute the solution to about 150 ml with water. Adjust the pH of the solution to a value between 5,5 and 5,7 with dilute ammonium hydroxide (4.12) using a pH meter (5.6). Continue the standardization in accordance with the procedure specified in 7.6. Record the volume of EDTA standard solution used in the titration as V_1 , V_2 and V_3 .

ISO 13545:2000(E)

Calculate the factors f_1 , f_2 and f_3 using the following equation:

$$f_1 = \frac{m_1}{V_1} \quad f_2 = \frac{m_2}{V_2} \quad f_3 = \frac{m_3}{V_3} \quad (1)$$

Calculate, to four significant figures, the mean factor, f , for the EDTA standard solution provided that the range of the values of f_1 , f_2 and f_3 does not exceed 0,02 mg/ml. If this range is exceeded, repeat the standardization.

4.29 Xylenol orange solution, (1 g/l)

Dissolve 0,1 g of xylenol orange in 100 ml of water.

5 Apparatus

Ordinary laboratory equipment and

5.1 Volumetric glassware, class A, complying with ISO 385-1, ISO 648, and ISO 1042 and used in accordance with ISO 4787.

5.2 Analytical balance, sensitive to 0,1 mg.

5.3 Platinum crucibles or zirconium crucibles.

5.4 Atomic absorption spectrometer (AAS), with lead hollow cathode lamp.

Instrument conditions:

— flame – air/acetylene;

[SIST ISO 13545:2001](https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001)

— wavelength – 217 or 283,3 nm.

<https://standards.iteh.ai/catalog/standards/sist/bee98d44-4aa6-45e5-9f05-cc5d3c768bc9/sist-iso-13545-2001>

5.5 ICP atomic emission spectrometer (ICP), optional.

5.6 pH meter.

6 Sampling**6.1 Test sample**

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE An air-equilibrated test sample is not required if predried test portions are to be used (see annex A).

6.2 Test portion

Taking multiple increments, extract a mass of test portion from the test sample and weigh 0,25 g to 0,5 g to the nearest 0,1 mg. The test portion weighed shall contain about 200 mg lead. At the same time as test portions are being weighed for analysis, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599. Alternatively, the method specified in annex A may be used to prepare predried test portions directly from the laboratory sample.

7 Procedure

7.1 Number of determinations

Carry out the determinations at least in duplicate, as far as possible under repeatability conditions, on each test sample.

NOTE Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment within short intervals of time.

7.2 Blank test

Carry out a blank test in parallel with the analysis using the same quantities of all reagents but omitting the test portion.

7.3 Decomposition of test portion

Transfer the test portion to a 400 ml conical beaker and moisten with 5 ml of water. Add 10 ml to 20 ml of nitric acid (4.2) and 1 ml to 2 ml of bromine (4.14) in small portions, cover with a watch glass and heat gradually to decompose the test portion completely. Cool slightly, rinse the underside of the watch glass and the inside of the conical beaker with a minimum volume of warm water. Add 10 ml of dilute sulfuric acid (4.8) and heat until strong white fumes are evolved, then cool.

If the residue appears dark (presence of carbon), slowly add a small amount of the nitration mixture (4.11) to the hot solution until the solution is colourless or bluish and heat until strong white fumes are evolved, then cool.

Carefully add 5 ml of water and 10 ml of hydrobromic acid (4.7), heat gradually until strong white fumes are evolved then cool. Add 5 ml of dilute sulfuric acid (4.8) and 10 ml of hydrobromic acid (4.7), again heat gradually until strong white fumes are evolved then cool.

NOTE The above step is not required if the sample contains less than 0,5 % (m/m) of arsenic, tin, antimony and/or selenium.

7.4 Formation of lead sulfate

Carefully rinse the wall of the conical beaker with water and adjust the volume to about 100 ml with water. Heat gradually until boiling to dissolve the salts and cool to room temperature. Add 10 ml of ethanol or methanol (4.21), allow the lead sulfate precipitate to settle for at least 2 h.

NOTE It is preferable to allow the lead to settle overnight using the method described in NOTE 1 under 7.5.

7.5 Separation and dissolution of lead sulfate

Filter the precipitate through a fine porosity filter paper and wash the inside of the beaker two or three times with dilute sulfuric acid washing solution (4.10). Wash the precipitate on the filter paper three or four times with dilute sulfuric acid washing solution (4.10), then with a small amount of water. Reserve the filtrate and washing in a beaker (400 ml) for determination of lead by AAS (as described in 7.7). Rinse the precipitate into the original 400 ml conical beaker with warm water.

NOTE 1 Instead of using the above steps, the following method is available:

Initial decanting of liquid through a fine porosity filter paper leaving precipitate in the beaker. Washing the precipitate three or four times with dilute sulfuric acid washing solution (4.10) in the beaker by decantation, then with water. Washing the precipitate on the filter paper three or four times with dilute sulfuric acid washing solution (4.10) then with water. Reserving the filtrate and washing in a beaker (400 ml) for determination of lead by AAS (as described in 7.7).

Place the original conical beaker containing the main precipitate under the original funnel. Add 30 ml of warm ammonium acetate solution (4.19) to the filter paper in order to dissolve the lead sulfate on the filter paper, then wash with hot water. Collect the washing in the original conical beaker. Wash around the inside of the beaker with