



SLOVENSKI STANDARD
SIST ISO 13291:2000
01-junij-2000

Prečiščeni koncentri sulfidov železa -- Določitev vsebnosti železa -- Postopek ekstrakcije s topilom in titrimetrična metoda

Zinc sulfide concentrates -- Determination of zinc content -- Solvent extraction and EDTA titrimetric method

iTeh STANDARD PREVIEW

Concentrés sulfurés de zinc -- Dosage du zinc -- Méthode par extraction à l'aide d'un solvant et titrage à l'EDTA

Ta slovenski standard je istoveten z: [SIST ISO 13291:2000](https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a05700597/sist-iso-13291-2000)
ISO 13291:1997

ICS:

73.060.99 Druge rude Other metalliferous minerals

SIST ISO 13291:2000 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 13291:2000

<https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000>

INTERNATIONAL
STANDARD

ISO
13291

First edition
1997-11-15

**Zinc sulfide concentrates — Determination
of zinc content — Solvent extraction and
EDTA titrimetric method**

*Concentrés sulfurés de zinc — Dosage du zinc — Méthode par extraction à
l'aide d'un solvant et titrage à l'EDTA*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13291:2000](https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000)

[https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-
d87a03700597/sist-iso-13291-2000](https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000)



Reference number
ISO 13291:1997(E)

ISO 13291:1997(E)

| Contents | Page |
|-------------------------------|------|
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Principle | 1 |
| 4 Reagents | 2 |
| 5 Apparatus | 3 |
| 6 Sample | 3 |
| 7 Procedure | 3 |
| 8 Expression of results | 5 |
| 9 Precision | 6 |
| 10 Test report | 8 |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Annexes

[SIST ISO 13291:2000
https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000](https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000)

| | |
|--|----|
| A (normative) Procedure for the preparation and determination of the mass of a predried test portion | 9 |
| B (normative) Flowchart of the procedure for the acceptance of analytical values for test samples | 11 |
| C (normative) Elements that interfere with this method | 12 |
| D (informative) Derivation of precision equations | 13 |
| E (informative) Bibliography | 18 |

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

iTeh STANDARD PREVIEW

International Standard ISO 13291 was prepared by Technical Committee ISO/TC 183, *Copper, lead and zinc ores and concentrates*.

Annexes A to C form an integral part of this International Standard.

Annexes D and E are for information only.
<https://standards.iteh.ai/catalog/standards/sist/13291-2000/iso-13291-1997>
d87a03700597/sist-iso-13291-2000

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13291:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000>

Zinc sulfide concentrates — Determination of zinc content — Solvent extraction and EDTA titrimetric method

1 Scope

This International Standard specifies a solvent extraction/titrimetric method for the determination of the zinc content of zinc sulfide concentrates.

The method is applicable to zinc sulfide concentrates with zinc content in the range from 11 % (*m/m*) to 62 % (*m/m*).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-1:1984, *Laboratory glassware — Burettes - Part I: General requirements.*

[SIST ISO 13291:2000](https://standards.iteh.ai/SIST/ISO/13291/2000)

ISO 648:1977, *Laboratory glassware — One-mark pipettes.*

<https://standards.iteh.ai/standards/iso/648/1977/iso-648-1977/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000>

ISO 1042:—¹⁾, *Laboratory glassware — One-mark volumetric flasks.*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods.*

ISO 4787: 1984, *Laboratory glassware — Volumetric glassware — Methods for use and testing of capacity.*

ISO 9599: 1991, *Copper, lead and zinc sulfide concentrates — Determination of hygroscopic moisture in the analysis sample — Gravimetric method.*

ISO Guide 35: 1989, *Certification of reference materials — General and statistical principles.*

3 Principle

A test portion of zinc concentrate is dissolved in bromine and nitric acid. Any remaining insoluble residue is dissolved in hydrofluoric and perchloric acids. A zinc thiocyanate complex is selectively extracted into methyl isobutyl ketone after screening of some elements with thiourea and citrate ions. Partially extracted cadmium is screened with iodide ions before the final titration as explained in annex C. Cobalt is extracted and must be determined separately if present at concentration levels exceeding 0,05 %. Zinc is determined by titration with EDTA solution at pH 5,5.

1) To be published. (Revision of ISO 1042:1983)

4 Reagents

During the analysis, only reagents of recognized analytical grade and water that complies with grade 2 of ISO 3696 shall be used.

4.1 Zinc metal, minimum purity 99,99 %, free from oxide prior to use.

The surface of the metal may be cleaned by immersing the metal in hydrochloric acid (4.2), diluted 1+9 for 1 min, washed well with water followed by an acetone rinse and dried in an oven at 50°C.

4.2 Hydrochloric acid, (ρ_{20} 1,16 g/ml to 1,19 g/ml).

4.3 Bromine

4.4 Nitric acid, (ρ_{20} 1,42 g/ml)

4.5 Hydrochloric acid, (ρ_{20} 1,16 g/ml to 1,19 g/ml) diluted (1+4)

Add 200 ml of hydrochloric acid (4.2) to 800 ml of water.

4.6 Hydrofluoric acid, (ρ_{20} 1,13 g/ml to 1,15 g/ml)

4.7 Perchloric acid, (ρ_{20} 1,54 g/ml)

4.8 Ammonia, (ρ_{20} 0,89 g/ml)

4.9 4-methyl-2-pentanone (methyl isobutyl ketone)

4.10 Ethanol, pure or denatured

4.11 Screening solution

[SIST ISO 13291:2000
https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000](https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000)

Dissolve 60 g of thiourea, 100 g of di-ammonium citrate and 200 g of ammonium thiocyanate in water and dilute to 1 l. Filter if necessary.

4.12 Sodium fluoride solution (20 g/l)

Dissolve 20 g of sodium fluoride in water. Dilute to 1 l.

4.13 Thiourea solution (100 g/l)

Dissolve 100 g of thiourea in water and dilute to 1 l.

4.14 Buffer solution

Dissolve 250 g of hexamethylenetetramine in water. Add 60 ml of acetic acid (ρ_{20} 1,05 g/ml) and dilute to 1 l.

4.15 EDTA standard volumetric solution (0,05 mol/l)

Dissolve 18,6 g of the di-sodium salt of ethylenediaminetetraacetic acid dihydrate (EDTA) in water. Dilute to 1 l.

4.16 Potassium iodide solution (1 000 g/l)

Dissolve 100 g of potassium iodide in water and dilute to 100 ml.

Prepare fresh on the day of use.

4.17 Xylenol orange indicator (1 % *m/m*)

Mix 1 g of the sodium salt of xylenol orange with 99 g of potassium nitrate crystals by gently grinding in a ceramic mortar with a pestle. Mixing is considered complete when the colour is uniform throughout.

4.18 Iron stock solution

Dissolve 45 g of iron(III) nitrate nonahydrate ($\text{Fe}(\text{NO}_3)_3 \cdot 9\text{H}_2\text{O}$) in water and dilute to 1 l.

5 Apparatus

5.1 Ordinary laboratory equipment and

5.2 Volumetric glassware, of class A complying with ISO 385-1, ISO 648 and ISO 1042 and used in accordance with ISO 4787.

5.3 Platinum crucibles, of 25 ml capacity.

5.4 Balance, capable of being read to 0,1 mg.

5.5 Oven, with temperature controlled at $105\text{ °C} \pm 5\text{ °C}$.

5.6 Muffle furnace, having a maximum required operating temperature higher than 800 °C.

5.7 Laboratory hotplate.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

6 Sample

[SIST ISO 13291:2000
https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000](https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000)

6.1 Test sample

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE — A test sample is not required if predried test portions are to be used (see annex A).

6.2 Test portion

Take multiple increments, extract a test portion from the test sample in such a manner that it is representative of the dish or tray. Weigh, to the nearest 0,1 mg, 2,5 g of test sample. At the same time as the test portion is weighed, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599.

Alternatively, the method specified in annex A may be used to prepare predried test portions directly from the laboratory sample.

7 Procedure

7.1 Number of determinations

Carry out the determinations at least in duplicate, as far as possible under repeatability conditions, on each test sample.

NOTE — Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment within short intervals of time.

7.2 Blank test

Determine a reagent blank. It is advisable to perform duplicate blank determinations every time an analysis is carried out on a laboratory sample. The blank samples are carried through the whole procedure apart from where no laboratory sample test portion is required. However, 5 ml of iron stock solution (4.18) should be added to assist in the determination of turbidity. The volume of EDTA titrant used is V_b .

7.3 Dissolution of test portion

Place the test portion in a 300 ml narrow-necked conical flask. Moisten the material with about 20 ml of water and add 2 ml to 3 ml of bromine (4.3). Allow to react at ambient temperature for 15 min swirling the flask and contents from time to time. Add 15 ml of nitric acid (4.4) and leave for a further 15 min. Place the flask on a hotplate (5.7) and bring gently to the boil to expel all bromine vapours. Cool, add 100 ml of water, heat to boiling, cool.

If no insoluble material is present, transfer the liquid to a 500 ml one-mark volumetric flask, rinsing the conical flask thoroughly. Make up to the mark with water.

If insoluble material is present, filter through a medium speed filter paper into a 500 ml one-mark volumetric flask. Rinse the filter thoroughly with water. Place the filter and insoluble residue in a platinum crucible (5.3) (see Note) and gently ash the paper in the muffle furnace (5.6) set at 800 °C. Add 2 ml of hydrofluoric acid (4.6) and then 5 ml of perchloric acid (4.7). Heat until dense perchloric acid fumes appear. Allow to cool, dilute with about 25 ml of water. Filter if a lead sulfate precipitate appears. Transfer the filtrate to the same one-mark volumetric flask used above. Rinse the filter paper thoroughly and make up to the mark with water.

NOTE — If the sample contains lead, damage to the platinum crucible may occur. In this case, fusion with sodium peroxide in a zirconium crucible is preferable.

7.4 Extraction

Pipette 50,00 ml of the solution obtained in 7.3 into a 250 ml separating funnel. Add ammonia (4.8) dropwise until a slight turbidity develops. Add 5 ml of dilute hydrochloric acid (4.5) and 50 ml of screening solution (4.11). Mix well. Add 80 ml of 4-methyl-2-pentanone (4.9) and shake for 1 min. Allow the phases to separate and slowly transfer the lower aqueous phase to another separating funnel. Perform a second extraction with 20 ml of 4-methyl-2-pentanone (4.9). Separate the phases and discard the aqueous phase. Combine the two separate organic phases in a 400 ml low-form beaker.

Place 1 ml of dilute hydrochloric acid (4.5) and 70 ml of ethanol (4.10) into each of the two separating funnels. Shake well and discharge the contents from both funnels into the 400 ml low-form beaker.

7.5 Titration

Add successively 10 ml of sodium fluoride solution (4.12), 10 ml of thiourea solution (4.13), 20 ml of buffer solution (4.14), 5 ml of potassium iodide solution (4.16) and 0,1 g of xylenol orange indicator (4.17).

Titrate with EDTA solution (4.15) until the colour changes from red to yellow. Titrate very slowly when approaching the equivalence point. Note the volume, V_t , of titrant used.

7.6 Determination of the titration factor of the EDTA standard solution

NOTE — In order to obtain a relative accuracy of between 0,1 % and 0,2 % it is necessary to standardize the EDTA solution with zinc at the same time and under the same conditions as the analysis. It is thus advisable for the calibration to follow the complete set of operating conditions set down for the analysis. Likewise, to improve the repeatability of the calibration it is useful to prepare several zinc reference solutions. Iron is added to the standard solution to assist in the determination of turbidity in 7.4.

The EDTA standard solution should be standardized as follows:

- Weigh into three separate 300 ml conical flasks, between 0,25 g and 1,625 g of zinc (4.1), to the nearest 0,000 1 g, depending on the zinc content of the test sample. Record these masses as m_1 , m_2 and m_3 .
- Add 15 ml of water, 15 ml of nitric acid (4.4) and 5 ml of iron stock solution (4.18). After dissolution of the zinc, boil gently to expel nitrogen oxide gases.
- Cool and transfer to a 500 ml one-mark volumetric flask. Rinse the initial flask thoroughly and add the washings to the volumetric flask. Make up to the mark. Continue the procedure as described in 7.4 and 7.5. Record the volumes of EDTA standard solution used in the titrations as V_1 , V_2 and V_3 .

Calculate the intermediate factor, f_{i_x} , for each beaker using the following equation:

$$f_{i_x} = m_x / V_x \quad \text{for } x = 1 \text{ to } 3 \quad \text{--- (1a)}$$

where

f_{i_x} is the factor obtained from the titration;

m_x is the mass of zinc weighed, in grams;

V_x is the volume of EDTA solution, in millilitres.

If the range of values for f_{i_1} , f_{i_2} , f_{i_3} exceeds 0,000 01 g/ml then repeat the standardization. Otherwise calculate the mean factor as follows:

$$f = \frac{f_{i_1} + f_{i_2} + f_{i_3}}{3} \quad \text{--- (1b)}$$

SIST ISO 13291:2000
<https://standards.iteh.ai/catalog/standards/sist/7d7f7b18-3d73-4b60-99fd-d87a03700597/sist-iso-13291-2000>

8 Expression of results

The zinc content of the test portion, W_{Zn} , expressed as a percentage by mass, is given by the following equation:

$$W_{Zn} = \frac{(V_t - V_b) \times f \times 100}{m} \times \frac{100}{100 - H} \quad \text{... (2)}$$

where

f is the zinc equivalence factor, in grams per millilitre, determined in 7.6;

H is the hygroscopic moisture content, as a percentage of the test portion (in the case of a predried test portion being used $H = 0$);

m is the mass, in grams, of the test portion;

V_b is the volume of EDTA solution (4.15), in millilitres, used to titrate the blank solution;

V_t is the volume of EDTA solution (4.15), in millilitres, used to titrate the sample solution.

Calculate the zinc content of the test portion to the second decimal place.