

Designation: D 4670 - 97 (Reapproved 2002)

Standard Test Method for Polyurethane Raw Materials: Determination of Suspended Matter In Polyols ¹

This standard is issued under the fixed designation D 4670; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This test method covers a procedure for visual inspection to determine the presence of insoluble foreign material in polyols.
- 1.2 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Note 1-There is no similar or equivalent ISO standard.

2. Referenced Documents

2.1 *ASTM Standards*: ² D 883 Terminology Relating to Plastics

3. Terminology

3.1 Terminology in this test method is in accordance with Terminology D 883.

4. Significance and Use

4.1 This test method is suitable as a quality control or specification test.

5. Procedure

5.1 Invert a transparent glass bottle containing the sample and examine by transmitted light for the presence of suspended matter.

6. Report

6.1 Report the presence or absence of suspended matter.

7. Precision and Bias

7.1 No statement is made about the precision or the bias since this test method merely states whether there is conformance to the criteria for success specified in the procedure.

8. Keywords

8.1 polyols; polyurethane raw materials; suspended matter

Current edition approved November 10, 2002. Published January 2003. Originally approved in 1987. Last previous edition approved in 1997 as D 4670 – 97.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).

¹ This test method is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.22 on Cellular Materials—Plastics and Elastomers. It was recommended to ASTM by the Society of The Plastics Industry Polyurethane Raw Materials Analysis Committee.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.