

### SLOVENSKI STANDARD SIST EN 60424-5:2009

01-julij-2009

## Feritna jedra - Vodilo o omejitvah površinskih neregularnosti - 5. del: Planarna jedra (IEC 60424-5:2009)

Ferrite cores - Guide on the limits of surface irregularities - Part 5: Planar-cores (IEC 60424-5:2009)

Ferritkerne - Leitfaden für Grenzwerte von sichtbaren Beschädigungen der Kernoberfläche - Teil 5: Planarkerne (IEC 60424-5:2009) VIE W

Noyaux ferrites - Guide relatif aux limites des irrégularités de surface - Partie 5: Noyaux planaires (CEI 60424-5:2009) <u>SIST EN 60424-5:2009</u> https://standards.iteh.ai/catalog/standards/sist/a85f3591-b63c-4319-b458-

Ta slovenski standard je istoveten z: EN 60424-5-2009

<u>ICS:</u>

29.100.10 Magnetne komponente

Magnetic components

SIST EN 60424-5:2009

en



### iTeh STANDARD PREVIEW (standards.iteh.ai)

#### SIST EN 60424-5:2009

## EUROPEAN STANDARD NORME FUROPÉENNE **EUROPÄISCHE NORM**

### EN 60424-5

May 2009

ICS 29,100,10

English version

### Ferrite cores -Guide on the limits of surface irregularities -Part 5: Planar-cores

(IEC 60424-5:2009)

Noyaux ferrites -Guide relatif aux limites des irrégularités de surface -Partie 5: Noyaux planaires (CEI 60424-5:2009)

Ferritkerne -Leitfaden für Grenzwerte von sichtbaren Beschädigungen der Kernoberfläche -Teil 5: Planarkerne (IEC 60424-5:2009)

## iTeh STANDARD PREVIEW

This European Standard was approved by CENELEC on 2009-04-01. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard withou tany alteration 4-5:2009

https://standards.iteh.ai/catalog/standards/sist/a85f3591-b63c-4319-b458 Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## **CENELEC**

European Committee for Electrotechnical Standardization Comité Européen de Normalisation Electrotechnique Europäisches Komitee für Elektrotechnische Normung

#### Central Secretariat: Avenue Marnix 17, B - 1000 Brussels

© 2009 CENELEC -All rights of exploitation in any form and by any means reserved worldwide for CENELEC members.

#### Foreword

The text of document 51/947/FDIS, future edition 1 of IEC 60424-5, prepared by IEC TC 51, Magnetic components and ferrite materials, was submitted to the IEC-CENELEC parallel vote and was approved by CENELEC as EN 60424-5 on 2009-04-01.

The following dates were fixed:

-	latest date by which the EN has to be implemented at national level by publication of an identical national standard or by endorsement	(dop)	2010-01-01
-	latest date by which the national standards conflicting with the EN have to be withdrawn	(dow)	2012-04-01

Annex ZA has been added by CENELEC.

#### **Endorsement notice**

The text of the International Standard IEC 60424-5:2009 was approved by CENELEC as a European Standard without any modification.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

### - 3 -

### Annex ZA

#### (normative)

## Normative references to international publications with their corresponding European publications

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

Publication	<u>Year</u>	Title	<u>EN/HD</u>	<u>Year</u>
IEC 60424-1	_ 1)	Ferrite cores - Guide on the limits of surface irregularities - Part 1: General specification	EN 60424-1	1999 <sup>2)</sup>
IEC 62317-9	- <sup>1)</sup>	Ferrite cores - Dimensions - Part 9: Planar cores	EN 62317-9	2006 <sup>2)</sup>

### iTeh STANDARD PREVIEW (standards.iteh.ai)

<sup>&</sup>lt;sup>1)</sup> Undated reference.

<sup>&</sup>lt;sup>2)</sup> Valid edition at date of issue.



### iTeh STANDARD PREVIEW (standards.iteh.ai)



## **IEC 60424-5**

Edition 1.0 2009-02

# INTERNATIONAL STANDARD

### Ferrite cores – Guideon the limits of surface irregularities Part 5: Planar-cores (standards.iteh.ai)

<u>SIST EN 60424-5:2009</u> https://standards.iteh.ai/catalog/standards/sist/a85f3591-b63c-4319-b458b99f29b81096/sist-en-60424-5-2009

INTERNATIONAL ELECTROTECHNICAL COMMISSION

PRICE CODE

ICS 29.100.10

ISBN 2-8318-1032-6

N

### CONTENTS

FOF	REWO	RD		3
1	Scope	э		5
2	Norm	ative ret	ferences	5
3	Limits	of surf	ace irregularities	6
	3.1	Chips a	Ind ragged edges	6
		3.1.1	Chips and ragged edges on the mating surfaces (see Figures 1, 2 and 3)	6
		3.1.2	Chips and ragged edges on other surfaces	7
	3.2			
	3.3			
	3.4	Pull-ou	t	10
Figu	ure 1 -	- Chip lo	ocation for planar EL-core	6
Figu	ure 2 -	- Chip Io	ocation for low profile E-core	6
-		-	ocation for low profile ER-core	
Figu	ure 4 -	- Cracks	and pull-out location for planar EL-core	10
Figu	ure 5 -	- Cracks	and pull-out location for low profile E-core	11
Figu	ure 6 -	- Cracks	and pull out location for low profile ER core V.I.E.W.	11
Figu	ure 7 -	- Refere	nce dimensions for EL-core and international	11
Figu	ure 8 -	- Refere	nce dimensions for El-core	12
-			nce dimensions for ER-core60424-5:2009 https://standards.iteh.ai/catalog/standards/sist/a85f3591-b63c-4319-b458- b99f29b81096/sist-en-60424-5-2009	
Tab	le 1 –	Allowat	ble areas of chips in mm <sup>2</sup> for planar EL-core	7
Tab	le 2 –	Allowat	ble areas of chips in mm <sup>2</sup> for low profile E-core	8
Tab	le 3 –	Allowat	ble areas of chips in mm <sup>2</sup> for low profile ER-core	8
Tab	le 4 –	Area ar	nd length reference for visual inspection	9
Tab	le 5 –	Limits o	of cracks for planar EL-core	. 12
			of cracks for low profile E-core	
Tab	le 7 –	Limits o	of cracks for low profile ER-core	. 14

60424-5 © IEC:2009(E)

#### INTERNATIONAL ELECTROTECHNICAL COMMISSION

### FERRITE CORES – GUIDE ON THE LIMITS OF SURFACE IRREGULARITIES –

#### Part 5: Planar-cores

### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of the IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC provides no marking procedure to indicate its approval and cannot be rendered responsible for any equipment declared to be in conformity with an IEC Publication.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60424-5 has been prepared by IEC technical committee 51: Magnetic components and ferrite materials.

The text of this standard is based on the following documents:

FDIS	Report on voting
51/947/FDIS	51/950/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 60424 series, under the general title *Ferrite cores – Guide on the limits of surface irregularities*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the maintenance result date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

### iTeh STANDARD PREVIEW (standards.iteh.ai)

### FERRITE CORES – GUIDE ON THE LIMITS OF SURFACE IRREGULARITIES –

#### Part 5: Planar-cores

#### 1 Scope

This part of IEC 60424 gives guidance on allowable limits of surface irregularities applicable to planar-cores in accordance with the relevant generic specification defined in IEC 60424-1.

The relations between the main dimensions of planar E-, ER- and EL-cores differ from those of standard cores. For example, the width of planar cores is larger while the total height is much smaller. Also the thickness of the legs is in most cases smaller than compared to standard cores. Therefore the concept of fixed reference dimensions to determine the length of crack limits yield crack lengths which are not acceptable for this type of core. This part of IEC 60424 follows another concept which relates the crack length to dimensions of the surface on which the crack occurs.

Also the concept to determine the maximum area of chips based on the total mating surface fails in the case of planar cores. The outer legs of planar cores are much thinner than those of standard cores which makes overlapping and gluing much more difficult. A single chip of maximum size on the outer leg may risk the functionality of the core set. Therefore this standard uses as a reference the mating surface on which the chip occurs.

Windings of planar cores are often PCB's which are glued to the inner surfaces of the planar core. For this reason the inner surfaces of standard cores better quality than the inner surfaces of standard cores better quality that allowable area of pull outs in the inner surfaces.

This standard is considered as a sectional specification useful in the negotiation between ferrite core manufacturers and users about surface irregularities.

#### 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60424-1, Ferrite cores – Guide on the limits of surface irregularities – Part 1: General specification

IEC 62317-9, Ferrite cores – Dimensions – Part 9: Planar-cores