
Električni kabli - Nizkonapetostni energetska kabli z nazivno napetostjo do vključno 450/750 V (U_o/U) - 2-12. del: Kabli za splošno uporabo - Raztegljivi priključni vodi s termoplastično PVC izolacijo

Electric cables - Low voltage energy cables of rated voltages up to and including 450/750 V (U_o/U) - Part 2-12: Cables for general applications - Cables with thermoplastic PVC insulation for extensible leads

Kabel und Leitungen - Starkstromleitungen mit Nennspannungen bis 450/750 V (U_o/U) - Teil 2-12: Starkstromleitungen für allgemeine Anwendungen - Wendelleitungen mit thermoplastischer PVCIsolierung

Câbles électriques - Câbles d'énergie basse tension assignée au plus égale à 450/750 V (U_o/U) - Partie 2-12: Câbles pour applications générales - Câbles isolés en PVC thermoplastique pour cordons extensibles

Ta slovenski standard je istoveten z: EN 50525-2-12:2011

ICS:

29.060.20 Kabli Cables

SIST EN 50525-2-12:2011 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 50525-2-12:2011](#)

<https://standards.iteh.ai/catalog/standards/sist/f9b0ad8e-1e66-497d-93fa-1e3765a07a76/sist-en-50525-2-12-2011>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 50525-2-12

May 2011

ICS 29.060.20

Supersedes HD 21.10 S2:2001

English version

**Electric cables -
Low voltage energy cables of rated voltages up to and including 450/750 V
(U_0/U) -
Part 2-12: Cables for general applications -
Cables with thermoplastic PVC insulation for extensible leads**

Câbles électriques -
Câbles d'énergie basse tension de tension
assignée au plus égale à 450/750 V
(U_0/U) -
Partie 2-12: Câbles pour applications
générales -
Câbles isolés en PVC thermoplastique
pour cordons extensibles

Kabel und Leitungen -
Starkstromleitungen mit Nennspannungen
bis 450/750 V (U_0/U) -
Teil 2-12: Starkstromleitungen für
allgemeine Anwendungen -
Wendelleitungen mit thermoplastischer
PVC-Isolierung

[SIST EN 50525-2-12:2011](https://standards.iteh.ai/catalog/standards/sist/19b0ad8e-1e66-497d-93fa-1e3765a07a76/sist-en-50525-2-12-2011)

<https://standards.iteh.ai/catalog/standards/sist/19b0ad8e-1e66-497d-93fa-1e3765a07a76/sist-en-50525-2-12-2011>

This European Standard was approved by CENELEC on 2011-01-17. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the Central Secretariat has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

This European Standard was prepared by the Technical Committee CENELEC TC 20, Electric cables.

The text of the draft was submitted to the formal vote and was approved by CENELEC as EN 50525-2-12 on 2011-01-17.

This document, which is one of a multipart series, supersedes HD 21.10 S2:2001.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN and CENELEC shall not be held responsible for identifying any or all such patent rights.

The following dates were fixed:

- latest date by which the EN has to be implemented
at national level by publication of an identical
national standard or by endorsement (dop) 2012-01-17
- latest date by which the national standards conflicting
with the EN have to be withdrawn (dow) 2014-01-17

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 50525-2-12:2011](https://standards.iteh.ai/catalog/standards/sist/19b0ad8e-1e66-497d-93fa-1e3765a07a76/sist-en-50525-2-12-2011)

<https://standards.iteh.ai/catalog/standards/sist/19b0ad8e-1e66-497d-93fa-1e3765a07a76/sist-en-50525-2-12-2011>

Contents

	Page
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 General purpose cables	5
4.1 Light duty cables – H03VVH8-F and H03VVH2H8-F	5
4.2 Ordinary duty cables – H05VVH8-F and H05VVH2H8-F	6
Annex A (normative) Post-coiling requirements for marking	8
Annex B (normative) Pre-coiling tests for cables to EN 50525-2-12	9
Annex C (normative) Post-coiling tests for cables to EN 50525-2-12	10
Annex D (normative) General data	11
Annex E (normative) Requirements for compatibility test	13
E.1 Test conditions	13
E.2 Requirements	13
Annex F (normative) Requirements for mechanical tests	14
F.1 Extension tests for extensible leads	14
F.2 Endurance test for extensible leads	14
Bibliography	15

iTech STANDARD PREVIEW
(standards.itech.ai)

Tables

[SIST EN 50525-2-12:2011](https://standards.itech.ai/catalog/standards/sist/19b0ad8e-1e66-497d-93fa-1e3765a07a76/sist-en-50525-2-12-2011)

Table B.1	9
Table C.1	10
Table D.1 – Cables rated at 300/300 V	11
Table D.2 – Cables rated at 300/500 V	12
Table E.1	13

1 Scope

EN 50525-2-12 applies to thermoplastic (PVC) insulated and PVC sheathed extensible leads.

The cables are of rated voltages U_0/U up to and including 300/500 V.

The cables are intended for the connection of domestic appliances to the fixed supply.

Circular cables and flat cables are included.

The maximum conductor operating temperature for each of the cables in this standard is 70 °C.

NOTE HD 516 contains extensive guidance on the safe use of cables in this standard.

This EN 50525-2-12 should be read in conjunction with EN 50525-1, which specifies general requirements.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE One or more references to the standards below are in respect of a specific sub-division of that standard, for instance a clause, a table, a class or a type. Cross-references to these standards are undated and, at all times, the latest version applies.

EN 50363-3	Insulating, sheathing and covering materials for low voltage energy cables - Part 3: PVC insulating compounds
EN 50363-4-1	Insulating, sheathing and covering materials for low voltage energy cables - Part 4-1: PVC sheathing compounds
EN 50395	Electrical test methods for low voltage energy cables
EN 50396	Non electrical test methods for low voltage energy cables
EN 50525-1	Electric cables - Low voltage energy cables of rated voltages up to and including 450/750 V (U_0/U) - Part 1: General requirements
EN 60228	Conductors of insulated cables (IEC 60228)
EN 60811-1-2	Insulating and sheathing materials of electric and optical cables - Common test methods - Part 1-2: General application - Thermal ageing methods (IEC 60811-1-2)
EN 60811-1-4	Insulating and sheathing materials of electric and optical cables - Common test methods - Part 1-4: General application - Tests at low temperature (IEC 60811-1-4)

3 Terms and definitions

For the purposes of this document the terms and definitions given in Clause 3 of EN 50525-1 apply.

4 General purpose cables

4.1 Light duty cables – H03VVH8-F and H03VVH2H8-F

4.1.1 Construction – Pre-coiling

4.1.1.1 Conductor

The conductor shall be class 5, according to EN 60228.

4.1.1.2 Sizes of cable

The sizes of cable shall be:

- circular cables – 0,5 mm² and 0,75 mm² – 2 and 3 core;
- flat cables – 0,5 mm² and 0,75 mm² – 2 core only.

4.1.1.3 Insulation

The insulation shall be polyvinyl chloride compound of Type TI 2 to EN 50363-3.

4.1.1.4 Assembly

The cables shall be assembled as follows:

- circular cable: the cores shall be twisted together;
- flat cable: the cores shall be laid parallel.

NOTE A tape may be applied around the core assembly before application of the sheath.

4.1.1.5 Sheath

The sheath shall be polyvinyl chloride compound of Type TM 2 to EN 50363-4-1.

The sheath shall fill the spaces between the cores, thus forming a filling.

4.1.1.6 Marking

The cable shall be marked with the CENELEC code H03VVH8-F for circular cables, or H03VVH2H8-F for flat cables. The marking shall comply with Clause 6 of EN 50525-1.

4.1.2 Construction – Post-coiling

The cables shall be coiled in the form of a helical lead and caused substantially to maintain this form during use.

Slight deformation of the cables, created by the coil forming process, is acceptable provided that the thickness of the insulation and sheath meet the requirements.

The original marking, if any, on the pre-coiled cable may be affected by the coiling process but this is acceptable provided that traceability is not impaired.

The producer of the extensible lead, if different from the producer of the pre-coiled cable, shall apply an additional mark, as indication of origin, as required by Annex A.

4.1.3 Requirements

Each cable shall comply with the appropriate requirements given in EN 50525-1, and the particular requirements of this Part.

Testing at the pre-coiling stage shall be in accordance with Annex B, and the relevant tests indicated in column 6. Testing at the post-coiling stage shall be in accordance with Annex C, and the relevant tests indicated in column 6.

The dimensions of the cables (pre-coiling) and the thickness of insulation and sheath (post-coiling) shall conform to Table D.1 for the relevant size. The requirements of 5.3.3 of EN 50525-1 shall apply for the insulation thickness and of 5.7.3 of EN 50525-1 for the sheath thickness.

The requirements to be met for the compatibility test shall be as given in Annex E.

The requirements to be met for the mechanical tests shall be as given in Annex F.

4.2 Ordinary duty cables – H05VVH8-F and H05VVH2H8-F

4.2.1 Construction – Pre-coiling

4.2.1.1 Conductor

The conductor shall be class 5, according to EN 60228.

4.2.1.2 Sizes of cable

The sizes of cable shall be:

- circular cables – 0,75 mm² to 1,5 mm² – 2 and 3 core;
- flat cables – 0,75 mm² – 2 core only

4.2.1.3 Insulation

The insulation shall be polyvinyl chloride compound of Type TI 2 to EN 50363-3.

4.2.1.4 Assembly

The cables shall be assembled as follows:

- circular cable: the cores shall be twisted together;
- flat cable: the cores shall be laid parallel.

For circular cable having two cores, the space between the cores shall be filled either by separate fillers or by the sheath filling the interstices.

NOTE A tape may be applied around the core assembly before application of the sheath.

4.2.1.5 Sheath

The sheath shall be polyvinyl chloride compound of Type TM 2 to EN 50363-4-1.

The sheath shall fill the spaces between the cores, thus forming a filling.

4.2.1.6 Marking

The cable shall be marked with the CENELEC code H05VVH8-F for circular cables, or H05VVH2H8-F for flat cables. The marking shall comply with Clause 6 of EN 50525-1.

4.2.2 Construction – Post-coiling

The cables shall be coiled in the form of a helical lead and caused substantially to maintain this form during use.

Slight deformation of the cables, created by the coil forming process, is acceptable provided that the thickness of the insulation and sheath meets the requirements.

The original marking, if any, on the pre-coiled cables may be affected by the coiling process but this is acceptable provided that traceability is not impaired.

The producer of the extensible lead, if different from the producer of the pre-coiled cable, shall apply an additional mark, as indication of origin, as required by Annex A.

4.2.3 Requirements

Each cable shall comply with the appropriate requirements given in EN 50525-1, and the particular requirements of this Part.

Testing at the pre-coiling stage shall be in accordance with Annex B, and the relevant tests indicated in column 7. Testing at the post-coiling stage shall be in accordance with Annex C, and the relevant tests indicated in column 7.

The dimensions of the cables (pre-coiling) and the thickness of insulation and sheath (post-coiling) shall conform to Table D.2 for the relevant size. The requirements of 5.3.3 of EN 50525-1 shall apply for the insulation thickness and of 5.7.3 of EN 50525-1 for the sheath thickness.

The requirements to be met for the compatibility test shall be as given in Annex E.

The requirements to be met for the mechanical tests shall be as given in Annex F.