



# SLOVENSKI STANDARD SIST EN 1402-1:2004

01-maj-2004

BUXca Yý U  
SIST ENV 1402-1:1998

---

## Neoblikovani ognjevzdržni izdelki - 1. del: Uvod in razvrstitev

Unshaped refractory products - Part 1: Introduction and classification

Ungeformte feuerfeste Erzeugnisse - Teil 1: Einführung und Klassifizierung

Produits réfractaires non façonnés - Partie 1: Introduction et classification  
**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: EN 1402-1:2003**

[https://standards.iteh.ai/catalog/standards/sist/0682f71e-bb8b-4085-83aa-  
adf172ed17bc/sist-en-1402-1-2004](https://standards.iteh.ai/catalog/standards/sist/0682f71e-bb8b-4085-83aa-<br/>adf172ed17bc/sist-en-1402-1-2004)

### **ICS:**

01.040.81	Ùc\  æ•\ æÁ^ æ ã } æ ã å • dæU   çæD	Glass and ceramics industries (Vocabularies)
81.080	Ognjevzdržni materiali	Refractories

**SIST EN 1402-1:2004**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 1402-1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/0682f71e-bb8b-4085-83aa-adf172ed17bc/sist-en-1402-1-2004>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN 1402-1**

October 2003

ICS 01.040.81; 81.080

Supersedes ENV 1402-1:1994

English version

## Unshaped refractory products - Part 1: Introduction and classification

Produits réfractaires non façonnés - Partie 1: Introduction et classification

Ungeformte feuerfeste Erzeugnisse - Teil 1: Einführung und Klassifizierung

This European Standard was approved by CEN on 20 June 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and United Kingdom.

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)  
<https://standards.iteh.ai/catalog/standards/sist/0682f71e-bb8b-4085-83aa-adf172ed17bc/sist-en-1402-1-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Contents

	page
Foreword .....	3
Introduction .....	4
1 Scope.....	5
2 Normative references.....	5
3 3 Terms and definitions .....	5
4 Product types and methods of placement.....	5
4.1 Refractory castables .....	5
4.1.1 General .....	5
4.1.2 Regular castable.....	6
4.1.3 Deflocculated castable .....	6
4.1.4 4.1.4 Chemically bonded castable.....	6
4.2 Refractory gunning materials .....	6
4.3 Refractory ramming materials .....	6
4.3.1 Refractory ramming mixes .....	6
4.3.2 Plastic refractory materials .....	6
4.4 4.4 Refractory jointing materials .....	7
4.5 Other unshaped refractory products .....	7
4.5.1 Dry mixes .....	7
4.5.2 Injection mixes .....	7
4.5.3 Coatings .....	7
4.5.4 Taphole mixes .....	7
5 Type of chemical composition.....	7
5.1 Alumina-silica products.....	7
5.2 Basic products .....	7
5.3 Special products .....	7
5.4 Carbon-containing products.....	8
6 Classification .....	8
6.1 Basis of classification.....	8
6.2 Type of products and method of placement .....	8
6.3 Main raw material .....	8
6.4 Classification temperature .....	9
7 Designation of an unshaped refractory material .....	10
Bibliography.....	13

## Foreword

This document (EN 1402-1:2003) has been prepared by Technical Committee CEN/TC 187 "Refractory products and materials", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2004, and conflicting national standards shall be withdrawn at the latest by April 2004.

This document supersedes ENV 1402-1:1994.

EN 1402 "Unshaped refractory products" consists of eight parts:

- *Part 1: Introduction and classification*
- *Part 2: Sampling for testing*
- *Part 3: Characterization as received*
- *Part 4: Determination of consistency of castables*

- *Part 5: Preparation and treatment of test pieces*

- *Part 6: Measurement of physical properties*

- *Part 7: Tests on pre-formed shapes*

- *Part 8: Determination of complementary properties*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Luxembourg, Malta, Netherlands, Norway, Portugal, Slovakia, Spain, Sweden, Switzerland and the United Kingdom.

iteh STANDARD PREVIEW  
(standards.iteh.ai)

[SIST EN 1402-1:2004](#)

<http://standards.cen/catalog/standards/sist/0682f71e-bb8b-4085-83aa-adf172ed17bc/sist-en-1402-1-2004>

**EN 1402-1:2003 (E)****Introduction**

The general objective of this part of EN 1402 is to define, with as much accuracy as possible, the control of unshaped refractory products with special reference to:

- a) quality control;
- b) checking the conformity of the delivery as compared with claimed properties;
- c) the control of batch homogeneity;
- d) the final control of linings.

Properties are unavoidably influenced by industrial placing as a result of the equipment, environmental conditions and often by specific site conditions (target date, location). Quality control and final control of lining should not be considered in the same documents, since the former requires accuracy and clean operative methods while the latter requires the control of the placing.

Unshaped refractory products used in industrial linings are not fired, so that firing which results from use creates complicated conditions that make control difficult. The main points to be mentioned are:

- i) the temperature gradient, the consequence of which is a property gradient;
- ii) the level of maximum temperature reached on the hot face directly depends on the working temperature of the equipment;
- iii) the life of the equipment may be numbered in hours or in years.

It should be noted that properties measured in the laboratory frequently do not reflect the properties of the material when installed.

## 1 Scope

This part of this European Standard defines terms relating to unshaped refractory products and establishes the classification for the various types of products.

Raw materials and crushed or granulated refractory materials which do not contain any binder are excluded.

## 2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1094-4, *Insulating refractory products - Part 4: Determination of bulk density and true porosity*.

EN 1402-6, *Unshaped refractory products - Part 6: Measurement of physical properties*.

ISO 565, *Test sieves - Metal wire cloth, perforated metal plate and electroformed sheet - Nominal sizes of openings*.

## iTeh STANDARD PREVIEW

## 3 Terms and definitions (standards.iteh.ai)

For the purposes of this European Standard, the following terms and definitions apply.

### 3.1

#### unshaped refractory materials

mixtures which consist of an aggregate and a bond or bonds, prepared ready for use either directly in the condition in which they are supplied or after the addition of one or more suitable liquids

NOTE 1 They can contain metallic, organic or ceramic fibre material.

NOTE 2 These mixtures are either dense or insulating. Insulating mixtures are those whose true porosity is not less than 45 % when determined in accordance with EN 1094-4, using a test piece fired to specified conditions.

### 3.2

#### pre-formed shapes

shapes made from unshaped refractory materials, cast or moulded and pre-treated by the manufacturer, so that they can be directly placed in service

NOTE They may have a thermal pre-treatment.

## 4 Product types and methods of placement

### 4.1 Refractory castables

#### 4.1.1 General

Mixtures of refractory aggregates and bond(s), mainly supplied dry and used after the addition and mixing with water or another liquid. They are placed by casting with vibration, by casting without vibration (self-flowing), by rodding, by shotcreting or when necessary by tamping. The bond is formed and hardening takes place without heating.

**EN 1402-1:2003 (E)****4.1.2 Regular castable**

Hydraulically bonded refractory castable containing cement but without deflocculant.

**4.1.3 Deflocculated castable**

Hydraulically bonded refractory castable containing cement, a minimum of 2 % by weight of ultra fine particles (less than one micron) and at least one deflocculating agent.

This type is in turn sub-divided into the four categories given in Table 1.

**Table 1 — Categories of deflocculated cement castable**

Category	Content (%) CaO	
	Min	Max
Medium cement castable (MCC)	> 2,5	-
Low cement castable (LCC)	> 1,0	≤ 2,5
Ultra low cement castable (ULCC)	> 0,2	≤ 1,0
No cement castable (NCC)	0	≤ 0,2

**4.1.4 Chemically bonded castable**

Refractory castable containing one or more chemical bonds (see 3.3) which cause hardening.

**4.2 Refractory gunning materials**

Mixtures of refractory aggregates and bond(s) specially prepared for placing by pneumatic or mechanical projection.

They may be either:

- castables (see 4.1) (dense or insulating) which are supplied dry and used after the addition of water during or before gunning;
- plastics (see 4.3.2) which are especially designed for gunning under high air pressure with special equipment, and are normally delivered in a ready to use state.

According to the type of bond, a further distinction is made between hydraulically bonded, chemically bonded and ceramic bonded gunning materials.

**4.3 Refractory ramming materials****4.3.1 Refractory ramming mixes**

Materials which are non-coherent before use, made up of refractory aggregates, bond(s) and if necessary liquid(s). According to the type of product, the main bond may be ceramic, chemical (inorganic or organic-inorganic) or organic.

The materials are used as delivered or after the addition of liquid(s) and placed by ramming (manual or mechanical) or vibration. They harden under the action of heat above ambient temperature.

**4.3.2 Plastic refractory materials**

Materials which are coherent and ready for use, with a plastic consistency, made up of refractory aggregates, bond(s) and liquid(s). According to the type of product, the main bond may be ceramic, chemical (inorganic or organic-inorganic) or organic.



The materials are supplied in soft, pre-formed blocks or slices and placed by ramming (manual or mechanical). Installation without shuttering is possible. They harden under the action of heat above ambient temperature.

Plastic refractory materials have indices of workability (see EN 1402-3) of greater than 14 after stabilization.

#### 4.4 Refractory jointing materials

Materials intended for laying and jointing bricks or blocks by trowelling, grouting in the joints, or dipping the brick or block to be bonded. They are mixtures of fine refractory aggregates and bond(s), supplied in the dry state or mixed with water ready for use. There are two main types:

- a) heat setting jointing materials, which harden at elevated temperature by chemical or ceramic bonds,
- b) air setting jointing materials, which harden at ambient temperature by chemical or hydraulic bonds.

#### 4.5 Other unshaped refractory products

##### 4.5.1 Dry mixes

These materials are specially designed to be placed in the dry state by vibration, "vibrocompaction" or ramming. During placing they reach a maximum compaction and it becomes possible to remove the former either before or after heating. They may include a temporary bond but are eventually ceramic bonded.

##### 4.5.2 Injection mixes

These materials are specially designed to be injected by a pump, using pressures of between 10 bar and 200 bar. They may be supplied ready to use, or may require mixing.

##### 4.5.3 Coatings

Mixture of fine refractory aggregates and bond(s), supplied ready for use with a higher water or other liquid content than materials for placing or jointing. The principal bond may be ceramic, hydraulic, chemical (inorganic or organic-inorganic) or organic. The mixtures are applied manually (with a brush or trowel), by pneumatic or mechanical projection, or by spraying.

##### 4.5.4 Taphole mixes

Materials which are ready for use, having a plastic consistency and made up of refractory aggregates, bond(s) and liquid(s). After firing the materials are mainly carbon bonded.

NOTE These materials are specially designed to fill blast furnace tap holes.

## 5 Type of chemical composition

### 5.1 Alumina-silica products

Alumina-silica products consisting mainly of aggregates of alumina, silica, and alumino-silicates.

### 5.2 Basic products

Basic products, consisting mainly of aggregates of magnesia, doloma, magnesiachrome, chrome ore and spinel.

### 5.3 Special products

Special products, consisting mainly of oxide or non-oxide aggregates other than those given in 5.1 and 5.2.

NOTE These can include silicon carbide, silicon nitride, zircon and zirconia.