

INTERNATIONAL STANDARD



Coaxial communication cables –
Part 1-303: Mechanical test methods – Test for silver and tin plating thickness
(standards.iteh.ai)

[IEC 61196-1-303:2018](#)

<https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018>



THIS PUBLICATION IS COPYRIGHT PROTECTED

Copyright © 2018 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

IEC Catalogue - webstore.iec.ch/catalogue

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

Electropedia - www.electropedia.org

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

IEC'S STANDARD PREVIEW
(standards.iec.ch)

INTERNATIONAL STANDARD



**Coaxial communication cables –
Part 1-303: Mechanical test methods – Test for silver and tin plating thickness**

STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 33.120.10

ISBN 978-2-8322-5238-3

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
1 Scope.....	5
2 Normative references	5
3 Terms and definitions	5
4 Procedure.....	5
4.1 Test equipment and method.....	5
4.2 Test solution	5
4.3 Test sample	6
4.4 Procedure	6
5 Test report.....	8
6 Requirements	9
Figure 1 – Example of a conductor with a diameter of 0,3 mm.....	6
Figure 2 – Conductor before and after measurement	7
Figure 3 – Measure the length of the removed silver or tin	8
Table 1 – Length of the test sample in dependence upon the diameter of the conductor.....	6

iteh.STANDARD PREVIEW

(standards.iteh.ai)

[IEC 61196-1-303:2018](https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018)

<https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

COAXIAL COMMUNICATION CABLES –**Part 1-303: Mechanical test methods –
Test for silver and tin plating thickness**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
<https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822a348b987/iec-61196-1-303-2018>
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61196-1-303 has been prepared by subcommittee 46A: Coaxial cables, of IEC technical committee 46: Cables, wires, waveguides, RF connectors, RF and microwave passive components and accessories.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
46A/1348/FDIS	46A/1355/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

This publication is to be read in conjunction with IEC 61196-1:2005.

A list of all the parts in the IEC 61196 series published under the general title *Coaxial communication cables* can be found on the IEC website.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

A bilingual version of this publication may be issued at a later date.

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[IEC 61196-1-303:2018](https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018)

<https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018>

COAXIAL COMMUNICATION CABLES –

Part 1-303: Mechanical test methods – Test for silver and tin plating thickness

1 Scope

This part of IEC 61196 defines the requirements for measuring the plating thickness for silver and tin conductors for coaxial cables used in analogue and digital communication systems.

This test method uses a procedure for determining the plating thickness of silver and tin coatings on conductors by galvanic removal (coulometric method).

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 61196-1:2005, *Coaxial communication cables – Part 1: Generic specification – General, definitions and requirements* (standards.iteh.ai)

3 Terms and definitions

<https://standards.iteh.ai/catalog/standards/sist/20025850-d7d8-4a51-ad25-5822d348b987/iec-61196-1-303-2018>

For the purposes of this document, the terms and definitions given in IEC 61196-1 apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

4 Procedure

4.1 Test equipment and method

The thickness of the silver or tin coating shall be measured with an electronic thickness tester.

In a conventional measuring equipment, the reading for the amount of coating is reduced to a time reading by metering with direct current. The voltage in the test sample changes significantly if the coating to be measured is completely removed. This voltage impulse is amplified and acts to terminate the measurement procedure.

The electronic tester measures the time for the removal of the silver or tin coating and is proportional to the average plating thickness.

4.2 Test solution

The test solution specified by the equipment manufacturer should be used.

In case the specified solution is not available, the following test solutions may be used:

- for silver: 180 g potassium thiocyanate with 1 000 ml of distilled water (H₂O);
- for tin: 100 ml of 37 % concentrated hydrochloric acid.

Special care shall be taken when handling the test solutions. The user should establish appropriate safety and health procedures.

4.3 Test sample

Cut a straight length of the conductor to be tested to approximately 200 mm. Lay the conductor sample under test on a flat surface along a ruler and mark with a crayon (or equivalent) to a length according to the diameter of the conductor (see Table 1 and Figure 1) from one end of the conductor.




Figure 1 – Example of a conductor with a diameter of 0,3 mm

The test sample should be given an open 180° bend half way between the crayon mark and the end to allow them to be submerged in the test solution without touching the beaker.

Table 1 – Length of the test sample in dependence upon the diameter of the conductor

Diameter of the conductor mm	Length of the test sample mm
0,050 to 0,140	100 ± 5
0,141 to 0,290	50 ± 5
0,291 to 0,700	25 ± 2
> 0,700	12 ± 2

The test samples shall be clean. If the wire is dirty or not free of oil, remove it with a solvent before testing.

4.4 Procedure

Connect the electronic thickness tester to the power 15 minutes before starting the measurement, to allow a warm-up of the tester. Follow the instruction of the manufacturer of the electronic thickness tester and make sure that the selector of the electronic tester is in the position “Silver” or “Tin”. Select the desired unit (inch or μm).

Fill the stainless steel beaker approximately 75 mm from the bottom with the test solution. Maintain the temperature of the solution at 20 °C to 25 °C, see Figure 2.

Do the calibration of the electronic test equipment according to the manufacturer's instruction for silver or tin wires.

Insert the test sample into the terminal on the horizontal arm of the accessory unit. Tighten the terminal so that the conductor is held firmly in a vertical position. Lower the conductor into the beaker until the test solution level is exactly at the crayon mark. Adjust the arm so that the conductor is in the approximate centre of the beaker.

Press the start button to start the measurement. Follow the instruction of the manufacturer of the electronic test equipment.

Make no adjustments at the test sample while the measurement is in operation. If an adjustment is necessary, the measurement has to be repeated on a new sample.



Figure 2 – Conductor before and after measurement

If the silver or tin plating is removed, the test equipment stops and the counter can read out.

If the silver plating after the measurement is not completely removed, the measurement has to be repeated with a new test solution.

If the tin plating after the measurement is not completely removed, the start button can be pressed again and both times (counter) can be added.