



Designation: C 995 – 01

Standard Test Method for Time of Flow of Fiber-Reinforced Concrete Through Inverted Slump Cone¹

This standard is issued under the fixed designation C 995; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This test method covers the determination of the inverted slump-cone time of fiber-reinforced concrete, both in the laboratory and in the field.

1.2 This test method is considered applicable to freshly mixed concrete having coarse aggregate up to 1½ in. (38 mm) in size. It is not applicable to concrete that flows freely through the cone.

1.3 The values stated in inch-pound units are to be regarded as the standard. SI units are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

C 29/C 29M Test Method for Unit Weight and Voids in Aggregate²

C 31/C 31M Practice for Making and Curing Concrete Test Specimens in the Field²

C 143/C 143M Test Method for Slump of Hydraulic Cement Concrete²

C 172 Practice for Sampling Freshly Mixed Concrete²

C 192 Practice for Making and Curing Concrete Test Specimens in the Laboratory²

C 670 Practice for Preparing Precision and Bias Statements for Test Methods for Construction Materials²

3. Summary of Test Method

3.1 This test method determines the time required for fiber-reinforced concrete to flow through an inverted slump cone under internal vibration.

¹ This test method is under the jurisdiction of ASTM Committee C09 on Concrete and Concrete Aggregates and is the direct responsibility of Subcommittee C09.42 on Fiber-Reinforced Concrete.

Current edition approved Nov. 10, 2001. Published January 2002. Originally published as C 995 – 83. Last previous edition C 995 – 94.

² *Annual Book of ASTM Standards*, Vol 04.02.

4. Significance and Use

4.1 This test method provides a measure of the consistency and workability of fiber-reinforced concrete.

4.2 The inverted slump-cone time is a better indicator than slump of the appropriate level of workability for fiber-reinforced concrete placed by vibration because such concrete can exhibit very low slump due to the presence of the fibers and still be easily consolidated. Mixtures with a time of flow less than 8 s, or with a slump greater than 2 in. (50 mm) shall be evaluated in terms of slump because the time of flow is too short to determine with satisfactory precision, or may not be determinable because the fiber-reinforced concrete flows freely through the inverted cone.

4.3 The results may be used for mixture proportioning, quality control both in the laboratory and in the field, and in development and research.

4.4 The results obtained using this test method may be influenced by vibrator diameter, amplitude, and frequency.

4.5 This test method may not be applicable to some concretes reinforced with fibers flexible and long enough to wrap around the vibrating element and dampen vibration.

5. Apparatus

5.1 *Cone*, shall be the mold specified in Test Method C 143.

5.2 *Bucket*—The container to receive the concrete shall be the 1-ft³ (30-L) capacity bucket specified in Test Method C 29/ C 29M.

5.3 *Positioning Device*—A device of the type shown in Fig. 1 shall be provided to center the cone in the bucket, prevent it from tilting, and maintain the small end of the cone $4 \pm \frac{1}{4}$ in. (100 ± 5 mm) from the bottom of the bucket.

5.4 *Vibrator*, shall be of the internal type specified in Practices C 31/C 31M or C 192, except that the vibrating element shall be $1 \pm \frac{1}{8}$ in. (25 ± 3 mm) in diameter.

5.5 *Stopwatch*—One that measures elapsed time to the nearest second or less.

5.6 *Screeding Rod*—The rod used for screeding shall be the tamping rod specified in Test Method C 143/C 143M.