

TECHNICAL SPECIFICATION



**Nanomanufacturing – Key control characteristics –
Part 2-4: Carbon nanotube materials – Test methods for determination
of resistance of individual carbon nanotubes**

IEC TS 62607-2-4:2020

<https://standards.iteh.ai/catalog/standards/sist/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020>



THIS PUBLICATION IS COPYRIGHT PROTECTED
Copyright © 2020 IEC, Geneva, Switzerland

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office
3, rue de Varembe
CH-1211 Geneva 20
Switzerland

Tel.: +41 22 919 02 11
info@iec.ch
www.iec.ch

About the IEC

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

About IEC publications

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigendum or an amendment might have been published.

IEC publications search - webstore.iec.ch/advsearchform

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

IEC Just Published - webstore.iec.ch/justpublished

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and once a month by email.

IEC Customer Service Centre - webstore.iec.ch/csc

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: sales@iec.ch.

Electropedia - www.electropedia.org

The world's leading online dictionary on electrotechnology, containing more than 22 000 terminological entries in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

IEC Glossary - std.iec.ch/glossary

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

[IEC TS 62607-2-4:2020](https://standards.iec.ch/catalog/standards/sis/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020)

<https://standards.iec.ch/catalog/standards/sis/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020>

TECHNICAL SPECIFICATION



**Nanomanufacturing – Key control characteristics –
Part 2-4: Carbon nanotube materials – Test methods for determination
of resistance of individual carbon nanotubes**

IEC TS 62607-2-4:2020

<https://standards.iteh.ai/catalog/standards/sist/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020>

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

ICS 07.030; 07.120

ISBN 978-2-8322-7968-7

Warning! Make sure that you obtained this publication from an authorized distributor.

CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references	6
3 Terms, definitions, and abbreviated terms	6
3.1 Terms and definitions.....	6
3.2 Abbreviated terms.....	8
4 Measurement of resistance.....	8
4.1 General.....	8
4.2 Method for processing and fabrication of DUT.....	8
4.3 4-probe measurement.....	8
5 Reporting data.....	9
6 Data analysis / interpretation of results (Annex A)	10
6.1 General.....	10
6.2 Measurement error	10
6.3 Need to prepare the proper electric probing circuit.....	11
6.4 Need to prepare the proper substrate and electric contact	11
6.5 Dynamic range.....	11
6.6 Current density	11
6.7 Voltage bias of the substrate.....	11
6.8 Measurement in vacuum	11
Annex A (informative) Case study.....	12
A.1 4-probe measurement of MWCNT.....	12
A.1.1 I - V measurements of MWCNT.....	12
A.1.2 Fabrication process information of MWCNT and DUT	14
A.2 4-probe measurement of SWCNT.....	15
A.2.1 I - V measurements of SWCNT	15
A.2.2 Fabrication process information of SWCNT and DUT.....	18
Bibliography.....	19
Figure 1 – 4-probe measurement in a SEM chamber.....	9
Figure 2 – A crooked/curved CNT under measurement	10
Figure 3 – I - V measurement of a sufficiently straight CNT.....	11
Figure A.1 – I - V measurements of a CNT with different lengths, L	12
Figure A.2 – I - V relationships for different CNT lengths – 2-probe measurement.....	13
Figure A.3 – I - V relationships for different CNT lengths – 2-probe measurement (0 to 0,5 V).....	13
Figure A.4 – I - V relationships for different CNT lengths – 4-probe measurement.....	14
Figure A.5 – Resistance vs. CNT length.....	14
Figure A.6 – I - V relationships of SWCNT	15
Figure A.7 – Resistance vs. SWCNT length	16
Figure A.8 – I - V relationships of SWCNT under the electron-beam exposure	17
Figure A.9 – Breakdown characteristics of SWCNT.....	18

INTERNATIONAL ELECTROTECHNICAL COMMISSION

**NANOMANUFACTURING –
KEY CONTROL CHARACTERISTICS –****Part 2-4: Carbon nanotube materials – Test methods for determination
of resistance of individual carbon nanotubes**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

The main task of IEC technical committees is to prepare International Standards. In exceptional circumstances, a technical committee may propose the publication of a Technical Specification when

- the required support cannot be obtained for the publication of an International Standard, despite repeated efforts, or
- the subject is still under technical development or where, for any other reason, there is the future but no immediate possibility of an agreement on an International Standard.

Technical Specifications are subject to review within three years of publication to decide whether they can be transformed into International Standards.

IEC TS 62607-2-4, which is a Technical Specification, has been prepared by IEC technical committee 113: Nanotechnology for electrotechnical products and systems.

The text of this Technical Specification is based on the following documents:

DTS	Report on voting
113/492/DTS	113/509/RVDTS

Full information on the voting for the approval of this Technical Specification can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 62607 series, published under the general title *Nanomanufacturing – Key control characteristics*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC website under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

IMPORTANT – The 'colour inside' logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

<https://standards.iteh.ai/catalog/standards/sis/372fac66-e0b0-4155-88bc-77ec3c956222/iec-ts-62607-2-4-2020>

INTRODUCTION

Carbon nanotubes (CNTs) are one-dimensional conductors that exhibit a rich variety of low-dimensional electric transport phenomena. Ballistic conduction is the typical nano-enabled characteristic that possesses the largest potential for industrial application. In the field of nanoelectronics, for example, CNT-based interconnects are a promising alternative to conventional Cu interconnects. However, even in the academic research society, the resistive characteristics have not yet been systematically investigated. This is because these characteristics are very sensitive to the protocol and the measurement conditions. Furthermore, since the individual CNT reaches the nanometre dimension, the contact resistance has a larger relative impact on the measurement. These bottlenecks impede not only the above-mentioned interconnect application but also developments of various electrotechnical applications, such as thermoelectric devices in which the electrical resistance is required to evaluate the figure of merit.

This document offers the accurate and reproducible test method for determining the resistance of CNT and the dependability of the measurement.

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

[IEC TS 62607-2-4:2020](https://standards.iteh.ai/catalog/standards/sist/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020)

<https://standards.iteh.ai/catalog/standards/sist/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020>

NANOMANUFACTURING – KEY CONTROL CHARACTERISTICS –

Part 2-4: Carbon nanotube materials – Test methods for determination of resistance of individual carbon nanotubes

1 Scope

This part of IEC 62607 specifies the test method for determining the resistivity and the contact resistance of an individual CNT and the dependability of the measurement.

This document includes:

- outlines of the experimental procedures used to measure resistance of carbon nanotubes,
- methods of interpretation of results and discussion of data analysis, and
- case studies.

2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

[IEC TS 62607-2-4:2020](#)

IEC 62624, *Test methods for measurement of electrical properties of carbon nanotubes*

ISO/TS 80004-1, *Nanotechnologies – Vocabulary – Part 1: Core terms*

NOTE IEC 62624 describes the general procedures for characterization of CNT. For example, no environmental condition is specifically required. On the other hand, this document focuses not only on the characterization of the individual CNT but also the reproducibility. To obtain the intrinsic nano-originated result and to measure up to the dependable measurement, in-vacuum non-destructive measurements are indispensable, and therefore this document (IEC TS 62607-2-4) is required.

3 Terms, definitions, and abbreviated terms

3.1 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO/TS 80004-1 and the following apply.

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

3.1.1

carbon nanotube

CNT

nanotube composed of carbon

[SOURCE: ISO/TS 80004-3:2010, 4.3]

3.1.2

single-wall carbon nanotube

SWCNT

single-walled carbon nanotube

carbon nanotube consisting of a single cylindrical graphene layer

Note 1 to entry: The structure can be visualized as a graphene sheet rolled into a cylindrical honeycomb structure.

[SOURCE: ISO/TS 80004-3:2010, 4.4]

3.1.3

multiwall carbon nanotube

MWCNT

multi-walled carbon nanotube

carbon nanotube composed of nested, concentric or near-concentric graphene sheets with interlayer distances similar to those of graphite

Note 1 to entry: The structure is normally considered to be many single-wall carbon nanotubes (3.1.2) nesting each other, and would be cylindrical for small diameters but tends to have a polygonal cross-section as the diameter increases.

[SOURCE: ISO/TS 80004-3:2010, 4.6]

3.1.4

device under test

DUT

sample attached to an apparatus for evaluation of a specific physical property such as electrical resistance or I - V behaviour

3.1.5

I - V characterization

measurement of the current-voltage characteristic

IEC TS 62607-2-4:2020

https://standards.iteh.ai/sist/372fac66-e0b0-4155-88be-77ec3c956222/iec-ts-62607-2-4-2020

Note 1 to entry: In 4-probe measurement, V is the voltage drop between two inner probes.

3.1.6

4-probe measurement

method to measure the resistance of a material with large sample dimensions whose measured value is independent on the probe resistance

Note 1 to entry: This is different from four-point probe measurement. With 4-probe measurement, the length of the DUT can be varied without causing damage to the CNT under measurement by changing the distance of the inner two probes.

[SOURCE: IEC 62607-2-1:2010, 2.1.6, modified – In the definition, "with large sample dimensions" has been added.]

3.1.7

nanoscale contact resistance

electrical resistance associated with a nanoscale contact

[SOURCE: IEC TS 80004-9:2017, 3.1.9]

3.1.8

scanning electron microscope

SEM

intermediate type of microscopic morphology observation instrument between transmitted electron microscope and light microscope which uses a focused beam of high-energy electrons to generate a variety of physical information signals

[SOURCE: ISO 17751-2:2016, 2.2]

3.2 Abbreviated terms

CVD	chemical vapour deposition
EBAC	electron beam absorbed current
SMU	source measure unit

4 Measurement of resistance

4.1 General

The accurate and reproducible test protocol of resistance measurement, together with the confirmation of the dependability, is standardized.

4.2 Method for processing and fabrication of DUT

Fabrication process information of DUT is to be reported, such as the method of dispersion and the method to apply it onto a substrate.

Fabrication process information of CNT is to be reported [CVD, laser ablation, electric arc, etc.], along with descriptions of any postgrowth treatments, such as a chemical purification, a disaggregation, a structural sorting, and a surface modification.

In order to avoid resistance measurement artefacts, the substrate with the higher electric resistance and the flat surface in nanometre scale, such as a thermally oxidized Si substrate with the insulating SiO₂ layer and a glass substrate, should be utilized as the substrate of DUT. In order to avoid resistance measurement artefacts, the electric resistance of the substrate (R_{sub}) should be higher than that of DUT (R_{dut}). The parallel current path in the substrate becomes smaller with the ratio of $R_{\text{dut}}/R_{\text{sub}}$. This value should be smaller than the error bar of the data. The surface of the substrate should be flat in nanometre scale, such as a thermally oxidized Si substrate with the insulating SiO₂ layer.

4.3 4-probe measurement

Experimental procedures and measurement conditions.

- 4-probe measurement of CNT is performed with a probing system in a SEM chamber, as shown in Figure 1.
- Firstly, a suitable probe type is chosen based on the diameter of the CNT to be measured.
- Before measurement, it is important to check the vacuum condition and SEM condition of the probing system in order to confirm the equipment condition for measurement.
Technical specification: The vacuum level should be lower than 10⁻⁵ Pa.
Technical specification: Check to see there is no measurable electromagnetic interference.
- For assuring high quality contact of probe onto CNT, the probe tip condition is confirmed under SEM observation. A probe with bent tip or contamination should be replaced.
- After loading the sample, the vacuum condition and SEM condition should be checked again to guarantee the qualified measuring condition.
- A fast SEM image is useful to search for proper CNT to measure. Straight isolated CNT with length long enough is preferred as it is easy to touch down probes with varying probe-to-probe distance.
- 4 probes are touched down onto CNT one by one.
- It is necessary to check the contact condition between probe and CNT before every measurement. In order to verify the contact condition, the current is measured while voltage is applied between the outer (or inner) two probes.
- The compliance current is set to protect CNT.

- Finally, 4-probe measurement of selected CNT is performed by applying voltage and observing current at the outer two probes while measuring voltage at the inner two probes.


Technical specification: I - V curves with at least 4 different lengths of the selected CNT.

NOTE 1 Hereinafter, outer probes may also be referred to as current probes and inner probes as voltage probes.

NOTE 2 One of the practical candidates to measure the vacuum level is an ionization gauge.

NOTE 3 One of the practical candidates to evaluate the electromagnetic interference is the SEM image.

The current compliance should be settled in order to avoid the breakdown. The example is shown in Figure A.9.



IEC

Figure 1 – 4-probe measurement in a SEM chamber

5 Reporting data

- Vacuum condition (before measurement)
- Vacuum condition (after loading sample)
- Material of the probe used
- I (as the I - V relationship with 2- and 4-probe measurements)
- V (as the I - V relationship with 2- and 4-probe measurements)
- CNT length in contact with the probes
- CNT length dependence of the resistance
- Resistance with the unit length and the error in the fitting analyses
- CNT diameter
- Substrate (material, thickness, electric property)
- Conditions of the SEM observation (acceleration voltage, magnification)

NOTE These sets of reporting data are shown in any manner, depending on the practical purpose.