
**Paints and varnishes — Corrosion
protection of steel structures by protective
paint systems —**

**Part 7:
Execution and supervision of paint work**

iTeh STANDARD PREVIEW

*Peintures et vernis — Anticorrosion des structures en acier par systèmes
de peinture*

Partie 7: Exécution et surveillance des travaux de peinture

[ISO 12944-7:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/2708161e-2b55-40bd-bbd3-8f7007db8b03/iso-12944-7-1998>



Contents	Page
1 Scope	1
2 Normative references.....	1
3 Preconditions for the execution of the paint work.....	2
3.1 Qualification	2
3.2 Condition of the substrate.....	2
3.3 Health and safety and environmental protection	2
4 Coating materials.....	3
4.1 Supply.....	3
4.2 Storage.....	3
5 Execution of the paint work	3
5.1 General	3
5.2 Application conditions.....	4
5.3 Application methods.....	5
5.4 Evaluation before work commences.....	5
6 Supervision of the paint work.....	5
6.1 General	5
6.2 Measurement and test instruments.....	6
6.3 Checking the paint coating	6
7 Reference areas.....	6
7.1 General	6
7.2 Previously coated surfaces.....	7
7.3 Reference area records	7
7.4 Assessment of coating	7
Annex A Number of reference areas	8

iTeh STANDARD PREVIEW

(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/2708161e-2b55-40bd-bb3-8f7007db8b03/iso-12944-7-1998>

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International Organizations, governmental and non governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 12944-7 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 14, *Protective paint systems for steel structures*.

ISO 12944 consists of the following parts under the general title *Paints and varnishes – Corrosion protection of steel structures by protective paint systems*:

- | | |
|----------------|---|
| <i>Part 1:</i> | <i>General introduction</i> |
| <i>Part 2:</i> | <i>Classification of environments</i> |
| <i>Part 3:</i> | <i>Design considerations</i> |
| <i>Part 4:</i> | <i>Types of surface and surface preparation</i> |
| <i>Part 5:</i> | <i>Protective paint systems</i> |
| <i>Part 6:</i> | <i>Laboratory performance test methods</i> |
| <i>Part 7:</i> | <i>Execution and supervision of paint work</i> |
| <i>Part 8:</i> | <i>Development of specifications for new work and maintenance</i> |
- bbd3-8f7007db8b03/iso-12944-7-1998
 bbd3-8f7007db8b03/iso-12944-7-1998

Annex A of this part of ISO 12944 is for information only.

Paints and varnishes — Corrosion protection of steel structures by protective paint systems —

Part 7: Execution and supervision of paint work

1 Scope

1.1 This part of ISO 12944 deals with the execution and supervision of paint work on steel structures in the workshop or on site.

1.2 This part of ISO 12944 does not apply to:

- the preparation of surfaces to be painted (see ISO 12944-4) and the supervision of such work,
- the application of metallic coatings,
- pre-treatment methods such as phosphating and chromating and paint application methods such as dipping, powder coating or coil coating.

iTech STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/2708161e-2b55-40bd-bbd3-8f7007db8b03/iso-12944-7-1998>

2 Normative references

<https://standards.iteh.ai/catalog/standards/sist/2708161e-2b55-40bd-bbd3-8f7007db8b03/iso-12944-7-1998>

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 12944. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 12944 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

- | | |
|------------------|--|
| ISO 1512:1991, | <i>Paints and varnishes – Sampling of products in liquid or paste form.</i> |
| ISO 1513:1992, | <i>Paints and varnishes – Examination and preparation of samples for testing.</i> |
| ISO 2409:1992, | <i>Paints and varnishes – Cross-cut test.</i> |
| ISO 2808:1997, | <i>Paints and varnishes – Determination of film thickness.</i> |
| ISO 4624:1978, | <i>Paints and varnishes – Pull-off test for adhesion.</i> |
| ISO 8502-4:1993, | <i>Preparation of steel substrates before application of paints and related products – Tests for the assessment of surface cleanliness – Part 4: Guidance on the estimation of the probability of condensation prior to paint application.</i> |
| ISO 9001:1994, | <i>Quality systems – Model for quality assurance in design, development, production, installation and servicing.</i> |
| ISO 9002:1994, | <i>Quality systems – Model for quality assurance in production, installation and servicing.</i> |

ISO 12944-1:1998, *Paints and varnishes – Corrosion protection of steel structures by protective paint systems - Part 1: General introduction.*

ISO 12944-4:1998, *Paints and varnishes – Corrosion protection of steel structures by protective paint systems - Part 4: Types of surface and surface preparation.*

ISO 12944-5:1998, *Paints and varnishes – Corrosion protection of steel structures by protective paint systems - Part 5: Protective paint systems.*

ISO 12944-8:1998, *Paints and varnishes – Corrosion protection of steel structures by protective paint systems - Part 8: Development of specifications for new work and maintenance.*

3 Preconditions for the execution of the paint work

3.1 Qualification

3.1.1 Companies contracted to apply protective paint systems to steel structures, and their personnel, shall be capable of carrying out the work properly and safely. Work requiring particular care with regard to its execution shall only be carried out by personnel having qualifications which have been certified by an approved body, provided no other agreements have been made between the parties concerned.

3.1.2 Where the contractor has a quality management system in operation, a quality plan shall be prepared by the contractor which includes his general standards of workmanship. A method statement shall be provided for each stage of the work.

The contractor shall show that he will be able to achieve the specified quality level at each stage. Evidence for this is, for example, given by the use of a quality assurance system in accordance with ISO 9001 or ISO 9002.

Unless otherwise agreed, the contractor shall provide the client with extracts of all execution and supervision standards given in his quality manual that are relevant to the specification.

3.2 Condition of the substrate

A protective paint system requires proper surface preparation, which depends on the initial and final condition of the surface. The respective requirements shall be specified in the painting specification and be capable of achievement.

Methods of surface preparation are described in ISO 12944-4. The prepared surfaces shall be assessed with regard to visual cleanliness, surface profile and chemical cleanliness, using the methods given in ISO 12944-4.

The requirements for the supervision of these aspects of the work, the frequency of assessment, and the location of the assessment work shall be agreed between the parties concerned.

If the condition of the surface differs from that described in the specification, the client shall be informed.

The temperature of the surface shall be without doubt above the dew point of the surrounding air, unless otherwise specified in the paint manufacturer's technical data sheet.

3.3 Health and safety and environmental protection

The applicable regulations concerning health and safety and environmental protection shall be complied with. See ISO 12944-1 and ISO 12944-8.

4 Coating materials

4.1 Supply

The coating materials shall be supplied in such a condition that they are ready for use by the application method specified at the time of ordering. Paint manufacturers' technical data sheets shall comprise all details which are necessary for their use.

If any testing is required, it shall be specified, indicating the methods to be used. Sampling and further processing of samples shall be in accordance with ISO 1512 and ISO 1513.

Any detail not included in the paint manufacturer's technical data sheet that could affect the application conditions or the final quality of the work shall be given by the manufacturer.

4.2 Storage

The manufacturer shall indicate on the container the date by which the coating materials should be used (shelf life). Unless other temperatures are indicated in the manufacturer's instructions or specified elsewhere, coating materials shall be stored at temperatures above +3 °C and under +30 °C. Water-borne coating materials, in particular, may become unusable after freezing.

Coating materials and any other materials used (solvents, thinners etc.) shall be stored in a secured area.

Paint containers shall be kept sealed until the contents are prepared for use. Partly used containers may be re-sealed and used later, if not otherwise indicated in the paint manufacturer's technical data sheet. Partly used containers shall be clearly marked.

STANDARD PREVIEW
(standards.iteh.ai)

5 Execution of the paint work

[ISO 12944-7:1998](#)

5.1 General <https://standards.iteh.ai/catalog/standards/sist/2708161e-2b55-40bd-bbd3-8f7007db8b03/iso-12944-7-1998>

The surfaces to be treated shall be safely accessible and well illuminated.

When using the coating materials, the manufacturer's technical data sheet shall be observed unless specifically stated otherwise in the painting specification.

Prior to and during the application, the coating materials shall be verified to ensure:

- conformity of the container label with the specified product description;
- no skin formation;
- no irreversible settling;
- usability under the given site conditions.

Any sediment present shall be easily redispersible.

Any viscosity adjustment – which may be necessary due to low application temperatures or different application methods – shall be made in accordance with the paint manufacturer's instructions. The client shall be informed, if required in the specification, of any such adjustment.

The application methods will depend on the type of coating material, the surface, the type and size of the structure and the local conditions. Regulations and requirements with regard to environmental protection may affect the choice of the application method. Unless otherwise specified, the application method shall be agreed.

The priming coat shall cover the entire surface profile of the steel surface. Each coat shall be applied as uniformly as possible and without leaving any areas uncovered.

Methods for the measurement of film thickness are described in ISO 2808. The procedure for checking nominal dry film thicknesses (instruments, calibration, and any allowance to be made for the contribution of the surface roughness to the result) shall be agreed between the interested parties.

Unless agreed otherwise, individual dry film thicknesses of less than 80 % of the nominal dry film thickness are not acceptable. Unless agreed otherwise, individual values between 80 % and 100 % of the nominal dry film thickness are acceptable provided that the overall average (mean) is equal to or greater than the nominal dry film thickness.

Care shall be taken to achieve the nominal dry film thickness and to avoid areas of excessive thickness. It is recommended that the maximum dry film thickness is not greater than 3 times the nominal film thickness. In the case of excessive maximum dry film thickness, expert agreement shall be found between the parties. For products or systems which have a critical maximum dry film thickness and in special cases, information given in the manufacturer's technical data sheet shall be observed.

All surfaces that are difficult to access and, for example, edges, corners, welds and riveted and bolted connections, shall be painted with particular care.

If additional edge protection is required, a stripe coat extending across a reasonable width (approximately 25 mm) on both sides of the edge shall be applied.

To assist in achieving the required dry film thickness, the wet film thickness shall be periodically checked during application.

The time interval between the application of coats, and between application of the final coat and use, given in the manufacturer's technical data sheet for the coating material, or as otherwise required by the specification, shall be adhered to.

Defects in any paint coat which may lead to a reduction in the protection provided by the coat, or which have a significant effect on the appearance, shall be repaired prior to application of the next coat. To avoid damage, the coating shall be sufficiently hard before transporting and handling.

Areas which are not to be painted or are to be painted with a low film thickness only, for example surfaces which will subsequently be welded and faying surfaces (those for which a close-tolerance fit is necessary) shall be identified to the contractor before painting commences.

5.2 Application conditions

In order to ensure the protection required from the coating, the ambient conditions on site shall be checked to ensure that they meet the requirements given in the paint manufacturer's technical data sheet for the particular coating material. This shall also apply to drying and reaction times.

During the planning stage before starting the work, measures shall be defined by which adverse effects on the environment can be avoided or reduced to a minimum.

During the execution of the corrosion protection work, care shall be taken that the work is not affected by any outside influences that could lead to a reduction in the quality of the coating. Paint work shall take place in an area separated or protected from the work of other trades (blast-cleaning, welding etc.). If adverse weather conditions occur during application, the work shall be stopped and the freshly coated area protected as far as practical.

The lowest and highest permissible temperature of the surface to be coated and of the surrounding air shall be as stated in the manufacturer's technical data sheet.

Coating materials shall not be applied at temperatures below 3 °C above the dew point, determined in accordance with ISO 8502-4. Wet surfaces shall only be painted with those coating materials which are permitted in the technical data sheet or approved by the paint manufacturer.

When painting components which are to be welded on site, such components shall be masked in all areas which will be subject to preheating and welding. In the case of multicoat systems, every coat shall be stepped back.

5.3 Application methods

5.3.1 Brush application

Brushes shall be suitable for their intended use. This applies particularly to corners, rivet heads, bolt heads, and angles and areas which are difficult to access. Details shall be given in the specification.

5.3.2 Roller application

The coating materials used shall be suitable for this method of application and shall have good levelling properties. The type and size of the roller shall be appropriate to the particular job. Roller application is normally not recommended for the application of anticorrosive primers.

5.3.3 Spray application

The following spraying methods are among those commonly used:

- conventional, low-pressure air spray;
- airless spray;
- air-assisted airless spray;
- electrostatic spray.

The paint viscosity, spraying pressure, type of nozzle, temperature of paint material, distance to the surface to be coated and spraying angle shall be selected so that uniform and continuous coatings are produced.

When using these methods, suitable precautions shall be taken to avoid spray mist spreading over the surroundings.

If the required film thickness cannot be achieved on edges, in corners or in areas of the structure which are difficult to access (spray shadows), these areas shall be precoated, by brushing, using a stripe coat, or spraying.

For coating materials having a tendency to settle, the paint container shall be fitted with a mechanical stirrer.

5.3.4 Other application methods

If other methods are used, for example flow-coating, application of hot-melt coating materials or application of anticorrosive tapes, they shall be carried out in accordance with the manufacturer's instructions.

5.4 Evaluation before work commences

The application method specified shall be evaluated using the specified materials to ensure that they give the required protection. If the application method and/or the specified materials are found to be unsuitable, the specification shall be amended accordingly by the parties involved and any consequences, e.g. cost, time, shall be taken into consideration.

6 Supervision of the paint work

6.1 General

The execution of the work shall be supervised at all stages. Supervision shall be undertaken by suitable qualified and experienced people. The contractor shall be responsible for carrying out this supervision himself, but additional supervision by the client – even for corrosion protection work in the workshop – is advisable.

When coating materials with which the contractor is unfamiliar are to be applied, the manufacturer of the coating material shall be consulted.

The level of supervision will depend on the type and importance of the project, the degree of difficulty of the work and local conditions, and on the type of coating and its intended service life. This supervision will require appropriate technical knowledge and experience.