

INTERNATIONAL  
STANDARD

**ISO**  
**7617-2**

Second edition  
1994-10-15

---

---

**Plastics-coated fabrics for upholstery —**

**Part 2:**

Specification for PVC-coated woven fabrics

iTeh STANDARD PREVIEW

(standards.iteh.ai)

*Supports textiles revêtus de plastique pour ameublement et garniture —*

*Partie 2: Spécifications des tissus revêtus de PVC*

<https://standards.iteh.ai/catalog/standards/sist/ca5dab4c-038e-44bb-a066-000430fe9e38/iso-7617-2-1994>

INTERNATIONAL

ISO



Reference number  
ISO 7617-2:1994(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 7617-2 was prepared by Technical Committee ISO/TC 45, *Rubber and rubber products*.

This second edition cancels and replaces the first edition (ISO 7617-2:1988), which has been technically revised.

ISO 7617 consists of the following parts, under the general title *Plastics-coated fabrics for upholstery*:

- Part 1: *Specification for PVC-coated knitted fabrics*
- Part 2: *Specification for PVC-coated woven fabrics*
- Part 3: *Specification for polyurethane-coated woven fabrics*

Annexes A, B and C form an integral part of this part of ISO 7617.

© ISO 1994

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Plastics-coated fabrics for upholstery —

## Part 2:

## Specification for PVC-coated woven fabrics

### 1 Scope

This part of ISO 7617 specifies requirements for coated fabrics for upholstered furniture, manufactured by applying to one side of a woven cloth a substantially continuous coating of a suitably plasticized polymer of vinyl chloride, or a copolymer the major constituent of which is vinyl chloride. Such coatings are known as polyvinyl chloride (PVC) coatings. The present specification covers two grades (A and B) of PVC-coated woven fabric.

ISO 105-B02:1994, *Textiles — Tests for colour fastness — Part B02: Colour fastness to artificial light: Xenon arc fading lamp test.*

ISO 105-X12:1993, *Textiles — Tests for colour fastness — Part X12: Colour fastness to rubbing.*

ISO 176:1976, *Plastics — Determination of loss of plasticizers — Activated carbon method.*

ISO 1421:1977, *Fabrics coated with rubber or plastics — Determination of breaking strength and elongation at break.*

ISO 2231:1989, *Rubber- or plastics-coated fabrics — Standard atmospheres for conditioning and testing.*

ISO 2286:1986, *Rubber- or plastics-coated fabrics — Determination of roll characteristics.*

ISO 2411:1991, *Rubber- or plastics-coated fabrics — Determination of coating adhesion.*

ISO 4674:1977, *Fabrics coated with rubber or plastics — Determination of tear resistance.*

ISO 5978:1990, *Rubber- or plastics-coated fabrics — Determination of blocking resistance.*

ISO 7854:—<sup>2)</sup>, *Rubber- or plastics-coated fabrics — Determination of resistance to damage by flexing.*

### 2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 7617. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 7617 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 105-A02:1993, *Textiles — Tests for colour fastness — Part A02: Grey scale for assessing change in colour.*

ISO 105-B01:—<sup>1)</sup>, *Textiles — Tests for colour fastness — Part B01: Colour fastness to light: Daylight.*

1) To be published. (Revision of ISO 105-B01:1989)

2) To be published. (Revision of ISO 7854:1984)

### 3 Technical requirements

#### 3.1 Physical requirements

The material shall comply with the appropriate requirements of table 1.

#### 3.2 Colour fastness requirements

The material shall comply with the requirements of table 2.

#### 3.3 Visual examination

The coating of the material shall be uniformly applied and shall be free from visible flaws and cracks and when viewed under a magnification of  $\times 10$  shall be substantially free from pinholes. The base fabric, unless coated with an unpigmented coating, shall not be visible when viewed from the coated side.

#### 3.4 Colour, grain and finish

The colour, grain and finish of the material, whether in single-colour or multicolour effects, shall be agreed between the purchaser and the supplier.

Colours shall be compared under the conditions stipulated in ISO 105-B01.

#### 3.5 Width of material

The usable width of material when measured in accordance with ISO 2286 shall be as agreed between the purchaser and the supplier. For this purpose, the term "usable width" means the width of material that is coated in such a manner that it complies with the requirements of 3.3.

#### 3.6 Flammability

A method of test for determination of the flammability characteristics of these materials shall be included as a mandatory requirement to be complied with in the absence of other, more stringent requirements of national authorities.<sup>3)</sup>

### 4 Sampling

If individual rolls can be identified with manufacturing batches, at least one sample shall be taken from each batch in the consignment. Each sample shall be regarded as being representative of its source, and suitable measures shall be taken to preserve the identity between the samples and batch numbers.

If individual rolls cannot be identified in this way, the number of samples to be regarded as being representative of the bulk shall be fixed by agreement between the purchaser and the supplier. Such samples shall be drawn at random.

### 5 Testing and compliance

Tests shall be conducted on a set of specimens selected from each sample.

The method of selecting specimens from each sample shall be in accordance with the requirements of annex A. If the specimens after testing comply with the appropriate requirements given in tables 1 and 2, the bulk of the coated fabric which the sample represents shall be deemed to comply with the requirements of this part of ISO 7617.

If any of the specimens tested do not comply with any of the appropriate requirements given in tables 1 and 2, the tests which the specimens have failed shall be repeated twice. For this purpose, two further samples shall be taken from the same source as the original sample, and test specimens shall be taken from each sample so that duplicate tests may be conducted. If all the re-test results comply with the appropriate requirements of table 1 and/or table 2, then the bulk represented by the samples from which the specimens for re-testing were taken, together with the original samples, shall be deemed to comply with the requirements of this part of ISO 7617. If any of the results of the re-tests do not comply with the appropriate requirements of table 1 or 2, the bulk represented by those samples shall be deemed not to comply with the requirements of this part of ISO 7617.

3) Details of the method to be employed for this purpose are under consideration by ISO/TC 136, *Furniture*.

Table 1 — Physical requirements

Property	Limit	Requirements		Method of test
		Grade A	Grade B	
Total mass/unit area (g/m <sup>2</sup> ) <sup>1)</sup>	min.	550	420	ISO 2286
Coating mass/unit area (g/m <sup>2</sup> ) <sup>1)</sup>	min.	300	240	ISO 2286
Tearing force (N)				} ISO 4674:1977, method A1
longitudinal	min.	44	31	
transverse	min.	44	31	
Coating adhesion (N per 50 mm width)	min.	26	26	ISO 2411
Breaking load (N)				} ISO 1421:1977, method B
longitudinal	min.	580	450	
transverse	min.	580	450	
Flex cracking (cycles) <sup>2)</sup>	min.	400 000	300 000	ISO 7854
Heat ageing (% coating mass loss)	max.	5	5	ISO 176
Print wear (change in appearance) (grey scale rating)	min.	3	3	See annex B
Thickness (mm) at 2 kPa, minimum individual reading	min.	0,4	0,4	ISO 2286
Blocking resistance	—	Separation without damage to surface		ISO 5978

1) The inclusion of minimum values for total mass/unit area and coating mass/unit area does not imply that a minimum value for base fabric mass/unit area may be calculated by subtraction.

2) In the event of dispute, Schildknecht apparatus shall be employed.

Table 2 — Colour fastness requirements

Property	Limit	Requirements		Method of test
		Grade A	Grade B	
Colour fastness				
to artificial light (xenon arc)	min.	6	6	ISO 105-B02
to rubbing (wet and dry)	min.	4	4	See annex C

## 6 Marking

Each roll of fabric shall have a label attached bearing the following information:

- a) the name and/or distinctive mark of the manufacturer and an identification reference for that material;
- b) the batch number;
- c) the colour;
- d) the length;
- e) the usable width;
- f) the reference number of this part of ISO 7617 (i.e. ISO 7617-2) and the appropriate grade reference.

## Annex A (normative)

### Method of selecting test specimens

The specimens for testing shall be selected from the sample in accordance with the scheme illustrated in figure A.1, which shows the positions from which the specimens for each type of test shall be taken, except that the specimens required for testing colour fastness to light and those required for heat ageing tests shall be selected from any suitable portion of the sample. In the case of multicolour samples, the specimen shall if possible include all colours. If it is not possible to include all colours, sufficient specimens shall be taken to enable all colours to be tested.

#### Key to figure A.1

M	Mass determinations	Tn	Breaking load (longitudinal)
Tr	Tear strength (across longitudinal threads)	Tn	Breaking load (transverse)
Tr	Tear strength (across transverse threads)	Ad	Coating adhesion
		Fl	Resistance to flex cracking (longitudinal direction)
		Fl	Resistance to flex cracking (transverse direction)
			Heat ageing (any convenient location)
		Rb	Colour fastness to rubbing (wet and dry)
		P	Print wear (2 pieces, 230 mm × 50 mm)
		B	Blocking resistance

ISO 7617-2:1994

<https://standards.iteh.ai/catalog/standards/sist/ca5dab4c-038e-44bb-a066-000430fe9e38/iso-7617-2-1994>




Figure A.1 — Scheme for selection of test specimens

## Annex B (normative)

### Determination of resistance to print wear

#### B.1 Principle

A specimen is subjected to 500 cycles of simple harmonic abrasion using a known abradant under a known pressure. It is then assessed for colour difference with an unabraded portion using the grey scale for assessing change in colour.

#### B.2 Apparatus

The apparatus shall be as described in ISO 105-X12, but with the following modifications:

- a) The weightpiece applied to the rubbing finger, or peg, shall be such that a total mass of 1 500 g is brought to bear on the glass plate.
- b) The frequency of operation of the apparatus shall be 0,25 Hz (i.e. 0,5 strokes per second: each cycle comprises one outward stroke and one return stroke).
- c) Use as the abradant a cotton fabric, desized, scoured and bleached, free from fluorescent brightening agents, and having a fluidity not greater than 8, a mass per unit area of 93 g/m<sup>2</sup> and a construction of 40 ends/cm, 39 picks/cm, 11,36 tex warp and 9,23 tex weft in plain weave.
- d) Grey scale for assessing change in colour (see ISO 105-A02).

#### B.3 Test specimens

Cut out two specimens of coated fabric, each 230 mm × 50 mm, one with its length parallel to the longitudinal direction of the sample and the other with its length parallel to the transverse direction. Also cut out two circular pieces of the bleached cotton fabric each 30 mm in diameter, avoiding lumps and neps.

NOTE 1 Initially, four circular pieces of abradant cotton fabric can be cut out and a double thickness of cotton cloth mounted on the peg, so that only the outermost layer coming into contact with the coated fabric specimen needs to be renewed at each test.

#### B.4 Procedure

Condition the test specimens and bleached cotton fabric in accordance with ISO 2231.

Using the clamps, mount the test specimen securely on the bed of the machine with the coated side uppermost and under sufficient tension to hold the specimen flat.

Wipe the coated surface of the specimen with a clean, dry cloth to remove dust before testing.

Secure the conditioned bleached cotton fabric to the base of the brass peg, making sure that the face of the sateen is presented to the specimen under test, i.e. with the ribbed side of the bleached cotton fabric in contact with the brass peg. Lower the peg on to the specimen and run the machine for 500 cycles. Repeat the procedure using the second specimen and bleached cotton fabric.

Assess the degree of surface print wear on the specimens, using the grey scale as comparator in accordance with ISO 105-A02. If one specimen exhibits greater print wear than the other, the worse result of the two shall be taken as the test result.

#### B.5 Expression of results

Report the change in colour between the abraded and unabraded portions of the test specimen by reference to the grey scale for assessing change in colour.



## **Annex C**

(normative)

### **Determination of colour fastness to rubbing**

The method of test shall be as specified in ISO 105-X12:1993 but with the following changes:

- a) the frequency of operation of the apparatus shall be 0,25 Hz (i.e. 0,5 strokes per second: each cycle comprises one outward stroke and one return stroke);
- b) the number of strokes shall be 20 (10 outward and 10 return);
- c) the rubbing of the fabric shall be carried out as specified in annex B of this part of ISO 7617.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 7617-2:1994](https://standards.iteh.ai/catalog/standards/sist/ca5dab4c-038e-44bb-a066-000430fe9e38/iso-7617-2-1994)

<https://standards.iteh.ai/catalog/standards/sist/ca5dab4c-038e-44bb-a066-000430fe9e38/iso-7617-2-1994>