



**SLOVENSKI STANDARD
SIST EN ISO 307:2007**

01-september-2007

**BUKca Yý U
SIST EN ISO 307:2003**

Dc`ja Yfb]a UHYf]U]!'Dc`jUa]X]!' 8 c`c Ub`Y`yHYj]Uj]g_cnbcgh] f!GC ' \$+.&\$\$+L

Plastics - Polyamides - Determination of viscosity number (ISO 307:2007)

Kunststoffe - Polyamide - Bestimmung der Viskositätszahl (ISO 307:2007)

Plastiques - Polyamides - Détermination de l'indice de viscosité (ISO 307:2007)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: EN ISO 307:2007

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403fed9bfa/sist-en-iso-307-2007>

ICS:

83.080.20 Plastomeri Thermoplastic materials

SIST EN ISO 307:2007 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 307:2007

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffd9bfa/sist-en-iso-307-2007>

English Version

Plastics - Polyamides - Determination of viscosity number (ISO
307:2007)

Plastiques - Polyamides - Détermination de l'indice de
viscosité (ISO 307:2007)

Kunststoffe - Polyamide - Bestimmung der Viskositätszahl
(ISO 307:2007)

This European Standard was approved by CEN on 14 May 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 307:2007](https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffc9bfa/sist-en-iso-307-2007)

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffc9bfa/sist-en-iso-307-2007>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

This document (EN ISO 307:2007) has been prepared by Technical Committee ISO/TC 61 "Plastics" in collaboration with Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by November 2007, and conflicting national standards shall be withdrawn at the latest by November 2007.

This document supersedes EN ISO 307:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 307:2007 has been approved by CEN as EN ISO 307:2007 without any modifications.

STANDARD PREVIEW
(standards.iteh.ai)
SIST EN ISO 307:2007
<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffc99bfa/sist-en-iso-307-2007>

**Plastics — Polyamides — Determination
of viscosity number**

Plastiques — Polyamides — Détermination de l'indice de viscosité

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 307:2007](https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffd9bfa/sist-en-iso-307-2007)

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffd9bfa/sist-en-iso-307-2007>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 307:2007](https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffc9bfa/sist-en-iso-307-2007)

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffc9bfa/sist-en-iso-307-2007>



COPYRIGHT PROTECTED DOCUMENT

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions.....	2
4 Principle.....	3
5 Reagents and materials	3
5.1 Solvents and reagents.....	3
5.2 Cleaning liquids	4
6 Apparatus	4
7 Preparation of test samples.....	5
7.1 General.....	5
7.2 Samples containing less than 98 % (by mass) polyamide	5
8 Calculation of test portion	6
9 Selection of solvent.....	6
10 Procedure	7
10.1 Cleaning of the viscometer.....	7
10.2 Preparation of test solution	7
10.3 Measurement of flow times.....	9
11 Expression of results	10
12 Repeatability and reproducibility	10
13 Relationship between the viscosity number determined in 96 % (by mass) sulfuric acid solution and the viscosity determined in various solvents	11
14 Test report	11
Annex A (informative) Determination of the concentration of commercial sulfuric acid (95 % to 98 %) and adjustment to 96 % by titration	13
Annex B (informative) Determination of the concentration of sulfuric acid (95 % to 98 %) and adjustment to 96 % by flow time measurement in a small capillary viscometer	16
Annex C (informative) Determination of the concentration of commercial formic acid and adjustment to 90 % by titration	18
Annex D (informative) Determination of the concentration of commercial formic acid and adjustment to 90 % by density measurement.....	20
Annex E (informative) Relationship between the viscosity number determined in 96 % (by mass) sulfuric acid solution and the viscosity determined in various solvents	23
Bibliography	33

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 307 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

This fifth edition cancels and replaces the fourth edition (ISO 307:2003), which has been technically revised.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 307:2007

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffc99bfa/sist-en-iso-307-2007>

Introduction

This International Standard specifies a method for the determination of the viscosity number of dilute solutions of polyamides in certain specified solvents. The determination of the viscosity number of a polyamide provides a value that depends on the molecular mass of the polymer, but does not strictly correlate with the molecular mass.

Additives such as flame-retardants and modifiers often interfere with the viscosity measurement and may have an increasing effect on the viscosity number in one solvent and a decreasing effect in another solvent. The extent of the effect depends among others on the additive, the quantity of the additive, the presence of other additives and reactions.

The viscosity number of a polyamide sample containing additives that interfere with the viscosity measurement, measured in a specific solvent, represents a specific viscosity number for the polyamide under investigation and the actual measurement conditions. The measured viscosity number cannot, in principle, be converted from one solvent to another and is only suitable for intra-product comparison.

The viscosity number of pure polyamides or polyamides containing additives that do not interfere with the viscosity measurement can be converted from one solvent to another by a general relationship for that type of polyamide.

Polyamide test samples for the determination of the viscosity number must be completely soluble in the solvents mentioned. Additives contained in them, like glass and carbon fibres, must be separated from the solution.

As it is not possible to distinguish between extractables such as caprolactam, its oligomers and other extractable additives, these are considered as an essential part of the sample and therefore included in the sample mass.

The test method is applicable for production control and intra-product comparison even if the polyamide contains additives that do interfere with the viscosity measurement. However, it should be realised that deviations of the viscosity number can be caused by either the polyamide itself, effects caused by the additives present, or a combination of these.

The interference of additives with the viscosity determination can be checked by comparing the viscosity results of dry blend mixtures and regular production samples at several concentrations of the additive under investigation and in the solvents concerned. It should be noted that the other additives present also could influence the viscosity result.

The repeatability and reproducibility of the test method are strongly influenced by the correctness of the solvent concentration, the use of the Hagenbach correction if applicable and the temperature of the solvent on diluting the sample solution.

In this International Standard two specific viscometers are recommended. Furthermore, other types of viscometers listed in ISO 3105 may also be used, provided that the results are demonstrated to be equivalent to those measured with the recommended viscometers. It is to be expected that in the next revision the use of the other types of viscometers will be excluded.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 307:2007

<https://standards.iteh.ai/catalog/standards/sist/c471b67a-affc-4c6f-941e-9403ffd9bfa/sist-en-iso-307-2007>

Plastics — Polyamides — Determination of viscosity number

1 Scope

This International Standard specifies a method for the determination of the viscosity number of dilute solutions of polyamides in certain specified solvents.

Polyamide samples must be completely soluble in the solvents mentioned. Additives such as flame-retardants and modifiers often interfere with the viscosity measurement, having an increasing effect on the viscosity number in formic acid and a decreasing effect on the viscosity number in sulfuric acid. The extent of the effect for polyamide compounds depends on the additive, the quantity of the additive, the presence of other additives and the compounding conditions.

For pure polyamides or polyamides containing additives that do not interfere with the viscosity measurement, the determination of the viscosity number of a polyamide provides a measure of the molecular mass of the polymer. The viscosity number of pure polyamides or polyamides which contain additives that do not interfere with the viscosity measurement can be converted from one solvent to another.

The viscosity number of polyamides containing additives that do interfere with the viscosity measurement is specific to the solvent used and the material composition. In this case, the measured viscosity number cannot be converted from one solvent to another.

The method is applicable to the polyamides designated PA 46, PA 6, PA 66, PA 69, PA 610, PA 612, PA 11, PA 12, PA 6T/66, PA 6I/6T, PA 6T/6I/66, PA 6T/6I, PA 6I/6T/66 and PA MXD6 as defined in ISO 1874-1, as well as to copolyamides, compounds of polyamides and other polyamides that are soluble in one of the specified solvents under the specified conditions.

The method is not applicable to polyamides produced by anionic polymerization of lactams or produced with cross-linking agents; such polyamides are normally insoluble in the specified solvents.

The viscosity number is determined by the general procedure specified in ISO 1628-1, observing the particular conditions specified in this International Standard.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 1042, *Laboratory glassware — One-mark volumetric flasks*

ISO 1628-1, *Plastics — Determination of the viscosity of polymers in dilute solution using capillary viscometers — Part 1: General principles*

ISO 1874-1, *Plastics — Polyamide (PA) moulding and extrusion materials — Part 1: Designation*

ISO 3105, *Glass capillary kinematic viscometers — Specifications and operating instructions*

ISO 3451-4, *Plastics — Determination of ash — Part 4: Polyamides*

ISO 15512, *Plastics — Determination of water content*

ASTM D789, *Standard test methods for determination of relative viscosity of polyamide (PA)*

JIS K 6920-2:2000, *Plastics — Polyamide (PA) moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in ISO 1628-1 and the following apply.

3.1 viscosity number of a polymer
 number calculated by the following formula for the viscometers mentioned in this International Standard and flow times long enough so that no kinetic energy correction need be applied:

$$VN = \left(\frac{\eta}{\eta_0} - 1 \right) \times \frac{1}{c} \tag{1}$$

where

η is the viscosity of a solution of the polymer in a specified solvent, in Pascal seconds or N/m²·s;

η_0 is the viscosity of the solvent, expressed in the same units as η ;

$\frac{\eta}{\eta_0}$ is the relative viscosity of a solution of the polymer in a specified solvent;

c is the concentration, in grams per millilitre, of the polymer in the solution;

VN is the viscosity number, expressed in millilitres per gram.

NOTE 1 For a particular viscometer used and with substantially equal densities of the solvent and solution, the viscosity ratio is given by the flow time ratio for the solution concentration:

$$\frac{\eta}{\eta_0} \tag{2}$$

where

$\frac{\eta}{\eta_0}$ is the relative viscosity of a solution of the polymer in a specified solvent.

NOTE 2 As mentioned in ISO 3105, in case of flow times below 200 s and 60 s, for type 1 and type 2 Ubbelohde viscometers respectively, a correction for kinetic correction has to be applied: the so-called Hagenbach correction. For other types of viscometers, the kinetic energy correction has to be applied if the correction is $\geq 0,15\%$.

NOTE 3 The flow time of a liquid is related to its viscosity by the formula

$$v = \frac{\eta}{\rho} = C \times t - \left(\frac{A}{t^2} \right) \tag{3}$$

where

- ν is the viscosity/density ratio, in metres squared per second;
- ρ is the density of the liquid, in kilograms per cubic metre;
- C is the constant of the viscometer, in metres squared per second squared;
- t is the flow time, in seconds;
- A is the parameter of the kinetic correction in metres squared seconds.

NOTE 3 For a particular viscometer used, with substantially equal densities of the solvent and solution and a given kinetic factor, the viscosity ratio

$$\frac{\eta}{\eta_0} \quad (4)$$

is given by the flow time ratio for the solution concentration in this International Standard, each flow time reduced with the so-called Hagenbach correction (in seconds) given by the manufacturer for the viscometer as a function of the flow time.

4 Principle

The times of flow of a solvent and a solution of the polyamide at a concentration of 0,005 g/ml in the solvent are measured at 25 °C, the same viscometer being used for both measurements. The viscosity number is calculated from these measurements and from the known concentration of the solution.

(standards.iteh.ai)

5 Reagents and materials

SIST EN ISO 307:2007

5.1 Solvents and reagents

Only reagents of recognised analytical grade and only distilled water or water of equivalent purity shall be used.

WARNING — Some chemicals, for example 1,1,2,2-tetrachloroethane, are prohibited in some countries. The user shall check on the national regulations before applying the chemicals mentioned in this standard.

Avoid contact with the skin and inhalation of any vapours of the solvents and cleaning liquids.

5.1.1 Sulfuric acid, 96,00 % ± 0,20 % (by mass) solution.

For the determination of the concentration of commercial sulfuric acid (95 % to 98 %) and adjustment to 96,00 %, see Annexes A and B.

5.1.2 Formic acid, 90,00 % ± 0,15 % (by mass) solution.

The solvent shall be stored in a brown glass bottle. Its concentration shall be checked at least every 2 weeks. It shall not contain more than 0,2 % acetic acid or methyl formate.

For the determination of the concentration of commercial formic acid (90 %) and adjustment to 90,00 % ± 0,15 %, see Annexes C and D.

5.1.3 *m*-Cresol, meeting the following specifications:

- appearance: clear and colourless
- *m*-cresol content: 99 % (by mass) min.