
8 c`c Ub^_cb bYUYfcVbYV]cfUn[fUX`^j cgh`dc`ja Yfb] \ `a UYf]Ucj `j `j cXbYa
a YX]f `E`AYfcXU`n`a Yf`b`Ya `dcfUY`_]g]_Uj `nUdfhYa `fYgd]fca Yfi fIGC
%,) %%% -- Ł

Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium - Method by measuring the oxygen demand in a closed respirometer (ISO 14851:1999)

Bestimmung der vollständigen aeroben Bioabbaubarkeit von Kunststoff-Materialien in einem wässrigen Medium - Verfahren mittels Messung des Sauerstoffbedarfs in einem geschlossenen Respirometer (ISO 14851:1999)

Evaluation de la biodégradabilité aérobie ultime des matériaux plastiques en milieu aqueux - Méthode par détermination de la demande en oxygene dans un respirometre fermé (ISO 14851:1999)

Ta slovenski standard je istoveten z: EN ISO 14851:2004

ICS:

| | | |
|-----------|--------------------------------|---------------------|
| 83.080.01 | Polimerni materiali na splošno | Plastics in general |
|-----------|--------------------------------|---------------------|

SIST EN ISO 14851:2004**en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14851:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 14851

July 2004

ICS 83.080.01

English version

Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium - Method by measuring the oxygen demand in a closed respirometer (ISO 14851:1999)

Evaluation de la biodégradabilité aérobie ultime des matériaux plastiques en milieu aqueux - Méthode par détermination de la demande en oxygène dans un respiromètre fermé (ISO 14851:1999)

This European Standard was approved by CEN on 21 June 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN ISO 14851:2004 (E)**Foreword**

The text of ISO 14851:1999 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 14851:2004 by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2005, and conflicting national standards shall be withdrawn at the latest by January 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 14851:1999 has been approved by CEN as EN ISO 14851:2004 without any modifications.

NOTE Normative references to International Standards are listed in Annex ZA (normative).

<https://standards.itih.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

Annex ZA (normative)

Normative references to international publications with their relevant European publications

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

NOTE Where an International Publication has been modified by common modifications, indicated by (mod.), the relevant EN/HD applies.

| <u>Publication</u> | <u>Year</u> | <u>Title</u> | <u>EN</u> | <u>Year</u> |
|--------------------|-------------|---|--------------|-------------|
| ISO 10634 | 1995 | Water quality - Guidance for the preparation and treatment of poorly water-soluble organic compounds for the subsequent evaluation of their biodegradability in an aqueous medium | EN ISO 10634 | 1995 |

[SIST EN ISO 14851:2004](https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14851:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

INTERNATIONAL STANDARD

ISO 14851

First edition
1999-05-15

Corrected version
2003-07-15

Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium — Method by measuring the oxygen demand in a closed respirometer

iTeh STANDARD PREVIEW
*Évaluation de la biodégradabilité aérobie ultime des matériaux plastiques
en milieu aqueux — Méthode par détermination de la demande en oxygène
dans un respiromètre fermé.*
(standards.iteh.ai)

[SIST EN ISO 14851:2004](https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>



Reference number
ISO 14851:1999(E)

ISO 14851:1999(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 14851:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 14851 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 5, *Physical-chemical properties*.

Annexes A to G of this International Standard are for information only.

This corrected version of ISO 14851:1999 incorporates the following corrections:

- in Clause 2, the year of publication of ISO 9408 has been inserted and the footnote deleted;
- the remaining footnotes have been renumbered;
- in Annex C, errors in the key to Figure C.1 have been corrected and minor improvements made to the figure itself;
- in the Bibliography, references [1] and [2] have been updated.

SIST EN ISO 14851:2004
<https://standards.iteh.ai/catalog/standards/sist/271dfc3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

Introduction

With the increasing use of plastics, their recovery and disposal have become a major issue. As a first priority, recovery should be promoted. Complete recovery of plastics, however, is difficult. For example, plastic litter, which comes mainly from consumers, is difficult to recover completely. Additional examples of plastics which are difficult to recover are fishing tackle, agricultural mulches and water-soluble polymers. These plastic materials tend to leak from closed waste-management cycles into the environment. Biodegradable plastics are now emerging as one of the options available to solve such environmental problems. Plastic materials, such as products or packaging, which are sent to composting facilities should be potentially biodegradable. Therefore it is very important to determine the potential biodegradability of such materials and to obtain an indication of their biodegradability in natural environments.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 14851:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

Determination of the ultimate aerobic biodegradability of plastic materials in an aqueous medium — Method by measuring the oxygen demand in a closed respirometer

WARNING — Sewage, activated sludge, soil and compost may contain potentially pathogenic organisms. Therefore appropriate precautions should be taken when handling them. Toxic test compounds and those whose properties are unknown should be handled with care.

1 Scope

This International Standard specifies a method, by measuring the oxygen demand in a closed respirometer, for the determination of the degree of aerobic biodegradability of plastic materials, including those containing formulation additives. The test material is exposed in an aqueous medium under laboratory conditions to an inoculum from activated sludge, compost or soil.

If an unadapted activated sludge is used as the inoculum, the test simulates the biodegradation processes which occur in a natural aqueous environment; if a mixed or pre-exposed inoculum is used, the method can be used to investigate the potential biodegradability of a test material.

The conditions used in this International Standard do not necessarily correspond to the optimum conditions allowing maximum biodegradation to occur, but the standard is designed to determine the potential biodegradability of plastic materials or give an indication of their biodegradability in natural environments.

The method enables the assessment of the biodegradability to be improved by calculating a carbon balance (optional, see annex E).

The method applies to the following materials:

- Natural and/or synthetic polymers, copolymers or mixtures thereof.
- Plastic materials which contain additives such as plasticizers, colorants or other compounds.
- Water-soluble polymers.
- Materials which, under the test conditions, do not inhibit the microorganisms present in the inoculum. Inhibitory effects can be determined using an inhibition control or by another appropriate method (see e.g. ISO 8192^[3]). If the test material is inhibitory to the inoculum, a lower test concentration, another inoculum or a pre-exposed inoculum can be used.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 8245:1999, *Water quality — Guidelines for the determination of total organic carbon (TOC) and dissolved organic carbon (DOC)*.

ISO 9408:1999, *Water quality — Evaluation of ultimate aerobic biodegradability of organic compounds in aqueous medium by determination of oxygen demand in a closed respirometer*.

ISO 10634:1995, *Water quality — Guidance for the preparation and treatment of poorly water-soluble organic compounds for the subsequent evaluation of their biodegradability in an aqueous medium*.

ISO/TR 15462:1997, *Water quality — Selection of tests for biodegradability*.

3 Definitions

For the purposes of this International Standard, the following definitions apply:

3.1

ultimate aerobic biodegradation

the breakdown of an organic compound by microorganisms in the presence of oxygen into carbon dioxide, water and mineral salts of any other elements present (mineralization) plus new biomass

3.2

activated sludge

biomass produced in the aerobic treatment of waste water by the growth of bacteria and other microorganisms in the presence of dissolved oxygen

3.3

concentration of suspended solids in an activated sludge

the amount of solids obtained by filtration or centrifugation of a known volume of activated sludge and drying at about 105 °C to constant mass

[SIST EN ISO 14851:2004](https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004)

<https://standards.iteh.ai/catalog/standards/sist/27fd3e-0e54-4584-9992-7c3f277b7f83/sist-en-iso-14851-2004>

3.4

biochemical oxygen demand

BOD

the mass concentration of the dissolved oxygen consumed under specified conditions by the aerobic biological oxidation of a chemical compound or organic matter in water, expressed as milligrams of oxygen uptake per milligram or gram of test compound

3.5

theoretical oxygen demand

ThOD

the theoretical maximum amount of oxygen required to oxidize a chemical compound completely, calculated from the molecular formula, expressed as milligrams of oxygen uptake per milligram or gram of test compound

3.6

total organic carbon

TOC

all the carbon present in organic matter which is dissolved or suspended in water

3.7

dissolved organic carbon

DOC

that part of the organic carbon in water which cannot be removed by specified phase separation, for example by centrifugation at 40 000 m·s⁻² for 15 min or by membrane filtration using membranes with pores of 0,2 µm to 0,45 µm diameter