



**SLOVENSKI STANDARD**  
**SIST EN ISO 12571:2001**  
**01-september-2001**

---

**Higrotermalne lastnosti gradbenih materialov in proizvodov - Ugotavljanje higroskopnosti (ISO 12571:2000)**

Hygrothermal performance of building materials and products - Determination of hygroscopic sorption properties (ISO 12571:2000)

Wärme- und feuchtetechnisches Verhalten von Baustoffen und Bauprodukten - Bestimmung der hygroskopischen Sorptionseigenschaften (ISO 12571:2000)

Performance hygrothermique des matériaux et produits pour le bâtiment - Détermination des propriétés de sorption hygrosopique (ISO 12571:2000)

<https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001>

**Ta slovenski standard je istoveten z: EN ISO 12571:2000**

---

**ICS:**

91.100.01	Gradbeni materiali na splošno	Construction materials in general
91.120.30	Zaščita pred vlago	Waterproofing

**SIST EN ISO 12571:2001**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 12571:2001](#)

<https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

EN ISO 12571

March 2000

ICS 91.100.01

English version

Hygrothermal performance of building materials and products -  
Determination of hygroscopic sorption properties (ISO  
12571:2000)

Performance hygrothermique des matériaux et produits  
pour le bâtiment - Détermination des propriétés de sorption  
hygroscopique (ISO 12571:2000)

Wärme- und feuchtetechnisches Verhalten von Baustoffen  
und Bauprodukten - Bestimmung der hygroscopischen  
Sorptionseigenschaften (ISO 12571:2000)


This European Standard was approved by CEN on 20 May 1999.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Central Secretariat: rue de Stassart, 36 B-1050 Brussels

<b>Contents</b>		<b>Page</b>
	Foreword	3
1	Scope	4
2	Normative reference	4
3	Definitions, symbols and units	4
4	Principle	5
5	Apparatus	6
6	Test specimens	6
7	Procedure	7
8	Calculation and expression of results	9
9	Accuracy of measurement	9
10	Test report	10
	Annex A (informative) Relative air humidities above saturated solutions in equilibrium	11
	Annex B (informative) Preparation of saturated solutions	13
	Annex C (informative) Example of the procedure for determining a point on a sorption curve	16
	Annex D (informative) Bibliography	17

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

SIST EN ISO 12571:2001

<https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-69550c41e0aa/sist-en-iso-12571-2001>

## Foreword

The text of EN ISO 12571:2000 has been prepared by Technical Committee CEN/TC 89 "Thermal performance of buildings and building components", the secretariat of which is held by SIS, in collaboration with Technical Committee ISO/TC 163 "Thermal insulation".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2000, and conflicting national standards shall be withdrawn at the latest by December 2001.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Czech Republic, Denmark, Finland, France, Germany, Greece, Iceland, Ireland, Italy, Luxembourg, Netherlands, Norway, Portugal, Spain, Sweden, Switzerland and the United Kingdom.

This standard is one of a series of standards, which specify test methods for the thermal and moisture related properties of building materials and products.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 12571:2001](https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001)

<https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001>

## 1 Scope

This standard specifies two alternative methods for determining hygroscopic sorption properties of porous building materials and products:

- a) using desiccators and weighing cups (desiccator method);
- b) using a climatic chamber (climatic chamber method).

The desiccator method is the reference method.

The standard does not specify the method for sampling.

The methods specified in this standard can be used to determine the moisture content of a sample in equilibrium with air at a specific temperature and humidity.

## 2 Normative reference

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references, latest edition of the publication referred to applies.

EN ISO 9346	Thermal insulation - Mass transfer - Physical quantities and definitions (ISO 9346)
EN ISO 12570	Hygrothermal performance of building materials and products - Determination of moisture content by drying at elevated temperature (ISO 12570)

IT-EN STANDARD PREVIEW  
(standards.iteh.ai)  
SIST EN ISO 12571:2001  
<https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001>

## 3 Definitions, symbols and units

### 3.1 Definitions

For the purposes of this standard, the definitions given in EN ISO 9346 and the following apply:

#### 3.1.1 hygroscopic sorption

exchange of water vapour between ambient air and a porous material until the point of equilibrium is reached

#### 3.1.2 moisture content mass by mass

mass of evaporable water divided by mass of dry material

#### 3.1.3 moisture content volume by volume

volume of evaporable water divided by volume of dry material

**3.1.4 moisture content mass by volume**

mass of evaporable water divided by volume of dry material

NOTE The mass of water is determined by weighing the specimen before and after drying at the appropriate drying temperature until constant mass is reached.

**3.1.5 sorption curve**

curve that establishes a relationship between the moisture content of a material at equilibrium with the environment and the relative humidity of the ambient air, at a specified temperature

**3.1.6 adsorption curve**

sorption curve established at a series of increasing equilibrium relative humidities

**3.1.7 desorption curve**

sorption curve established at a series of decreasing equilibrium relative humidities

**3.2 Symbols and units**

Symbol	Quantity	Unit
$m$	mass of test specimen	kg
$m_0$	mass of dried test specimen	kg
$u$	moisture content mass by mass	kg/kg
$\psi$	moisture content volume by volume	$\text{m}^3/\text{m}^3$
$w$	moisture content mass by volume	$\text{kg}/\text{m}^3$

SIST EN ISO 12571:2001

**4 Principle** <https://standards.iteh.ai/catalog/standards/sist/d2eed5bb-cf57-440c-b2c2-65330e41eafa/sist-en-iso-12571-2001>**4.1 Adsorption curve**

The specimen is dried to constant mass. Whilst maintaining a constant temperature, the specimen is placed consecutively in a series of test environments, with relative humidity increasing in stages. The moisture content is determined when equilibrium with each environment is reached. Equilibrium with the environment is established by weighing the specimen until constant mass is reached. A minimum of four test atmospheres shall be selected in the humidity range under consideration.

After establishing the moisture content at each relative humidity the adsorption curve can be drawn.

**4.2 Desorption curve**

The starting point for desorption is a relative humidity of at least 95 %. This might be the last point of the adsorption curve or might be reached by adsorption from a dried test specimen. Whilst maintaining a constant temperature, the specimen is placed consecutively in a series of test environments, with relative humidity decreasing in stages. The moisture content is determined when equilibrium with each environment is reached. Equilibrium with the environment is established by weighing the specimen until constant mass is reached. A minimum of four test atmospheres shall be selected in the humidity range under consideration. Finally, the specimen is dried to constant mass.

After establishing the moisture content at each relative humidity the desorption curve can be drawn.

NOTE A defined starting point for desorption has been chosen for better reproducibility.

## 5 Apparatus

### 5.1 Desiccator method

The test apparatus shall include:

- a) weighing cups which do not absorb water and with tight-fitting lids;
- b) balance, capable of weighing to an accuracy of  $\pm 0,01$  % of the mass of the test specimen;

NOTE If larger weighing cups are used, the weighing accuracy can be determined with respect to the total mass and the required accuracy of the test results.

- c) drying oven, in accordance with EN ISO 12570;
- d) desiccator, capable of maintaining the relative humidity within  $\pm 2$  % relative humidity;
- e) constant-temperature chamber, capable of maintaining the specified test temperature to an accuracy of  $\pm 0,5$  K.

### 5.2 Climatic chamber method

The test apparatus shall include:

- a) weighing cups which do not absorb water;
- b) balance, capable of weighing to an accuracy of  $\pm 0,01$  % of the mass of the test specimen;

NOTE If larger weighing cups are used, the weighing accuracy can be determined with respect to the total mass and the required accuracy of the test results.

- c) drying oven, in accordance with EN ISO 12570;
- d) climatic chamber capable of maintaining the relative humidity within  $\pm 5$  % relative humidity and the temperature within  $\pm 2$  K over the whole test area.

## 6 Test specimens

### 6.1 Specification of the test specimens

A test specimen shall be representative of the product and have a mass of at least 10 g. Specimens of materials with a dry density less than  $300 \text{ kg/m}^3$  shall have an area of at least  $100 \text{ mm} \times 100 \text{ mm}$ .



If it can be demonstrated from other references that the result will not be affected, a test specimen can be cut or crushed into smaller pieces to reduce the time to reach equilibrium with the environment.

## 6.2 Number of test specimens

A minimum of three specimens shall be tested. The procedure in clause 7 shall be applied to each specimen.

## 7 Procedure

### 7.1 Test conditions

Reference sorption curves shall be established at a temperature of  $(23 \pm 0,5)$  °C. If agreed between the parties, sorption curves can be established at other temperatures for specific applications.

### 7.2 Desiccator method

#### 7.2.1 General

Make up the appropriate saturated aqueous solution to achieve the necessary relative humidity in the desiccator.

NOTE Annex A gives the relative air humidities of various saturated solutions in equilibrium, and annex B describes the preparation of various solutions.

Place the desiccator in the constant-temperature chamber.

#### 7.2.2 Adsorption curve

Weigh the weighing cup and lid when empty and dry.

Put the test specimen into the weighing cup without the lid and dry it until constant mass in the drying oven at the temperature specified in EN ISO 12570.

Constant mass is reached if the change of mass between three consecutive weighings, each made at least 24 h apart, is less than 0,1 % of the total mass.

Put the test specimen in the weighing cup, with the lid beside it, into the desiccator containing the salt solution needed to give the appropriate relative humidity.

Periodically weigh the specimen until it is in equilibrium with the environment (constant mass). Immediately after removing the lid of the desiccator, put on the lid of the weighing cup, and move the weighing cup to the balance. After weighing the cup, return it to the desiccator with the lid beside it.

NOTE 1 Annex C gives an example of a detailed weighing procedure.