



SLOVENSKI STANDARD

SIST EN 3833:2005

01-junij-2005

BUXca Yý U
SIST EN 3833:2004

Aerospace series - Bolts, MJ threads, in heat resisting nickel base alloy NI-PH2601 (Inconel 718), passivated - Classification: 1 550 MPa (at ambient temperature) / 650 °C - Technical specification

Aerospace series - Bolts, MJ threads, in heat resisting nickel base alloy NI-PH2601 (Inconel 718), passivated - Classification: 1 550 MPa (at ambient temperature) / 650 °C - Technical specification
(standards.iteh.ai)

Luft- und Raumfahrt - Schrauben, MJ-Gewinde aus hochwarmfester Nickelbasislegierung NI-PH2601 (Inconel 718), passiviert - Klasse: 1 550 MPa (bei Raumtemperatur) / 650 °C - Technische Lieferbedingungen

Série aérospatiale - Vis a filetage MJ, en alliage résistant a chaud a base de nickel NI-PH2601 (Inconel 718), passivées - Classification : 1 550 MPa (a température ambiante) / 650 °C - Spécification technique

Ta slovenski standard je istoveten z: EN 3833:2004

ICS:

49.030.20 Sorniki, vijaki, stebelni vijaki Bolts, screws, studs

SIST EN 3833:2005

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3833:2005](https://standards.iteh.ai/catalog/standards/sist/7a97ffd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005)

<https://standards.iteh.ai/catalog/standards/sist/7a97ffd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005>

English version

Aerospace series - Bolts, MJ threads, in heat resisting nickel base alloy NI-PH2601 (Inconel 718), passivated - Classification: 1 550 MPa (at ambient temperature) / 650° C - Technical specification

Série aérospatiale - Vis à filetage MJ, en alliage résistant à chaud à base de nickel NI-PH2601 (Inconel 718), passivées - Classification : 1 550 MPa (à température ambiante) / 650° C - Spécification technique

Luft- und Raumfahrt - Schrauben, MJ-Gewinde, aus hochwarmfester Nickelbasislegierung NI-PH2601 (Inconel 718), passiviert - Klasse: 1 550 MPa (bei Raumtemperatur) / 650° C - Technische Lieferbedingungen

This European Standard was approved by CEN on 11 September 2003.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

[SIST EN 3833:2005](https://standards.iteh.ai/SIST/EN/3833/2005)

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword.....		3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Quality assurance	6
5	Requirements	6
Annex A (normative) Passivation treatment for bolts		26
Annex B (informative) Tensile, stress rupture and tension fatigue – Areas and loads formulae		27

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3833:2005](https://standards.iteh.ai/catalog/standards/sist/7a97ffcd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005)

<https://standards.iteh.ai/catalog/standards/sist/7a97ffcd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005>

Foreword

This document (EN 3833:2004) has been prepared by the European Association of Aerospace Manufacturers - Standardization (AECMA-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2005, and conflicting national standards shall be withdrawn at the latest by May 2005.

This document supersedes EN 3833:2003.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 3833:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/7a97ffcd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005>

EN 3833:2004 (E)

1 Scope

This standard specifies the characteristics, qualification and acceptance requirements for bolts with MJ threads in NI-PH2601, passivated, for aerospace applications.

Classification: 1 550 MPa ¹⁾ /650 °C ²⁾

It is applicable whenever referenced.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- ISO 2859-1, *Sampling procedures for inspection by attributes – Part 1: Sampling schemes indexed by acceptable quality limit (AQL) for lot-by-lot inspection*
- ISO 3452, *Non-destructive testing – Penetrant inspection – General principles*
- ISO 4288, *Geometrical Product Specifications (GPS) – Surface texture: Profile method – Rules and procedures for the assessment of surface texture*
- ISO 6508-1, *Metallic materials – Rockwell hardness test – Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*
- ISO 6892, *Metallic materials – Tensile testing at ambient temperature*
- ISO 7961, *Aerospace – Bolts – Test methods*
- ISO 9227, *Corrosion tests in artificial atmospheres – Salt spray tests*
- EN 9133, *Aerospace series – Quality management systems – Qualification procedure for aerospace standard parts* ³⁾
- ASTM E 112-96, *Standard Test Methods for Determining Average Grain Size* ⁴⁾

3 Terms and definitions

For the purposes of this standard, the following terms and definitions apply.

3.1

batch

quantity of finished parts, of the same type and same diameter, produced from the same material obtained from the same melt, manufactured in the course of the same production cycle, following the same manufacturing route and having undergone all the relevant heat treatments and surface treatments.

3.2

inspection lot

quantity of parts from a single production batch with the same part number which completely defines the part

1) Minimum tensile strength of the material at ambient temperature

2) Maximum test temperature of the parts

3) Published as AECMA Prestandard at the date of publication of this standard

4) Published by: American Society for Testing and Materials (ASTM), 1916 Race street, Philadelphia, PA 19103-1187, USA

3.3 Surface discontinuities

3.3.1

crack

rupture in the material which may extend in any direction and which may be intercrystalline or transcrystalline in character

3.3.2

seam

open surface defect

3.3.3

lap

surface defect caused by folding over metal fins or sharp corners and then rolling or forging them into the surface

3.3.4

inclusions

non-metallic particles originating from the material manufacturing process. These particles may be isolated or arranged in strings

3.4

test temperature

ambient temperature unless otherwise specified

3.5

simple random sampling

the taking of n items from a population of N items in such a way that all possible combinations of n items have the same probability of being chosen

3.6

critical defect

a defect that, according to judgement and experience, is likely to result in hazardous or unsafe conditions for individuals using, maintaining, or depending upon the considered product, or that is likely to prevent performance of the function of a major end item

3.7

major defect

a defect other than critical, that is likely to result in a failure or to reduce materially the usability of the considered product for its intended purpose

3.8

minor defect

a defect that is not likely to reduce materially the usability of the considered product for its intended purpose, or that is a departure from established specification having little bearing on the effective use or operation of this product

3.9

sampling plan

a plan according to which one or more samples are taken in order to obtain information and possibly to reach a decision

3.10

limiting quality (LQ₁₀)

in a sampling plan, the quality limit which corresponds to a specified 10 % probability of acceptance

3.11

acceptance quality limit (AQL)

a quality limit which in a sampling plan corresponds to a specified but relatively high probability of acceptance

It is the maximum per cent defective (or the maximum number of defects per hundred units) that, for purposes of sampling inspection can be considered satisfactory as a process average.

EN 3833:2004 (E)**3.12****finished bolt**

a bolt ready for use, inclusive of any possible treatments and/or surface coatings, as specified in the product standard or definition document

3.13**definition document**

document specifying all the requirements for finished bolts

4 Quality assurance**4.1 Qualification**

EN 9133

Qualification inspections and tests (requirements, methods, numbers of bolts) are specified in Table 1. They shall be carried out on:

- each type and diameter of bolt;
- 25 bolts selected from a single inspection lot by simple random sampling.

The test programme may possibly be reduced, or the qualification of a bolt be granted without inspection or testing. Any such decision shall be based on the results obtained on similar types and diameters of bolts provided that the design and manufacturing conditions are identical.

Table 2 indicates the allocation of bolt samples for the inspections and tests.

4.2 Acceptance

[SIST EN 3833:2005
https://standards.iteh.ai/catalog/standards/sist/7a97ffcd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005](https://standards.iteh.ai/catalog/standards/sist/7a97ffcd-a3d7-4065-a896-8060bf04d37d/sist-en-3833-2005)

4.2.1 Purpose

The purpose of acceptance inspections and tests is to check, as simply as possible, by a method representative of actual use conditions, with the uncertainty inherent to statistical sampling, that the bolts constituting the batch satisfy the requirements of this standard.

4.2.2 Conditions

Acceptance inspections and tests (requirements, methods, numbers of bolts) are specified in Table 1 ; they shall be carried out on each batch. Bolts from the batch to be tested shall be selected by simple random sampling.

Each bolt may be submitted to several inspections or tests.

If a more stringent inspection is deemed necessary, all or part of the qualification inspections and tests may be performed during the acceptance inspection and testing. In this case, the number of bolts submitted to these inspections and tests is the same as that submitted for qualification inspection and tests.

4.2.3 Responsibility

Acceptance inspections and tests shall be carried out by the manufacturer, or under his responsibility.

4.2.4 Inspection and test report

A test report showing actual numerical values shall be provided if specified in the purchase order.

5 Requirements

See Table 1.

Table 1 — Technical requirements and test methods

Clause	Characteristic	Requirement	Inspection and test method	Q/A ^a	Sample size
5.1	Material	In accordance with the product standard or definition document	Chemical analysis or certificate of compliance issued by the manufacturer of the semi-finished product	Q	
				A	
5.2	Dimensions, tolerances and tolerances of form and position	In accordance with the product standard or definition document	Standard gauging	Q	25
				A	Tables 3 and 4
5.3	Manufacturing				
5.3.1	Forging	<p>The head of the bolts shall be formed by hot or cold forging. If hot forged, the forging temperature shall be between 1 040 °C and 1 080 °C and they shall be air cooled.</p> <p>The equipment shall ensure a uniform temperature throughout the batch.</p>	<p>The method of forging shall be indicated.</p> <p>The equipment shall be approved.</p>	Q	
5.3.2	Heat treatment	<p>The heat treatment medium or atmosphere shall not cause any surface contamination except as permitted by 5.5.6.</p> <p>Any scale not removed by subsequent machining shall be removed by abrasive blasting with an appropriate equipment.</p> <p>The headed blanks shall be precipitation heat treated at (720 ± 5) °C, held at temperature for 8 h ± 15 min, furnace cooled at (55 ± 5) °C per hour to (620 ± 5) °C, held at 620 °C for 8 h ± 15 min, followed by air cooling or faster.</p> <p>Instead of the 55 °C per hour cooling rate to 620 °C, parts may be furnace cooled at any rate provided the time at 620 °C is adjusted to give a total precipitation time of 18 h min.</p>	<p>Calibration of the heat treatment equipment shall be confirmed.</p> <p>Visual examination</p> <p>Examination of the heat treatment specification</p>	Q	

continued

Table 1 (continued)

Clause	Characteristic	Requirement	Inspection and test method	Q/A ^a	Sample size
5.3.3	Removal of surface contamination by machining	<p>After precipitation treatment the headed blanks shall have the shank and bearing surface of the head machined:</p> <p>a) for the removal of all surface contamination and oxide penetration;</p> <p>b) to obtain a clean smooth surface.</p> <p>The amount of material removed (see Figure 1) shall be as little as practicable and shall not exceed the limits of Table 5.</p>	<p>See 5.5.6.</p> <p>See 5.5.1.</p>		
5.3.4	Head to shank fillet	<p>After completion of heat treatment and machining, the underhead fillet radius shall be cold rolled to remove all visual signs of machining and to create cold working.</p> <p>This may cause distortion which shall not exceed the values in Figure 2, unless otherwise specified on the product standard or definition document.</p> <p>For parts with compound radii between head and shank (e.g. T head bolts), only the radius that blends with the head shall be cold worked, however it is acceptable for cold work to extend over the compound radius.</p> <p>The fillet shall not show seams or inclusions (see Table 6).</p>	Dimensional check (see 5.2) and visual examination	Q	25
				A	Tables 3 and 4
5.3.5	Threads	Shall be formed by a single rolling process after full heat treatment (see Figure 3).		Q	
5.3.6	Surface roughness	In accordance with the product standard or definition document	ISO 4288 Visual examination	Q	3
				A	Tables 3 and 4
5.3.7	Passivation treatment	<p>Uncoated finished bolts shall be passivated in accordance with Annex A (normative).</p> <p>After 2 h of salt spray, bolts shall show no evidence of corrosion or staining.</p>	ISO 9227, neutral salt spray (NSS) test Visual examination	Q	5
				A	100 %
5.3.8	Surface coating	In accordance with the product standard or definition document	See applicable coating standard.	Q	3
				A	Tables 3 and 4

continued

Table 1 (continued)

Clause	Characteristic	Requirement	Inspection and test method	Q/A ^a	Sample size
5.4	Mechanical properties	A test sample shall be selected from each diameter of bar/wire taken from each cast, and shall be heat treated together with a production batch of bolts. The sample selected shall be sufficient to provide tensile and stress rupture test specimens. The test specimens shall meet the mechanical properties required by the material standard.			
5.4.1	Tensile strength	The finished bolts shall withstand the minimum tensile loads specified in Table 7. Externally wrenched bolts shall not fail in the head to shank area when subjected to the tensile test. Tensile tests are not applicable to the following: a) protruding head bolts of grip length < twice the nominal shank diameter; b) countersunk head bolts of grip length < $\times 2,5$ the nominal shank diameter; c) threaded to head bolts of overall length < $\times 3$ the nominal shank diameter or bolts having an overall length < 18 mm; d) bolts of diameters of < 4 mm. In such cases acceptability shall be based on the results from test bars of the same material heat treated within the same process cycle.			
5.4.1.1	– at ambient temperature		ISO 7961 for bolts ISO 6892 for test specimens	Q A	4 Table 8 or Table 9
5.4.1.2	– at elevated temperature	(650 \pm 5) °C	ISO 7961 for bolts ISO 6892 for test specimens	Q	4
5.4.2	Stress rupture	The finished bolts shall be maintained at (650 \pm 2) °C while the load specified in Table 7 is applied continuously. There shall be no rupture in less than 23 h.	ISO 7961	Q	3

continued

Table 1 (continued)

Clause	Characteristic	Requirement	Inspection and test method	Q/A ^a	Sample size
5.4.3	Tension fatigue strength	<p>The test shall be carried out on finished bolts.</p> <p>Tension fatigue tests are not applicable to the following:</p> <p>a) protruding head bolts of nominal length < 3 D;</p> <p>b) countersunk head bolts of nominal length < 3 D;</p> <p>c) bolts having a nominal length < 18 mm;</p> <p>d) diameters < 5 mm;</p> <p>e) bolts with drilled shanks;</p> <p>f) bolts threaded to head.</p> <p>Life:</p> <p>– mean value: min. 65 000 cycles</p> <p>– individual value: min. 45 000 cycles max. 130 000 cycles</p> <p>Frequency: 140 Hz max.</p> <p>Loads: see Table 10.</p> <p>For individual fatigue life values less than 65 000 cycles, the breaking:</p> <p>a) shall occur in the thread in the case of parts with full or pitch diameter shanks;</p> <p>b) is acceptable in the groove or relieved diameter for such parts;</p> <p>c) is not allowed in the underhead fillet radius.</p> <p>For individual fatigue life values exceeding 65 000 cycles, breaking may occur in any place.</p> <p>Unbroken bolts shall be rendered unusable.</p>	ISO 7961	Q	5
5.4.4	Hardness	<p>Before surface coating is applied, the hardness shall be 45 HRC min., when measured at the end of the bolt (thread end).</p> <p>The hardness of the threads and the head to shank fillet area may be higher.</p>	ISO 6508-1	Q	4
				A	Table 8
5.4.5	Recess removal torque	As specified by the product standard or definition document	See the product standard or definition document.	Q	5
				A	Tables 3 and 4

continued