

Designation: C 1071 - 00

Standard Specification for Fibrous Glass Duct Lining Insulation (Thermal and Sound Absorbing Material)¹

This standard is issued under the fixed designation C 1071; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification covers fibrous glass insulation used as a thermal and sound absorbing liner for interior surfaces of ducts, plenums, and other air handling equipment that handle air up to 250° F (121° C).

1.2 The values stated in inch-pound units are the standard. The SI values in parentheses are for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:
- C 167 Test Methods for Thickness and Density of Blanket or Batt Thermal Insulations²
- C 168 Terminology Relating to Thermal Insulating Materials²
- C 177 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of (the Guarded-Hot-Plate Apparatus²
- C 390 Criteria for Sampling and Acceptance of Preformed Thermal Insulation Lots²
- C 411 Test Method for Hot-Surface Performance of High-Temperature Thermal Insulation²
- C 423 Test Method for Sound Absorption and Sound Absorption Coefficients by the Reverberation Room Method²
- C 518 Test Method for Steady-State Heat Flux Measurements and Thermal Transmission Properties by Means of the Heat Flow Meter Apparatus²
- C 665 Specification for Mineral-Fiber Blanket Thermal Insulation for Light Frame Construction and Manufactured $Housing^2$
- C 1104/C 1104M Test Method for Determining the Water

Vapor Sorption of Unfaced Mineral Fiber Insulation²

- C 1114 Test Method for Steady-State Thermal Transmission Properties by Means of the Thin-Heater Apparatus²
- C 1304 Test Method for Assessing the Odor Emission of Thermal Insulation Materials²
- C 1338 Test Method for Determining Fungi Resistance of Insulation Materials and Facings²
- E 84 Test Method for Surface Burning Characteristics of Building Materials³
- E 795 Practices for Mounting Test Specimens During Sound Absorption Tests²
- G 21 Practice for Determining Resistance of Synthetic Polymer Materials to Fungi⁴
- G 22 Practice for Determining Resistance of Plastics to Bacteria⁴
- 2.2 Other Standards:
- NAIMA Fibrous Glass Duct Liner Standard⁵
- SMACNA HVAC Duct Construction Standards⁶
- UL 723 Test for Surface Burning Characteristics of Building Materials⁷
- NFPA 255 Standard Method of Test of Surface Burning Characteristics of Building Materials⁸
- NFPA 259 Standard Test Method for Potential Heat of Building Materials⁸
- CAN/ULC-S102-M88 Standard Method of Test for Surface Burning Characteristics of Building Materials and Assemblies⁹

3. Terminology

3.1 For definitions of terms used in this specification, see Terminology C 168.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.23 on Blanket and Loose Fill Insulation.

Current edition approved Dec. 10, 2000. Published January 2001. Originally published as C 1071 - 86. Last previous edition C 1071 - 98.

² Annual Book of ASTM Standards, Vol 04.06.

³ Annual Book of ASTM Standards, Vol 04.07.

⁴ Annual Book of ASTM Standards, Vol 14.04.

⁵ Available from North American Insulation Manufacturers Association, 44 Canal Center Plaza, Suite 310, Alexandria, VA 22314.

⁶ Available from Sheet Metal and Air Conditioning Contractors National Association, Inc., 4201 Lafayette Center Drive, Chantilly, VA 22021-1209.

⁷ Available from Underwriters Laboratories Inc., 333 Pfingsten Road, Northbrook, Illinois 60062–2096.

⁸ Available from National Fire Protection Association, 1 Batterymarch Park, PO Box 9101, Quincy, MA 02269–9101.

⁹ Available from Underwriters Laboratories of Canada, 7 Crouse Road, Scarborough, Ontario, Canada M1R 3A9.

4. Classification

4.1 The insulation covered by this specification shall be of the following types:

4.1.1 *Type I*—Blanket in roll form up to 200 ft (61 m) in length, 36 to 72 in. (914 to 1829 mm) in width, and thicknesses of $\frac{1}{2}$ to 3 in. (13 to 76 mm), in $\frac{1}{2}$ -in. (13-mm) increments.

4.1.2 *Type II*—Board in sheet form, up to 120 in. (3048 mm) in length, up to 48 in. (1219 mm) in width, and thicknesses of $\frac{1}{2}$ to 3 in. (13 to 76 mm) in $\frac{1}{2}$ -in. (13-mm) increments.

5. Ordering Information

5.1 Purchasers should select the preferred options permitted herein and include the following information in procurement documents:

5.1.1 Title, designation, and year of this specification.

5.1.2 Type of insulation (see 4.1).

5.1.3 Length, width, and thickness required (see 4.1).

5.1.4 Packaging required (see 16.1).

5.1.5 Marking required (see 16.2 and 16.3).

5.1.6 Material weight should be obtained from supplier.

6. Materials and Manufacture

6.1 *Basic Material*— The basic material shall be made from glass processed from the molten state into fibrous form with a binder added to form dimensionally stable insulation. Asbestos shall not be used as an ingredient or component part of the product.

6.2 Air Stream Surface—Depending on the insulation surface characteristics and service air velocity, the air stream surface may be plain or coated with a temperature resistant coating or faced with a plain or coated fibrous mat or fabric.

7. Physical Requirements

7.1 *Corrosiveness*— When tested in accordance with 12.3, the metal plate in contact with the back side (non-air surface side) of the insulation shall show no corrosion greater than the comparative plates in contact with sterile cotton which has been tested in the same manner.

7.2 *Water Vapor Sorption*—When tested in accordance with 12.4, the water vapor sorption of the insulation shall not be more than 3 % by weight.

7.3 *Fungi Resistance*— When tested in accordance with 12.5, the insulation shall be observed as having no fungal growth.

7.4 *Temperature Resistance*—When tested in accordance with 12.6, the air stream surface shall have no evidence of flaming, glowing, smoldering, visible smoke, or delamination, cracking, deformation or reduction in thickness.

7.5 *Erosion Resistance*—When tested in accordance with 12.7, the insulation shall not break away, crack, peel, flake off, or show evidence of delamination or continued erosion when air is passed through typical duct sections at a velocity specified in 12.7.

7.6 *Odor Emission*— When tested in accordance with 12.8, a detectable odor of objectionable nature recorded by more than two of the five panel members shall constitute failure of the material.

7.7 Surface Burning Characteristics—When tested in accordance with 12.9, the air stream surface of the insulation shall have a maximum flame spread index of 25 and a maximum smoke developed index of 50.

7.8 Apparent Thermal Conductivity—When tested in accordance with 12.10, the apparent thermal conductivity (k) of the insulation, expressed as Btu·in/h·ft²·°F or W/m·K for the specified thickness shall not exceed the values shown in Table 1.

7.9 Sound Absorption Coefficients—When tested in accordance with 12.11, the insulation shall have sound absorption coefficients not less than that in Table 2 at the specified frequencies.

7.10 *Bacteria Resistance*—When tested in accordance with 12.12, the insulation shall be observed as having no growth.

7.11 *Combustion Characteristics*—When tested in accordance with 12.13, the material shall have a potential heat value not exceeding 3500 Btu/lb (8141 kJ/kg).

8. Dimensional Tolerances

8.1 After conditioning for a minimum of 24 h at $70\pm 3^{\circ}$ F (21 \pm 1.6°C) and 50 \pm 5% relative humidity, the insulation shall conform to the dimensional tolerances listed in Table 3.

9. Workmanship, Finish, and Appearance

9.1 The insulation units shall indicate good workmanship in fabrication and shall not have visible defects which adversely affect their service qualities.

10. Sampling Co. 21

10.1 The insulation shall be sampled in accordance with Criteria C 390. Specific provisions for sampling shall be agreed upon between the purchaser and supplier as part of the purchase contract.

0/1-00

11. Qualification Requirements 7ba4/astm-c1071-00

11.1 The following requirements shall be employed for the purpose of initial material or product qualification:

11.1.1 Corrosiveness,

11.1.2 Water vapor sorption,

11.1.3 Fungi resistance,

- 11.1.4 Temperature resistance,
- 11.1.5 Erosion resistance,
- 11.1.6 Odor emission,

11.1.7 Surface burning characteristics,

11.1.8 Apparent thermal conductivity,

11.1.9 Sound absorption coefficients,

11.1.10 Bacteria resistance, and

11.1.11 Combustion characteristics.

11.2 The manufacturer shall furnish a certificate of compliance for qualification requirements upon request (see Criteria C 390).

TABLE 1 Apparent Thermal Conductivity (maximum), Btu·in/h·ft ².°F (W/m·K)

Mean Temperature, °F (°C)	Туре І	Туре II
75 (24)	0.31 (0.045)	0.27 (0.039)