

---

---

**Implants for surgery — Metallic materials —**

**Part 4:**

Cobalt-chromium-molybdenum casting alloy

*Implants chirurgicaux — Produits à base de métaux —*

**iTeh STANDARD PREVIEW**  
*Partie 4: Alliage à couler à base de cobalt, de chrome et de molybdène*  
**(standards.iteh.ai)**

ISO 5832-4:1996

<https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996>



## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 5832-4 was prepared by Technical Committee ISO/TC 150, *Implants for surgery*, Subcommittee SC 1, *Materials*.

This second edition cancels and replaces the first edition (ISO 5832-4:1978), which has been technically revised.

ISO 5832 consists of the following parts, under the general title *Implants for surgery — Metallic materials*:

- Part 1: *Wrought stainless steel*
- Part 2: *Unalloyed titanium*
- Part 3: *Wrought titanium 6-aluminium 4-vanadium alloy*
- Part 4: *Cobalt-chromium-molybdenum casting alloy*
- Part 5: *Wrought cobalt-chromium-tungsten-nickel alloy*
- Part 6: *Wrought cobalt-nickel-chromium-molybdenum alloy*
- Part 7: *Forgeable and cold-formed cobalt-chromium-nickel-molybdenum-iron alloy*
- Part 8: *Wrought cobalt-nickel-chromium-molybdenum-tungsten-iron alloy*

© ISO 1996

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

- *Part 9: Wrought high nitrogen stainless steel*
- *Part 10: Wrought titanium 5-aluminium 2,5-iron alloy*
- *Part 11: Wrought titanium 6-aluminium 7-niobium alloy*
- *Part 12: Wrought cobalt-chromium-molybdenum alloy*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 5832-4:1996](https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996)

<https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996>

## Introduction

No known surgical implant material has ever been shown to cause absolutely no adverse reactions in the human body. However, long-term clinical experience of the use of the material referred to in this part of ISO 5832 has shown that an acceptable level of biological response can be expected, when the material is used in appropriate applications.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 5832-4:1996](https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996)

<https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996>

# Implants for surgery — Metallic materials —

## Part 4:

### Cobalt-chromium-molybdenum casting alloy

#### 1 Scope

This part of ISO 5832 specifies the characteristics of, and corresponding test methods for, cobalt-chromium-molybdenum casting alloy for use in the manufacture of surgical implants.

NOTE 1 The mechanical properties of a sample obtained from a finished product made of this alloy may not necessarily comply with the specifications given in this part of ISO 5832.

#### 2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this part of ISO 5832. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this part of ISO 5832 are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 6892:1984, *Metallic materials — Tensile testing*.

#### 3 Chemical composition

The heat analysis of a representative sample of the alloy when determined in accordance with clause 6 shall comply with the chemical composition specified in table 1.

Requirements for the major and minor elemental constituents for cobalt-chromium-molybdenum casting alloy are listed in table 1.

Table 1 — Chemical composition

Element	Compositional limits, % (m/m)
Chromium	26,5 to 30,0
Molybdenum	4,5 to 7,0
Nickel	1,0 max.
Iron	1,0 max.
Carbon	0,35 max.
Manganese	1,0 max.
Silicon	1,0 max.
Cobalt	Balance

#### 4 Mechanical properties

##### 4.1 Tensile

The tensile properties of the alloy, when tested in accordance with clause 5, shall comply with the specified values in table 2.

Table 2 — Mechanical properties

Tensile strength	Proof stress of nonproportional elongation	Percentage elongation after fracture <sup>1)</sup>
$R_m$ min. MPa	$R_{p0,2}$ min. MPa	$A$ min.
665	450	8

1) Gauge length =  $5,65 \sqrt{S_0}$  or 50 mm, where  $S_0$  is the original cross-sectional area, in square millimetres.

Should any of the test pieces not meet the specified requirements, or should they break outside the gauge limits, two further test pieces representative of the same batch shall be tested in the same manner. The alloy shall be deemed to comply only if both additional test pieces meet the specified requirements.

NOTE 2 However, the manufacturer may re-heat-treat the material and resubmit it for testing in accordance with this part of ISO 5832. In this case, all parts should be heat-treated in the same fashion.

## 5 Test methods

The test methods used in determining compliance with this part of ISO 5832 shall be those given in table 3.

Representative test pieces for the determination of mechanical properties shall be prepared in accordance with ISO 6892.

Table 3 — Test methods

Parameter	Relevant clause	Test method
Chemical composition	3	Recognized analytical procedures (ISO methods where these exist)
Mechanical properties	4	
Tensile strength		ISO 6892
Proof stress of nonproportional elongation		ISO 6892
Percentage elongation		ISO 6892

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

ISO 5832-4:1996

<https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996>

**iTeh STANDARD PREVIEW**  
This page intentionally left blank  
**(standards.iteh.ai)**

ISO 5832-4:1996

<https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 5832-4:1996

<https://standards.iteh.ai/catalog/standards/sist/8bf94aea-c1fc-4f93-927f-f92c00121fd4/iso-5832-4-1996>

---

---

### ICS 11.040.40

**Descriptors:** medical equipment, surgical implants, metallurgical products, cobalt alloys, chromium containing alloys, molybdenum containing alloys, specifications, materials specifications, chemical composition, mechanical properties, tests.

Price based on 2 pages

---

---