



SLOVENSKI STANDARD

SIST EN 622-3:2004

01-september-2004

BUKca Yý U
SIST EN 622-3:1998

J`U_bYbY`d`cý Y!`GdYWZ_UWY`Y!" "XY.`NU HJ YnUgfYXbY`d`cý Y

Fibreboards - Specifications - Part 3: Requirements for medium boards

Faserplatten - Anforderungen - Teil 3: Anforderungen an mittelharte Platten

Panneaux de fibres - Exigences - Partie 3: Exigences pour panneaux mi-durs
iTeh STANDARD PREVIEW
(standards.iteh.ai)

Ta slovenski standard je istoveten z: **SIST EN 622-3:2004**

<https://standards.iteh.ai/catalog/standards/sist/f9dba0f9-ae85-428d-87cf-924b3e7b87b4/sist-en-622-3-2004>

ICS:

79.060.20 X|a } ^ } ^ ^ / ^ / ^ ^ / [z ^ Fibre and particle boards

SIST EN 622-3:2004

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 622-3:2004

<https://standards.iteh.ai/catalog/standards/sist/f9dba0f9-ae85-428d-87cf-924b3e7b87b4/sist-en-622-3-2004>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 622-3

April 2004

ICS 79.060.20

Supersedes EN 622-3:1997

English version

Fibreboards - Specifications - Part 3: Requirements for medium boards

Panneaux de fibres - Exigences - Partie 3: Exigences pour panneaux mi-durs

Faserplatten - Anforderungen - Teil 3: Anforderungen an mittelharte Platten

This European Standard was approved by CEN on 2 February 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/9dba0f9-ae85-428d-87cf-924b3e7b87b4/sist-en-622-3-2004>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions.....	5
4 Requirements	6
4.1 General.....	6
4.2 Requirements for general purpose boards.....	6
4.2.1 Requirements for boards for use in dry conditions.....	6
4.2.2 Requirements for boards for use in humid conditions.....	7
4.2.3 Requirements for boards for use in exterior conditions	7
4.3 Requirements for load-bearing boards	8
4.3.1 General.....	8
4.3.2 Requirements for boards for use in humid conditions.....	8
4.3.3 Requirements for boards for use in humid conditions.....	9
5 Verification of compliance	10
5.1 General.....	10
5.2 External control.....	10
5.3 Factory production control.....	10
6 Marking	10
6.1 General purpose boards	10
6.2 Load-bearing boards	11
6.3 Colour coding.....	11
Annex A (normative) Supplementary properties	12
Annex B (normative) Boil test according to EN 1087-1:1995 — Modified procedure	13
Annex C (normative) Determination of bending strength after boil test according to EN 1087-1:1995 — Modified procedure.....	14
Bibliography	15

Foreword

This document (EN 622-3:2004) has been prepared by Technical Committee CEN/TC 112 "Wood-based panels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2004, and conflicting national standards shall be withdrawn at the latest by October 2004.

This standard is one of a series specifying requirements for fibreboards. The other parts of this series are listed in clause 2 and in the bibliography.

This document supersedes EN 622-3:1997.

The following, modifications have been made:

- a) The quality requirements of the panel types MBH.H, MBH.E, MBH.LA2, MBH.HLS1 and MBH.HLS2 have been modified.
- b) The test interval for moisture resistance has been reduced in accordance with EN 13986.

Annexes A, B and C are normative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 622-3:2004 (E)**1 Scope**

This European Standard specifies the requirements for hardboards as defined in EN 316.

The values listed in this standard relate to product properties but they are not characteristic values to be used in design calculations¹⁾.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 310:1993, *Wood-based panels — Determination of modulus of elasticity in bending and of bending strength*.

EN 317, *Particleboards and Fibreboards — Determination of swelling in thickness after immersion in water*.

EN 318, *Wood based panels - Determination of dimensional changes associated with changes in relative humidity*

EN 319, *Particleboards and Fibreboards — Determination of tensile strength perpendicular to the plane of the board*.

EN 326-1, *Wood-based panels — Sampling, cutting and inspection — Part 1: Sampling and cutting of test pieces and expression of test results*.

EN 326-2, *Wood-based panels — Sampling, cutting and inspection — Part 2: Quality control in the factory*.

EN 326-3, *Wood-based panels — Sampling, cutting and inspection — Part 3: Inspection of an isolated lot of panels*.

EN 622-1, *Fibreboards — Specifications — Part 1: General requirements*.

EN 1087-1:1995, *Particleboards - Determination of moisture resistance - Part 1: Boil test*

EN 12871, *Wood-based panels — Performance specifications and requirements for load-bearing boards for use in floors, walls and roofs*.

EN 13986:2002, *Wood-based panels for use in construction — Characteristics, evaluation of conforming and marking*.

ENV 1995-1-1:1993, *Eurocode 5 — Design of timber structures Part 1-1: General rules and rules for buildings*.

ISO 3340, *Fibre building boards — Determination of sand content*.

1) Such characteristic values (e.g. for use in design calculation in ENV 1995-1-1) are either given EN 12369-1 or derived by testing according to EN 789, EN 1058 and ENV 1156.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

dry conditions

conditions corresponding to service class 1 of ENV 1995-1-1:1993 which is characterised by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air only exceeding 65 % for a few weeks per year
[EN 13986:2002]

3.2

humid conditions

conditions corresponding to service class 2 of ENV 1995-1-1:1993 which is characterised by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air only exceeding 85 % for a few weeks per year
[EN 13986:2002]

3.3

external conditions

conditions corresponding to service class 3 of ENV 1995-1-1:1993 which is characterised by climatic conditions leading to higher moisture contents than in service class 2
[EN 13986:2002]

3.4

general purpose use

all non-load bearing applications, e.g. furniture and fittings

3.5

load-bearing use

use in a load-bearing construction, i.e. an organized assembly of connected parts designed to provide mechanical resistance and stability to the works. Also referred to as "structure"

3.6

load duration category

see Table 1

Table 1 — Load duration categories

Load duration category	Order of accumulated duration of characteristic load	Examples of loading
Permanent	more than 10 years	self weight
Long-term	6 months to 10 years	storage
Medium-term	1 week to 6 months	imposed load
Short-term	less than 1 week	snow ^a , wind
Instantaneous		accidental loading

^a In areas which have a heavy snow load for a prolonged period of time, part of the load should be regarded as medium-term.

EN 622-3:2004 (E)

4 Requirements

4.1 General

Medium boards shall comply with the general requirements of EN 622-1 together with the relevant requirements set out in 4.2 and 4.3 of this standard. The requirements for some supplementary properties are given in annex A.

The requirements in Tables 2 to 8 shall be met by 5 percentile values (95 percentile values in the case of swelling in thickness), based on the mean test values for individual panels and calculated in accordance with EN 326-1. In the case of swelling in thickness, they shall be equal to or less than the values in the Tables, and in the case of all other properties, they shall be equal to or greater than the values in the Tables. The values in the Tables for both bending strength and modulus of elasticity shall apply to test results obtained in any direction in the plane of the panel.

Properties not required for specific board types are marked “—”.

With the exception of swelling in thickness, internal bond after boil test (see Tables 7, 8) and bending strength after boil test (see Tables 3, 4, 8), the values given in the Tables are characterised by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of 65 %. The values given for swelling in thickness, internal bond after boil test and bending strength after boil test are characterised by a moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of 65 % before the treatment (immersion in water or boil treatment).

The moisture resistance of medium boards for use in humid and exterior conditions (see Tables 3, 4, 7 and 8) is assessed either as internal bond after boil test (according to EN 1087-1), with the modified procedure given in annex B, or as bending strength after boil test (according to EN 1087-1), with the modified procedure given in annex C. These two testing procedures are regarded as equivalent alternatives. Where requirements for both procedures are given, compliance with only one set of specifications is required (see Table 8).

4.2 Requirements for general purpose boards

4.2.1 Requirements for boards for use in dry conditions

Table 2 specifies the requirements for general purpose boards for use in dry conditions, e.g. interior fitments including furniture.

Table 2 — Requirements for general purpose boards for use in dry conditions (types MBL and MBH)

Property	Test method	Unit	Ranges of nominal thickness (mm) Board types			
			≤ 10		> 10	
			MBL	MBH	MBL	MBH
Swelling in thickness 24 h	EN 317	%	20	15	20	15
Internal bond	EN 319	N/mm ²	—	0,10	—	0,10
Bending strength	EN 310	N/mm ²	10	15	8	12

4.2.2 Requirements for boards for use in humid conditions

Table 3 specifies the requirements for general purpose boards for use in humid conditions.

Table 3 — Requirements for general purpose boards for use in humid conditions (types MBL.H and MBH.H)

Property	Test method	Unit	Ranges of nominal thickness (mm) Board types			
			≤ 10		> 10	
			MBL.H	MBH.H	MBL.H	MBH.H
Swelling in thickness 24 h	EN 317	%	15	12	15	12
Internal bond	EN 319	N/mm ²	—	0,30	—	0,30
Bending strength	EN 310	N/mm ²	12	18	10	15
Bending strength after boil test	EN 310 EN 1087-1	N/mm ²	—	6	—	5 ^a
^a For the determination of bending strength after boil test, the modified procedure given in annex C applies. Bending strength after boil test is calculated on the initial dimensions of the test piece (before boil treatment).						

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4.2.3 Requirements for boards for use in exterior conditions

Table 4 specifies the requirements for general purpose boards for use in exterior conditions.

SIST EN 622-3:2004

Table 4 — Requirements for general purpose boards for use in exterior conditions (types MBL.E and MBH.E)

Property	Test method	Unit	Ranges of nominal thickness (mm) Board types			
			≤ 10		> 10	
			MBL.E	MBH.E	MBL.E	MBH.E
Swelling in thickness 24 h	EN 317	%	9	7	9	7
Internal bond	EN 319	N/mm ²	—	0,30	—	0,30
Bending strength	EN 310	N/mm ²	14	18	12	18
Modulus of elasticity in bending	EN 310	N/mm ²	—	2 200	—	2 200
Bending strength after boil test ^a	EN 310 EN 1087-1	N/mm ²	—	6	—	6
^a For the determination of bending strength after boil test, the modified procedure given in annex C applies. Bending strength after boil test is calculated on the initial dimensions of the test piece (before boil treatment).						