



**SLOVENSKI STANDARD**  
**SIST EN 14977:2006**  
**01-september-2006**

---

**Baker in bakrove zlitine - Ugotavljanje natezne napetosti - Preskus s 5-odstotnim amoniakom**

Copper and copper alloys - Detection of tensile stress - 5 % ammonia test

Kupfer und Kupferlegierungen - Auffinden von Zugspannungen - 5 % Ammoniakprüfung

Cuivre et alliages de cuivre - Détection des contraintes de traction - Essai à l'ammoniaque à 5 %

**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: EN 14977:2006**

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>

**ICS:**

77.120.30

**SIST EN 14977:2006**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 14977:2006

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>

ICS 77.150.30

English Version

## Copper and copper alloys - Detection of tensile stress - 5 % ammonia test

Cuivre et alliages de cuivre - Détection des contraintes de traction - Essai à l'ammoniaque à 5 %

Kupfer und Kupferlegierungen - Auffinden von Zugspannungen - 5 % Ammoniakprüfung

This European Standard was approved by CEN on 15 May 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 14977:2006](https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006)

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Contents

Page

Foreword.....	3
Introduction .....	4
1 Scope .....	5
2 Principle.....	5
3 Terms and definitions .....	5
4 Test solution.....	5
5 Test pieces .....	6
6 Procedure .....	6
7 Test requirements.....	6
8 Test report .....	6
Bibliography.....	7

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 14977:2006](https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006)

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>

## Foreword

This document (EN 14977:2006) has been prepared by Technical Committee CEN/TC 133 “Copper and copper alloys”, the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2006, and conflicting national standards shall be withdrawn at the latest by December 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 14977:2006

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>

## Introduction

This test was developed to achieve three aims in particular:

- firstly to avoid health and environmental risks which are associated with the use of media other than ammonia, (e.g. with the use of compounds of mercury and recovery of mercury polluted test pieces), but with a similar sensitivity as the test according to EN ISO 196;
- secondly to combine a test on tensile stress with a test on stress corrosion cracking;
- thirdly to reduce the test duration from usually 24 h, as specified in ISO 6957, to 16 h.

It is not intended to replace and withdraw EN ISO 196 in favour of this standard. In so far as a rapid result is required, the test according to EN ISO 196 can be used.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 14977:2006](https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006)

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>

## 1 Scope

This standard specifies a medium-duration test using an ammoniacal atmosphere for the purpose of detecting the presence of tensile stress, residual or applied, in grades of copper or copper-alloy products that might bring about failure of a component in service or storage through stress corrosion cracking.

The field of application of this standard is specified in the technical delivery specifications of semi-finished or finished products in grades of copper and copper alloys, or by prior agreement between purchaser and supplier.

## 2 Principle

Exposure of test pieces to an ammoniacal atmosphere for 16 h, followed by examination at a magnification of  $\times 6$  to  $\times 10$ , e.g. for cracks.

## 3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

### 3.1

#### **stress corrosion cracking**

cracking of metals under the combined action of corrosion and tensile stress, residual or applied

### 3.2

#### **applied stress**

tensile stress that is set up and exists in a body during application of an external load

[SIST EN 14977:2006](https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006)

### 3.3

#### **residual stress**

tensile stress that remains within a body as a result of plastic deformation

<https://standards.iteh.ai/catalog/standards/sist/300e0f4a-0abf-4319-a075-4663bac95f77/sist-en-14977-2006>

## 4 Test solution

### 4.1 General

Use only reagents of recognised analytical grade and distilled or deionised water for the test solution.

### 4.2 Test solution No. 1

The test solution is an aqueous solution containing approx. 50 g  $\text{NH}_3$  per litre of solution, density at 20 °C: 0,976 g/ml to 0,978 g/ml.

The solution can be used several times, provided that  $\text{NH}_3$  concentration is maintained.

### 4.3 Test solution No. 2

Dissolve 107 g of pure  $\text{NH}_4\text{Cl}$ , suitable for analysis, in approx. 0,75 l of distilled or deionised water, add a solution of 440 g of  $\text{NaOH}$  per litre until a pH of 10 ( $\pm 0,1$ ) at 22 °C is achieved. Dilute the solution with distilled water to one litre. This does not modify significantly the pH. The test solution can be reused several times, provided the pH is checked at least every two weeks, and corrected if necessary.

Because of the consumption of  $\text{NH}_4\text{Cl}$ , after every three months a new test solution shall be prepared.

## 5 Test pieces

The test pieces shall be at least 150 mm long and shall be degreased. Oxide layers, if any, shall be removed by means of 10 %-sulphuric acid solution (mass fraction), produced by diluting 62 ml of concentrated sulphuric acid ( $\rho = 1,84$  g/ml), with water up to 1 000 ml.

The test pieces shall not be deformed and shall be free from identification stamping or any other mechanical damage. The test pieces shall be dry when the test begins.

## 6 Procedure

Pour the test solution into a desiccator or an air-tight vessel, maintain the ratio between the volume of the test vessel and the volume of the test solution between 10 : 1 and 20 : 1.

The test pieces shall be arranged in the vessel and above the solution so that the vapour can act from all sides. The test pieces shall neither touch each other nor come into direct contact with the solution.

The test temperature shall be between 20 °C and 25 °C and shall remain constant. The duration of the test shall be 16 h.

At the end of the test period, the test pieces shall be briefly pickled in 10 %-sulphuric acid solution (mass fraction) produced by diluting 62 ml of concentrated sulphuric acid ( $\rho = 1,84$  g/ml), with water up to 1 000 ml or 36 %-nitric acid solution (mass fraction), produced by diluting 440 ml of concentrated nitric acid, ( $\rho = 1,43$  g/ml), with water up to 1 000 ml, dried and examined for cracking under a magnifying glass. The magnification should be between  $\times 6$  and  $\times 10$ . Before inspection, it may be necessary to deform the test piece slightly so that fine cracks are opened up and are more readily seen.

Light-gauge test pieces, i.e. pieces with a thickness of less than 2 mm, shall be tested with solution No. 2. Test pieces with a thickness of equal to or greater than 2 mm shall be tested with solution No. 1.

## 7 Test requirements

The interpretation of the visual appearance of the test pieces (e.g. existence of cracks) after testing is a matter for the product specification and/or has to be agreed between the purchaser and the supplier, e.g. no crack shall be visible on the surface of the test piece when examined under low power magnification.

Cracks within a 5 mm wide zone along cut or sawn edges, or around stamped markings, originating from the test piece preparation shall be disregarded.

## 8 Test report

The test report shall include the following information:

- a) identification of the sample, and the location of the test piece in the sample if the test was carried out on a test piece taken from the sample, rather than on the sample itself;
- b) reference of the test method used;
- c) pH-value of the solution producing the ammonical atmosphere;
- d) exposure temperature;
- e) number of replicate test pieces tested;
- f) test results: cracks or no cracks (as required in the appropriate product specification);
- g) any unusual features noted during the determination;
- h) any operation not included in this European Standard or in the document to which reference is made or regarded as optional;
- i) date of the test and/or date of preparation or signature of the test report.