



Designation: C 1099 – 92 (Reapproved 1997)

Standard Test Method for Modulus of Rupture of Carbon-Containing Refractory Materials at Elevated Temperatures¹

This standard is issued under the fixed designation C 1099; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This test method covers the determination of the modulus of rupture of carbon-containing refractories at elevated temperatures in air.

1.2 The values stated in inch-pound units and degrees Fahrenheit are to be regarded as standard. The values given in parentheses are for information only.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.* For specific hazard statements, see Section 5.

2. Referenced Documents

2.1 ASTM Standards:

C 583 Test Method for Modulus of Rupture of Refractory Materials at Elevated Temperatures²
E 220 Method for Calibration of Thermocouples by Comparison Technique³

2.2 ISO Standard:

ISO Recommendation 5013 Determination of the Hot Modulus of Rupture of Shaped and Unshaped Dense and Insulating Refractory Products⁴

3. Significance and Use

3.1 The modulus of rupture of carbon-containing refractories at elevated temperatures has become accepted as a useful measurement in quality control testing and in research and development. These measurements are also used to determine the suitability of particular products for various applications and to develop specifications. The sample may undergo some oxidation during the test.

3.2 In 1988, ruggedness testing was conducted on this test procedure. The following variables were studied:

3.2.1 Testing temperature (2525 (1385) versus 2575°F (1413°C)),

3.2.2 Air atmosphere versus argon atmosphere in the furnace,

3.2.3 Hold time prior to breaking the sample (12 versus 18 min), and

3.2.4 Loading rate on the sample (175 (778) versus 350 lb/min (1556 N/min)).

3.3 Resin bonded magnesia-carbon brick containing approximately 17 % carbon after coking where tested in two separate ruggedness tests. Metal-free brick were tested in the first ruggedness test, while aluminum-containing brick were tested in the second. Results were analyzed at a 95 % confidence level.

3.4 For the metal-free brick, the presence of an argon atmosphere and hold time had statistically significant effects on the modulus of rupture at 2550°F (1400°C). The argon atmosphere yielded a lower modulus of rupture. The samples tested in air had a well-sintered decarburized zone on the exterior surfaces, possibly explaining the higher moduli of rupture. The longer hold time caused a lower result for the metal-free brick.

3.5 For the aluminum-containing brick, testing temperature, the presence of an argon atmosphere, and loading rate had statistically significant effects on the modulus of rupture at 2550°F (1400°C). The higher testing temperature increased the measured result, the presence of an argon atmosphere lowered the result, and the higher loading rate increased the result.

4. Apparatus

4.1 *Electrically-Heated Furnace*—An electrically heated furnace should be used. The furnace will contain an air atmosphere.

4.2 *Lower Bearing Edges*, at least one pair, made from volume-stable refractory material (Note 1) shall be installed in the furnace on 5-in. (127-mm) centers.

4.3 *Thrust Column*, containing the top bearing edge that is made from the same volume-stable refractory material used for the lower bearing edges, shall extend outside the furnace where means are provided for applying a load.

4.3.1 The lower bearing edges and the bearing end of the support column shall have rounded bearing surfaces having about a ¼-in. (6 mm) radius (Note 2). The lower bearing surfaces may be made adjustable, but must attain the standard

¹ This test method is under the jurisdiction of ASTM Committee C-8 on Refractories and is the direct responsibility of Subcommittee C08.08 on Basic Refractories.

Current edition approved Aug. 15, 1992. Published October 1992.

² *Annual Book of ASTM Standards*, Vol 15.01.

³ *Annual Book of ASTM Standards*, Vol 14.03.

⁴ Available from the American National Standards Institute, 11 W. 42nd St., 13th Floor, New York, NY 10036.