



SLOVENSKI STANDARD
SIST ISO 13930:2000

01-junij-2000

Železne rude -- Dinamični test za nizkotemperaturno redukcijo in razpadanje

Iron ores -- Dynamic test for low-temperature reduction-disintegration

Minerais de fer -- Essai dynamique de désagrégation par réduction à basse température

Ta slovenski standard je istoveten z: **ISO 13930:1998**

[SIST ISO 13930:2000](https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000)

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>

ICS:

73.060.10 Železove rude Iron ores

SIST ISO 13930:2000

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 13930:2000

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>

INTERNATIONAL
STANDARD

ISO
13930

First edition
1998-08-01

**Iron ores — Dynamic test for
low-temperature reduction-disintegration**

*Minerais de fer — Essai dynamique de désagrégation par réduction
à basse température*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13930:2000](https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000)

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>



Reference number
ISO 13930:1998(E)

ISO 13930:1998(E)

Content

1 Scope	1
2 Normative references	1
3 Definitions and abbreviations	1
4 Principle	2
5 Apparatus	2
6 Test conditions	3
7 Sampling and sample preparation	3
8 Procedure	4
9 Expression of results	5
10 Test report	5
11 Verification	6
Annex A (normative) Repeatability and number of tests	9
Annex B (informative) Bibliography	10

iTech STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 13930:2000](https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25e7-4ef1-b44e-78d81838b6df/sist-iso-13930-2000)

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25e7-4ef1-b44e-78d81838b6df/sist-iso-13930-2000>

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 13930 was prepared by Technical Committee ISO/TC 102, *Iron ores*, Subcommittee SC 3, *Physical testing*.

Annex A forms an integral part of this International Standard. Annex B is for information only.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 13930:2000](https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000)

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>

Introduction

This International Standard describes a test method for evaluating the disintegration behaviour of iron ores reduced in a rotating tube under specific conditions. The proportions of coarse fines, generated fines and dust remaining are a measure of the degree of reduction-disintegration. The specific features of this test are:

- a) the placing of a test portion of a specified size in a rotating tube;
- b) isothermal reduction at a temperature of 500 °C;
- c) measurement of the disintegration of the test portion by sieving after the reduction.

The method provides an indication of the physical stability of blast furnace burden materials under conditions resembling those at the beginning of reduction under a weakly reducing atmosphere.

The results of this test should be considered in conjunction with the results of other reduction tests, particularly those conducted at high temperatures.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 13930:2000](https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000)

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>

Iron ores — Dynamic test for low-temperature reduction-disintegration

WARNING — This standard may involve hazardous materials, operations or equipment. It does not purport to address all the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of any regulatory limitations prior to use.

1 Scope

This International Standard specifies a method for testing the disintegration of iron ores during reduction in a rotating tube at a temperature of 500 °C.

The method is applicable to lump ores and pellets as blast furnace burden materials.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 3082:1998, *Iron ores — Sampling and sample preparation procedures*.

ISO 3310-1:—¹⁾, *Test sieves — Requirements and tests — Part 1: Metal wire cloth sieves*.

ISO 10836:1994, *Iron ores — Method of sampling and sample preparation for physical testing*.

ISO 11323:1996, *Iron ores — Vocabulary*.

3 Definitions and abbreviations

3.1 Definitions

For the purposes of this International Standard the definitions given in ISO 11323 and the following apply:

3.1.1

low-temperature disintegration indices

Relative indications of the size degradation of pellets and lump ores under conditions prevailing in the upper part of a blast furnace shaft and obtained by a reduction test performed in a rotating tube. The indices are expressed as the percentages represented by the +6,3 mm sieve fraction, the –3,15 mm sieve fraction and the –0,5 mm sieve fraction, respectively.

1) To be published. (Revision of ISO 3310-1:1990)

3.2 Abbreviations

For the purposes of this International Standard, the following abbreviations apply:

LTD _{+6,3}	the disintegration index expressed in terms of the mass % of the +6,3 mm sieve fraction (the so-called disintegration strength)
LTD _{-3,15}	the disintegration index expressed in terms of the mass % of the -3,15 mm sieve fraction (the so-called disintegration index)
LTD _{-0,5}	the disintegration index expressed in terms of the mass % of the -0,5 mm sieve fraction (the so-called disintegration abrasion)

4 Principle

A test portion with a specified size range is reduced in a rotating tube at a temperature of 500 °C using reducing gas consisting of carbon monoxide (CO), carbon dioxide (CO₂), hydrogen (H₂) and nitrogen (N₂).

After 60 min reduction time, the test portion is cooled to a temperature below 100 °C and sieved with test sieves having square mesh apertures of 6,3 mm, 3,15 mm and 0,5 mm.

The low-temperature disintegration (LTD) values are calculated as a quantitative measure of the degree of disintegration of an iron ore that has been reduced while tumbling: the percentage masses of material greater than 6,3 mm, less than 3,15 mm and less than 0,5 mm, respectively, are related to the total mass of the test portion after reduction.

iteh STANDARD PREVIEW
(standards.iteh.ai)

5 Apparatus

SIST ISO 13930:2000

Figure 1 shows a schematic example of the low-temperature disintegration test apparatus.

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>

Figure 2 shows an example of an installation which could be used to measure the temperature and the temperature distribution within the gas stream and the test portion in the reduction tube.

The test apparatus shall consist of the following main components:

5.1 Gas supply system, capable of supplying the gases and regulating the gas flow rates (flow meters indicated by 1 in figure 1).

5.2 Reduction tube (6 in figure 1), made of non-scaling, heat-resisting metal to withstand a temperature higher than 500 °C. The inside diameter of the reduction tube shall be 150 mm and its inside length 540 mm. Four equally spaced lifters 540 mm long, 20 mm wide and 4 mm thick shall be mounted longitudinally inside the tube.

5.3 Thermocouples, for measuring the furnace temperature (4 in figure 1) and the temperature within the reduction tube (2 in figure 1).

5.4 Furnace (7 in figure 1), having a heating capacity sufficient to reach the test temperature within 45 min and to maintain the entire test portion at 500 °C ± 5 °C.

5.5 Dust collector (11 in figure 1), to trap any fine particles carried out of the tube in the gas stream during the test.

5.6 Test sieves, having square mesh apertures of the following nominal sizes in accordance with ISO 3310-1:

16,0 mm; 12,5 mm; 11,2 mm; 10,0 mm; 6,3 mm; 3,15 mm and 0,5 mm.

5.7 Weighing device, capable of weighing the load to an accuracy of 0,1 g.

6 Test conditions

Gas volumes and flow rates used in this International Standard are as measured at a temperature of 0 °C and at atmospheric pressure (101,325 kPa)²⁾.

6.1 Composition of reducing gas

The reducing gas shall consist of:

CO	20 % ± 0,5 % (V/V)
CO ₂	20 % ± 0,5 % (V/V)
H ₂	2 % ± 0,2 % (V/V)
N ₂	58 % ± 1,0 % (V/V)

Impurities in the reducing gas shall not exceed:

O ₂	0,1 % (V/V)
H ₂ O	0,2 % (V/V)

6.2 Flow rate of reducing gas

The reducing-gas flow rate shall, during the test period, be maintained at 20 l/min ± 1 l/min.

6.3 Temperature of test

By appropriate design of the test rig, the reducing gas shall be preheated before entering the reduction tube to maintain the temperature of the test portion at 500 °C ± 5 °C during the entire test period.

<https://standards.iteh.ai/catalog/standards/sist/7d9b5d67-25c7-4cfl-b44c-78d81838b6df/sist-iso-13930-2000>

7 Sampling and sample preparation

7.1 Sampling

The sample and test sample shall be taken in accordance with ISO 3082 and ISO 10836.

7.2 Test sample preparation

Oven-dry the test samples at 105 °C ± 5 °C for 2 h and cool to room temperature.

The total mass of the test sample shall be approximately 2 kg on a dry basis, being prepared as follows:

- a) Pellets, size 10,0 mm to 12,5 mm

The test sample in the size range of 10,0 mm to 12,5 mm shall be obtained by sieving and, after sieving, only pellets taken at random, e.g. by riffing, shall be used for the test.

- b) Pellets, size 12,5 mm to 16,0 mm

The test sample in the size range of 12,5 mm to 16,0 mm shall be obtained by sieving and, after sieving, only pellets taken at random, e.g. by riffing, shall be used for the test.

2) 1 mmHg = 0,133 3 kPa; 1 atm = 0,101 325 MPa