

# INTERNATIONAL STANDARD



GROUP SAFETY PUBLICATION

**Tests on electric and optical fibre cables under fire conditions –  
Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or  
cables – Category A**

Document Preview

[IEC 60332-3-22:2018](#)

<https://standards.iteh.ai/catalog/standards/iec/7e81787f-57d3-45e9-8fbc-50727b12d5a3/iec-60332-3-22-2018>





**THIS PUBLICATION IS COPYRIGHT PROTECTED**  
**Copyright © 2018 IEC, Geneva, Switzerland**

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either IEC or IEC's member National Committee in the country of the requester. If you have any questions about IEC copyright or have an enquiry about obtaining additional rights to this publication, please contact the address below or your local IEC member National Committee for further information.

IEC Central Office  
3, rue de Varembe  
CH-1211 Geneva 20  
Switzerland

Tel.: +41 22 919 02 11  
[info@iec.ch](mailto:info@iec.ch)  
[www.iec.ch](http://www.iec.ch)

**About the IEC**

The International Electrotechnical Commission (IEC) is the leading global organization that prepares and publishes International Standards for all electrical, electronic and related technologies.

**About IEC publications**

The technical content of IEC publications is kept under constant review by the IEC. Please make sure that you have the latest edition, a corrigenda or an amendment might have been published.

**IEC Catalogue - [webstore.iec.ch/catalogue](http://webstore.iec.ch/catalogue)**

The stand-alone application for consulting the entire bibliographical information on IEC International Standards, Technical Specifications, Technical Reports and other documents. Available for PC, Mac OS, Android Tablets and iPad.

**IEC publications search - [webstore.iec.ch/advsearchform](http://webstore.iec.ch/advsearchform)**

The advanced search enables to find IEC publications by a variety of criteria (reference number, text, technical committee,...). It also gives information on projects, replaced and withdrawn publications.

**IEC Just Published - [webstore.iec.ch/justpublished](http://webstore.iec.ch/justpublished)**

Stay up to date on all new IEC publications. Just Published details all new publications released. Available online and also once a month by email.

**Electropedia - [www.electropedia.org](http://www.electropedia.org)**

The world's leading online dictionary of electronic and electrical terms containing 21 000 terms and definitions in English and French, with equivalent terms in 16 additional languages. Also known as the International Electrotechnical Vocabulary (IEV) online.

**IEC Glossary - [std.iec.ch/glossary](http://std.iec.ch/glossary)**

67 000 electrotechnical terminology entries in English and French extracted from the Terms and Definitions clause of IEC publications issued since 2002. Some entries have been collected from earlier publications of IEC TC 37, 77, 86 and CISPR.

**IEC Customer Service Centre - [webstore.iec.ch/csc](http://webstore.iec.ch/csc)**

If you wish to give us your feedback on this publication or need further assistance, please contact the Customer Service Centre: [sales@iec.ch](mailto:sales@iec.ch).

[IEC 60332-3-22:2018](https://standards.iteh.ai/catalog/standards/iec/7e81787f-57d3-45e9-8fbc-50727b12d5a3/iec-60332-3-22-2018)

<https://standards.iteh.ai/catalog/standards/iec/7e81787f-57d3-45e9-8fbc-50727b12d5a3/iec-60332-3-22-2018>



IEC 60332-3-22

Edition 2.0 2018-07  
REDLINE VERSION

# INTERNATIONAL STANDARD



GROUP SAFETY PUBLICATION

Tests on electric and optical fibre cables under fire conditions –  
Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or  
cables – Category A

Document Preview

[IEC 60332-3-22:2018](https://standards.iteh.ai/catalog/standards/iec/7e81787f-57d3-45e9-8fbc-50727b12d5a3/iec-60332-3-22-2018)

<https://standards.iteh.ai/catalog/standards/iec/7e81787f-57d3-45e9-8fbc-50727b12d5a3/iec-60332-3-22-2018>

INTERNATIONAL  
ELECTROTECHNICAL  
COMMISSION

ICS 13.220.40; 29.060.20

ISBN 978-2-8322-5889-7

**Warning! Make sure that you obtained this publication from an authorized distributor.**

## CONTENTS

FOREWORD.....	3
INTRODUCTION.....	5
1 Scope.....	6
2 Normative references.....	6
3 Terms and definitions .....	7
4 Test apparatus .....	7
4.1 General.....	7
4.2 Ignition source .....	7
5 Test procedure .....	7
5.1 Test sample .....	7
5.2 Determination of the number of test pieces .....	8
5.3 Mounting of the test sample.....	8
5.3.1 Cables having at least one conductor above 35 mm <sup>2</sup> .....	8
5.3.2 Cables having conductors 35 mm <sup>2</sup> and below and optical cables .....	9
5.4 Flame application time .....	10
6 Evaluation of test results.....	10
7 Performance requirements.....	10
8 Retest procedure .....	10
9 Test report.....	10
Annex A (normative) Guidance on cable selection for type approval testing.....	12
Annex B (informative) Recommended performance requirements.....	13
Bibliography .....	14
Figure 1 – Spaced cables mounted on the front side of the standard ladder .....	11
Figure 2 – Spaced cables mounted on the front side of the wide ladder.....	11
Figure 3 – Touching cables mounted on front side of the standard ladder (arrays of cables in contact) .....	11
Table A.1 – Summary of test conditions.....	12

IEC 60332-3-22:2018

<https://standards.iteh.ai/> <https://standards.iteh.ai/standards/iec-60332-3-22-2018>

## INTERNATIONAL ELECTROTECHNICAL COMMISSION

### TESTS ON ELECTRIC AND OPTICAL FIBRE CABLES UNDER FIRE CONDITIONS –

#### Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A

#### FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

**This redline version of the official IEC Standard allows the user to identify the changes made to the previous edition. A vertical bar appears in the margin wherever a change has been made. Additions are in green text, deletions are in strikethrough red text.**

International Standard IEC 60332-3-22 has been prepared by IEC technical committee 20: Electric cables.

This second edition cancels and replaces the first edition published in 2000 and Amendment 1:2008. This edition constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) adjustments have been made to the title, and elsewhere, to emphasise the standard is applicable to optical fibre cables as well as metallic conductor types;
- b) details of the way in which cables are mounted on the ladder have been better defined in order to improve repeatability and reproducibility.

It has the status of a group safety publication in accordance with IEC Guide 104.

The text of this International Standard is based on the following documents:

FDIS	Report on voting
20/1799/FDIS	20/1816/RVD

Full information on the voting for the approval of this International Standard can be found in the report on voting indicated in the above table.

This document has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts in the IEC 60332 series, published under the general title *Tests on electric and optical fibre cables under fire conditions*, can be found on the IEC website.

Future standards in this series will carry the new general title as cited above. Titles of existing standards in this series will be updated at the time of the next edition.

The committee has decided that the contents of this document will remain unchanged until the stability date indicated on the IEC website under "http://webstore.iec.ch" in the data related to the specific document. At this date, the document will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

**IMPORTANT – The “colour inside” logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this publication using a colour printer.**

## INTRODUCTION

IEC 60332-3-22 is part of a series of publications dealing with tests on electric and optical fibre cables under fire conditions.

The IEC 60332-1 and IEC 60332-2 series specify methods of test for flame spread characteristics for a single vertical insulated wire or cable. It cannot be assumed that, because a cable or wire meets the requirements of the IEC 60332-1 and IEC 60332-2 series, a vertical bunch of similar cables or wires will behave in a similar manner. This is because flame spread along a vertical bunch of cables depends on a number of features, such as

- a) the volume of combustible material exposed to the fire and to any flame which may be produced by the combustion of the cables;
- b) the geometrical configuration of the cables and their relationship to an enclosure;
- c) the temperature at which it is possible to ignite the gases emitted from the cables;
- d) the quantity of combustible gas released from the cables for a given temperature rise;
- e) the volume of air passing through the cable installation;
- f) the construction of the cable, for example armoured or unarmoured, multi- or single-core.

All of the foregoing assume that the cables are able to be ignited when involved in an external fire.

The IEC 60332-3 series gives details of a test where a number of cables are bunched together to form various test sample installations. For easier use and differentiation of the various test categories, the parts are designated as follows:

- Part 3-10: Apparatus
- Part 3-21: Category A F/R
- Part 3-22: Category A
- Part 3-23: Category B
- Part 3-24: Category C
- Part 3-25: Category D

Parts from 3-21 onwards define the various categories and the relevant procedures. The categories are distinguished by test duration, the volume of non-metallic material of the test sample and the method of mounting the sample for the test. In all categories, cables having at least one conductor of cross-sectional area greater than 35 mm<sup>2</sup> are tested in a spaced configuration, whereas cables of conductor cross-sectional area of 35 mm<sup>2</sup> or smaller and optical fibre cables are tested in a touching configuration.

The categories are not necessarily related to different safety levels in actual cable installations. The actual installed configuration of the cables may be a major determinant in the level of flame spread occurring in an actual fire.

The method of mounting described as category A F/R (Part 3-21) is intended for special cable designs used in particular installations.

Categories A, B, C and D (Part 3-22 to Part 3-25 respectively) are for general use where different non-metallic volumes are applicable.

~~Additional categories, especially to cover the use of small diameter communication cables in closely bunched configurations, will be further considered when more data are available.~~

## TESTS ON ELECTRIC AND OPTICAL FIBRE CABLES UNDER FIRE CONDITIONS –

### Part 3-22: Test for vertical flame spread of vertically-mounted bunched wires or cables – Category A

#### 1 Scope

~~The series of International Standards covered by Parts 3-10, 3-21, 3-22, 3-23, 3-24 and 3-25~~  
This part of IEC 60332 ~~specifies~~ covers category A for methods of test for the assessment of vertical flame spread of vertically mounted bunched wires or cables, electrical or optical, under defined conditions.

This document relates to cables installed on the test ladder to achieve a nominal total volume of non-metallic material of 7 l/m of test sample. The flame application time is 40 min. The method of mounting uses the front of the ladder, a standard or wide ladder being used for cables having a conductor cross-section greater than 35 mm<sup>2</sup> according to the number of test pieces required, and a standard ladder for conductor cross-sections 35 mm<sup>2</sup> and smaller. The category is intended for general use where high volumes of non-metallic material are required to be evaluated.

The test is intended for type approval testing. The requirements for the selection of cables for testing are given in Annex A. The flame spread is measured as the extent of damage of the cable sample. This procedure ~~may~~ can be used to demonstrate the cable's ability to limit flame spread.

A recommended performance requirement is given in Annex B.

NOTE For the purposes of this document the term "electric wire or cable" covers all insulated metallic conductor cables used for the conveyance of energy or signals.

#### 2 Normative references

The following documents are referred to in the text in such a way that some or all of their content constitutes requirements of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60332-3-10, *Tests on electric and optical fibre cables under fire conditions – Part 3-10: Test for vertical flame spread of vertically-mounted bunched wires or cables – Apparatus*

~~IEC 60695-4, Fire hazard testing – Part 4: Terminology concerning fire tests~~

~~IEC 60811-1-3, Insulating and sheathing materials of electric cables – Common test methods Part 1: General application – Section 3: Methods for determining the density – Water absorption tests – Shrinkage test~~

IEC 60811-606, *Electric and optical fibre cables – Test methods for non-metallic materials – Part 606: Physical tests – Methods for determining the density*

~~IEC Guide 104, The preparation of safety publications and the use of basic safety publications and group safety publications~~



### 3 Terms and definitions

For the purposes of this document, the following terms and definitions apply. ~~The definitions are taken from IEC 60695-4.~~

ISO and IEC maintain terminological databases for use in standardization at the following addresses:

- IEC Electropedia: available at <http://www.electropedia.org/>
- ISO Online browsing platform: available at <http://www.iso.org/obp>

#### 3.1 ignition source

source of energy that initiates combustion

[SOURCE: ISO 13943:2017, 3.219]

#### 3.2 char

carbonaceous residue resulting from pyrolysis or incomplete combustion

[SOURCE: ISO 13943:2017, 3.47]

#### 3.3 flame spread

propagation of a flame front

[SOURCE: ISO 13943:2017, 3.168]

### 4 Test apparatus

#### 4.1 General

The apparatus specified in IEC 60332-3-10 shall be used.

#### 4.2 Ignition source

The ignition source shall be one or two ribbon-type propane gas burners as specified in IEC 60332-3-10.

A single burner shall be used with the standard ladder and two burners with the wide ladder.

### 5 Test procedure

#### 5.1 Test sample

The test sample shall comprise a number of test pieces of cable from the same production length, each having a minimum length of 3,5 m.

The total number of test pieces in the test sample shall be that number required to provide a nominal total volume of non-metallic material of 7 l/m of test sample.

The test sample for type approval shall be ~~chosen within the limitations given~~ in accordance with Annex A.

The test pieces forming the test sample shall be conditioned at a temperature of  $(20 \pm 10) ^\circ\text{C}$  for at least 16 h before commencing the test. The test pieces shall be dry.

## 5.2 Determination of the number of test pieces

In order to calculate the appropriate number of test pieces, it is necessary to determine the volume per metre of non-metallic material of one test piece.

A length of cable which shall be not less than 0,3 m long is carefully cut to ensure that the surfaces are at right angles to the cable axis, thus enabling precise measurements of its length.

The density of each non-metallic component (including cellular material) shall be measured in an appropriate way, for example ~~clause 8 of IEC 60811-1-3~~ according to IEC 60811-606, in order to obtain values expressed to the second decimal place.

Each non-metallic material  $C_i$  shall be removed from the test piece and weighed. Any non-metallic material making up less than 5 % of the total non-metallic mass of the test piece shall be assumed to have a density of  $1,0 \text{ kg/dm}^3$ .

Where semi-conducting screens cannot be removed from the insulating material, the components may be considered as one for the purpose of measuring their mass and density.

The volume  $V_i$  (litres per metre of cable) of each non-metallic material  $C_i$  is calculated as follows:

$$V_i = \frac{M_i}{\rho_i \times l}$$

where

$M_i$  is the mass of the component  $C_i$  (kg);

$\rho_i$  is the density of the component  $C_i$  ( $\text{kg/dm}^3$ );

$l$  is the length of the test piece of cable (m).

The total volume,  $V$ , of the non-metallic materials contained in 1 m of cable is equal to the sum of the individual volumes  $V_1, V_2$ , etc.

The number of test pieces to be mounted is obtained by taking the closest integer (0,5 and above corresponding to 1) of ~~the number of test pieces to be mounted is obtained by dividing the ratio of the volume per metre specified in 5.1 and the total volume,  $V$ , of non-metallic material per metre of cable, subject to a minimum number of two test pieces.~~

## 5.3 Mounting of the test sample

### 5.3.1 Cables having at least one conductor above $35 \text{ mm}^2$

For cables having at least one conductor with a cross-section exceeding  $35 \text{ mm}^2$ , each test piece shall be attached individually to each rung of the ladder by means of metal wire (steel or copper). For cables up to and including 50 mm diameter, use wire between 0,5 mm and 1,0 mm in diameter. For cables above 50 mm diameter, use wire between 1,0 mm and ~~1,5~~ 2,5 mm in diameter.

Test pieces shall be attached to the front of the ladder in a single layer with a space between each test piece of 0,5 times the cable diameter but not exceeding 20 mm. The ladder may be either standard or wide depending on whichever is necessary to ensure that there shall be a minimum distance of 50 mm between the edge of the test sample and the inside of the ladder uprights. ~~Where it is not possible to ensure that there shall be a minimum distance of 50 mm~~

between the edge of the test sample and the inside of the standard ladder, the wide ladder shall be used.

The maximum width of the test sample for the standard ladder shall be 300 mm and for the wide ladder 600 mm (see Figures 1 and 2). When the wide ladder is used, there shall not be more cable than the number necessary to form a single layer of 600 mm width, allowing for a space between each cable of either half the cable diameter or 20 mm, whichever is the smaller.

When mounting the test pieces, the first test piece shall be positioned approximately in the centre of the ladder and further test pieces added on either side so that the whole array of test pieces is approximately centred on the ladder.

Mount all test pieces on the ladder with the bending (due to bending of the cable on the reel), if any, in the same direction, towards the back side of the test chamber as much as possible.

To achieve straight test pieces between the steel rungs below and above the burner position, it is permitted to fix the test pieces to an additional horizontal support 200 mm to 300 mm lower than the steel rung below the burner position.

NOTE The objective is to improve the repeatability and reproducibility of the test.

### 5.3.2 Cables having conductors 35 mm<sup>2</sup> and below and optical cables

For cables having all conductors with cross-sections of 35 mm<sup>2</sup> or smaller and optical cables, each test piece shall be attached, either individually or as part of an array, to each rung of the ladder by means of metal wire (steel or copper) between 0,5 mm and 1,0 mm in diameter.

Test pieces shall be attached to the front of the standard ladder in touching formation in one or more layers up to a maximum total width of 300 mm. There shall be a minimum distance of 50 mm between the edge of the test sample and the inside of the ladder uprights.

When mounting the test pieces, the first test piece or array of test pieces shall be positioned approximately in the centre of the ladder and further test pieces or arrays added on either side so that the test sample is approximately centred on the ladder.

Mount all test pieces on the ladder with the bending (due to bending of the cable on the reel), if any, in the same direction, towards the back side of the test chamber as much as possible.

To achieve straight test pieces between the steel rungs below and above the burner position, it is permitted to fix the test pieces to an additional horizontal support 200 mm to 300 mm lower than the steel rung below the burner position.

In order to ensure that the test pieces are straight on the ladder, the test pieces shall be maintained under tension manually while attaching the test pieces to the rung of the ladder by means of a metal wire.

NOTE The objective is to improve the repeatability and reproducibility of the test.

If a second (or more) layer of test pieces is required after the full width of the ladder has been utilized for the first (or following) layer, then the first test piece or array of test pieces in the second (or following) layer shall be positioned approximately in the centre of the ladder and further test pieces or arrays added on either side so that the second (or following) layer is approximately centred on the ladder.

If a large number of test pieces is required to make up a test sample, the test pieces may be attached to each rung of the ladder in flat arrays of cables of a maximum width of five test pieces using the specified metal wire. For consistency, it is recommended that adjacent

arrays of cables are secured together at every rung to ensure that they are in touching formation (see Figure 3).

#### 5.4 Flame application time

The test flame shall be applied for 40 min, after which it shall be extinguished. The air flow rate through the test chamber shall be maintained until cable burning or glowing has ceased, or until a maximum duration of 1 h, after which any remaining cable burning or glowing shall be extinguished.

### 6 Evaluation of test results

After all cable burning or glowing has ceased or been extinguished, the test sample shall be wiped clean.

All soot is to be ignored if, when wiped off, the original surface is undamaged. Softening or any deformation of the non-metallic material is also to be ignored. The flame spread shall be measured as the extent of the damage. It shall be measured in metres to two decimal places from the bottom edge of the burner to the onset of char. The onset of char is determined as follows:

- press against the cable surface with a sharp object, for example a knife blade. Where the surface changes from a resilient to a brittle (crumbling) surface, this indicates the onset of char.

### 7 Performance requirements

The performance requirements for a particular type or class of wire or cable should preferably be given in the individual cable standard. In the absence of any given requirement, the recommended performance requirements given in Annex B should be used.

### 8 Retest procedure

In case of a disputed failure, two further tests shall be undertaken as detailed in Clause 5. The test shall be deemed as satisfactory if both tests meet the stated requirement.

### 9 Test report

The test report shall include the following information:

- a) full description of the cable tested;
- b) manufacturer of the cable tested;
- c) the part of the standard against which the test was carried out;
- d) the number of test pieces;
- e) the total volume of non-metallic material, per metre of test sample, of the test pieces;
- f) the method of mounting (i.e. spaced or touching);
- g) the number of layers and number of test pieces in each layer;
- h) flame application time (i.e. 40 min);
- i) the number of burners (i.e. one or two);
- j) the extent of damage;
- k) the time to extinction of all burning or glowing.