



SLOVENSKI STANDARD

SIST EN 4287:2005

01-maj-2005

Aeronavtika - Aluminijeva zlitina AL-P7010 - Material za kovanje

Aerospace series - Aluminium alloy AL-P7010 - Forging stock

Luft- und Raumfahrt - Aluminiumlegierung AL-P7010 - Schmiedevormaterial

Série aérospatiale - Alliage d'aluminium AL-P7010 - Produits destinés a la forge

Ta slovenski standard je istoveten z: EN 4287:2005

[SIST EN 4287:2005](https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005)

<https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005>

ICS:

49.025.20 Aluminij Aluminium

SIST EN 4287:2005 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4287:2005

<https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005>

EUROPEAN STANDARD

EN 4287

NORME EUROPÉENNE

EUROPÄISCHE NORM

February 2005

ICS 49.025.20

English version

Aerospace series - Aluminium alloy AL-P7010 - Forging stock

Série aérospatiale - Alliage d'aluminium AL-P7010 -
Produits destinés à la forgeLuft- und Raumfahrt - Aluminiumlegierung AL-P7010 -
Schmiedevormaterial

This European Standard was approved by CEN on 10 September 2004.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 4287:2005
<https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
Foreword.....		3
0 Introduction		4
1 Scope		4
2 Normative references		4

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 4287:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005>

Foreword

This document (EN 4287:2005) has been prepared by the European Association of Aerospace Manufacturers - Standardization (AECMA-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2005, and conflicting national standards shall be withdrawn at the latest by August 2005.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 4287:2005](https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005)

<https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005>

EN 4287:2005 (E)

0 Introduction

This document is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This document has been prepared in accordance with EN 4500-2.

1 Scope

This document specifies the requirements relating to:

Aluminium alloy AL-P7010
Forging stock

for aerospace applications.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 4400-6, *Aerospace series — Aluminium and aluminium- and magnesium- alloys — Technical specification — Part 6: Aluminium alloy forging stock.*¹⁾

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use.*

EN 4500-2, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 2: Specific rules for aluminium, aluminium alloys and magnesium alloys.*¹⁾

1) Published as AECMA Prestandard at the date of publication of this standard

1	Material designation		Aluminium alloy AL-P7010-												
2	Chemical composition %	Element	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Zr	Ti	Others		Al
													Each	Total	
		min.	—	—	1,5	—	2,1	—	—	5,7	0,10	—	—	—	—
max.	0,12	0,15	2,0	0,10	2,6	0,05	0,05	6,7	0,16	0,06	0,05	0,15			
3	Method of melting		—												
4.1	Form		Ingot or billet				Rod, bar or section				Plate				
4.2	Method of production		Cast				Extruded				Hot rolled				
4.3	Limit dimension(s)	mm	a or $D \leq 1000$				a or $D \leq 400$				a ≤ 400				
5	Technical specification		EN 4400-6				EN 4400-6				EN 4400-6				

6.1	Delivery condition	03	F	F
	Heat treatment	—	—	—
6.2	Delivery condition code	U	U	U
7	Use condition	03	F	F
	Heat treatment	Delivery condition	Delivery condition	Delivery condition

Characteristics

8.1	Test sample(s)	See EN 4400-6		See EN 4400-6	See EN 4400-6
8.2	Test piece(s)	See EN 4400-6		See EN 4400-6	See EN 4400-6
8.3	Heat treatment	T74 (see line 29)		T74 (see line 29)	T74 (see line 29)
9	Dimensions concerned	mm	See EN 4400-6	See EN 4400-6	See EN 4400-6
10	Thickness of cladding on each face	%	—		—
11	Direction of test piece	L		L	L
12	Temperature	θ	°C	Ambient	Ambient
13	Proof stress	$R_{p0,2}$	MPa	$\geq 435^a$	$\geq 435^a$
14	Strength	R_m	MPa	$\geq 435^a$	$\geq 435^a$
15	Elongation	A	%	$\geq 9^a$	$\geq 9^a$
16	Reduction of area	Z	%	—	—
17	Hardness			—	—
18	Shear strength	R_c	MPa	—	—
19	Bending	k	—	—	—
20	Impact strength			—	—
21	Temperature	θ	°C	—	—
22	Time			—	—
23	Stress	σ_a	MPa	—	—
24	Elongation	a	%	—	—
25	Rupture stress	σ_R	MPa	—	—
26	Elongation at rupture	A	%	—	—
27	Notes (see line 98)			a	—

EN 4287:2005 (E)

29	Reference heat treatment	—	Forged test pieces (cast stock, extruded stock or plate) or delivery condition (extruded stock)
44	External defects	—	See EN 4400-6
61	Internal defects	—	See EN 4400-6
87	Back – end defect	—	See EN 4400-6
		3	Extruded forging stock
		7	See EN 4400-6
88	Peripheral coarse grain	—	See EN 4400-6
		3	Extruded forging stock
		7	Level A
<p>iTeh STANDARD PREVIEW (standards.iteh.ai)</p> <p><u>SIST EN 4287:2005</u> https://standards.iteh.ai/catalog/standards/sist/9464d72a-3f37-4e64-b198-b3002b514480/sist-en-4287-2005</p>			
95	Marking inspection	—	See EN 4400-6
96	Dimensional inspection	—	See EN 4400-6
98	Notes	—	^a The “capability clause” may apply
99	Typical use	—	