



**Designation: A 283/A 283M – 00**

## **Standard Specification for Low and Intermediate Tensile Strength Carbon Steel Plates<sup>1</sup>**

This standard is issued under the fixed designation A 283/A 283M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

*This standard has been approved for use by agencies of the Department of Defense.*

### **1. Scope**

1.1 This specification<sup>2</sup> covers four grades (A, B, C, and D) of carbon steel plates of structural quality for general application.

1.2 When the steel is to be welded, a welding procedure suitable for the grade of steel and intended use or service is to be utilized. See Appendix X3 of Specification A 6/A 6M for information on weldability.

1.3 The values stated in either inch-pound units or SI units are to be regarded separately as standard. Within the text, the SI units are shown in brackets. The values stated in each system are not exactly equivalents; therefore, each system is to be used independently of the other, without combining values in any way.

1.4 For plate produced from coil, the additional requirements, including additional testing requirements and the reporting of additional test results, of Specification A 6/A 6M apply.

1.5 This specification contains notes or footnotes, or both, that provide explanatory material. Such notes and footnotes, excluding those in tables and figures, do not contain any mandatory requirements.

### **2. Referenced Documents**

#### *2.1 ASTM Standards:*

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling<sup>3</sup>

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel, and Related Alloys, and is the direct responsibility of Subcommittee A01.02 on Structural Steel for Bridges, Buildings, Rolling Stock, and Ships.

Current edition approved March 10, 2000. Published May 2000. Originally published as A 283 – 46T. Last previous edition A 283/A 283M – 98.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-283/SA 283M in Section II of that Code.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.04.

### **3. General Requirements for Delivery**

3.1 Material furnished under this specification shall conform to the requirements of the current edition of Specification A 6/A 6M, for the ordered material, unless a conflict exists in which case this specification shall prevail.

3.1.1 Coiled product is excluded from qualification to this specification until it is decoiled, leveled and cut to length. Plates produced from coil means plates that have been cut to individual lengths from a coiled product and are furnished without heat treatment. The processor decoils, levels, cuts to length and marks the product. The processor is responsible for performing and certifying all tests, examinations, repairs, inspections or operations not intended to affect the properties of the material. For plate produced from coils, two test results shall be reported for each qualifying coil.

NOTE 1—Additional requirements regarding plate produced from coil are described in Specification A 6/A 6M.

### **4. Process**

4.1 The steel shall be made by one or more of the following processes: open-hearth, basic-oxygen, or electric-furnace.

### **5. Chemical Requirements**

5.1 The heat analysis shall conform to the requirements prescribed in Table 1.

5.2 The steel shall conform on product analysis to the requirements prescribed in Table 1, subject to the product analysis tolerances in Specification A 6/A 6M.

### **6. Tensile Requirements**

6.1 Material as represented by the test specimens shall conform to the requirements as to tensile properties prescribed in Table 2.