



SLOVENSKI STANDARD

SIST EN 60793-1-42:2014

01-januar-2014

Optična vlakna - 1-42. del: Metode merjenja in preskusni postopki - Kromatična disperzija

Optical fibres - Part 1-42: Measurement methods and test procedures - Chromatic dispersion

Lichtwellenleiter - Teil 1-42: Messmethoden und Prüfverfahren - Chromatische Dispersion

Fibres optiques - Partie 1-42: Méthodes de mesure de la dispersion chromatique

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 60793-1-42:2014](https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-106982a01240/sist-en-60793-1-42-2014)

Ta slovenski standard je istoveten z: **EN 60793-1-42:2013**

ICS:

33.180.10 (Optična) vlakna in kabli Fibres and cables

SIST EN 60793-1-42:2014

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 60793-1-42:2014](https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06982a01240/sist-en-60793-1-42-2014)

<https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06982a01240/sist-en-60793-1-42-2014>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 60793-1-42

April 2013

ICS 33.180.10

Supersedes EN 60793-1-42:2007

English version

**Optical fibres -
Part 1-42: Measurement methods and test procedures -
Chromatic dispersion
(IEC 60793-1-42:2013)**

Fibres optiques -
Partie 1-42: Méthodes de mesure
et procédures d'essai -
Dispersion chromatique
(CEI 60793-1-42:2013)

Lichtwellenleiter -
Teil 1-42: Messmethoden
und Prüfverfahren -
Chromatische Dispersion
(IEC 60793-1-42:2013)

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

This European Standard was approved by CENELEC on 2013-02-28. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of document 86A/1419/CDV, future edition 3 of IEC 60793-1-42, prepared by SC 86A "Fibres and cables" of IEC/TC 86 "Fibre optics" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 60793-1-42:2013.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2013-11-28
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2016-02-28

This document supersedes EN 60793-1-42:2007.

EN 60793-1-42:2013 includes the following significant technical changes with respect to EN 60793-1-42:2007:

- a) the inclusion of category B6 single-mode fibres;
- b) the deletion of test method D (interferometry).

This standard should be read in conjunction with EN 60793-1-1.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

[SIST EN 60793-1-42:2014](https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06921e0-240/sist-en-60793-1-42-2014)

[https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-](https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06921e0-240/sist-en-60793-1-42-2014)

[f06921e0-240/sist-en-60793-1-42-2014](https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06921e0-240/sist-en-60793-1-42-2014)

Endorsement notice

The text of the International Standard IEC 60793-1-42:2013 was approved by CENELEC as a European Standard without any modification.

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60793-1-1	2008	Optical fibres - Part 1-1: Measurement methods and test procedures - General and guidance	EN 60793-1-1	2008
IEC 60793-1-41	-	Optical fibres - Part 1-41: Measurement methods and test procedures - Bandwidth	EN 60793-1-41	-
IEC 60793-2	-	Optical fibres - Part 2: Product specifications - General	EN 60793-2	-

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 60793-1-42:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06982a01240/sist-en-60793-1-42-2014>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 60793-1-42:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06982a01240/sist-en-60793-1-42-2014>



IEC 60793-1-42

Edition 3.0 2013-01

INTERNATIONAL STANDARD

NORME INTERNATIONALE



Optical fibres – **iTeh STANDARD PREVIEW**
Part 1-42: Measurement methods and test procedures – Chromatic dispersion
(standards.iteh.ai)

Fibres optiques –
Partie 1-42: Méthodes de mesure et procédures d'essai – Dispersion
chromatique

SIST EN 60793-1-42:2014

f06982a01240/sist-en-60793-1-42-2014

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

U

ICS 33.180.10

ISBN 978-2-83220-576-1

Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.

CONTENTS

FOREWORD.....	4
1 Scope.....	6
2 Normative references	7
3 Overview of methods	7
3.1 Method A, phase shift.....	7
3.2 Method B, spectral group delay in the time domain.....	7
3.3 Method C, differential phase shift	7
4 Reference test methods.....	8
4.1 Category A1 and sub-category A4f, A4g and A4h multimode fibres	8
4.2 Class B single-mode fibres	8
5 Apparatus.....	8
5.1 General.....	8
5.2 Launch optics	8
5.3 High-order mode filter (single-mode)	8
5.4 Input positioning apparatus	8
5.5 Output positioning apparatus.....	8
5.6 Computation equipment.....	9
6 Sampling and specimens.....	9
6.1 Specimen length.....	9
6.2 Specimen end face.....	9
6.3 Reference fibre.....	9
7 Procedure.....	9
8 Calculations	9
8.1 General.....	9
8.2 Category A1 and sub-category A4f, A4g, A4h multimode fibres and category B1.1, B1.3 and sub-category B6_a1 and B6_a2 single-mode fibres	10
8.3 Category B1.2 single-mode fibres.....	10
8.4 Category B2 single-mode fibres.....	10
8.5 Category B4 and B5 single-mode fibres.....	11
9 Results	11
9.1 Report the following information with each measurement:	11
9.2 The following information shall be available upon request:	11
10 Specification information	11
Annex A (normative) Requirements specific to method A, phase-shift	12
Annex B (normative) Requirements specific to method B, spectral group delay in the time domain	17
Annex C (normative) Requirements specific to method C, differential phase-shift	21
Annex D (normative) Chromatic dispersion fitting.....	26
Bibliography.....	28
Figure A.1 – Chromatic dispersion measurement set, multiple laser system (typical)	13
Figure A.2 – Typical delay and dispersion curves.....	13
Figure A.3 – Chromatic dispersion measurement set, LED system (typical)	15
Figure B.1 – Block diagram, fibre Raman laser system	18
Figure B.2 – Block diagram, multiple laser diode system.....	18

Figure C.1 – Chromatic differential phase dispersion measurement set, multiple laser system	22
Figure C.2 – Chromatic differential phase dispersion measurement set, LED system	23
Figure C.3 – Chromatic dispersion measurement set, differential phase by dual wavelength method	23
Figure C.4 – Chromatic dispersion measurement set, differential phase by double demodulation	24
Table D.1 – Definition of fit types and fit coefficients; equations for group delay and dispersion coefficient	26
Table D.2 – Slope equations	26
Table D.3 – Zero-dispersion wavelength and slope equations	27

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 60793-1-42:2014](https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06982a01240/sist-en-60793-1-42-2014)

<https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-f06982a01240/sist-en-60793-1-42-2014>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

OPTICAL FIBRES –

**Part 1-42: Measurement methods and test procedures –
Chromatic dispersion**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as “IEC Publication(s)”). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
<https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-7122a120c01d/iec-60793-1-42-2014>
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 60793-1-42 has been prepared by subcommittee 86A: Fibres and cables, of IEC technical committee 86: Fibre optics.

This third edition cancels and replaces the second edition, published in 2007. It constitutes a technical revision.

This edition includes the following significant technical changes with respect to the previous edition:

- a) the inclusion of category B6 single-mode fibres;
- b) the deletion of test method D (interferometry).

This standard should be read in conjunction with IEC 60793-1-1.

The text of this standard is based on the following documents:

CDV	Report on voting
86A/1419/CDV	86A/1443/RVC

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all the parts in the IEC 60793 series, published under the general title *Optical fibres*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "http://webstore.iec.ch" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW

IMPORTANT – The 'colour inside logo on the cover page of this publication indicates that it contains colours which are considered to be useful for the correct understanding of its contents. Users should therefore print this document using a colour printer.

<https://standards.iteh.ai/catalog/standards/sist/6f6987c7-b412-4235-b325-106982a01240/sist-en-60793-1-42-2014>

(standards.iteh.ai)
SIST EN 60793-1-42:2014
106982a01240/sist-en-60793-1-42-2014

OPTICAL FIBRES –

Part 1-42: Measurement methods and test procedures – Chromatic dispersion

1 Scope

This part of IEC 60793 establishes uniform requirements for measuring the chromatic dispersion of optical fibre, thereby assisting in the inspection of fibres and cables for commercial purposes.

Chromatic dispersion varies with wavelength. Some methods and implementations measure the group delay as a function of wavelength and the chromatic dispersion and dispersion slope are deduced from the derivatives (with respect to wavelength) of this data. This differentiation is most often done after the data are fitted to a mathematical model. Other implementations can allow direct measurement (of the chromatic dispersion) at each of the required wavelengths.

For some (sub-) categories of fibre, the chromatic dispersion attributes are specified with the parameters of a specific model. In these cases, the relevant recommendation or standard defines the model appropriate for the definition of the specified parameters. For other fibre (sub-) categories, the dispersion is specified to be within a given range for one or more specified wavelength intervals. In the latter case, either direct measurements may be made at the wavelength extremes or some fitting model may be used to either allow group delay measurement methods or implementations, or to allow storage of a reduced set of parameters that may be used to calculate the interpolated dispersion for particular wavelengths which may not have actual direct measurement values.

Annex D gives a general description of chromatic dispersion fitting and outlines a number of fitting equations suitable for use with any of the measurement methods or fibre categories.

This standard gives three methods for measuring chromatic dispersion:

- method A: phase shift;
- method B: spectral group delay in the time domain;
- method C: differential phase shift.

Methods A, B, and C apply to the measurement of chromatic dispersion of the following fibres from IEC 60793-2 over a specified wavelength range:

- category A1 graded-index multimode fibres;
- sub-category A4f, A4g and A4h multimode fibres;
- category B1, B2, B4, B5 and sub-categories B6_a1 and B6_a2 single-mode fibres.

The methods can be applied to laboratory, factory and field measurements of chromatic dispersion, and the wavelength range of the measurements can be tailored as required. Measurements are made at temperature as stated in Table 1 of IEC 60793-1-1:2008, Standard range of atmospheric conditions.

The methods are suitable for fibre or cable lengths greater than 1 km. They may also be applied to shorter lengths, but accuracy and repeatability may be compromised.

Information common to all methods is contained in Clauses 1 to 8, and information pertaining to each individual method appears in Annexes A, B and C, respectively.