

Designation: F 626 - 96a (Reapproved 2003)

# Standard Specification for Fence Fittings<sup>1</sup>

This standard is issued under the fixed designation F 626; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon  $(\epsilon)$  indicates an editorial change since the last revision or reapproval.

#### 1. Scope

- 1.1 This specification covers the materials, coating requirements, and inspection of fence accessories for chain-link fence for the following:
  - 1.1.1 Post and line caps,
  - 1.1.2 Rail and brace ends,
  - 1.1.3 Top rail sleeves,
  - 1.1.4 Tie wires, clips, and fasteners,
  - 1.1.5 Tension and brace bands,
  - 1.1.6 Tension bars,
  - 1.1.7 Truss rod assembly,
  - 1.1.8 Barbed wire arms,
  - 1.1.9 Color coating of fittings, and
  - 1.1.10 Fitting size terminology.
- 1.2 The values stated in inch-pound units are to be regarded as the standard. The SI values given in parentheses are for information only.

#### 2. Referenced Documents

- 2.1 ASTM Standards:
- A 641 Specification for Zinc-Coated (Galvanized) Carbon Steel Wire<sup>2</sup>
- A 641M Specification for Zinc-Coated (Galvanized) Carbon Steel Wire (Metric)<sup>2</sup>
- A 809 Specification for Aluminum-Coated (Aluminized) Carbon Steel Wire<sup>2</sup>
- A 817 Specification for Metallic-Coated Steel Wire for Chain Link Fence Fabric<sup>2</sup>
- B 26/B 26M Specification for Aluminum-Alloy Sand Castings<sup>3</sup>
- B 85 Specification for Aluminum-Alloy Die Castings<sup>3</sup>
- B 108 Specification for Aluminum-Alloy Permanent Mold Castings<sup>3</sup>
- B 117 Practice for Operating Salt Spray (Fog) Testing Apparatus<sup>4</sup>
- $^{1}$  This specification is under the jurisdiction of ASTM Committee F14 on Fences and is the direct responsibility of Subcommittee F14.40 on Chain Link Fence and Wire Accessories.
- Current edition approved January 10, 2003. Published March 2003. Originally approved in 1979. Last previous edition approved in 1996 as F 626 96a.
  - <sup>2</sup> Annual Book of ASTM Standards, Vol 01.06.
  - <sup>3</sup> Annual Book of ASTM Standards, Vol 02.02.
  - <sup>4</sup> Annual Book of ASTM Standards, Vol 03.02.

- B 209 Specification for Aluminum and Aluminum-Alloy Sheet and Plate<sup>3</sup>
- B 209M Specification for Aluminum and Aluminum-Alloy Sheet and Plate (Metric)<sup>3</sup>
- B 211 Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire<sup>3</sup>
- B 211M Specification for Aluminum and Aluminum-Alloy Bar, Rod, and Wire (Metric)<sup>3</sup>
- B 221 Specification for Aluminum-Alloy Extruded Bars, Rods, Wire, Shapes, and Tubes<sup>3</sup>
- B 221M Specification for Aluminum-Alloy Extruded Bars, Rods, Wire, Shapes, and Tubes (Metric)<sup>3</sup>
- B 429 Specification for Aluminum-Alloy Extruded Structural Pipe and Tube<sup>3</sup>
- B 800 Specification for 8000 Series Aluminum Alloy Wire for Electrical Purposes: Annealed and Intermediate Tempers
- F 552 Terminology Relating to Chain Link Fencing<sup>2</sup>
- F 668 Specification for Poly(Vinyl Chloride) (PVC)-Coated Steel Chain-Link Fence Fabric<sup>2</sup>
- F 934 Specification for Standard Colors for Polymer Coated Chain Link Fence Materials<sup>2</sup>
- 2.2 U.S. Government Standard:
- MIL-R-60346-C Roving, Glass, Fibrous (For Prepreg Tape and Roving, Filament Winding, and Pultrusion Applications)<sup>5</sup>

### 3. Post and Line Caps

- 3.1 Post and line caps shall be fabricated from pressed steel or cast iron and hot-dip galvanized with a minimum of 1.2 oz/ft [366 g/m²] of zinc coating of surface area, or from aluminum alloy 360.0 conforming to die cast Specification B 85, or sand cast or permanent mold alloy 356.0 or 713.0 conforming to Specification B 26/B 26M or B 108.
- 3.2 Post and line caps shall be designed to fit snugly over posts and exclude moisture from inside when tubular posts are used.

<sup>&</sup>lt;sup>5</sup> Available from Standardization Documents Order Desk, Bldg. 4 Section D, 700 Robbins Ave., Philadelphia, PA 19111–5094, Attn: NPODS.

#### 4. Rail and Brace Ends

- 4.1 Rail and brace ends, when required, shall be fabricated from pressed steel or cast iron, and hot-dip galvanized with a minimum of 1.2 oz/ft<sup>2</sup> [366 g/m<sup>2</sup>] of zinc coating of surface area, or from aluminum alloy 360.0 (see Specification B 85), or alloy 356.0 or 713.0 (see Specification B 26/B 26M or Specification B 108).
- 4.2 Rail and brace ends, or other approved means of connection, shall be provided when top rail or brace are required.

## 5. Top Rail Sleeves

- 5.1 Top rail sleeves shall be fabricated from pressed steel or round steel tubing and hot-dip galvanized with a minimum of 1.2 oz/ft<sup>2</sup> [366 g/m<sup>2</sup>] of zinc coating of surface area, or from aluminum alloy 6063-T6 (see Specification B 221, B 221M or Specification B 429).
- 5.2 Rail sleeve material shall be a minimum of 0.051 in. [1.3 mm] in thickness if steel, or a minimum of 0.062 in. [1.8 mm] in thickness if aluminum alloy, and a minimum of 6 in. [152.4 mm] in length.
- 5.3 The rail sleeve must be fabricated to prevent movement along the rail.

### 6. Tie Wires and Clips

- 6.1 Tie wires or clips, or both, for attaching chain-link fabric to round tubular or rectangular roll-formed horizontal rails and intermediate posts shall be one of the following systems, as selected by the purchaser:
- 6.1.1 Standard Round Wire Ties with either a preformed hook or pigtail at one end, designed to engage one picket of the chain-link fabric at the preformed end, wrap around the rail or post a minimum of 180°, and wrap around one picket of the chain link fabric at least one full turn at the other end in a manner that will draw up tightly around the rail or post. Standard round wire ties shall be of one of the following materials, as selected by the purchaser:
- 6.1.1.1 Twelve-gage (0.106  $\pm$  0.004-in. [2.69  $\pm$  0.10-mm]) steel with a tensile strength range from 55 to 65 ksi and with one of the following coatings, as selected by the purchaser:
- (1) A minimum of 0.80 oz/ft<sup>2</sup> [230 g/m<sup>2</sup>] of zinc in accordance with Specification A 641 (A 641M), Class 3 or A coating.
- (2) A minimum of 0.35 oz/ft<sup>2</sup> [107 g/m<sup>2</sup>] of aluminum in accordance with Specification A 809.
- 6.1.1.2 Nine-gage (0.148  $\pm$  0.005-in. [3.76  $\pm$  0.10-mm]) steel with a tensile strength range from 55 to 65 ksi and with one of the following coatings, as selected by the purchaser:
- (1) A minimum of 0.90 oz/ft<sup>2</sup> [270 g/m<sup>2</sup>] of zinc in accordance with Specification A 641 (A 641M), Class 3 or A coating.
- (2) A minimum of 0.40 oz/ft<sup>2</sup> [122 g/m<sup>2</sup>] of aluminum in accordance with Specification A 809.

Note 1—Heavier zinc coatings than those listed in 6.1.1.1 (I) and 6.1.1.2 (I) may be specified if desired, to match the minimum zinc coating specified for the fence fabric.

- 6.1.1.3 Nine-gage (0.148  $\pm$  0.005-in. [3.76  $\pm$  0.125-mm]) or (6-gage 0.192  $\pm$  0.005-in. [4.88  $\pm$  0.125-mm]) aluminum Alloy 1350-H19 or approved equal.
- 6.1.2 *High-Security Round Wire Ties* shall be one of the following, as selected by the purchaser:
- 6.1.2.1 Power-Fastened Round Wire Ties, preformed to the radius of the rail or post and configurated to wrap a full 360° around the rail or post and minimum of one complete diamond of the chain-link fabric. The two ends of the tie shall be preformed in such a manner that they can be twisted together in a close helix of  $1\frac{1}{2}$  machine turns, which is equivalent to 3 full twists, thereby drawing up tightly around the rail or post and the chain-link fabric. Power-fastened round wire ties shall be of either 6-gage (0.192  $\pm$  0.005-in. [4.88  $\pm$  0.125-mm]) or 9-gage (0.148  $\pm$  0.005-in. [3.76  $\pm$  0.125-mm]) steel as selected by the purchaser, with a tensile strength range from 65 to 75 ksi, and with one of the following coatings, as selected by the purchaser:
- (1) A minimum of 2.00 oz/ft<sup>2</sup> [600 g/m<sup>2</sup>] of zinc for 6-gage or 1.80 oz/ft<sup>2</sup> [540 g/m<sup>2</sup>] of zinc for 9-gage in accordance with Specification A 641 (A 641M), Class B coating.
- (2) A minimum of 0.40 oz/ft<sup>2</sup> [122 g/m<sup>2</sup>] of aluminum for 6-gage or 9-gage in accordance with Specification A 809.
- 6.1.2.2 Manually Fastened Round Wire Ties, of sufficient length to weave through the fence fabric, wrap around the post or rail a full  $360^\circ$  and be twisted securely with three full twists. At the contractor's option, these ties may be power twisted. After twisting, the protruding wire ends shall be cut off to prevent untwisting by hand. Manually fastened round wire ties shall be of either 6-gage  $(0.192 \pm 0.005\text{-in.} [4.88 \pm 0.125 \text{ mm}])$  or 9-gage  $(0.148 \pm 0.005\text{-in.} [3.76 \pm 0.125\text{-mm}])$  steel as selected by the purchaser, with a tensile strength range from 55 to 65 ksi, and with one of the following coatings, as selected by the purchaser:
- (1) A minimum of 1.2 oz/ft<sup>2</sup> [366 g/m<sup>2</sup>] of zinc in accordance with Specification A 817, Type 2, Class 1.
- (2) A minimum of 0.40 oz/ft<sup>2</sup> [122 g/m<sup>2</sup>] of aluminum in accordance with Specification A 809.
- 6.1.3 Interlocking Flat Wire Ties, preformed to the radius of the rail or post and configurated to wrap a full  $360^{\circ}$  around the rail or post and one picket of the chain-link fabric. The ends of the tie shall be preformed in such a manner that they will interlock and flatten down into a double closed loop against the rail or post. Interlocking flat wire ties shall be fabricated from 0.0625 by 0.375-in. [1.59 by 9.53-mm] flat aluminum Alloy 5052-H32 wire with a tolerance of  $\pm 0.005$  in. [ $\pm 1.25$  mm].
- 6.1.4 *Power-Driven Fasteners*, consisting of a knurled pin of carbon steel, heat treated to a hardness of RC 52–56 and a minimum tensile strength of 240 000 psi [1655 MPa]. Finish shall be zinc electroplating of 0.0003-in. [0.0076-mm] minimum thickness, evaluated for corrosion resistance for 72 consecutive hours with no signs of rust or corrosion when tested in accordance with Practice B 117. Cap shall be Type 304 stainless steel <sup>3</sup>/<sub>32</sub> in. [2.38 mm] thick. For 9-gage or 11-gage fabric other than <sup>3</sup>/<sub>8</sub>-in. [9.53-mm] mesh, the pin shall be 1 in. [25.4 mm] long. For <sup>3</sup>/<sub>8</sub>-in. mesh and 6-gage fabric, the pin shall be 1½ in. [31.75 mm] long.