INTERNATIONAL STANDARD

ISO 14192

First edition 1998-04-15

Aerospace — Airframe spherical roller bearings, single-row, self-aligning, shielded, intermediate duty — Metric series

Aéronautique et espace — Roulements pour structures d'aéronefs: roulements, à rotule, sur une rangée de rouleaux, avec flasques de protection, série intermédiaire — Série métrique

(standards.iteh.ai)

ISO 14192:1998

https://standards.iteh.ai/catalog/standards/sist/4405a478-f39a-4175-bcd9-7375fcfdb84b/iso-14192-1998



ISO 14192:1998(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 14192 was prepared by Technical Committee ISO/TC 20, *Aircraft and space vehicles*, Subcommittee SC 15, *Airframe bearings*.

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14192:1998 https://standards.iteh.ai/catalog/standards/sist/4405a478-f39a-4175-bcd9-7375fcfdb84b/iso-14192-1998

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Aerospace — Airframe spherical roller bearings, single-row, self-aligning, shielded, intermediate duty — Metric series

1 Scope

This International Standard specifies the characteristics, boundary dimensions, tolerances, internal clearances and permissible loads of metric series single-row, self-aligning, shielded, intermediate duty spherical roller bearings used in airframe applications. These bearings are designed to withstand only slow rotations and oscillations under load and are intended for use between fixed and moving parts of an aircraft structure and their control surfaces.

The airframe roller bearings covered by this International Standard are designed to operate in the temperature range of -54 °C to +150 °C.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards SO 14192:1998

https://standards.iteh.ai/catalog/standards/sist/4405a478-f39a-4175-bcd9-

ISO 15:1998, Rolling bearings — Radial bearings Boundary dimensions, general plan.

ISO 683-17:—1), Heat-treated steels, alloy steels and free-cutting steels — Part 17: Ball and roller bearing steels.

ISO 1132:1980, Rolling bearings — Tolerances — Definitions.

ISO 2082:1986, Metallic coatings — Electroplated coatings of cadmium on iron or steel.

ISO 4520:1981, Chromate conversion coatings on electroplated zinc and cadmium coatings.

ISO 5593:1997, Rolling bearings — Vocabulary.

ISO 8075:1985, Aerospace — Surface treatment of hardenable stainless steel parts.

ISO 14190:1998, Aerospace — Airframe rolling bearings: ball and spherical roller bearings — Technical specification.

AMS 2417E:1993, Plating, zinc-nickel alloy.²⁾

¹⁾ To be published. (Revision of ISO 683-17:1976)

²⁾ Available from: SAE International 400 Commonwealth Drive Warrendale, PA 15096-0001 USA

ISO 14192:1998(E) © ISO

3 Definitions

For the purposes of this International Standard, the definitions given in ISO 5593 apply.

4 Symbols

- **4.1** For the purposes of this International Standard, the symbols given in ISO 1132 apply. The symbols (except those for tolerances) shown in figure 1 and the values given in table 1 denote nominal dimensions unless otherwise specified.
- 4.2 Additional symbols for bearings covered by this International Standard are the following:
 - C_s permissible static radial load
 - $F_{\text{a max}}$ permissible static axial load

5 Required characteristics

5.1 Dimensions — Tolerances — Internal clearances — Loads

Values are given in table 1. Where plating is specified, tolerances are applicable after plating.

NOTE — With the exception of chamfer dimensions, boundary dimensions are in accordance with ISO 15.

Configuration is given in figure 1. The configuration for and installation process of shields are at the manufacturer's option.

(standards.iteh.ai)

5.2 Surface roughness

ISO 14192:1998

Inner and outer ring raceways and rolling elements shall have a surface roughness of $R_a = 0.2 \,\mu m$ max.

Bore, side faces and cylindrical outer surface shall have a surface roughness of $R_a = 0.8 \,\mu m$ max. before surface treatment.

6 Materials

6.1 Low alloy through hardening bearing steel (code letters F, D, M and Z)

Rings: bearing steel — ISO 683-17, type 1, surface hardness 59 HRC to 64 HRC (710 HV to 840 HV).

Rollers: bearing steel — ISO 683-17, type 1, heat treated to 59 HRC to 64 HRC (710 HV to 840 HV).

6.2 Corrosion-resistant stainless steel (code letters C and H)

Rings: bearing steel — ISO 683-17, type 21, hardness \geq 58 HRC (\geq 670 HV).

Rollers: bearing steel — ISO 683-17, type 21, hardness ≥ 58 HRC (≥ 670 HV).

6.3 General

Shields: corrosion-resistant steel.

7 Surface treatment

7.1 All elements manufactured from corrosion-resistant steel which are not cadmium plated (code letter C) shall be passivated in accordance with ISO 8075 or cleaned by mechanical method.

- **7.2** If made of corrosion-resistant steel, cadmium plating (code letter H) shall be subject to agreement between the customer and the manufacturer.
- **7.3** Where cadmium plating is specified (code letters D, M and H), it shall be in accordance with ISO 2082. The external surfaces of bearing rings, except the bore of the inner ring, shall be cadmium plated. Plating on the internal surfaces shall be at the manufacturers option, except the raceways shall not be plated. The thickness of the plating shall not be less than 7 μ m and not more than 15 μ m, except plating on the chamfers of the bore may vary from the specified thickness. The bearing shall be embrittlement-relieved within 4 h of plating by heat treatment at 140 °C \pm 10 °C for a minimum of 8 h followed by chromate treatment in accordance with ISO 4520 (code letters D and H only).
- **7.4** Where zinc-nickel plating is specified (code letter Z), it shall be in accordance with AMS 2417E, type 2. The surface coverage of the plating shall be as specified in 7.3. The thickness of the plating shall not be less than 7 μ m or more than 15 μ m.

8 Lubrication

The bearing shall be prelubricated with either grease A or B, as specified by the customer.

NOTE — Descriptions of grease A and grease B are contained in ISO 14190:1998, annex H.


(standards.iteh.ai)

9 Designation

ISO 14192:1998

Bearings in accordance by this international Standard shall be designated only as shown in the following example.

EXAMPLE



ISO 14192:1998(E) © ISO

where the following codes are applied:

— greases:

A = ester type grease;

B = synthetic hydrocarbon type grease;

— materials/surface treatments:

F = material: low alloy bearing steel;

surface treatment: none;

D = material: low alloy bearing steel;

surface treatment: cadmium plated with chromate treatment;

M = material: low alloy bearing steel;

surface treatment: cadmium plated without chromate treatment;

Z = material: low alloy bearing steel;

surface treatment: zinc-nickel plated;

C = material: corrosion-resistant stainless steel;

surface treatment: none;

H = material: corrosion-resistant stainless steel;

surface treatment: cadmium plated with chromate treatment;

– variations: iTeh STANDARD PREVIEW

1 = dimensional variation of diameter code 08 0210.ds.iteh.ai)


ISO 14192:1998

10 Identification marking//standards.iteh.ai/catalog/standards/sist/4405a478-f39a-4175-bcd9-7375fcfdb84b/iso-14192-1998

In addition to the manufacturer's name or trademark, each bearing shall be permanently and legibly marked, using the identity block as defined in clause 9. Marking position and method are at the manufacturer's option.

11 Technical specification

Airframe roller bearings supplied to this International Standard shall conform to the requirements of ISO 14190.



NOTE — The misalignment angle, α , is a minimum for manufacturers and a maximum for users.

iTeh STANDARD PREVIEW

(standards.iteh.ai)

Dimensions in millimetres, tolerances in micrometres

Diameter code	d	D	В	С	<i>d</i> ₁	F	G O 1419	Δ _{dmp}	$arDelta_{d}$ s	$\Delta_{D\! ext{mp}}$	$arDelta_{D}$ s	V _{Bs}	V _{Cs}	r	Mass
code			0 http20://	0 stan t20 °d	s.iteh.ai/	catalog/	standar	ds/sist/4	405a47	8-f39a-	4175-bcd9				
06	6	24	12	8	11,973	375 16 fdl	20,5 sc	-14192	-1998	0 - 9	+ 2 - 11				21
08	8	26	15	10	12,3	13	22		+ 2 - 10						37
08 1)	8	30		10	14,3	12	25								49
10	10	٥.	16	40	40.0	13	20	0 -8				20	20	0,3 to	70
10 ¹⁾	10	35	20	12	16,9	17	29			0	+ 3			0,8	72
12	12	40		13	19,9] ''	33,5			-11	- 14				108
15	15	47	47 24	14	23,9	20	40		+ 3 - 11						153
17	17	., 2-1	27	15	25,9	20	41								163

		clearances .m	Radial runout tolerances radial		Starting torque	Permissible static radial limit load	Permissible static axial limit load	
Diameter code	Radial	Axial	μ	m	max.	$C_{\rm s}$	F _{a max} kN	
	G_{r}	G _a max.	K _{ia} max.	K _{ea} max.	mN·m	kN		
06	2 to 6	180			6	15,9	4,8	
80				40	8	22,8	6,9	
08 1)	2 to 7				12	27,8	8,4	
10	2 10 7		25		16	32,9	10	
10 ¹⁾		210	25		10	02,3		
12					20	45	13,6	
15	3 to 9				25	54,2	16,4	
17					30	69,4	21	
1) Dimension	nal variant.							

ISO 14192:1998(E) © ISO

iTeh STANDARD PREVIEW (standards.iteh.ai)

ISO 14192:1998 https://standards.iteh.ai/catalog/standards/sist/4405a478-f39a-4175-bcd9-7375fcfdb84b/iso-14192-1998

ICS 49.035

Descriptors: aircraft industry, rolling bearings, airframe bearings, roller bearings, single-row bearings, spherical bearings, self-aligning bearings, specifications, materials specifications, dimensions, overall dimensions, dimensional tolerances, dimensional deviations, clearances, load capacity, surface treatment, lubrification, designation, marking, metric system.

Price based on 5 pages