



# SLOVENSKI STANDARD SIST EN ISO 13704:2009

01-april-2009

---

DYf c\_Ya ] bU]bXi glf]Uhf ]bXi glf]UnUdfYXYUj c`bUZY]b`nYa Y`g\_Y[ Ud`]bU!  
=fU i b`XYVY]bY[ fYbYWj ]j`fU]bYf]U`bUZY]fGC`%+\$(.8\$\$+L

Petroleum, petrochemical and natural gas industries - Calculation of heater-tube thickness in petroleum refineries (ISO 13704:2007)

Erdöl- und Erdgasindustrie - Berechnung der Wanddicke von Heizrohren in Erdölraffinerien (ISO 13704:2007)

Industries du pétrole, de la pétrochimie et du gaz naturel - Calcul de l'épaisseur des tubes de fours de raffineries de pétrole (ISO 13704:2007)

[https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)

[e1ba8804297f/sist-en-iso-13704-2009](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)

**Ta slovenski standard je istoveten z: EN ISO 13704:2007**

---

## **ICS:**

75.180.20      Predelovalna oprema      Processing equipment

**SIST EN ISO 13704:2009**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 13704:2009

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN ISO 13704**

November 2007

ICS 75.180.20

English Version

**Petroleum, petrochemical and natural gas industries -  
Calculation of heater-tube thickness in petroleum refineries (ISO  
13704:2007)**

Industries du pétrole, de la pétrochimie et du gaz naturel -  
Calcul de l'épaisseur des tubes de fours de raffineries de  
pétrole (ISO 13704:2007)

Erdöl- und Erdgasindustrie - Berechnung der Wanddicke  
von Heizrohren in Erdölraffinerien (ISO 13704:2007)

This European Standard was approved by CEN on 3 November 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/c-4615a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**Contents**

Page

Foreword.....3

**iTeh STANDARD PREVIEW  
(standards.iteh.ai)**

SIST EN ISO 13704:2009

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>

## Foreword

This document (EN ISO 13704:2007) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by May 2008, and conflicting national standards shall be withdrawn at the latest by May 2008.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

### Endorsement notice

The text of ISO 13704:2007 has been approved by CEN as a EN ISO 13704:2007 without any modification.

**(standards.iteh.ai)**

[SIST EN ISO 13704:2009](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 13704:2009

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>

# INTERNATIONAL STANDARD

**ISO  
13704**

Second edition  
2007-11-15

---

---

## **Petroleum, petrochemical and natural gas industries — Calculation of heater-tube thickness in petroleum refineries**

*Industries du pétrole, de la pétrochimie et du gaz naturel — Calcul de  
l'épaisseur des tubes de fours de raffineries de pétrole*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 13704:2009](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)

[https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-  
e1ba8804297f/sist-en-iso-13704-2009](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)



Reference number  
ISO 13704:2007(E)

© ISO 2007

**ISO 13704:2007(E)****PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 13704:2009](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland



## Contents

Page

Foreword .....	iv
<b>1 Scope .....</b>	<b>1</b>
<b>2 Terms and definitions .....</b>	<b>1</b>
<b>3 General design information .....</b>	<b>3</b>
3.1 Information required .....	3
3.2 Limitations for design procedures .....	4
<b>4 Design .....</b>	<b>4</b>
4.1 General .....	4
4.2 Equation for stress .....	7
4.3 Elastic design (lower temperatures) .....	7
4.4 Rupture design (higher temperatures) .....	8
4.5 Intermediate temperature range .....	8
4.6 Minimum allowable thickness .....	8
4.7 Minimum and average thicknesses .....	8
4.8 Equivalent tube metal temperature .....	9
4.9 Component fittings .....	13
<b>5 Allowable stresses .....</b>	<b>15</b>
5.1 General .....	15
5.2 Elastic allowable stress .....	16
5.3 Rupture allowable stress .....	16
5.4 Rupture exponent .....	16
5.5 Yield and tensile strengths .....	16
5.6 Larson-Miller parameter curves .....	16
5.7 Limiting design metal temperature .....	17
5.8 Allowable stress curves .....	17
<b>6 Sample calculations .....</b>	<b>18</b>
6.1 Elastic design .....	18
6.2 Thermal-stress check (for elastic range only) .....	19
6.3 Rupture design with constant temperature .....	23
6.4 Rupture design with linearly changing temperature .....	25
<b>Annex A (informative) Estimation of remaining tube life .....</b>	<b>28</b>
<b>Annex B (informative) Calculation of maximum radiant section tube skin temperature .....</b>	<b>33</b>
<b>Annex C (normative) Thermal-stress limitations (elastic range) .....</b>	<b>44</b>
<b>Annex D (informative) Calculation sheets .....</b>	<b>48</b>
<b>Annex E (normative) Stress curves (SI units) .....</b>	<b>50</b>
<b>Annex F (normative) Stress curves (USC units) .....</b>	<b>70</b>
<b>Annex G (normative) Derivation of corrosion fraction and temperature fraction .....</b>	<b>90</b>
<b>Annex H (informative) Data sources .....</b>	<b>98</b>
<b>Bibliography .....</b>	<b>103</b>

## ISO 13704:2007(E)

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 13704 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 6, *Processing equipment and systems*.

**iTeh STANDARD PREVIEW**

This second edition cancels and replaces the first edition (ISO 13704:2001), which has been technically revised.

[SIST EN ISO 13704:2009](https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009)

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-e1ba8804297f/sist-en-iso-13704-2009>

# Petroleum, petrochemical and natural gas industries — Calculation of heater-tube thickness in petroleum refineries

## 1 Scope

This International Standard specifies the requirements and gives recommendations for the procedures and design criteria used for calculating the required wall thickness of new tubes and associated component fittings for petroleum-refinery heaters. These procedures are appropriate for designing tubes for service in both corrosive and non-corrosive applications. These procedures have been developed specifically for the design of refinery and related process-fired heater tubes (direct-fired, heat-absorbing tubes within enclosures). These procedures are not intended to be used for the design of external piping.

This International Standard does not give recommendations for tube retirement thickness; Annex A describes a technique for estimating the life remaining for a heater tube.

## 2 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

### 2.1

#### actual inside diameter

 $D_i$ 

inside diameter of a new tube

NOTE The actual inside diameter is used to calculate the tube skin temperature in Annex B and the thermal stress in Annex C.

### 2.2

#### component fitting

fitting connected to the fired heater tubes

EXAMPLES Return bends, elbows, reducers.

NOTE 1 There is a distinction between standard component fittings and specially designed component fittings; see 4.9.

NOTE 2 Typical material specifications for standard component fittings are ASTM A 234, ASTM A 403 and ASTM B 366.

### 2.3

#### corrosion allowance

 $\delta_{CA}$ 

additional material thickness added to allow for material loss during the design life of the component

### 2.4

#### design life

 $t_{DL}$ 

operating time used as a basis for tube design

NOTE The design life is not necessarily the same as the retirement or replacement life.

**ISO 13704:2007(E)****2.5****design metal temperature** $T_d$ 

tube-metal or skin temperature used for design

NOTE This is determined by calculating the maximum tube metal temperature ( $T_{max}$  in Annex B) or the equivalent tube metal temperature ( $T_{eq}$  in 2.8) and adding an appropriate temperature allowance (see 2.16). A procedure for calculating the maximum tube metal temperature from the heat-flux density is included in Annex B. When the equivalent tube metal temperature is used, the maximum operating temperature can be greater than the design metal temperature. When the equivalent tube metal temperature is used to determine the design metal temperature, this design metal temperature is only applicable to the rupture design. It is necessary to develop a separate design metal temperature applicable to the elastic design. The design metal temperature applicable to the elastic design is the maximum calculated tube metal temperature among all operating cases plus the appropriate temperature allowance.

**2.6****elastic allowable stress** $\sigma_{el}$ 

allowable stress for the elastic range

See 5.2.

**2.7****elastic design pressure** $p_{el}$ 

maximum pressure that the heater coil can sustain for short periods of time

NOTE This pressure is usually related to relief-valve settings, pump shut-in pressures, etc.

**2.8****equivalent tube metal temperature** $T_{eq}$ 

calculated constant metal temperature that in a specified period of time produces the same creep damage as does a changing metal temperature

NOTE In 4.8 the equivalent tube metal temperature concept is described in more detail. It provides a procedure to calculate the equivalent tube metal temperature based on a linear change of tube metal temperature from start-of-run to end-of-run.

**2.9****inside diameter** $D_i^*$ 

inside diameter of a tube with the corrosion allowance removed; used in the design calculations

NOTE The inside diameter of an as-cast tube is the inside diameter of the tube with the porosity and corrosion allowances removed.

**2.10****minimum thickness** $\delta_{min}$ 

minimum required thickness of a new tube, taking into account all appropriate allowances

NOTE See Equation (5).

**2.11****outside diameter** $D_o$ 

outside diameter of a new tube

**2.12****rupture allowable stress** $\sigma_r$ 

allowable stress for the creep-rupture range

See 4.4.

**2.13****rupture design pressure** $p_r$ 

maximum operating pressure that the coil section can sustain during normal operation

**2.14****rupture exponent** $n$ 

parameter used for design in the creep-rupture range

NOTE See figures in Annexes E and F.

**2.15****stress thickness** $\delta_\sigma$ 

thickness, excluding all thickness allowances, calculated from an equation that uses an allowable stress

**2.16****temperature allowance** $T_A$ 

part of the design metal temperature that is included for process- or flue-gas mal-distribution, operating unknowns, and design inaccuracies

NOTE The temperature allowance is added to the calculated maximum tube metal temperature or to the equivalent tube metal temperature to obtain the design metal temperature (see 2.5).

**3 General design information****3.1 Information required**

The design parameters (design pressures, design fluid temperature, corrosion allowance and tube material) shall be defined. In addition, the following information shall be furnished:

- a) design life of the heater tube;
- b) whether the equivalent-temperature concept is to be applied and, if so, the operating conditions at the start and at the end of the run;
- c) temperature allowance (see ISO 13705), if any;
- d) corrosion fraction (if different from that shown in Figure 1);
- e) whether elastic-range thermal-stress limits are to be applied.

If any of items a) to e) are not furnished, use the following applicable parameters:

- design life equal to 100 000 h;
- design metal temperature based on the maximum metal temperature (the equivalent-temperature concept shall not apply);

**ISO 13704:2007(E)**

- temperature allowance equal to 15 °C (25 °F);
- corrosion fraction given in Figure 1;
- elastic-range thermal-stress limits.

**3.2 Limitations for design procedures**

**3.2.1** The allowable stresses are based on a consideration of yield strength and rupture strength only; plastic or creep strain has not been considered. Using these allowable stresses can result in small permanent strains in some applications; however, these small strains do not affect the safety or operability of heater tubes.

**3.2.2** No considerations are included for adverse environmental effects, such as graphitization, carburization or hydrogen attack. Limitations imposed by hydrogen attack can be developed from the Nelson curves in API 941 [1].

**3.2.3** These design procedures have been developed for seamless tubes. They are not applicable to tubes that have a longitudinal weld. ISO 13705 allows only seamless tubes.

**3.2.4** These design procedures have been developed for thin tubes (tubes with a thickness-to-outside-diameter ratio,  $\delta_{\min}/D_o$ , of less than 0,15). Additional considerations can apply to the design of thicker tubes.

**3.2.5** No considerations are included for the effects of cyclic pressure or cyclic thermal loading.

**3.2.6** Limits for thermal stresses are provided in Annex C. Limits for stresses developed by mass, supports, end connections and so forth are not discussed in this International Standard.

**3.2.7** Most of the Larson-Miller parameter referenced curves in 5.6 are not Larson-Miller curves in the traditional sense but are derived from the 100 000 h rupture strength as explained in Clause H.3. Consequently, the curves might not provide a reliable estimate of the rupture strength for a design life that is less than 20 000 h or more than 200 000 h.

**3.2.8** The procedures in this International Standard have been developed for systems in which the heater tubes are subject to an internal pressure that exceeds the external pressure. There are some cases in which a heater tube can be subject to a greater external pressure than the internal pressure. This can occur, for example, in vacuum heaters or on other types of heaters during shutdown or trip conditions, especially when a unit is cooling or draining, forming a vacuum inside the heater tubes. Conditions where external pressures exceed the internal pressures can govern heater-tube wall thickness. Determination of this (i.e. vacuum design) is not covered in this International Standard. In the absence of any local or national codes that can apply, it is recommended that a pressure vessel code, such as ASME VIII (Division 1, UG-28) or EN 13445, be used, as such codes also address external pressure designs.

**4 Design****4.1 General**

There is a fundamental difference between the behaviour of carbon steel in a hot-oil heater tube operating at 300 °C (575 °F) and that of chromium-molybdenum steel in a catalytic-reformer heater tube operating at 600 °C (1 110 °F). The steel operating at the higher temperature creeps, or deforms permanently, even at stress levels well below the yield strength. If the tube metal temperature is high enough for the effects of creep to be significant, the tube eventually fails due to creep rupture, although no corrosion or oxidation mechanism is active. For the steel operating at the lower temperature, the effects of creep are non-existent or negligible. Experience indicates that, in this case, the tube lasts indefinitely, unless a corrosion or an oxidation mechanism is active.

Since there is a fundamental difference between the behaviour of the materials at these two temperatures, there are two different design considerations for heater tubes: elastic design and creep-rupture design. Elastic design is design in the elastic range, at lower temperatures, in which allowable stresses are based on the yield strength (see 4.3). Creep-rupture design (which is referred to below as rupture design) is the design for the creep-rupture range, at higher temperatures, in which allowable stresses are based on the rupture strength (see 4.4).

The temperature that separates the elastic and creep-rupture ranges of a heater tube is not a single value; it is a range of temperatures that depends on the alloy. For carbon steel, the lower end of this temperature range is about 425 °C (800 °F); for type 347 stainless steel, the lower end of this temperature range is about 590 °C (1 100 °F). The considerations that govern the design range also include the elastic design pressure, the rupture design pressure, the design life and the corrosion allowance.

The rupture design pressure is never more than the elastic design pressure. The characteristic that differentiates these two pressures is the relative length of time over which they are sustained. The rupture design pressure is a long-term loading condition that remains relatively uniform over a period of years. The elastic design pressure is usually a short-term loading condition that typically lasts only hours or days. The rupture design pressure is used in the rupture design equation, since creep damage accumulates as a result of the action of the operating, or long-term, stress. The elastic design pressure is used in the elastic design equation to prevent excessive stresses in the tube during periods of operation at the maximum pressure.

The tube shall be designed to withstand the rupture design pressure for long periods of operation. If the normal operating pressure increases during an operating run, the highest pressure shall be taken as the rupture design pressure.

In the temperature range near or above the point where the elastic and rupture allowable stress curves cross, both elastic and rupture design equations are to be used. The larger value of  $\delta_{\min}$  should govern the design (see 4.5). A sample calculation that uses these methods is included in Clause 6. Calculation sheets (see Annex D) are available for summarizing the calculations of minimum thickness and equivalent tube metal temperature.

SIST EN ISO 13704:2009

The allowable minimum thickness of a new tube is given in Table 1.

<https://standards.iteh.ai/catalog/standards/sist/e4815a7f-36fc-4705-bd1a-c1ba88042971/sist-en-iso-13704-2009>

All of the design equations described in Clause 4 are summarized in Table 2.