



SLOVENSKI STANDARD
SIST EN 683-1:2007

01-marec-2007

BUXca Yý U
SIST EN 683-1:1998

5`i a]b]^[b`Ui a]b]Yj Y`n`j]bY!`<`UXbc`j U`Ub]`dc`]nXY_]`nU`hd`ctbY`]na Yb`Yj Ub]_Y
!`%`XY.`HY b] b]`dc[c`j`nU`dfYj nYa `]b`XcVUj c

Aluminium and aluminium alloys - Finstock - Part 1: Technical conditions for inspection and delivery

Aluminium und Aluminiumlegierungen - Vormaterial für Wärmeaustauscher (Finstock) - Teil 1: Technische Lieferbedingungen

Aluminium et alliages d'aluminium - Bandes pour échangeurs thermiques - Partie 1 : Conditions techniques de contrôle et de livraison

Ta slovenski standard je istoveten z: EN 683-1:2006

ICS:

77.150.10 Alumijski izdelki Aluminium products

SIST EN 683-1:2007 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 683-1:2007

<https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-e976adaa9f52/sist-en-683-1-2007>

English Version

Aluminium and aluminium alloys - Finstock - Part 1: Technical conditions for inspection and delivery

Aluminium et alliages d'aluminium - Bandes pour échangeurs thermiques - Partie 1 : Conditions techniques de contrôle et de livraison

Aluminium und Aluminiumlegierungen - Vormaterial für Wärmeaustauscher (Finstock) - Teil 1: Technische Lieferbedingungen

This European Standard was approved by CEN on 25 November 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 683-1:2007](https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-e976adaa9f52/sist-en-683-1-2007)

<https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-e976adaa9f52/sist-en-683-1-2007>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Ordering information	4
5 Requirements	5
5.1 Production and manufacturing processes	5
5.2 Quality control.....	5
5.3 Chemical composition	6
5.4 Mechanical properties.....	6
5.5 Freedom from defects	6
5.6 Tolerances on dimensions and form	6
5.7 Special properties.....	6
6 Test procedure	6
6.1 Sampling.....	6
6.2 Methods of testing.....	7
6.3 Retests	8
7 Inspection documents.....	8
8 Marking of products	8
9 Packaging	9
10 Complaints of non-conformity	9
Bibliography	10

iTech STANDARD PREVIEW
(standards.itech.ai)

[SIST EN 683-1:2007](#)

<https://standards.itech.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-e976adaa9f52/sist-en-683-1-2007>

Foreword

This document (EN 683-1:2006) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2007, and conflicting national standards shall be withdrawn at the latest by June 2007.

This document supersedes EN 683-1:1996.

Within its programme of work, Technical Committee CEN/TC 132 entrusted CEN/TC 132/WG 6 "Foil and finstock" to revise EN 683-1:1996.

The following modifications have been made:

- scope is changed into gauge ranges from 60 μm to 400 μm ;
- Clause 3 refers now to EN 12258-1;
- Clause 4: title is changed, and list is amended;
- Clause 5: subclause 5.2 is modified;
- Clause 6: subclauses 6.1.1 and 6.2.1 are modified;
- Clause 7: completely ammended;
- addition of Bibliography.

EN 683 comprises the following parts under the general title "*Aluminium and aluminium alloys — Finstock*":

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Tolerances on dimensions and form*

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN shall not be held responsible for identifying any or all such patent rights.

CEN/TC 132 affirms it is its policy that in the case when a patentee refuses to grant licences on standardised standard products under reasonable and not discriminatory conditions, then this product shall be removed from the corresponding standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

1 Scope

This document specifies the technical conditions for inspection and delivery of wrought aluminium and wrought aluminium alloy finstock.

The gauge range covered is 60 μm to 400 μm .

It does not apply to clad finstock.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 515, *Aluminium and aluminium alloys — Wrought products — Temper designations*

EN 573-3, *Aluminium and aluminium alloys — Chemical composition and form of wrought products — Part 3: Chemical composition*

EN 683-2, *Aluminium and aluminium alloys — Finstock — Part 2: Mechanical properties*

EN 683-3, *Aluminium and aluminium alloys — Finstock — Part 3: Tolerances on dimensions and form*

EN 12258-1:1998, *Aluminium and aluminium alloys — Terms and definitions — Part 1: General terms*

EN 14242, *Aluminium and aluminium alloys - Chemical analysis - Inductively coupled plasma optical emission spectral analysis*

[SIST EN 683-1:2007](https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-e076d8a9572/sist/en-683-1-2007)

[https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-](https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-e076d8a9572/sist/en-683-1-2007)

EN 14361, *Aluminium and aluminium alloys - Chemical analysis - Sampling from metal melts*

3 Terms and definitions

For the purposes of this document, the terms and definitions of EN 12258-1:1998 and the following applies.

3.1 finstock
flat, cold rolled product of rectangular cross section and thickness in the range 60 μm to 400 μm suitable for heat exchanger applications

4 Ordering information

The order shall specify the product required and shall contain the following information:

- a) type and form of product:
 - the designation of the aluminium or aluminium alloy;
 - the form of the product;
- b) temper designation of the material to be delivered as specified in EN 515;
- c) number of this European Standard (EN 683-1) or separate specification, if any;

- d) dimensions of the product:
- thickness;
 - width and type of specified tolerance on width as defined in EN 683-3 (symmetrical, only plus, only minus), or as agreed between supplier and purchaser;
 - internal and external diameter of the coil/reel;
 - core size and type;
- e) quantity (mass);
- f) any special requirements agreed between supplier and purchaser, e.g.:
- test certificates and inspection reports;
 - marking of the products, e.g. identification;
 - reference to drawings, e.g. for packaging, coil axis orientation, etc.;
 - whether surface degreasing is required.

Where special requirements are specified, the application shall be stated.

iTeh STANDARD PREVIEW (standards.iteh.ai)

5 Requirements

5.1 Production and manufacturing processes

Unless otherwise specified in the order, the production and manufacturing processes shall be left to the discretion of the supplier. Unless it is explicitly stated in the order, no obligation shall be placed on the supplier to use the same processes for subsequent and similar orders.

5.2 Quality control

The manufacturer shall establish and maintain a quality management system, which should be at least equivalent to EN ISO 9001.

The manufacturer shall establish and maintain inspection plans defining all inspections and tests to be performed on the product to fulfil the requirements of this standard and any other requirement agreed according to Clause 6 of the present standard, their frequency and the type of record to be established. The inspection plan shall specify for each inspection or test whether it is to be performed per cast, per heat treatment batch, per inspection lot as defined in EN 12258-1 or per any other lot of importance. The inspection plan shall conform as a minimum to the test procedures and test requirements stipulated in this standard. The inspection plan shall include additional schemes for appropriate process control. If required the inspection plan shall be submitted to the purchaser for approval before start of production.

The manufacturer shall be responsible for carrying out all inspections and tests required by this standard, prior to the shipment of the product. If the purchaser wishes to inspect the product at the manufacturer's site of production, he shall stipulate this at the time of placing the order.

The extent of inspections shall be in accordance with Clause 6 of the present standard. Unless explicitly stated quality controls and inspections shall be performed on inspection lots. Products included in one inspection lot shall be manufactured in the same production unit.

5.3 Chemical composition

The chemical composition shall be in conformity with the requirements specified in EN 573-3, unless otherwise agreed between supplier and purchaser.

5.4 Mechanical properties

The mechanical properties shall be in conformity with EN 683-2, unless otherwise agreed between supplier and purchaser.

5.5 Freedom from defects

The product shall be free from defects prejudicial to its suitable and proper use.

5.6 Tolerances on dimensions and form

The tolerances on dimensions and form shall be in conformity with EN 683-3.

5.7 Special properties

Any special property requirements shall be agreed between purchaser and supplier.

6 Test procedure

iTeh STANDARD PREVIEW
(standards.iteh.ai)

6.1 Sampling

6.1.1 Samples for chemical analysis

[SIST EN 683-1:2007](https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-97791efc0183/EN-14361-1-2007)

[https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-](https://standards.iteh.ai/catalog/standards/sist/e00f28d0-4742-482d-b3f4-97791efc0183/EN-14361-1-2007)

Sampling shall be carried out at the time of casting according to EN 14361. The average content of each sample shall be within the specification for the chemical composition.

NOTE EN 14361 includes criteria how to determine number, volume and shape of samples, about time and location of sampling and about the design and maintenance of the tools, in order to make sure that the average chemical composition of the sample is representative of the average chemical composition of the whole melt.

6.1.2 Specimens for mechanical testing

6.1.2.1 Location and size

Specimens shall be taken from samples in such a way that it is possible to orientate the test pieces in relation to the product, as specified in 6.1.2.2. The specimens shall be large enough to allow manufacture of the test pieces necessary to carry out the required tests and shall include sufficient metal to allow manufacture of test pieces for any retests required.

6.1.2.2 Orientation

Specimens shall be taken in such a manner that the test pieces can be prepared in the longitudinal direction.

6.1.2.3 Identification

Each specimen shall be identified in such a way that after removal, it is still possible to identify the product from which it was taken and its location and orientation. If during the course of subsequent operations removal of the markings cannot be avoided, new markings shall be made before the originals are removed.

6.1.2.4 Preparation

Specimens shall be taken from the sample after completion of all the mechanical and heat treatment operations that the product has to undergo before delivery and which can influence the mechanical properties of the metal. In cases where this is not possible, the sample or specimens may be taken at an earlier stage, but they shall be subjected to the same treatment as that to which it is intended to submit the product concerned.

Cutting shall be carried out in such a manner that it does not change the characteristics of the part of the specimen from which the test pieces are to be prepared. Thus, the dimensions of the specimens shall provide an adequate allowance to permit removal of the zone affected by cutting.

Specimens shall not be treated in any way that alters their mechanical properties.

6.1.2.5 Number

One specimen shall be taken from each inspection lot of 10 000 kg or part thereof. For single coils weighing more than 10 000 kg each, only one specimen per coil shall be taken.

6.1.3 Test pieces for tensile test

6.1.3.1 Identification

Each test piece shall be marked in such a manner that it is possible to identify the inspection lot from which it was taken and, if required, its location and orientation in the product.

If a test piece is identified by stamping, this shall not be in a place or manner which can interfere with subsequent testing. Where it is not convenient to mark a test piece, an identification tag may be attached.

6.1.3.2 Number

One test piece shall be taken from each specimen.

6.1.3.3 Type

Flat test pieces shall be used for all thicknesses covered by EN 683-2. The test piece shall be prepared so that both rolled surfaces are included undisturbed.

6.1.3.4 Machining

Any machining necessary shall be carried out in such a manner that it does not change the characteristics of the metal in the test piece.

6.2 Methods of testing

6.2.1 Analysis of chemical composition

The ranges of application and the accuracy of the test procedure used shall be validated and proved by the supplier.

In case of dispute concerning the chemical composition, referee analysis shall be carried out in accordance with EN 14242.

NOTE For the rapid determination of the chemical composition different spectral analysis methods are used (e.g. S-OES, XRF, GDOES). For S-OES see EN 14726.