
Superprevodnost - 18. del: Merjenje mehanskih lastnosti - Natezni preskus Ag-in/ali z Ag zlitino oplaščenih Bi-2223 in Bi-2212 kompozitnih superprevodnikov pri sobni temperaturi (IEC 61788-18:2013)

Superconductivity - Part 18: Mechanical properties measurement - Room temperature tensile test of Ag- and/or Ag alloy-sheathed Bi-2223 and Bi-2212 composite superconductors

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Supraconductivité - Partie 18: Mesure des propriétés mécaniques - Essai de traction à température ambiante des supraconducteurs composites Bi-2223 et Bi-2212 avec gaine Ag et/ou en alliage d'Ag

Ta slovenski standard je istoveten z: EN 61788-18:2013

ICS:

29.050	Superprevodnost in prevodni materiali	Superconductivity and conducting materials
--------	---------------------------------------	--

SIST EN 61788-18:2014

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 61788-18:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 61788-18

December 2013

ICS 29.050

English version

**Superconductivity -
Part 18: Mechanical properties measurement -
Room temperature tensile test of Ag- and/or Ag alloy-sheathed Bi-2223
and Bi-2212 composite superconductors
(IEC 61788-18:2013)**

Supraconductivité -
Partie 18: Mesure des propriétés mécaniques -
Essai de traction à température ambiante des
supraconducteurs composites Bi-2223 et
Bi-2212 avec gaine Ag et/ou en alliage d'Ag
(CEI 61788-18:2013)

Supraleitfähigkeit -
Teil 18: Messung der mechanischen
Eigenschaften -
Zugversuch von Ag und/oder Ag-Legierung
ummantelten Bi-2223 und Bi-2212
Verbundsupraleitern bei Raumtemperatur
(IEC 61788-18:2013)

[SIST EN 61788-18:2014](https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014)

<https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014>

This European Standard was approved by CENELEC on 2013-10-17. CENELEC members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CENELEC member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CENELEC member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CENELEC members are the national electrotechnical committees of Austria, Belgium, Bulgaria, Croatia, Cyprus, the Czech Republic, Denmark, Estonia, Finland, Former Yugoslav Republic of Macedonia, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, the Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland, Turkey and the United Kingdom.

CENELEC

European Committee for Electrotechnical Standardization
Comité Européen de Normalisation Electrotechnique
Europäisches Komitee für Elektrotechnische Normung

CEN-CENELEC Management Centre: Avenue Marnix 17, B - 1000 Brussels

Foreword

The text of document 90/326/FDIS, future edition 1 of IEC 61788-18, prepared by IEC/TC 90 "Superconductivity" was submitted to the IEC-CENELEC parallel vote and approved by CENELEC as EN 61788-18:2013.

The following dates are fixed:

- latest date by which the document has to be implemented at national level by publication of an identical national standard or by endorsement (dop) 2014-07-17
- latest date by which the national standards conflicting with the document have to be withdrawn (dow) 2016-10-17

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CENELEC [and/or CEN] shall not be held responsible for identifying any or all such patent rights.

iTeh **Endorsement notice** **PREVIEW** (standards.iteh.ai)

The text of the International Standard IEC 61788-18:2013 was approved by CENELEC as a European Standard without any modification.

[https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-](https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56f1b0d3f4/sist-en-61788-18-2014)

[8107-ec56f1b0d3f4/sist-en-61788-18-2014](https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56f1b0d3f4/sist-en-61788-18-2014)

In the official version, for Bibliography, the following notes have to be added for the standards indicated:

IEC 61788-6	NOTE	Harmonized as EN 61788-6.
ISO 3611:2010	NOTE	Harmonized as EN ISO 3611:2010 (not modified).

Annex ZA (normative)

Normative references to international publications with their corresponding European publications

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

NOTE When an international publication has been modified by common modifications, indicated by (mod), the relevant EN/HD applies.

<u>Publication</u>	<u>Year</u>	<u>Title</u>	<u>EN/HD</u>	<u>Year</u>
IEC 60050	series	International Electrotechnical Vocabulary	-	-
ISO 376	-	Metallic materials - Calibration of force-proving instruments used for the verification of uniaxial testing machines	EN ISO 376	-
ISO 6892-1	-	Metallic materials - Tensile testing Part 1: Method of test at room temperature	EN ISO 6892-1	-
ISO 7500-1	-	Metallic materials - Verification of static uniaxial testing machines Part 1: Tension/compression testing machines - Verification and calibration of the force-measuring system	EN ISO 7500-1	-
ISO 9513	-	Metallic materials - Calibration of extensometer systems used in uniaxial testing	EN ISO 9513	-

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 61788-18:2014](#)

<https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014>



IEC 61788-18

Edition 1.0 2013-09

INTERNATIONAL STANDARD

NORME INTERNATIONALE

Superconductivity – Mechanical properties measurement – Room temperature tensile test of Ag- and/or Ag alloy-sheathed Bi-2223 and Bi-2212 composite superconductors

[SIST EN 61788-18:2014](https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8197-6511a6810588)

Supraconductivité – Mesure des propriétés mécaniques – Essai de traction à température ambiante des supraconducteurs composites Bi-2223 et Bi-2212 avec gaine Ag et/ou en alliage d'Ag

INTERNATIONAL
ELECTROTECHNICAL
COMMISSION

COMMISSION
ELECTROTECHNIQUE
INTERNATIONALE

PRICE CODE
CODE PRIX

W

ICS 29.050

ISBN 978-2-8322-1051-2

**Warning! Make sure that you obtained this publication from an authorized distributor.
Attention! Veuillez vous assurer que vous avez obtenu cette publication via un distributeur agréé.**

CONTENTS

1	Scope.....	7
2	Normative references	7
3	Terms and definitions	7
4	Principle	9
5	Apparatus.....	9
5.1	General	9
5.2	Testing machine	9
5.3	Extensometer	9
6	Specimen preparation.....	9
6.1	General	9
6.2	Length of specimen	10
6.3	Removing insulation	10
6.4	Determination of cross-sectional area (S_0).....	10
7	Testing conditions	10
7.1	Specimen gripping.....	10
7.2	Setting of extensometer.....	10
7.3	Testing speed.....	10
7.4	Test.....	10
8	Calculation of results	12
8.1	Modulus of elasticity (E).....	12
8.2	0,2 % proof strength ($R_{p0,2}$).....	13
8.3	Tensile stress at specified strains (R_A).....	13
8.4	Fracture strength (R_f).....	14
9	Uncertainty of measurement.....	14
10	Test report.....	14
10.1	Specimen	14
10.2	Results.....	15
10.3	Test conditions	15
	Annex A (informative) Additional information relating to Clauses 1 to 14	16
	Annex B (informative) Uncertainty considerations	26
	Annex C (informative) Specific examples related to evaluation of uncertainties for Ag/Bi-2223 and Ag/Bi-2212 wires	30
	Figure 1 – Typical stress-strain curve and definition of modulus of elasticity and 0,2 % proof strengths of an externally laminated Ag/Bi-2223 wire by brass foil	11
	Figure 2 – Typical stress-strain curve of an Ag/Bi-2223 wire where the 0,2 % proof strengths could not be determined and definition of tensile stresses at specified strains	12
	Figure A.1 – Low mass Siam twin type extensometer with a gauge length of ~ 12,3 mm (total mass ~ 0,5 g).....	16
	Figure A.2 – Low mass double extensometer with a gauge length of ~ 25,6 mm (total mass ~ 3 g).....	17
	Figure A.3 – An example of the extensometer provided with balance weight and vertical specimen axis.....	18
	Figure A.4 – Original raw data of an Ag/Bi-2223 wire measurement in form of load and displacement graph.....	19

Figure A.5 – Typical stress versus strain of an Ag/Bi-2223 wire up to the elastic limit corresponding to the transition region from elastic to plastic deformation (point G)	20
Figure C.1 – Measured stress versus strain curve for Bi-2223 wire	31
Table A.1 – Results of relative standard uncertainty values achieved on different Ag/Bi-2223 wires during the international round robin tests	23
Table A.2 – Selected data for F test for E_0 of Sample E bare wire	24
Table A.3 – Results of F-test for the variations of E_0 of four kinds of Bi-2223 wires	24
Table B.1 – Output signals from two nominally identical extensometers	27
Table B.2 – Mean values of two output signals	27
Table B.3 – Experimental standard deviations of two output signals.....	27
Table B.4 – Standard uncertainties of two output signals	27
Table B.5 – Coefficient of variations of two output signals.....	28
Table C.1. – Load cell specifications according to manufacturer's data sheet.....	32
Table C.2 – Uncertainties from various factors for stress measurement	33
Table C.3 – Uncertainties with respect to measurement of strain measurement	35
Table C.4 – Summary of evaluated uncertainties caused by various factors	35
Table C.5 – Results of uncertainty evaluation for the modulus of elasticity ($E_0 = 86,1$ GPa) as a function of initial cross head rate.....	36
Table C.6 – Uncertainties from various factors for stress measurement	37
Table C.7 – Results of uncertainty evaluation for the stress ($R = 42,5$ MPa) as a function of initial strain rate	37

[SIST EN 61788-18:2014](https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014)

<https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014>

INTERNATIONAL ELECTROTECHNICAL COMMISSION

SUPERCONDUCTIVITY –

**Part 18: Mechanical properties measurement –
Room temperature tensile test of Ag- and/or Ag alloy-sheathed
Bi-2223 and Bi-2212 composite superconductors**

FOREWORD

- 1) The International Electrotechnical Commission (IEC) is a worldwide organization for standardization comprising all national electrotechnical committees (IEC National Committees). The object of IEC is to promote international co-operation on all questions concerning standardization in the electrical and electronic fields. To this end and in addition to other activities, IEC publishes International Standards, Technical Specifications, Technical Reports, Publicly Available Specifications (PAS) and Guides (hereafter referred to as "IEC Publication(s)"). Their preparation is entrusted to technical committees; any IEC National Committee interested in the subject dealt with may participate in this preparatory work. International, governmental and non-governmental organizations liaising with the IEC also participate in this preparation. IEC collaborates closely with the International Organization for Standardization (ISO) in accordance with conditions determined by agreement between the two organizations.
- 2) The formal decisions or agreements of IEC on technical matters express, as nearly as possible, an international consensus of opinion on the relevant subjects since each technical committee has representation from all interested IEC National Committees.
- 3) IEC Publications have the form of recommendations for international use and are accepted by IEC National Committees in that sense. While all reasonable efforts are made to ensure that the technical content of IEC Publications is accurate, IEC cannot be held responsible for the way in which they are used or for any misinterpretation by any end user.
- 4) In order to promote international uniformity, IEC National Committees undertake to apply IEC Publications transparently to the maximum extent possible in their national and regional publications. Any divergence between any IEC Publication and the corresponding national or regional publication shall be clearly indicated in the latter.
- 5) IEC itself does not provide any attestation of conformity. Independent certification bodies provide conformity assessment services and, in some areas, access to IEC marks of conformity. IEC is not responsible for any services carried out by independent certification bodies.
- 6) All users should ensure that they have the latest edition of this publication.
- 7) No liability shall attach to IEC or its directors, employees, servants or agents including individual experts and members of its technical committees and IEC National Committees for any personal injury, property damage or other damage of any nature whatsoever, whether direct or indirect, or for costs (including legal fees) and expenses arising out of the publication, use of, or reliance upon, this IEC Publication or any other IEC Publications.
- 8) Attention is drawn to the Normative references cited in this publication. Use of the referenced publications is indispensable for the correct application of this publication.
- 9) Attention is drawn to the possibility that some of the elements of this IEC Publication may be the subject of patent rights. IEC shall not be held responsible for identifying any or all such patent rights.

International Standard IEC 61788-18 has been prepared by IEC technical committee 90: Superconductivity.

The text of this standard is based on the following documents:

FDIS	Report on voting
90/326/FDIS	90/327/RVD

Full information on the voting for the approval of this standard can be found in the report on voting indicated in the above table.

This publication has been drafted in accordance with the ISO/IEC Directives, Part 2.

A list of all parts of the IEC 61788 series, published under the general title *Superconductivity*, can be found on the IEC website.

The committee has decided that the contents of this publication will remain unchanged until the stability date indicated on the IEC web site under "<http://webstore.iec.ch>" in the data related to the specific publication. At this date, the publication will be

- reconfirmed,
- withdrawn,
- replaced by a revised edition, or
- amended.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 61788-18:2014

<https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014>

INTRODUCTION

Several types of composite superconductors have now been commercialised. Especially, high temperature superconductors such as Ag- and/or Ag alloy-sheathed Bi-2223 (Ag/Bi-2223) and Ag- and/or Ag alloy-sheathed Bi-2212 (Ag/Bi-2212) wires are now manufactured in industrial scale. Commercial composite superconductors have a high current density and a small cross-sectional area. The major applications of composite superconductors are to build electrical power devices and superconducting magnets. While the magnet is being manufactured, complicated stresses/strains are applied to its windings and, while it is being energized, a large electromagnetic force is applied to the superconducting wires because of its high current density. It is therefore indispensable to determine the mechanical properties of the superconductive wires from which the windings are made.

The Ag/Bi-2223 and Ag/Bi-2212 superconductive composite wires fabricated by the powder-in-tube method are composed of a number of oxide filaments with silver and silver alloy as a stabilizer and supporter. In the case that the external reinforcement of Ag/Bi-2223 and Ag/Bi-2212 wires by using thin stainless or Cu alloy foils has been adopted in order to resist the large electromagnet force, this standard shall be also applied.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 61788-18:2014](https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014)

<https://standards.iteh.ai/catalog/standards/sist/75040cb7-db39-44b4-8107-ec56fdb0d3f4/sist-en-61788-18-2014>

SUPERCONDUCTIVITY –

Part 18: Mechanical properties measurement – Room temperature tensile test of Ag- and/or Ag alloy-sheathed Bi-2223 and Bi-2212 composite superconductors

1 Scope

This International Standard specifies a test method detailing the tensile test procedures to be carried out on Ag/Bi-2223 and Ag/Bi-2212 superconductive composite wires at room temperature.

This test is used to measure the modulus of elasticity and to determine the 0,2 % proof strength.

When the 0,2 % proof strength could not be determined due to earlier failure, the stress level at apparent strains of 0,05 %, 0,1 %, 0,15 %, 0,2 %, 0,25 % with increment of 0,05 % is measured.

The values for elastic limit, fracture strength, percentage elongation after fracture and the fitted type of 0,2 % proof strength serve only as a reference (see Clauses A.4, A.5, A.6 and A.10).

The sample covered by this test procedure should have a round or rectangular cross-section with an area of 0,3 mm² to 2,0 mm² (corresponding to the tape-shaped wires with width of 2,0 mm to 5,0 mm and thickness of 0,16 mm to 0,4 mm).

SIST EN 61788-18:2014

2 Normative references

The following documents, in whole or in part, are normatively referenced in this document and are indispensable for its application. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

IEC 60050 (all parts), *International Electrotechnical Vocabulary* (available at <<http://www.electropedia.org>>)

ISO 376, *Metallic materials – Calibration of force-proving instruments used for the verification of uniaxial testing machines*

ISO 6892-1, *Metallic materials – Tensile testing – Part 1: Method of test at room temperature*

ISO 7500-1, *Metallic materials – Verification of static uniaxial testing machines – Part 1: Tension/compression testing machines – Verification and calibration of the force-measuring system*

ISO 9513, *Metallic materials – Calibration of extensometer systems used in uniaxial testing*

3 Terms and definitions

For the purposes of this document, terms and definitions given in IEC 60050-815 and ISO 6892-1, as well as the following terms and definitions apply.