

---

---

**Carbonaceous materials used in the  
production of aluminium — Cold and  
tepid ramming pastes — Preparation of  
unbaked test specimens and  
determination of apparent density after  
compaction**

iTeh STANDARD PREVIEW

(standards.iteh.ai)  
*Produits carbonés utilisés pour la production de l'aluminium — Pâtes de  
brasquage froides et tièdes — Préparation d'éprouvettes non cuites et  
détermination de la densité apparente après compactage*

[ISO 14427:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 14427:2004

<https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 14427 was prepared by Technical Committee ISO/TC 47, *Chemistry*, Subcommittee SC 7, *Aluminium oxide, cryolite, aluminium fluoride, sodium fluoride, carbonaceous products for the aluminium industry*.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 14427:2004](https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004)

<https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 14427:2004

<https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004>

# Carbonaceous materials used in the production of aluminium — Cold and tepid ramming pastes — Preparation of unbaked test specimens and determination of apparent density after compaction

## 1 Scope

This International Standard describes the preparation of unbaked test specimens made by compacting carbonaceous ramming pastes. It also includes a method for the determination of the apparent density after compaction.

Unbaked test specimens of ramming paste need to be prepared not only for the determination of the apparent density of the paste after compaction, but also for the determination of the dimensional change during baking and for the subsequent determination of properties of baked test specimens.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5725-2, *Accuracy (trueness and precision) of measurement methods and results — Part 2: Basic method for the determination of repeatability and reproducibility of a standard measurement method*

ISO 14422, *Carbonaceous materials used in the production of aluminium — Cold-ramming pastes — Methods of sampling*

## 3 Principle

The carbonaceous ramming paste is compacted in a cylindrical mould by a defined number of impacts at a specified force in a ramming apparatus. The bulk density is calculated from the mass and the dimensions of the resulting compacted test specimen. The test specimen may subsequently be baked, if desired, for further testing.

## 4 Apparatus and materials

An example of a rammer mould is shown in Figure 1.

**4.1 Rammer cylinder**, made of steel, with an inner diameter of 50 mm.

**4.2 Ram base**, made of steel. The ram base shall fit into the rammer cylinder and act as the bottom of the cylinder.

**4.3 Rammer**, consisting of a steel piston, a falling weight mounted so that it can be dropped onto the top of the piston, and a height-measuring device accurate to 0,1 mm. The mass of the falling weight shall be 6,35 kg and the weight shall travel a constant distance to impact of  $(50 \pm 0,1)$  mm.

**4.4 Box (with lid)**, capable of containing the amount of ramming paste needed to produce one test specimen. The free space over the paste shall not be more than 50 % of the volume of the paste.

**4.5 Heating/cooling cabinet**, capable of being maintained at a constant temperature  $\pm 0,5$  °C in the range 5 °C to 100 °C.

**4.6 Insulation layer** (for example, 1-cm-thick polystyrene), for insulation of the rammer cylinder, or **thermostatically controlled surround** (see Figure 1).

**4.7 Balance**, accurate to 0,1 g.

## 5 Sampling

Sample the paste in accordance with ISO 14422.

NOTE Experience has shown that 150 g to 200 g of ramming paste is necessary for each test specimen.

## 6 Procedure

Ensure the cylinder, the ram base and the piston are clean.

Weigh the necessary amount of ramming paste (to the nearest 0,1 g) into a suitable box (4.4). If the amount of ramming paste to be used is not known, determine the required mass by preliminary tests [the height of the test specimen after compaction has to be  $(50 \pm 5)$  mm (see below)]. Seal the box. Heat or cool the box together with the rammer cylinder (4.1), the ram base (4.2) and the insulation/surround (4.6) to the test temperature (agreed between the interested parties) in the heating/cooling cabinet (4.5) for 2 h to 3 h.

Transfer the paste to the cylinder. Protect the cylinder with the insulation or surround (4.6). Place the cylinder in the rammer (4.3) and lower the piston until it is resting on the paste. Compact the ramming paste with 100 impacts at a rate of about 1 impact per second.

Read the height  $h$  of the test specimen (to the nearest 0,1 mm) from the scale on the ramming apparatus, with the piston head resting on the specimen. If the height of the compacted test specimen is not equal to  $(50 \pm 5)$  mm, discard the result and repeat the test with another sample mass.

Remove the test specimen. Clean the cylinder, the ram base and the piston carefully after each test.

## 7 Expression of results

### 7.1 Apparent density of unbaked paste

Calculate the apparent density  $\rho$ , in  $\text{g}\cdot\text{cm}^{-3}$ , of the unbaked test specimen from Equation (1):

$$\rho = \frac{m}{\pi r^2 h} \quad (1)$$

where

$m$  is the mass, in g, of the ramming paste placed in the cylinder, accurate to 0,1 g;

$r$  is the inner radius of the ramming cylinder, in cm, accurate to 0,01 cm;

$h$  is the height of the unbaked test specimen as read from the rammer scale, in cm, accurate to 0,01 cm.

Round the result to the nearest  $0,001 \text{ g}\cdot\text{cm}^{-3}$ .

## 7.2 Precision (determined in accordance with ISO 5725-2)

Repeatability ( $r$ ) = 0,023 (in g·cm<sup>-3</sup>)

Reproducibility ( $R$ ) = 0,042 (in g·cm<sup>-3</sup>)


The number of degrees of freedom, i.e. number of laboratories (6) × number of samples (4), was 24.

## 8 Test report

The test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary for identification of the sample tested;
- c) the temperature used for the test;
- d) the result of the test, i.e. the apparent density of the unbaked paste after compaction;
- e) the date of the test;
- f) details of any unusual features noted during the determination;
- g) details of any operation not included in this International Standard or regarded as optional.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**  
<https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004>



**Key**

- 1 piston
- 2 steel cylinder
- 3 ramming paste
- 4 insulation or thermostatically controlled surround
- 5 ram base

**Figure 1 — Rammer mould**



**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

ISO 14427:2004

<https://standards.iteh.ai/catalog/standards/sist/109e3db7-1066-433d-be01-ffc059744211/iso-14427-2004>