



**SLOVENSKI STANDARD**  
**SIST EN ISO 11502:2005**

**01-oktober-2005**

---

**Polimerni materiali - Filmi in folije - Ugotavljanje odpornosti proti zlepljenju (ISO 11502:1995)**

Plastics - Film and sheeting - Determination of blocking resistance (ISO 11502:1995)

Kunststoffe - Folien und Bahnen - Bestimmung des Blockwiderstandes (ISO 11502:1995)

Plastiques - Film et feuille - Détermination du pouvoir bloquant (ISO 11502:1995)

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

**Ta slovenski standard je istoveten z: EN ISO 11502:2005**

SIST EN ISO 11502:2005  
<https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb5-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005>

---

**ICS:**

83.140.10      Filmi in folije

Films and sheets

**SIST EN ISO 11502:2005**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 11502:2005](#)

<https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb3-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005>

EUROPEAN STANDARD  
NORME EUROPÉENNE  
EUROPÄISCHE NORM

**EN ISO 11502**

July 2005

ICS 83.140.10

English Version

**Plastics - Film and sheeting - Determination of blocking  
resistance (ISO 11502:1995)**

Plastiques - Film et feuille - Détermination du pouvoir  
bloquant (ISO 11502:1995)

Kunststoffe - Folien und Bahnen - Bestimmung des  
Blockwiderstandes (ISO 11502:1995)

This European Standard was approved by CEN on 7 July 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

SIST EN ISO 11502:2005

<https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb3-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

**EN ISO 11502:2005 (E)****Foreword**

The text of ISO 11502:1995 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 11502:2005 by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2006, and conflicting national standards shall be withdrawn at the latest by January 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

**Endorsement notice**

The text of ISO 11502:1995 has been approved by CEN as EN ISO 11502:2005 without any modifications.

**STANDARD PREVIEW**  
**(standards.iteh.ai)**  
SIST EN ISO 11502:2005  
<https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb3-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005>

INTERNATIONAL  
STANDARD

**ISO**  
**11502**

First edition  
1995-09-15

---

---

**Plastics — Film and sheeting —  
Determination of blocking resistance**

**iTeh STANDARD PREVIEW**

*Plastiques — Film et feuille — Détermination du pouvoir bloquant*  
**(standards.iteh.ai)**

[SIST EN ISO 11502:2005](https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb3-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005)

<https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb3-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005>



Reference number  
ISO 11502:1995(E)

**ISO 11502:1995(E)****Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 11502 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

**ITIH STANDARD PREVIEW**  
**(standards.iteh.ai)**  
SIST EN ISO 11502:2005  
<https://standards.iteh.ai/catalog/standards/sist/3637a73d-0eb3-4bc5-a87a-01fc0500f856/sist-en-iso-11502-2005>

© ISO 1995

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case Postale 56 • CH-1211 Genève 20 • Switzerland

Printed in Switzerland

# Plastics — Film and sheeting — Determination of blocking resistance

## 1 Scope

This International Standard specifies two methods for assessing the tendency of flexible plastic films and sheets to adhere to one another when left in contact for some time, at a specified temperature and under light pressure. One method is qualitative and the other is quantitative.

## 2 Normative reference

The following standard contains provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the edition indicated was valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent edition of the standard indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 291:1977, *Plastics — Standard atmospheres for conditioning and testing*.

## 3 Definition

For the purposes of this International Standard, the following definition applies.

**3.1 blocking:** Unintentional adherence between materials.

## 4 Method A: Qualitative method

### 4.1 Principle

Pieces of film or sheeting are kept in contact with one another for a minimum of 24 h at 50 °C under a pressure of 7 kPa. Blocking is considered to have oc-

curred if the surfaces suffer damage when they are separated or if the force of adherence between them is sufficient to lift a given weight.

Alternative times, temperatures and pressures may be used depending on the nature of the plastic film or sheeting under test and the proposed end use of the material.

## 4.2 Apparatus

**4.2.1 Glass plates,** measuring 100 mm × 76 mm and approximately 2 mm thick.

**4.2.2 Strips of filter paper,** measuring 150 mm × 76 mm.

**4.2.3 Oven,** capable of being maintained at 50 °C ± 2 °C, with provision for placing the test assemblies on shelves so that they are no less than 50 mm from each other and from the sides of the oven.

**4.2.4 Weights,** of mass 5,4 kg.

**4.2.5 Metal bars,** of rectangular cross-section, 15 mm wide × 76 mm long, weighing 50 g and 100 g.

**4.2.6 Metal clip,** with arms approximately 100 mm long.

**4.2.7 Double-sided adhesive tape,** approximately 12,5 mm wide.

## 4.3 Test specimens

### 4.3.1 Shape and dimensions

The specimens shall consist of strips measuring 150 mm × 76 mm. In the case of film or sheeting

with a printed or embossed surface, this side shall be known as the face. The opposite side is called the back. If there is no print or embossing, one side shall be called the face and marked accordingly.

#### 4.3.2 Preparation

Six specimens shall be taken, provided that for printed or coloured film or sheet these include all the colours or colour combinations of the print and base sheeting. If this requirement is not satisfied, additional specimens shall be taken. In the case of rolls, all specimens shall be taken at least 100 mm from the edge and more than 1 m from the beginning or the end of the roll. The minimum time between manufacture and testing shall be 16 h.

#### 4.4 Procedure

**4.4.1** Condition the specimens, together with the glass plates (4.2.1) and strips of filter paper (4.2.2) in one of the standard atmospheres defined in ISO 291 for a period of 24 h.

**4.4.2** Stack two specimens, strips of filter paper and glass plates on top of each other in the following order: glass plate, strip of filter paper, specimen with face uppermost, specimen with face downwards, strip of filter paper, glass plate.

Align the components of the assembly along one of their 76 mm edges so that the specimens and strips of filter paper extend 50 mm beyond the glass plates at the opposite edge, in order to facilitate handling (see figure 1).

Prepare two more assemblies in the same way, except that in the second the specimens shall be back to back and in the third back to face.

**4.4.3** Place each assembly in the oven (4.2.3) and load each with a weight of mass 5,4 kg (4.2.4) to give a uniform pressure of 7 kPa over the area under test. Maintain the oven temperature at  $50\text{ °C} \pm 2\text{ °C}$  for 24 h, after which time the weights shall be removed, and the assemblies taken from the oven and kept at standard atmospheric conditions for not less than 2 h but not more than 24 h.

**4.4.4** Carefully remove each pair of specimens from its assembly and lay them flat on a plane horizontal surface.

Attach a metal bar (4.2.5) of mass 50 g or 100 g, depending on the surface of the specimens under test,

to the free end of the lower specimen of each pair by double-faced adhesive tape (4.2.7) and allow it to rest freely on the horizontal surface (see figure 2).

For unprinted surfaces, use a 50 g metal bar.

For printed surfaces, use a 100 g metal bar.

Test sunken or sandwich print sheeting as unprinted surfaces.

Insert the free end of the upper specimen into a metal clip (4.2.6) so that the whole width of the specimen is held in the clip and raise the clip manually at a uniform rate of  $25\text{ mm/s} \pm 2,5\text{ mm/s}$  until the specimens have completely separated. Note whether or not the metal bar is lifted off the horizontal surface.

Examine the surfaces of the specimens that were in contact with one another for visible signs of damage.

**4.4.5** Blocking shall be considered to have occurred if, during separation of the specimens, the metal bar is lifted off the horizontal surface or if the separated specimens show surface damage.

#### 4.5 Test report

The test report shall include the following information:

- a reference to this International Standard and to the method used (method A);
- all details necessary for identification of the material tested;
- the metal bar used;
- whether or not blocking occurred, the damage observed, if any, and the surfaces involved in each case;
- the date of the test.

### 5 Method B: Quantitative method

#### 5.1 Principle

Specimens of film or sheeting are kept in contact with each other under specified conditions of time, temperature and pressure. The specimens are then fixed between two platens mounted in a universal testing machine, and the force necessary to separate them is determined.



## 5.2 Apparatus

**5.2.1 Constant-speed tensile-testing machine**, having a pair of 100 mm × 100 mm aluminium blocks mounted on the top and bottom jaws by means of suitable adapters.

**5.2.2 Glass plates**, measuring 100 mm × 76 mm and approximately 2 mm thick.

**5.2.3 Strips of filter paper**, measuring 100 mm × 76 mm.

**5.2.4 Weights**, of mass 2,3 kg.

**5.2.5 Oven**, capable of being maintained at 50 °C ± 2 °C.

**5.2.6 Double-sided adhesive tape**.

## 5.3 Test specimens

### 5.3.1 Shape and dimensions

Specimens shall consist of strips measuring 150 mm × 76 mm, cut so that the longest side coincides with the machine direction of the film or sheeting.

### 5.3.2 Preparation

Ten specimens shall be taken from several locations across the width of the material. In the case of rolls, all specimens shall be taken at least 100 mm from the edge and more than 1 m from the beginning or the end of the roll. The minimum time between manufacturing and testing shall be 16 h.

## 5.4 Procedure

**5.4.1** Condition the specimens, together with the glass plates (5.2.2) and strips of filter paper (5.2.3), in one of the standard atmospheres defined in ISO 291 for a period of 24 h.

**5.4.2** Prepare five assemblies, each containing two specimens held between strips of filter paper and glass plates in the same way as described in method A, but aligning the edges of the layers as shown in figure 3. The orientation of the specimen surfaces with respect to each other in the assemblies is left to the discretion of the user (it may, for instance, depend in the results of testing using the qualitative method), but it shall be the same in each of the five assemblies. Place a weight of mass 2,3 kg (equivalent to 3 kPa) on each assembly and

heat them in the oven (5.2.5) for 3 h at 50 °C ± 2 °C. After this time, remove the weights and take the assemblies from the oven. Carefully remove each pair of specimens from its assembly and keep at standard atmospheric conditions for not less than 2 h but not more than 24 h.

**5.4.3** Using a wide-bladed knife or spatula, transfer one of the pairs of specimens carefully to the lower block in the tensile-testing machine, placing it so that its ends project out equally on each side of the block (see figure 4).

**5.4.4** Raise the lower block until the upper block is resting on the specimen directly above the lower block.

**5.4.5** Carefully separate the ends of the pair of specimens using the sharp edge of the knife blade and peel back to the edges of the blocks on each side.

**5.4.6** Using the double-sided adhesive tape (5.2.6), fix the two ends of the upper specimen to the upper block and the two ends of the lower specimen to the lower block (see figure 5).

**5.4.7** Adjust the chart speed to 50 mm/min and the crosshead speed to 5 mm/min.

**5.4.8** Start the chart and crosshead travel and allow the testing machine to record the force required to separate the two layers completely.

**5.4.9** Repeat the process for the four other pairs of specimens.

**5.4.10** Note the maximum force for each pair of specimens, and calculate the average of the five determinations.

NOTE 1 This method may be used to measure the force necessary to separate already blocked items. However, since the conditions under which blocking occurred will not be known, and may differ from the conditions specified in this method, direct comparison with the results obtained by the above method is not possible.

## 5.5 Precision

The precision of this test method is not known because inter-laboratory data are not available. When inter-laboratory data are obtained, a precision statement will be added at the following revision.

## 5.6 Test report

The test report shall include the following information: