
**Nerjavna jekla – 4. del: Tehnični dobavni pogoji za tanko in debelo pločevino
in trakove iz nerjavnih konstrukcijskih jekel**

Stainless steels - Part 4: Technical delivery conditions for sheet/plate and strip of
corrosion resisting steels for construction purposes

iTeh Standards
(<https://standards.iteh.ai>)
Document Preview

[SIST EN 10088-4:2009](https://standards.iteh.ai/catalog/standards/sist/c6bc5bec-d7ce-4feb-ab69-4d832e014d0b/sist-en-10088-4-2009)

<https://standards.iteh.ai/catalog/standards/sist/c6bc5bec-d7ce-4feb-ab69-4d832e014d0b/sist-en-10088-4-2009>

December 2005

ICS

English Version

**Stainless steels - Part 4: Technical delivery conditions for
sheet/plate and strip of corrosion resisting steels for construction
purposes**

Aciers inoxydables - Partie 4: Conditions techniques de
livraison des tôles et bandes en acier de résistance à la
corrosion pour usage de construction

Nichtrostende Stähle - Teil 4: Technische
Lieferbedingungen für Blech und Band aus
korrosionsbeständigen Stählen für das Bauwesen

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee ECISS/TC 23.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.

<https://standards.itc.eu/catalog/standards/sist/c6bc5bec-d7ce-4feb-ab69-4d832e014d0b/sist-en-10088-4-2009>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	5
4 Designation and ordering	6
4.1 Designation of steel grades	6
4.2 Order designation	6
5 Classification of grades	7
6 Requirements	7
6.1 Steelmaking process	7
6.2 Delivery condition	7
6.3 Chemical composition	7
6.4 Chemical corrosion properties	7
6.5 Mechanical properties	8
6.6 Surface quality	8
6.7 Internal soundness	8
6.8 Formability at room temperature	8
6.9 Dimensions and tolerances on dimensions and shape	8
6.10 Calculation of mass and tolerances on mass	8
7 Inspection and testing	9
7.1 General	9
7.2 Agreement on tests and inspection documents	9
7.3 Specific inspection and testing	10
7.4 Test methods	10
7.5 Retests	11
8 Evaluation of Conformity	11
8.1 General	11
8.2 Initial type testing	11
8.3 Factory production control (FPC)	12
9 Marking	14
10 Dangerous substances	14
Annex A (informative) Guidelines for further treatment (including heat treatment) in fabrication	34
Annex B (informative) Atmospheric applications of corrosion resisting steel grades	38
Annex ZA (informative) Relationship between this European Standard and the Essential Requirements of EU Directive 89/106/EEC, EU Construction Products Directive	39
Bibliography	45

Foreword

This document (prEN 10088-4:2005) has been prepared by Technical Committee ECISS/TC 23 "Steels for heat treatment, alloy steels and free-cutting steels - Qualities and dimensions", the secretariat of which is held by DIN.

This document is currently submitted to the CEN Enquiry.

This document has been prepared under mandate M/120 given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of the EU Construction Products Directive.

For relationship with the EU Construction Products Directive, see informative Annex ZA, which is an integral part of this document.

EN 10088, under the general title "Stainless steels", consists of the following parts:

- Part 1: List of stainless steels (including a table of European Standards, in which these stainless steels are further specified, see annex D),
- Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes,
- Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes.
- Part 4: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for construction purposes,
- Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes. [EN 10088-4:2009](https://standards.iteh.ai/catalog/standards/sist/c6bc5bec-d7ce-4feb-ab69-4d832e014d0b/sist-en-10088-4-2009)

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

1 Scope

1.1 The scope of this part of EN 10088 is to specify the technical delivery conditions for hot or cold rolled sheet/plate and strip of standard and special grades of corrosion resisting stainless steels for construction purposes in addition to the general technical delivery conditions specified in EN 10021.

1.2 This European Standard does not apply to components manufactured by further processing of the product forms listed in 1.1 with quality characteristics altered as a result of such further processing.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 10002-1, *Metallic materials - Tensile testing - Part 1: Method of test at ambient temperature.*

EN 10002-5, *Metallic materials - Tensile testing - Part 5: Method of test at elevated temperature.*

EN 10021, *General technical delivery requirements for steel and steel products.*

EN 10027-1, *Designation systems for steels - Part 1: Steel names.*

EN 10027-2, *Designation systems for steels - Part 2: Numerical system.*

EN 10029, *Hot rolled steel plates 3 mm thick or above - Tolerances on dimensions, shape and mass.*

EN 10045-1, *Metallic materials - Charpy impact test - Part 1: Method of test.*

EN 10048, *Hot rolled narrow steel strip - Tolerances on dimensions and shape.*

EN 10051, *Continuously hot rolled uncoated plate, sheet and strip of non alloy and alloy steels – Tolerances on dimensions and shape (includes amendment A1:1997).*

EN 10052, *Vocabulary of heat treatment terms for ferrous products.*

EN 10079, *Definition of steel products.*

EN 10088-1, *Stainless steels - Part 1: List of stainless steels.*

EN 10088-2, *Stainless steels – Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes.*

EN 10163-1, *Delivery requirements for surface condition of hot rolled steel plates, wide flats and sections - Part 1: General requirements.*

EN 10163-2, *Delivery requirements for surface condition of hot rolled steel plates, wide flats and sections - Part 2: Plates and wide flats.*

EN 10168, *Steel products – Inspection documents – List of information and description.*

EN 10204, *Metallic products - Types of inspection documents.*

EN 10258, *Cold-rolled stainless steel narrow strip and cut lengths - Tolerances on dimensions and shape.*

EN 10259, *Cold-rolled stainless steel wide strip and plate/sheet - Tolerances on dimensions and shape.*

CR 10261, *ECISS Information Circular 11 – Iron and steel – Review of available methods of chemical analysis.*

EN 10307, *Non-destructive testing - Ultrasonic testing of austenitic and austenitic-ferritic stainless steels flat products of thickness equal to or greater than 6 mm (reflection method).*

EN ISO 377, *Steel and steel products - Location and preparation of samples and test pieces for mechanical testing (ISO 377:1997).*

EN ISO 3651-2, *Determination of resistance to intergranular corrosion of stainless steels - Part 2: Ferritic, austenitic and ferritic-austenitic (duplex) stainless steels - Corrosion test in media containing sulfuric acid (ISO 3651-2:1998).*

EN ISO 6506-1, *Metallic materials - Brinell hardness test - Part 1: Test method (ISO 6506-1:1999).*

EN ISO 6507-1, *Metallic materials - Vickers hardness test - Part 1: Test method (ISO 6507-1:1997).*

EN ISO 6508-1, *Metallic materials - Rockwell hardness test - Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T) (ISO 6508-1:1999).*

EN ISO 9001, *Quality management systems - Requirements (ISO 9001:2000).*

EN ISO 14284, *Steel and iron - Sampling and preparation of samples for the determination of chemical composition (ISO 14284:1996).*

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply

3.1 stainless steels

the definition in EN 10088-1:2005 applies

3.2 corrosion resisting steels

steels with at least 10,5 % Cr and max. 1,20 % C if their resistance to corrosion is of primary importance

3.3 product forms

the definitions in EN 10079 apply

3.4 types of heat-treatment

the definitions in EN 10052 apply

3.5 standard grades

grades with a relatively good availability and a wider range of application

3.6 special grades

grades for special use and/or with limited availability

4 Designation and ordering

4.1 Designation of steel grades

The steel names and steel numbers (see Tables 1 to 4) are allocated in accordance with EN 10027-1 and EN 10027-2 respectively.

4.2 Order designation

The complete designation for ordering a product according to this European Standard shall contain the following information:

- the desired quantity;
- the product form (strip or sheet/plate);
- the nominal dimensions, the number of the appropriate standard (see normative references) plus any choice of requirements;
- the type of material (steel);
- the number of this European Standard;
- the steel name or steel number;
- the symbol for the desired heat treatment or cold worked condition, if for the relevant steel in the tables for the mechanical properties more than one treatment condition is covered;
- the desired process route (see symbols in Table 6);
- verification of internal soundness, if required (flat products with thickness ≥ 6 mm shall be tested in accordance with EN 10307);
- an inspection document, if required. Its designation according to EN 10204;
- regulatory marking requirements (see Annex ZA).

EXAMPLE 10 plates of a steel grade with the name X5CrNi18-10 and the number 1.4301 as specified in EN 10088-4 with nominal dimensions thickness = 8 mm, width = 2000 mm, length = 5000 mm; tolerances on dimensions, shape and mass as specified in EN 10029 with thickness tolerance class A and "normal" flatness tolerance class, in process route 1D (see Table 6), inspection certificate 3.1 as specified in EN 10204 and declaration of conformity:

10 plates EN 10029-8A x 2000 x 5000
Steel EN 10088-4 - X5CrNi18-10+1D
Inspection certificate 3.1, CE

or

10 plates EN 10029-8A x 2000 x 5000
Steel EN 10088-4 - 1.4301+1D
Inspection certificate 3.1, CE

5 Classification of grades

Steels covered in this European Standard are classified according to their structure into

- ferritic steels,
- martensitic steels,
- precipitation hardening steels,
- austenitic steels,
- austenitic-ferritic steels.

See also Annex B to EN 10088-1.

6 Requirements

6.1 Steelmaking process

Unless a special steelmaking process is agreed at the time of enquiry and order, the steelmaking process for steels conforming to this European Standard shall be at the discretion of the manufacturer.

6.2 Delivery condition

The products shall be supplied in the delivery condition agreed at the time of enquiry and order by reference to the process route given in Table 6 and, where different alternatives exist, to the treatment conditions given in Tables 7 to 11, 13 and 14 (see also Annex A).

6.3 Chemical composition

6.3.1 The chemical composition requirements given in Tables 1 to 4 shall apply with respect to the chemical composition according to the cast analysis.

If grades other than those included in this European standard are required for construction purposes, they shall comply with part 2 and be in conjunction with the requirements of this European standard.

6.3.2 The product analysis may deviate from the limiting values for the cast analysis given in Tables 1 to 4 by the values listed in Table 5.

6.4 Chemical corrosion properties

Referring to resistance to intergranular corrosion as defined in EN ISO 3651-2, for ferritic, austenitic and austenitic-ferritic steels the specification in Tables 7, 10 and 11 shall apply.

NOTE 1 EN ISO 3651-2 is not applicable for testing martensitic and precipitation hardening steels.

NOTE 2 The corrosion resistance of stainless steels is very dependant on the type of environment and can therefore not always be clearly ascertained through laboratory tests. It is therefore advisable to draw on the available experience of the use of the steels.

6.5 Mechanical properties

6.5.1 The mechanical properties at room temperature as specified in Tables 7 to 11 shall apply for the relevant specified heat treatment condition. This does not apply to the process route 1U (hot rolled, not heat treated, not descaled).

If by agreement at the time of ordering the products are to be supplied in a non-heat-treated condition, the mechanical properties specified in 7 to 11 shall be obtained from reference test pieces which have received the appropriate heat treatment (simulated heat treatment).

For cold worked products, the tensile strength levels at ambient temperature as specified in Table 13 shall apply. The available tensile strength levels in the cold worked condition are indicated in Table 15.

Alternatively, cold worked products can be ordered according to their 0,2%-proof strength as given in Tables 14 and 16.

NOTE Austenitic steels are insensitive to brittle fracture in the solution annealed condition. Because they do not have a pronounced transition temperature, which is characteristic of other steels, they are also useful for application at cryogenic temperatures.

6.5.2 The values in Table 12 shall apply for the 0,2 %- and 1 %-proof strength of austenitic steels at elevated temperatures.

6.6 Surface quality

Slight surface imperfections, inherent in the rolling process, are permitted.

When products are delivered in coil form, the degree and extent of such imperfections may be expected to be greater, due to the impracticability of removing short lengths of coil. For hot-rolled quarto-plates (symbol P in Tables 7 to 11), the requirements in EN 10163-2, class A2, apply unless otherwise agreed. For other products, where necessary, more precise requirements on surface quality may be agreed at the time of enquiry and order.

6.7 Internal soundness

The products shall be free of internal defects which would exclude them from being used for their intended purpose. Ultrasonic testing of austenitic and austenitic-ferritic stainless steel flat products ≥ 6 mm may be agreed at the time of enquiry and order in accordance with EN 10307.

6.8 Formability at room temperature

Cold formability may be verified by elongation in tensile test.

6.9 Dimensions and tolerances on dimensions and shape

The dimensions and the tolerances on dimensions and shape shall be agreed at the time of enquiry and order, as far as possible and in so far they do not conflict with regulatory requirements with reference to the dimensional standards listed in the normative references. EN 10029 shall normally only be applied for product form P (individually rolled plates, "quarto plates") and not for product form H (continuously rolled strip and plate), for which EN 10051 shall be applied. When applying EN 10029, thickness tolerance class B shall apply, unless specifically agreed otherwise at the time of enquiry and order.

6.10 Calculation of mass and tolerances on mass

6.10.1 When calculating the nominal mass from the nominal dimensions the values given in EN 10088-1 shall be used as a basis for the density of the steel concerned.

6.10.2 If the tolerances on mass are not specified in the dimensional standard listed in the normative references, they may be agreed at the time of enquiry and order.

7 Inspection and testing

7.1 General

The appropriate process control, inspection and testing shall be carried out according to 8.3 to ensure that the product complies with the requirements of both this European standard and the order.

This includes the following:

- A suitable frequency of verification of the dimensions of the products.
- An adequate intensity of visual examination of the surface quality of the products.
- An appropriate frequency and type of test to ensure that the correct grade of steel is used.

The nature and frequency of these verifications, examinations and tests shall be determined in the light of the degree of conformity that has been determined by the evidence of the factory production control system. In view of this, verifications by additional specific tests for these requirements are not a requirement of this document.

7.2 Agreement on tests and inspection documents

7.2.1 At the time of ordering the type of inspection document in accordance with EN 10204 may be agreed for each delivery.

7.2.2 If it is agreed to issue a test report in accordance with EN 10204:2004, 2.2, it shall indicate the following information:

- a) the information groups A, B and Z of EN 10168:2004;
- b) the results of the cast analysis in accordance with the code numbers C71 to C92 in EN 10168:2004;
- c) the regulatory information (see Annex ZA).

7.2.3 If the issuing of an inspection certificate according to EN 10204:2004, 3.1 or 3.2, has been agreed, specific inspections according to 7.3 shall be carried out and the following information shall be given in the inspection document with the code numbers and details required by EN 10168:2004

- a) as under 7.2.2 a);
- b) as under 7.2.2 b);
- c) the results of the tests marked in Table 17, second column, by "m";
- d) the result of any optional test or inspections agreed at the time of enquiry and order;
- e) the regulatory information (see Annex ZA).

7.3 Specific inspection and testing

7.3.1 Extent of testing

The tests to be carried out and the composition and size of the test units and the number of sample products, samples and test pieces to be taken shall be as in Table 17.

7.3.2 Selection and preparation of samples and test pieces

7.3.2.1 Sampling and sample preparation shall be in accordance with the requirements of EN ISO 14284 and EN ISO 377. In addition, the stipulations in 7.3.2.2 apply for the mechanical tests.

7.3.2.2 The test samples for the tensile test shall be taken in accordance with Figure 1 in such a way that they are located halfway between the centre and a longitudinal edge. If it has been agreed that impact tests shall be carried out, the test samples shall be taken from the same location.

The samples shall be taken from products in the delivery condition. If agreed, the samples may be taken before flattening. For samples to be given a simulated heat treatment the conditions for annealing, hardening and tempering shall be agreed.

7.3.2.3 Samples for the hardness test and for the resistance to intergranular corrosion test, where requested, shall be taken from the same locations as those for the mechanical tests. For direction of bending the test piece in the resistance to intergranular corrosion test, see Figure 2.

7.4 Test methods

7.4.1 The chemical analysis shall be carried out using the appropriate European Standard for the element being analysed. In the absence of an appropriate European Standard, the choice of a suitable physical or chemical analytical method for the analysis shall be at the discretion of the manufacturer. The manufacturer shall declare the test method used, if required.

NOTE The list of available European Standards on chemical analysis is given in CR 10261.

7.4.2 The tensile test at room temperature shall be carried out in accordance with EN 10002-1 taking into account the additional or deviating conditions specified in Figure 1, footnote a.

The tensile strength, elongation after fracture and the 0,2 % proof strength shall be determined. In addition for austenitic steels only, the 1 %-proof strength shall be determined.

7.4.3 If the manufacturer wishes to claim a tensile test for austenitic steels at elevated temperature has been carried out, this shall be carried out in accordance with EN 10002-5. If the proof strength is to be verified for austenitic steels, the 0,2%- and the 1 %-proof strength shall be determined.

7.4.4 If the manufacturer wishes to claim an impact test has been carried out, it shall be carried out in accordance with EN 10045-1 on test pieces with a V-notch. The average obtained from three test pieces shall be considered to be the test result (see also EN 10021).

7.4.5 The Brinell hardness test shall be carried out in accordance with EN ISO 6506-1, the Rockwell hardness test in accordance with EN ISO 6508-1, and the Vickers hardness test in accordance with EN ISO 6507-1.

7.4.6 The resistance to intergranular corrosion shall be tested in accordance with EN ISO 3651-2.

7.4.7 Dimensions and dimensional tolerances of the products shall be tested in accordance with the requirements of the dimensional standard relevant to the product form.