



SLOVENSKI STANDARD

SIST EN 1425:2000/A1:2006

01-maj-2006

Bitumen in bitumenska veziva – Ugotavljanje vidnih lastnosti

Bitumen and bituminous binders - Characterization of perceptible properties

Bitumen und bitumenhaltige Bindemittel - Feststellung der äußeren Beschaffenheit

Bitumes et liants bitumineux - Caractérisation des propriétés sensorielles

Ta slovenski standard je istoveten z: EN 1425:1999/A1:2006

SIST EN 1425:2000/A1:2006
<https://standards.iteh.ai/catalog/standards/sist/756d58c2-51d6-4c67-b410-d695e30fe22c/sist-en-1425-2000-a1-2006>

ICS:

75.140	Voski, bitumni in drugi naftni proizvodi	Waxes, bituminous materials and other petroleum products
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST EN 1425:2000/A1:2006

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 1425:2000/A1:2006](https://standards.iteh.ai/catalog/standards/sist/736d38c2-5fd6-4c67-b4f0-d695e30fe22c/sist-en-1425-2000-a1-2006)

<https://standards.iteh.ai/catalog/standards/sist/736d38c2-5fd6-4c67-b4f0-d695e30fe22c/sist-en-1425-2000-a1-2006>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 1425:1999/A1

February 2006

ICS 75.140

English Version

Bitumen and bituminous binders - Characterization of perceptible properties

Bitumes et liants bitumineux - Caractérisation des propriétés sensorielles

Bitumen und bitumenhaltige Bindemittel - Feststellung der äußeren Beschaffenheit

This amendment A1 modifies the European Standard EN 1425:1999; it was approved by CEN on 28 December 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This amendment exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 1425:2000/A1:2006](https://standards.iteh.ai/catalog/standards/sist/736d38c2-5fd6-4c67-b4f0-d695e30fe22c/sist-en-1425-2000-a1-2006)

<https://standards.iteh.ai/catalog/standards/sist/736d38c2-5fd6-4c67-b4f0-d695e30fe22c/sist-en-1425-2000-a1-2006>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN 1425:1999/A1:2006 (E)

Foreword

This European Standard (EN 1425:1999/A1:2006) has been prepared by Technical Committee CEN/TC 336 “Bituminous binders”, the secretariat of which is held by AFNOR.

This Amendment to the European Standard EN 1425:1999 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2006, and conflicting national standards shall be withdrawn at the latest by August 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 1425:2000/A1:2006](https://standards.iteh.ai/catalog/standards/sist/736d38c2-5fd6-4c67-b4f0-d695e30fe22c/sist-en-1425-2000-a1-2006)

<https://standards.iteh.ai/catalog/standards/sist/736d38c2-5fd6-4c67-b4f0-d695e30fe22c/sist-en-1425-2000-a1-2006>

The last paragraph of the Foreword is amended to read as follows:

“According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.”

6.1 is changed to read:

6.1 Examine the sample in its original container at approximately ambient temperature or below.

6.4 is changed to read:

6.4 Examine the sample at approximately ambient temperature for the following perceptible properties:

- a) appearance of the surface (e.g. shiny, dull, coloured);
- b) presence of foreign materials (e.g. free water, dust, rust);
- c) consistency (e.g. liquid or solid);
- d) homogeneity of liquid binders, by gently stirring with the glass rod (4.1) (recording the presence of any lumps, agglomerates, sediments etc.);
- e) odour (the usual bitumen odour or other typical odour, e.g. from tar or solvent).

WARNING — Personnel who assess the odour characteristic of the samples should be aware of correct sniffing procedure and the hazards of potential dangerous chemicals. It is unlikely that occasional sniffing of refined bitumen will be harmful, but frequent testing of unknown materials (which may contain tar or harmful solvents) should not be done repeatedly by any one individual.

The results of the sensorial examination shall conform to the perceptible properties expected of the sample indicated on the sample container. If so, the material shall be accepted for further testing.

If the material does not conform to the perceptible properties expected, the container shall be closed immediately, and the person requesting the analysis of the sample shall be contacted and informed of the findings before the sample is handled further.