



**SLOVENSKI STANDARD  
SIST ISO/TR 14697:1998**

**01-februar-1998**

---

**Požarni preskusi - Navodila za izbiro podlag za gradbene proizvode**

Fire tests -- Guidance on the choice of substrates for building products

Essais au feu -- Lignes directrices sur le choix de subjectiles pour les produits du bâtiment

**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: ISO/TR 14697:1997**

<https://standards.iteh.ai/catalog/standards/sist/7a786b00-fl83-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998>

**ICS:**

13.220.50	Požarna odpornost gradbenih materialov in elementov	Fire-resistance of building materials and elements
-----------	---	--

**SIST ISO/TR 14697:1998**

**en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO/TR 14697:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998>

# TECHNICAL REPORT

# ISO/TR 14697

First edition  
1997-08-15

---

---

## Fire tests — Guidance on the choice of substrates for building products

*Essais au feu — Lignes directrices sur le choix de subjectiles  
pour les produits du bâtiment*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO/TR 14697:1998](https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998)

<https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998>



Reference number  
ISO/TR 14697:1997(E)

## ISO/TR 14697:1997(E)

Contents	Page
1 Scope	1
2 Definitions	1
3 Guidance rules	2
4 Storage of reference substrates	4
5 Methods of application to the substrate	5
Annex A: Bibliography	6

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO/TR 14697:1998](https://standards.iteh.ai/catalog/standards/sist/7a786b00-fl83-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998)

<https://standards.iteh.ai/catalog/standards/sist/7a786b00-fl83-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998>

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
Case postale 56 • CH-1211 Genève 20 • Switzerland  
Internet central@iso.ch  
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO members bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented in that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

The main task of technical committees is to prepare International Standards, but in exceptional circumstances a technical committee may propose the publication of a Technical Report of one of the following types:

- type 1, when the required support cannot be obtained for the publication of an International Standard, despite repeated efforts;
- type 2, when the subject is still under technical development or where for any other reason there is the future but not immediate possibility of an agreement on an International Standard;
- type 3, when a technical committee has collected data of a different kind from that which is normally published as an International Standard ("state of the art", for example).

[https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-](https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998)

Technical Reports of types 1 and 2 are subject to review within three years of publication, to decide whether they can be transformed into International Standards. Technical Reports of type 3 do not necessarily have to be reviewed until the data they provide are considered to be no longer valid or useful.

ISO/TR14697, which is a Technical Report of type 3, was prepared by Technical Committee ISO/TC 92, *Fire safety*, Subcommittee SC 1, *Reaction to fire tests*.

**iTeh STANDARD PREVIEW**  
This page intentionally left blank  
**(standards.iteh.ai)**

[SIST ISO/TR 14697:1998](#)

<https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998>

# Fire tests — Guidance on the choice of substrates for building products

## 1 Scope

This Technical Report gives guidance on the choice of substrates for building products when carrying out reaction-to-fire tests.

Many building products are produced and used in combination with other materials; for example, wall-coverings are adhered to many different substrates, which vary in their thickness, density, thermal conductivity and flammability characteristics. When selecting a substrate on which to fix a sample of building product for reaction-to-fire testing, the guidelines given in this Technical Report should be followed.

iteh STANDARD PREVIEW  
(standards.iteh.ai)

## 2 Definitions

[SIST ISO/TR 14697:1998](https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7e0313a4730d/iso-tr-14697-1998)

[https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-](https://standards.iteh.ai/catalog/standards/sist/7a786b00-f183-468a-9aa4-7e0313a4730d/iso-tr-14697-1998)

For the purpose of this Technical Report, the definitions given in ISO/IEC Guide 52 together with the following apply.

### 2.1

#### **assembly**

fabrication of materials and/or composites

NOTE — This may include an air gap.

EXAMPLE — Dry wall partition.

### 2.2

#### **coating**

product applied as a liquid or a powder to a substrate which will cure or dry into a continuous protective facing to the substrate

### 2.3

#### **composite**

combination of materials which are recognised in building construction as discrete entities

EXAMPLE — Coated, faced or laminated materials.

### 2.4

#### **exposed surface**

that surface of the product subjected to the heating conditions of the test or fire in end-use

## 2.5

### **facing**

thin pre-produced sheet material which is applied to the substrate using an adhesive or the self-adhesive properties of the substrate or fixing

## 2.6

### **material**

single basic substance or uniformly dispersed mixture

## 2.7

### **product**

material, composite or assembly about which information is required

## 2.8

### **spacers**

non-combustible material applied in the form of edge strips to a non-combustible substrate to provide an air gap behind a product for testing purposes

## 2.9

### **substrate**

material which is used or is representative of that used immediately beneath a surface in end-use

EXAMPLE — Plasterboard beneath a wallcovering.

NOTE — This definition of a substrate is different from that given in ISO 2424. For textile floor coverings, the substrate is considered to be part of the floor covering assembly below the use surface. In the context of this fire testing standard, the substrate should be chosen to represent the type of floor on which the textile or non-textile floor covering is placed.

<https://standards.iteh.ai/catalog/standards/sist/7a786b00-fl83-468a-9aa4-7ec03d3a4f30/sist-iso-tr-14697-1998>

## 3 Guidance rules

### 3.1 Rule 1: In all cases, end-use substrates are preferred

The term end-use substrate applies not only to the material immediately beneath the surface to be tested, but also to the method of attachment which must also be end-use in terms of the type and application, where appropriate.

If the product has both primary and secondary substrates in end-use practice, the test specimen should be prepared to incorporate both substrates (the second substrate may be an air gap); e.g. a paint coating to a steel plate which has an insulation substrate beneath as in a sandwich panel construction. The paint layer in this case should be tested together with the steel and the insulation.

NOTE 1 The test method will define the required specimen dimensions.

NOTE 2 In no test method should water or another highly conductive liquid be used as a secondary substrate.

This requirement for end-use testing is necessary since underlying layers of material and also various methods of attachment are known to have a profound effect on the fire performance of the surface product. The effects are more pronounced when assessing some parameters than others; for example, the choice of substrates when assessing the spread of flame performance of a material can make the difference



between having the lowest or highest level of performance for the same surface material. Choice of the method of attachment can also effect performance since partial delamination can create a significantly worse fire performance due to the insulatory air layer created between the material and the substrate.

In some actual uses, the substrate may be 'air' since an airgap is formed in the construction of the lining to wall, ceiling or floor surface, by the use of battens, etc. If an airgap is used in practice, then this should be simulated in the preparation and testing of the specimen.

**3.2 Rule 2: As an alternative option, for non-combustible (i.e.  $PCS^1 = 0$  when tested to ISO 1716) substrates or substrates of limited combustibility (i.e.  $PCS^1 < 1,0$  MJ/kg when tested to ISO 1716), the following reference substrates may be used to represent end use substrates having a density which is equal to or more than the nominal value of the density of the reference substrate (see table 1)**

**Table 1 — Reference substrates**

Reference substrate	Density ( $kg/m^3$ )	Thickness (mm)	Thermal inertia ( $W^2 \cdot s/m^4 K^2$ )	Fire performance when assessed to ISO 1716 or ISO 5658-2
a) Fibre cement board	$1800 \pm 100$	$6 \pm 1$	about $9,0 \times 10^4$	$PCS = 0$ kJ/kg
b) Calcium silicate board	$750 \pm 100$	$11 \pm 2$	about $9,0 \times 10^4$	$PCS = 0$ kJ/kg
c) Gypsum plasterboard <sup>1)</sup>	$800 \pm 100$	$12 \pm 1$	$5,8 \times 10^5$	$CFE^2) \geq 15,0$ kW/m <sup>2</sup> $Qsb^3) \geq 3,2$ MJ/m <sup>2</sup>
d) Mineral wool rock slab <sup>4)</sup>	$50 \pm 10^5$	$20 \pm 5$	about $1 \times 10^3$	$PCS < 1000$ kJ/kg
e) Steel sheet	$7850 \pm 50$	$0,8 \pm 0,1$	$2,4 \times 10^8$	Inert
f) Aluminium sheet	$2700 \pm 50$	$3 \pm 0,5$	$4,7 \times 10^6$	Inert
<sup>1)</sup> With paper not exceeding $300$ g/m <sup>2</sup> on either side. In some countries plasterboard is considered to be combustible. <sup>2)</sup> CFE = Crucial flux at extinguishment <sup>3)</sup> Qsb = Heat for sustained burning <sup>4)</sup> Mass loss less than 3 % at $550$ °C (ISO 1887). <sup>5)</sup> Purchase density.				

The substrates all have very little contribution to the "fire" itself in terms of combustibility but all effect the fire characteristics of the surface product due to their different thermal inertias.

Gypsum plasterboard has been included despite its similar density to calcium silicate board due to its different fire performance properties and the differences exhibited by various surfaces particularly in terms of spread of flame when tested using the two different substrates.

<sup>1)</sup> PCS = gross calorific potential