



SLOVENSKI STANDARD
SIST EN ISO 4625-1:2006

01-april-2006

JYn]j UnUVUfj Y]b`U_Y`E`I [cHJ`Ub`Y`na Y]y U`E`%`r`XY.`A`Y`r`c`X`U`g`d`f`g`h`b`c`a`]`b`
_`f`c`[`]`W`c`f`I`G`C`(`*`&`)!`%`&`\$`\$(`Ł

Binders for paints and varnishes - Determination of softening point - Part 1: Ring-and-ball method (ISO 4625-1:2004)

Bindemittel für Beschichtungsstoffe - Bestimmung der Erweichungstemperatur - Teil 1: Verfahren mit Ring und Kugel (ISO 4625-1:2004)

Liants pour peintures et vernis - Détermination du point de ramollissement - Partie 1: Méthode de l'anneau et de la bille (ISO 4625-1:2004)

Ta slovenski standard je istoveten z: EN ISO 4625-1:2006

ICS:

87.060.20 Veziva Binders

SIST EN ISO 4625-1:2006 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 4625-1:2006

<https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023B5668a/sist-en-iso-4625-1-2006>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 4625-1

February 2006

ICS 87.060.20

English Version

Binders for paints and varnishes - Determination of softening point - Part 1: Ring-and-ball method (ISO 4625-1:2004)

Liants pour peintures et vernis - Détermination du point de ramollissement - Partie 1: Méthode de l'anneau et de la bille (ISO 4625-1:2004)

Bindemittel für Beschichtungsstoffe - Bestimmung der Erweichungstemperatur - Teil 1: Verfahren mit Ring und Kugel (ISO 4625-1:2004)

This European Standard was approved by CEN on 16 January 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 4625-1:2006](https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023b5668a/sist-en-iso-4625-1-2006)

<https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023b5668a/sist-en-iso-4625-1-2006>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN ISO 4625-1:2006 (E)**Foreword**

The text of ISO 4625-1:2004 has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 4625-1:2006 by Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2006, and conflicting national standards shall be withdrawn at the latest by August 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice

The text of ISO 4625-1:2004 has been approved by CEN as EN ISO 4625-1:2006 without any modifications.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4625-1:2006](https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023B5668a/sist-en-iso-4625-1-2006)
<https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023B5668a/sist-en-iso-4625-1-2006>

INTERNATIONAL STANDARD

ISO
4625-1

First edition
2004-08-15

Binders for paints and varnishes — Determination of softening point —

Part 1: Ring-and-ball method

*Liants pour peintures et vernis — Détermination du point de ramollissement —
Partie 1: Méthode de l'anneau et de la bille*

SIST EN ISO 4625-1:2006

<https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023B5668a/sist-en-iso-4625-1-2006>



Reference number
ISO 4625-1:2004(E)

© ISO 2004

ISO 4625-1:2004(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 4625-1:2006](https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023B5668a/sist-en-iso-4625-1-2006)

<https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023B5668a/sist-en-iso-4625-1-2006>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
1 Scope.....	1
2 Normative references	1
3 Terms and definitions.....	1
4 Principle	1
5 Sampling and preparation of test pieces.....	2
6 Materials (heating-bath liquids).....	3
7 Manual ring-and-ball method.....	4
8 Automated ring-and-ball method	7
9 Expression of results.....	8
10 Precision and bias	8
11 Test report.....	10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 4625-1:2006](https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023b5668a/sist-en-iso-4625-1-2006)

<https://standards.iteh.ai/catalog/standards/sist/403540a3-7904-4129-a181-93023b5668a/sist-en-iso-4625-1-2006>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4625-1 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*.

It cancels and replaces ISO 4625:1980, which has been technically and editorially revised to harmonize it with ASTM E 28-99, *Standard Test Methods for Softening Point of Resins Derived from Naval Stores by Ring-and-Ball Apparatus*. The main changes are the introduction of an automated procedure and the splitting of the softening point values into four ranges: less than 35 °C, 35 °C to less than 80 °C, 80 °C to 150 °C and greater than 150 °C. The moulding method for the preparation of test pieces has been deleted.

ISO 4625 consists of the following parts, under the general title *Binders for paints and varnishes — Determination of softening point*:

- *Part 1: Ring-and-ball method*
- *Part 2: Cup-and-ball method*

Binders for paints and varnishes — Determination of softening point —

Part 1: Ring-and-ball method

1 Scope

This part of ISO 4625 specifies methods of determining the softening point of resins (including rosin) and similar materials by means of the ring-and-ball apparatus.

Both manual and automatic methods are specified.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 5725-1, *Accuracy (trueness and precision) of measurement methods and results — Part 1: General principles and definitions*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

IEC 60751, *Industrial platinum resistance thermometer sensors*

ASTM E 691, *Standard Practice for Conducting an Interlaboratory Study to Determine the Precision of a Test Method*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

softening point

temperature at which a disc of sample held within a horizontal ring is forced downward a distance of 25,4 mm under the weight of a steel ball as the disc is heated at a prescribed rate in a water, glycerol, silicone oil, ethylene glycol/water or glycerol/water bath

4 Principle

In general, with materials of the types mentioned in Clause 1, softening does not take place at a definite temperature. As the temperature rises, these materials gradually change from brittle or exceedingly thick and slow-flowing materials to softer and less viscous liquids. For this reason, the determination of the softening point must be made by a fixed, closely defined method if the results obtained are to be comparable.