



# SLOVENSKI STANDARD SIST EN ISO 17872:2007

01-julij-2007

---

6 Ufj Y]b`U\_]!'Ga Yfb]W'nU'i j UUb^Y'g`YX]fYncj 'j `dfYa Uh] `bU\_cj ]bg\_] `d`cý U  
nUdfYg\_i ýUb^Y'cXdcfbcgh]`dfch]`\_cfcnj]`fGC`%+, +& &\$+\$L

Paints and varnishes - Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing (ISO 17872:2007)

Beschichtungsstoffe - Leitfaden zum Anbringen von Ritzen durch eine Beschichtung auf Metallplatten für Korrosionsprüfungen (ISO 17872:2007)

Peintures et vernis - Lignes directrices pour la production de rayures au travers du revêtement de panneaux métalliques en vue des essais de corrosion (ISO 17872:2007)

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-c40ba0867d42/sist-en-iso-17872-2007>

Ta slovenski standard je istoveten z: EN ISO 17872:2007

---

## ICS:

87.040

Barve in laki

Paints and varnishes

SIST EN ISO 17872:2007

en;fr;de

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 17872:2007

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>

ICS 87.040

English Version

Paints and varnishes - Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing  
(ISO 17872:2007)

Peintures et vernis - Lignes directrices pour la production de rayures au travers du revêtement de panneaux métalliques en vue des essais de corrosion (ISO 17872:2007)

Beschichtungsstoffe - Leitfaden zum Anbringen von Ritzen durch eine Beschichtung auf Metallplatten für Korrosionsprüfungen (ISO 17872:2007)

This European Standard was approved by CEN on 17 February 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

## Foreword

This document (EN ISO 17872:2007) has been prepared by Technical Committee ISO/TC 35 "Paints and varnishes" in collaboration with Technical Committee CEN/TC 139 "Paints and varnishes", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2007, and conflicting national standards shall be withdrawn at the latest by September 2007.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

### Endorsement notice

The text of ISO 17872:2007 has been approved by CEN as EN ISO 17872:2007 without any modifications.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 17872:2007](https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007)

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>

---

---

**Paints and varnishes — Guidelines for  
the introduction of scribe marks through  
coatings on metallic panels for corrosion  
testing**

*Peintures et vernis — Lignes directrices pour la production de rayures  
au travers du revêtement de panneaux métalliques en vue des essais  
de corrosion*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST EN ISO 17872:2007

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 17872:2007](https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007)

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>

© ISO 2007

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

**Contents**

Page

<b>Foreword</b> .....	<b>iv</b>
<b>Introduction</b> .....	<b>v</b>
<b>1 Scope</b> .....	<b>1</b>
<b>2 Scribe marks</b> .....	<b>1</b>
<b>3 Apparatus</b> .....	<b>3</b>
<b>4 Test panels</b> .....	<b>3</b>
<b>5 Procedure</b> .....	<b>3</b>
<b>6 Shape verification of cross-section</b> .....	<b>4</b>
<b>7 Report</b> .....	<b>4</b>
<b>Annex A (informative) Scribing tools</b> .....	<b>5</b>
<b>Annex B (informative) Determination of shape and dimensions of scribe marks made using common scribing tools</b> .....	<b>8</b>
<b>Bibliography</b> .....	<b>10</b>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN ISO 17872:2007](https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007)

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 17872 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 17872:2007](https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007)

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>



## Introduction

Many International Standards deal with corrosion testing, where scribe marks are introduced through a coating to a metallic substrate. However, the method of scribe-mark introduction (scribing pattern, tools, etc.) is not standardized across these standards.

The main purposes of an intentionally inflicted damage in a coating prior to corrosion testing are as follows:

- a) to simulate and to investigate how a specific type of damage behaves during exposure;
- b) to obtain an accelerated response during a corrosion test, e.g. at quality control during production;
- c) to investigate the general durability of a coating by observation of the rate of corrosion spread after exposure.

Preliminary investigations have shown that several variants, both in terms of shape and dimensions, of scribing tools are used. This variation occurs both across countries and within countries. The effect of using different tools is the production of scribe marks with different cross-sectional shape, depth and exposed metal area. These differences will greatly affect test results obtained during corrosion tests, as the intention of introducing scribe marks into a coating system is such that oxygen and the electrolyte present during exposure testing can obtain access to a well-defined and active metal surface.

The actual method used to introduce a scribe mark depends on the coating type and thickness. However, in all cases it is preferable if the cross-section is as smooth as possible, the metallic substrate is exposed evenly and no coating remains on the exposed substrate. Additionally, it is desirable that scribing methods are consistent across related International Standards.

The scribing method greatly affects how the corrosion process occurs and the reproducibility when tests are repeated under the same conditions. In order to obtain anticorrosive results with high accuracy and reproducibility, accurate and consistent scribing is required.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN ISO 17872:2007

<https://standards.iteh.ai/catalog/standards/sist/114742e2-3480-40de-b22e-e40ba0867d42/sist-en-iso-17872-2007>

# Paints and varnishes — Guidelines for the introduction of scribe marks through coatings on metallic panels for corrosion testing

## 1 Scope

This International Standard describes methods of scribing coated steel or test-pieces for corrosion tests, where the coating system is applied at dry film thicknesses of less than 500 µm. It is intended as a guideline only, being based on the results of a collaborative trial with no subsequent corrosion testing having been carried out to determine the suitability of the introduced scribe marks for such tests.

This International Standard covers the scribing of metallic panels or test pieces made from

- steel,
- chemically treated steel,
- aluminium or aluminium alloy, and
- chemically treated aluminium.

It does not cover the scribing of galvanized or electroplated metal or clad aluminium panels.

**STANDARD PREVIEW**  
(standards.iteh.ai)

## 2 Scribe marks

SIST EN ISO 17872:2007

If not otherwise agreed or specified, a scribe mark is made as an X-shape, T-shape or single-line, through the coating to the metal substrate according to the agreed conditions. Examples of X-shaped, T-shaped and a single-line scribe mark are given in Figure 1. Typically, the suitable length of the scribed lines is in the range of 50 mm to 70 mm, depending on the coating thickness and the expected amount of corrosion.

The length of the scribe mark should be significantly more than the expected creep resulting from the corrosion test carried out.

The width of the scribe mark can also affect the result of a corrosion test. The smaller the width, the stronger is the tendency for the exposed metal surface to be passivated by deposition of sparingly soluble corrosion products. It is therefore important to select a scribing tool which will provide a suitable scribe width for the corrosion test being carried out.

The orientation of the scribed lines is often significant in terms of affecting corrosion test results. On panels with a slight inclination from the vertical, e.g. for salt-spray tests, more salt is collected in a horizontally exposed scribe mark. Also, a horizontally exposed scribe mark will generate an even salt distribution, whereas a diagonal, or more particularly a vertical, scribe mark tends to generate a gradient, with an increasing amount of salt along the lower edge of the scribe mark. An increased amount of salt usually leads to an increased corrosion rate, but on coated steel, high salt concentration might have an inhibiting effect on corrosion since the formed corrosion products are very dense.

The cross-section of the scribe mark should be as uniform as possible along its entire length. The coating should be cut smoothly along the direction of the scribe mark. The cross-sectional shape of the scribe may be either “V” or “U” shaped, depending upon the tool used, and should be such that for a “V”-shaped cut  $a > b > c$  and for a “U”-shaped cut  $a > b$ , with the width ( $b$ ) of both “V” and “U” shapes such that  $b \geq 0,2$  mm (see Figure 2 for an explanation of the symbols). Certain scribing tools may also produce a rectangular cross-section, where  $a$ ,  $b$  and  $c$  are approximately equal.

**NOTE** The shape, depth and uniformity of scribe marks resulting from the use of manual scribing tools will also depend on the operator carrying out the scribing procedure. To reduce this operator dependency, and hence variability in