
Dc`ja Yfb]a Uhf]U]`E`A Uhf]U]`bUcgbcj]_cdc`ja YfUYH`Yb#]b]U_c\ c`f9JC<LnU
cV]_cj Ub`Y]b`Y_glfi X]fUb`Y`E`%rXY. G]ghYa `cnbU Yj Ub`U]b`dcX`U] Y`nU
gdYWZ_UM`Y`fGC`%`**`!%%--Ł

Plastics - Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials -
Part 1: Designation system and basis for specifications (ISO 14663-1:1999)

Kunststoffe - Ethylen-Vinylalkohol (EVOH)-Copolymer-Formmassen - Teil 1:
Bezeichnungssystem und Basis für Spezifikationen (ISO 14663-1:1999)

(standards.iteh.ai)

Plastiques - Matériaux a base de copolymères éthylène/alcool vinylique (EVOH) pour
moulage et extrusion - Partie 1: Système de désignation et base de spécification (ISO
14663-1:1999) [https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-
ca8427fe8a7d/sist-en-iso-14663-1-2006](https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006)

Ta slovenski standard je istoveten z: EN ISO 14663-1:2006

ICS:

83.080.20

SIST EN ISO 14663-1:2006

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 14663-1:2006

<https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006>

ICS 83.080.20

English Version

Plastics - Ethylene/vinyl alcohol (EVOH) copolymer moulding
and extrusion materials - Part 1: Designation system and basis
for specifications (ISO 14663-1:1999)

Plastiques - Matériaux à base de copolymères
éthylène/alcool vinylique (EVOH) pour moulage et extrusion
- Partie 1: Système de désignation et base de spécification
(ISO 14663-1:1999)

Kunststoffe - Ethylen-Vinylalkohol (EVOH)-Copolymer-
Formmassen - Teil 1: Bezeichnungssystem und Basis für
Spezifikationen (ISO 14663-1:1999)

This European Standard was approved by CEN on 16 March 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 14663-1:1999 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 14663-1:2006 by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2006, and conflicting national standards shall be withdrawn at the latest by October 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice
iTeh STANDARD PREVIEW
(standards.iteh.ai)

The text of ISO 14663-1:1999 has been approved by CEN as EN ISO 14663-1:2006 without any modifications.

[SIST EN ISO 14663-1:2006](https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006)
<https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006>

**Plastics — Ethylene/vinyl alcohol (EVOH)
copolymer moulding and extrusion
materials —**

Part 1:

Designation system and basis for specifications

iTeh STANDARD PREVIEW
(standards.iteh.ai)

*Plastiques — Matériaux à base de copolymères éthylène/alcool vinylique
(EVOH) pour moulage et extrusion —*

Partie 1: Système de désignation et base de spécification

<https://standards.iteh.ai/catalog/standards/sist/0691b44f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006>



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 14663-1 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

ISO 14663 consists of the following parts, under the general title *Plastics — Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 14663-1:2006](https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006)

<https://standards.iteh.ai/catalog/standards/sist/0b9f344f-5abc-4886-bdc3-ca8427fe8a7d/sist-en-iso-14663-1-2006>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Plastics — Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials —

Part 1: Designation system and basis for specifications

1 Scope

1.1 This part of ISO 14663 establishes a system of designation for ethylene/vinyl alcohol (EVOH) copolymer thermoplastic materials, which may be used as the basis for specifications.

1.2 The types of ethylene/vinyl alcohol (EVOH) copolymer plastic are differentiated from each other by a classification system based on appropriate levels of the designatory property:

melt mass-flow rate

and on information about basic polymer parameters, intended application and/or method of processing, important properties, additives, colorants, fillers and reinforcing materials.

1.3 This part of ISO 14663 is applicable to copolymers of ethylene and vinyl alcohol containing from 15 % (*m/m*) to 60 % (*m/m*) of ethylene. It applies to materials ready for normal use in the form of powder, granules or pellets, unmodified or modified by colorants, additives, fillers, etc.

1.4 It is not intended to imply that materials having the same designation give necessarily the same performance. This part of ISO 14663 does not provide engineering data, performance data or data on processing conditions which may be required to specify a material for a particular application and/or method of processing.

If such additional properties are required, they shall be determined in accordance with the test methods described in part 2 of this International Standard, if suitable.

1.5 In order to specify a thermoplastic material for a particular application or to ensure reproducible processing, additional requirements may be given in data block 5 (see clause 3, introductory paragraph).

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 14663. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 14663 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 1043-1:1997, *Plastics — Symbols and abbreviated terms — Part 1: Basic polymers and their special characteristics*.

ISO 1133:1997, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics*.

ISO 14663-2:1999, *Plastics — Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials — Part 2: Preparation of test specimens and determination of properties*.

3 Designation system

The designation system for thermoplastics is based on the following standardized pattern:

Designation						
Description block (optional)	Identity block					
	International Standard number block	Individual-item block				
		Data block 1	Data block 2	Data block 3	Data block 4	Data block 5

The designation consists of an optional description block, reading “Thermoplastics”, and an identity block comprising the International Standard number and an individual-item block. For unambiguous designation, the individual-item block is subdivided into five data blocks comprising the following information:

- Data block 1: Identification of the plastic by its symbol EVOH in accordance with ISO 1043-1 and information about the polymerization process or composition of the polymer (see 3.1).
- Data block 2: Position 1: Intended application or method of processing (see 3.2).
Positions 2 to 8: Important properties, additives and supplementary information (see 3.2).
- Data block 3: Designatory properties (see 3.3).
- Data block 4: Fillers or reinforcing materials and their nominal content (see 3.4).
- Data block 5: For the purpose of specifications, a fifth data block may be added containing additional information. This kind of information is not relevant to this part of ISO 14663.

The first character of the individual-item block shall be a hyphen. The five data blocks shall be separated from each other by commas. If a data block is not used, this shall be indicated by doubling the separation sign, i.e. by two commas (,,).

3.1 Data block 1

In this data block, after the hyphen, ethylene/vinyl alcohol copolymers are identified by the symbol EVOH, in accordance with ISO 1043-1, and, after a space, a two-figure code-number giving the ethylene content of the copolymer as specified in table 1.

Table 1 — Code-numbers used for ethylene content in data block 1

Code-number	Range of ethylene content % (m/m)
18	> 15 but ≤ 20
23	> 20 but ≤ 25
28	> 25 but ≤ 30
33	> 30 but ≤ 35
38	> 35 but ≤ 40
43	> 40 but ≤ 45
48	> 45 but ≤ 50
53	> 50 but ≤ 55
58	> 55 but ≤ 60

The ethylene content shall be determined by the method specified in ISO 14663-2, annex B.

3.2 Data block 2

In this data block, information about intended application and/or method of processing is given in position 1 and information about important properties, additives and colour in positions 2 to 8. The code-letters used are specified in table 2.

If information is presented in positions 2 to 8 and no specific information is given in position 1, the letter X shall be inserted in position 1.

Table 2 — Code-letters used in data block 2

Code-letter	Position 1	Code-letter	Positions 2 to 8
A	Adhesives	A	Processing stabilized
B	Blow moulding	B	Antiblocking
		C	Coloured
		D	Powder
E	Extrusion		
F	Extrusion of films	F	Special burning characteristics
G	General use	G	Granules
		G1	Pellets
H	Coating	H	Heat-ageing stabilized
		L	Light or weather stabilized
M	Moulding		
		N	Natural (no colour added)
		P	Impact modified
		R	Mould release agent
		S	Lubricated
		T	Transparent
V	Thermoforming	V	Heat shrinkable
X	No indication	X	Crosslinkable
Y	Textile yarns, spinning	Y	Increased electrical conductivity
		Z	Antistatic