
Polimerni materiali - Materiali na osnovi kopolimera etilen/vinilalkohol (EVOH) za oblikovanje in ekstrudiranje – 2. del: Priprava preskušancev in ugotavljanje lastnosti (ISO 14663-2:1999)

Plastics - Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials - Part 2: Preparation of test specimens and determination of properties (ISO 14663-2:1999)

Kunststoffe - Ethylen-Vinylalkohol (EVOH)-Copolymer-Formmassen - Teil 2: Herstellung von Probekörpern und Bestimmung von Eigenschaften (ISO 14663-2:1999)

Plastiques - Matériaux à base de copolymères éthylène/alcool vinylique (EVOH) pour moulage et extrusion - Partie 2: Préparation des éprouvettes et détermination des propriétés (ISO 14663-2:1999)

Ta slovenski standard je istoveten z: EN ISO 14663-2:2006

ICS:

83.080.20

SIST EN ISO 14663-2:2006

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 14663-2:2006

<https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006>

ICS 83.080.20

English Version

Plastics - Ethylene/vinyl alcohol (EVOH) copolymer moulding
and extrusion materials - Part 2: Preparation of test specimens
and determination of properties (ISO 14663-2:1999)

Plastiques - Matériaux à base de copolymères
éthylène/alcool vinylique (EVOH) pour moulage et extrusion
- Partie 2: Préparation des éprouvettes et détermination
des propriétés (ISO 14663-2:1999)

Kunststoffe - Ethylen-Vinylalkohol (EVOH)-Copolymer-
Formmassen - Teil 2: Herstellung von Probekörpern und
Bestimmung von Eigenschaften (ISO 14663-2:1999)

This European Standard was approved by CEN on 16 March 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Foreword

The text of ISO 14663-2:1999 has been prepared by Technical Committee ISO/TC 61 "Plastics" of the International Organization for Standardization (ISO) and has been taken over as EN ISO 14663-2:2006 by Technical Committee CEN/TC 249 "Plastics", the secretariat of which is held by IBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by October 2006, and conflicting national standards shall be withdrawn at the latest by October 2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Endorsement notice
iTeh STANDARD PREVIEW
(standards.iteh.ai)

The text of ISO 14663-2:1999 has been approved by CEN as EN ISO 14663-2:2006 without any modifications.

[SIST EN ISO 14663-2:2006](https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006)
<https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006>

**Plastics — Ethylene/vinyl alcohol (EVOH)
copolymer moulding and extrusion
materials —**

Part 2:

Preparation of test specimens and determination
of properties

*Plastiques — Matériaux à base de copolymères éthylène/alcool vinylique
(EVOH) pour moulage et extrusion —*

Partie 2: Préparation des éprouvettes et détermination des propriétés



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 14663-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 9, *Thermoplastic materials*.

ISO 14663 consists of the following parts, under the general title *Plastics — Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials*:

- *Part 1: Designation system and basis for specifications*
- *Part 2: Preparation of test specimens and determination of properties*

Annexes A, B and C form an integral part of this part of ISO 14663.

STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 14663-2:2006
<https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet iso@iso.ch

Printed in Switzerland

Plastics — Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials —

Part 2: Preparation of test specimens and determination of properties

1 Scope

This part of ISO 14663 specifies the methods of preparation of test specimens and the test methods to be used in determining the properties of EVOH moulding and extrusion materials. Requirements for handling test material and for conditioning both the test material before moulding and the specimens before testing are given here.

Procedures and conditions are described for the preparation of test specimens, and procedures for measuring properties of the materials from which these specimens are made are given. Properties and test methods which are suitable and necessary to characterize EVOH moulding and extrusion materials are listed.

The properties have been selected from the general test methods in ISO 10350. Other test methods in wide use for or of particular significance to these moulding and extrusion materials are also included in this part of ISO 14663, as is the designatory property specified in part 1: melt mass-flow rate.

In order to obtain reproducible and comparable test results, it is necessary to use the methods of specimen preparation and conditioning, the specimen dimensions and the test procedures specified herein. Values determined will not necessarily be identical to those obtained using specimens of different dimensions or prepared using different procedures.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this part of ISO 14663. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this part of ISO 14663 are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 75-1:1993, *Plastics — Determination of temperature of deflection under load — Part 1: General test method.*

ISO 75-2:1993, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics and ebonite.*

ISO 178:1993, *Plastics — Determination of flexural properties.*

- ISO 179-1:—¹⁾, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test.*
- ISO 180:—²⁾, *Plastics — Determination of Izod impact strength.*
- ISO 291:1997, *Plastics — Standard atmospheres for conditioning and testing.*
- ISO 294-2:1996, *Plastics — Injection moulding of test specimens of thermoplastic materials — Part 2: Small tensile bars.*
- ISO 306:1994, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST).*
- ISO 527-1:1993, *Plastics — Determination of tensile properties — Part 1: General principles.*
- ISO 527-2:1993, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics.*
- ISO 899-1:1993, *Plastics — Determination of creep behaviour — Part 1: Tensile creep.*
- ISO 1133:1997, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics.*
- ISO 1183:1987, *Plastics — Methods for determining the density and relative density of non-cellular plastics.*
- ISO 2039-2:1987, *Plastics — Determination of hardness — Part 2: Rockwell hardness.*
- ISO 2818:1994, *Plastics — Preparation of test specimens by machining.*
- ISO 3146:1985, *Plastics — Determination of melting behaviour (melting temperature or melting range) of semi-crystalline polymers.*
- ISO 3167:1993, *Plastics — Multipurpose test specimens.*
- ISO 3451-1:1997, *Plastics — Determination of ash — Part 1: General methods.*
- ISO 10350:1993, *Plastics — Acquisition and presentation of comparable single-point data.*
- ISO 14663-1:1999, *Plastics — Ethylene/vinyl alcohol (EVOH) copolymer moulding and extrusion materials — Part 1: Designation system and basis for specifications.*
- IEC 60093:1980, *Methods of test for volume resistivity and surface resistivity of solid electrical insulating materials.*
- IEC 60112:1979, *Method for determining the comparative and the proof tracking indices of solid insulating materials under moist conditions.*
- IEC 60243-1:1998, *Electrical strength of solid insulating materials — Test methods — Part 1: Tests at power frequencies.*
- IEC 60250:1969, *Recommended methods for the determination of the permittivity and dielectric dissipation factor of electrical insulating materials at power, audio and radio frequencies including metre wavelengths.*
- IEC 60296:1982, *Specification for unused mineral insulating oils for transformers and switchgear.*
- IEC 60695-11-10:1999, *Fire hazard testing — Part 11-10: Test flames — 50 W horizontal and vertical flame test methods.*

¹⁾ To be published. (Revision of ISO 179:1993)

²⁾ To be published. (Revision of ISO 180:1993)

3 Preparation of test specimens

Specimens shall be prepared by injection moulding or by cutting from film. The method to be used is indicated in the list of properties (Table 2) for each test specimen. The code letter M is used to show that injection moulding is to be used; F is the code letter for film.

It is essential that specimens are always prepared using the same processing conditions. The standard conditions are given below.

The material shall be kept in moisture-proof containers until it is required for use.

The moisture content of filled or reinforced materials shall be expressed as a percentage of the total mass of the compound.

3.1 Treatment of the material before moulding

Before processing, the moisture content of the sample shall not exceed 0,3 % (*m/m*). If the moisture level exceeds this limit, the material shall be dried for 24 h \pm 2 h at a temperature of 105 °C \pm 5 °C *in vacuo* or in a stream of dried nitrogen.

To ensure that the moisture content remains low, it is recommended that the material in the feed hopper of the injection-moulding machine be blanketed with any suitable gas (dried air, nitrogen or argon, for example). Better results may be obtained using a dehumidifier hopper dryer.

3.2 Injection moulding

Injection-moulded specimens shall be prepared in accordance with ISO 294-2, using the conditions specified in Table 1.

Table 1 — Conditions for injection moulding of test specimens

Material		Melt temperature	Mould temperature	Average injection velocity	Hold pressure	Hold-pressure time	Maximum injection pressure	Cooling time	Total cycle time
Filler content % (<i>m/m</i>)	Ethylene content % (<i>m/m</i>)	°C	°C	mm/s	MPa	s	MPa	s	s
0	> 15 but \leq 30	220	50	150	80	15	80	45	50
0	> 30 but \leq 45	200	50	150	80	15	80	45	50
0	> 45 but \leq 60	180	50	150	80	15	80	45	50
\leq 30	> 15 but \leq 60	230	60	150	80	12	80	35	40
> 30	> 15 but \leq 60	250	80	150	80	12	100	35	40

3.3 Preparation of film specimens

Film specimens shall be cut from cast, blown or any other type of film. The recommended thickness is 20 μ m \pm 10 μ m. The thickness of the specimens shall be determined from the average thickness of the sample, measured mechanically: the variation in thickness shall not exceed 2 μ m. The specimens shall have smooth surfaces and shall be free from marks and other visible defects (streaks, pinholes, fish-eyes, etc.).

4 Conditioning of test specimens

Properties shall be determined on specimens in the dry-as-moulded state or on specimens in the moist state or on specimens in either state. The state of the specimens shall be reported.

4.1 Dry-as-moulded (DAM) state

Specimens shall be moulded from dry granules (see 3.1 and 3.2). Specimens are considered to be in the dry-as-moulded (DAM) state when they have been placed immediately after moulding in a moisture-proof container and stored at $23\text{ °C} \pm 2\text{ °C}$ for at least 24 h. The moisture content of DAM specimens may not exceed 0,3 % (*m/m*). Drying of specimens with moisture contents above this limit in order to reach this moisture content is not allowed.

To keep the absorbed moisture at a low level, DAM specimens shall be tested in as short a time as possible (maximum 30 min) after removal from the moisture-proof container.

4.2 Moist state

Test specimens are considered to be in the moist state when they have been conditioned at $23\text{ °C} \pm 2\text{ °C}$ and $(50 \pm 5)\%$ relative humidity until equilibrium has been reached (see annex A to ISO 291:1997).

4.3 Film conditioning

Non-oriented film shall be heat-treated under the following conditions:

temperature $20\text{ °C} \pm 2\text{ °C}$ below the melting temperature;

time 10 min.

ITeH STANDARD PREVIEW
(standards.iteh.ai)

Film shall be held in a frame by clamps during the heat treatment so that the dimensions do not change.

[SIST EN ISO 14663-2:2006](https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006)

[https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-](https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006)

[788714d38bb5/sist-en-iso-14663-2-2006](https://standards.iteh.ai/catalog/standards/sist/52475ba8-b33d-4e1e-a314-788714d38bb5/sist-en-iso-14663-2-2006)

5 Determination of properties

In the determination of properties and the presentation of data, the standards, supplementary instructions and notes given in ISO 10350 shall be applied. All tests shall be carried out in the standard laboratory atmosphere of $23\text{ °C} \pm 2\text{ °C}$ and $(50 \pm 5)\%$ relative humidity unless specifically stated otherwise in Tables 2 and 3.

Table 2 is taken from ISO 10350:1993, and the properties listed are those appropriate to ethylene/vinyl alcohol copolymer moulding and extrusion materials. These properties are those considered useful for comparisons of data generated for different thermoplastics.

Table 3 contains those properties, not found specifically in Table 2, which are in wide use or of particular significance in the practical characterization of ethylene/vinyl alcohol copolymer moulding and extrusion materials. Comparisons of different materials using these properties may well be restricted to those thermoplastics in the same generic families.

Table 2 — General properties and test conditions (selected from ISO 10350)

Property	Unit	Standard	Specimen type (dimensions in mm)	Specimen preparation ¹⁾	Test conditions and supplementary instructions
Rheological properties					
Melt mass-flow rate	g/10 min	ISO 1133	Moulding compound	—	Temperature 210 °C, load 2,16 kg (see also conditions given in ISO 14663-1)
Mechanical properties					
Tensile modulus	MPa	} ISO 527-1 ISO 527-2	ISO 3167, type A	M	Test speed 1 mm/min
Yield stress	MPa				Test speed 50 mm/min
Yield strain	%				Test speed 50 mm/min
Strain at break	%				Test speed 50 mm/min
Stress at 50 % strain	MPa				Test speed 50 mm/min
Stress at break	MPa				Test speed 50 mm/min
Nominal strain at break	%				Test speed 5 mm/min. Only to be quoted if stress at 50 % strain cannot be measured.
Tensile creep modulus	MPa	ISO 899-1	See ISO 3167	M	At 1 h At 1 000 h } Strain ≤ 0,5 %
Flexural modulus	} MPa	ISO 178	80 × 10 × 4	M	Test speed 2 mm/min
Flexural strength					
Charpy impact strength	kJ/m ²	} ISO 179-1	80 × 10 × 4	M	Method 1e (edgewise impact)
Charpy notched impact strength	kJ/m ²		80 × 10 × 4 V-notch, r = 0,25	M	Method 1eA (edgewise impact)
Thermal properties					
Melting temperature	°C	ISO 3146	Moulding compound	—	Method C (DSC or DTA). Use 10 °C/min.
Temperature of deflection under load	°C	ISO 75-1 ISO 75-2	110 × 10 × 4 edgewise or 80 × 10 × 4 flatwise	M	Method A (1,8 MPa)
Vicat softening temperature	°C	ISO 306	10 × 10 × 4	M	Heating rate 50 °C/h, load 50 N
Electrical properties					
Relative permittivity	—	} IEC 60250	≥ 80 × ≥ 80 × 1	M	Frequency 100 Hz and 1 MHz (compensate for electrode edge effect)
Dissipation factor	—				
Volume resistivity	Ω·m	} IEC 60093	≥ 80 × ≥ 80 × 1	M	Voltage 500 V
Surface resistivity	Ω				
Electric strength	kV/mm	IEC 60243-1	≥ 80 × ≥ 80 × 1 ≥ 80 × ≥ 80 × 3	M	Use 25 mm/75 mm coaxial-cylinder electrode configuration. Immerse in IEC 60296 transformer oil. Use short time (rapid rise) test.
Comparative tracking index	—	IEC 60112	≥ 15 × ≥ 15 × 4	M	Use solution A
Other properties					
Density	kg/m ³	ISO 1183	—	M	Use method B (pycnometer method). Use toluene/carbon tetrachloride as immersion liquids.
Flammability	s	IEC 60695-11-10	125 × 10 × 4	M	Method B — afterflame time of horizontal specimens
1) M = Injection moulding					